



Designation: B 243 – 01a

## Standard Terminology of Powder Metallurgy<sup>1</sup>

This standard is issued under the fixed designation B 243; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This terminology includes definitions of terms that are specific to the powder metallurgy industry. These definitions are helpful in the interpretation and application of powder metallurgy terms.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

B 331 Test Method for Compressibility of Metal Powders in Uniaxial Compaction<sup>2</sup>

### 3. Terminology

3.1 *Powder*—Terms associated with production, characterization, use, and testing of metal powders.

#### 3.1.1 Table of Contents

##### 1. Powders:

1.0 General, 3.1.2

1.1 Processes to Produce Powder, 3.1.3

1.2 Types of Powder, 3.1.4

1.3 Shapes of Powder Particles, 3.1.5

1.4 Additives to Powder, 3.1.6

1.5 Treatment of Powder, 3.1.7

1.6 Properties of Powder, 3.1.8

1.7 Procedures to Evaluate Powder, 3.1.9

1.8 Equipment to Evaluate Powder, 3.1.10

##### 2. Forming:

2.0 General, 3.2.1

2.1 Processes for Compacting, 3.2.2

2.2 Conditions of Compacting, 3.2.3

2.3 Tools Used for Compacting, 3.2.4

2.4 Phenomena Resulting from Compaction, 3.2.5

2.5 Properties of Compacts, 3.2.6

2.6 Forging, 3.2.7

2.7 Metal Injection Molding, 3.2.8

##### 3. Sintering:

3.1 Process for Sintering, 3.3.1

3.2 Conditions During Sintering, 3.3.2

3.3 Phenomena Resulting from Sintering, 3.3.3

3.4 Properties of Sintered Parts, 3.3.4

3.5 Procedure to Evaluate Sintered Parts, 3.3.5

3.6 Removal of Binders, 3.3.6

#### 4. Postsinter Treatments:

4.1 Processes, 3.4.1

#### 5. Miscellaneous:

5.1 Definitions, 3.5.1

5.2 Processes, 3.5.2

5.3 Materials, 3.5.3

##### 3.1.2 General:

**1001 agglomerate, n**—several particles adhering together.

**1002 particulate matter, n**—see **powder**.

**1003 P/M, n**—the acronym representing powder metallurgy. Used as **P/M Part**, **P/M Product**, **P/M Process**, and so forth.

**1004 powder metallurgy, n**—the production and utilization of metal powders.

**1005 powder, n**—particles that are usually less than 1000  $\mu\text{m}$  (1 mm) in size.

**1006 metal powder, n**—particles of elemental metals or alloys, normally less than 1000  $\mu\text{m}$  (1 mm) in size.

##### 3.1.3 Processes to Produce Powder:

**1101 atomization, n**—the dispersion of a molten metal into particles by a rapidly moving gas or liquid stream or by mechanical means.

**1102 granulation, n**—the production of coarse metal particles by pouring the molten metal through a screen into water (shotting) or by violent agitation of the molten metal while solidifying.

**1103 classification, n**—separation of a powder into fractions according to particle size.

**1104 air classification, n**—the separation of powder into particle size fractions by means of an air stream of controlled velocity.

**1105 gas classification, n**—the separation of powder into particle size fractions by means of a gas stream of controlled velocity.

**1106 chemical deposition, n**—the precipitation of one metal from a solution of its salts by the addition of another metal or reagent to the solution.

**1107 chemically precipitated metal powder, n**—powder produced by the reduction of a metal from a solution of its salts either by the addition of another metal higher in the electro-motive series or by other reducing agent.

<sup>1</sup> This terminology is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.01 on Nomenclature and Technical Data.

Current edition approved Oct. 10, 2001. Published December 2001. Originally published as B 243 – 49 T. Last previous edition B 243 – 01.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 02.05.



**1108 reduced metal powder, n**—metal powder produced, without melting, by the chemical reduction of metal oxides or other compounds.

**1109 disintegration, n**—the reduction of massive material to powder.

**1110 milling, n**—the mechanical treatment of metal powder, or metal powder mixtures, as in a ball mill, to alter the size or shape of the individual particles or to coat one component of the mixture with another.

**1111 pulverization, n**—the reduction in particle size of metal powder by mechanical means, a specific type of disintegration.

#### 3.1.4 *Types of Powder:*

**1201 atomized metal powder, n**—metal powder produced by the dispersion of a molten metal by a rapidly moving gas, or liquid stream, or by mechanical dispersion.

**1202 electrolytic powder, n**—powder produced by electrolytic deposition or by the pulverization of an electrodeposit.

**1203 dendritic powder, n**—particles, usually of electrolytic origin, having the typical pine tree structure.

**1204 carbonyl powder, n**—a metal powder prepared by the thermal decomposition of a metal carbonyl.

**1205 master-alloy powder, n**—a powder with high alloy concentration, designed to be diluted when mixed with a base powder to produce the desired composition.

**1206 pre-alloyed powder, n**—powder composed of two or more elements that are alloyed in the powder manufacturing process in which the particles are of the same nominal composition throughout. Synonymous with **completely alloyed powder**.

**1207 completely alloyed powder, n**—see **pre-alloyed powder**.

**1208 partially alloyed powder, n**—a powder in which the alloy addition or additions are metallurgically bonded to an elemental or pre-alloyed powder.

**1209 diffusion-alloyed powder, n**—a partially alloyed powder produced by means of a diffusion anneal.

**1210 mechanically alloyed powder, n**—a composite powder produced by mechanically incorporating other constituents which are generally insoluble within the deformable particles of the matrix metal.

**1211 matrix metal, n**—the continuous phase of a polyphase alloy or mechanical mixture; the physically continuous metallic constituent in which separate particles of another constituent are embedded.

**1212 composite powder, n**—a powder in which each particle consists of two or more distinct constituents.

**1213 spongy, n**—a porous condition in metal powder particles usually observed in reduced oxides.

**1214 sponge iron, n**—a coherent, porous mass of substantially pure iron produced by solid-state reduction of iron oxide (for example, iron ore or mill scale).

**1215 sponge iron powder, n**—ground and sized sponge iron, which may have been purified or annealed or both.

**1216 mixed powder, n**—a powder made by mixing two or more powders as uniformly as possible. The constituent powders will differ in chemical composition or in particle size or shape, or a combination thereof.

**1217 premix, n**—a uniform mixture of ingredients to a prescribed analysis, prepared by the powder producer, for direct use in compacting powder metallurgy products.

#### 3.1.5 *Shapes of Powder Particles:*

**1301 acicular powder, n**—needle-shaped particles.

**1302 needles, n**—elongated rod-like particles.

**1303 granular powder, n**—particles having approximately equidimensional nonspherical shapes.

**1304 nodular powder, n**—irregular particles having knotted, rounded, or similar shapes.

**1305 irregular powder, n**—particles lacking symmetry.

**1306 spherical powder, n**—globular-shaped particles.

**1307 flake powder, n**—flat or scale-like particles whose thickness is small compared with the other dimensions.

**1308 plates, n**—flat particles of metal powder having considerable thickness.

#### 3.1.6 *Additives to Powder:*

**1401 binder, n**—a cementing medium; either a material added to the powder to increase the green strength of the compact, and which is expelled during sintering; or a material (usually of relatively lower melting point) added to a powder mixture for the specific purpose of cementing together powder particles which alone would not sinter into a strong body.

**1402 feedstock, n**—*in metal injection molding (MIM)*, a moldable mixture of metal powder and binder.

**1403 powder lubricant, n**—an agent mixed with or incorporated in a powder to facilitate the pressing and ejecting of the compact.

**1404 dispersion-strengthened material, n**—a material consisting of a metal and finely dispersed, substantially insoluble, metallic or nonmetallic phase.

**1405 pore-forming material, n**—a substance included in a powder mixture that volatilizes during sintering and thereby produces a desired kind and degree of porosity in the finished compact.

#### 3.1.7 *Treatment of Powder:*

**1501 blending, n**—the thorough intermingling of powders of the same nominal composition (not to be confused with mixing).

**1502 equalizing, n**—see blending.

**1503 mixing, n**—the thorough intermingling of powders of two or more materials.

**1504 cross-product contamination, n**—the unintentional mixing of powders with distinct differences in either physical characteristics or chemical composition or both.

**1505 lubricating, n**—mixing with, or incorporating in, a powder, some agent to facilitate pressing and ejecting the compact from the die body; applying a lubricant to the die walls and punch surfaces.

#### 3.1.8 *Properties of Powder:*

**1601 apparent density, n**—the mass of a unit volume of powder, usually expressed as grams per cubic centimetre, determined by a specified method.

**1602 bulk density, n**—the mass per unit volume of a powder under nonstandard conditions, for example, in a shipping container (not to be confused with apparent density).

**1603 tap density, n**—the apparent density of the powder in a container that has been tapped under specified conditions.

**1604 flow rate, n**—the time required for a powder sample of standard weight to flow through an orifice in a standard instrument according to a specified procedure.

**1605 specific surface, n**—the surface area of one gram of powder, usually expressed in square centimetres.

**1606 compactibility, n**—a conceptual term, encompassing the powder characteristics of compressibility, green strength, edge retention, and lamination tendency, that relates to the ability of a powder to be consolidated into a usable green compact.

**1607 compressibility, n**—the capacity of a metal powder to be densified under a uniaxially applied pressure in a closed die.

*DISCUSSION*—Compressibility is measured in accordance with Test Method B 331 and may be expressed numerically as the pressure to reach a specified density, or alternatively the density at a given pressure.<sup>3</sup>

**1608 compression ratio, n**—the ratio of the volume of the loose powder to the volume of the compact made from it. Synonymous with **fill ratio**.

**1609 fill ratio, n**—see **compression ratio**.

**1610 oversize powder, n**—particles coarser than the maximum permitted by a given particle size specification.

**1611 plus sieve, n**—the portion of a powder sample retained on a standard sieve of specified number. (See **minus sieve**.)

**1612 minus sieve, n**—the portion of a powder sample which passes through a standard sieve of specified number. (See **plus sieve**.)

**1613 fines, n**—the portion of a powder composed of particles which are smaller than a specified size, currently less than 44 µm. See also **superfines**.

**1614 superfines, n**—the portion of a powder composed of particles that are smaller than a specified size, currently less than 10 µm.

**1615 fraction, n**—that portion of a powder sample that lies between two stated particle sizes. Synonymous with **cut**.

**1616 cut, n**—see **fraction**.

**1617 subsieve fraction, n**—particles all of which will pass through a 44-µm (No. 325) standard sieve.

**1618 sieve fraction, n**—that portion of a powder sample that passes through a standard sieve of specified number and is retained by some finer sieve of specified number.

**1619 particle size, n**—the controlling lineal dimension of an individual particle as determined by analysis with sieves or other suitable means.

**1620 particle size distribution, n**—the percentage by weight, or by number, of each fraction into which a powder sample has been classified with respect to sieve number or microns. (Preferred usage: “particle size distribution by frequency.”)

**1621 hydrogen loss, n**—the loss in weight of metal powder or of a compact caused by heating a representative sample for a specified time and temperature in a purified hydrogen atmosphere—broadly, a measure of the oxygen content of the sample when applied to materials containing only such oxides as are reducible with hydrogen and no hydride-forming element.

### 3.1.9 *Procedures to Evaluate Powder:*

**1701 sieve analysis, n**—particle size distribution; usually expressed as the weight percentage retained upon each of a series of standard sieves of decreasing size and the percentage passed by the sieve of finest size. Synonymous with **screen analysis**.

**1702 screen analysis, n**—see **sieve analysis**.

**1703 sieve classification, n**—the separation of powder into particle size ranges by the use of a series of graded sieves.

### 3.1.10 *Equipment to Evaluate Powder:*

**1801 powder flow meter, n**—an instrument for measuring the rate of flow of a powder according to a specified procedure.

**3.2 Forming**—Terms associated with consolidation of metal powders and mixes, including tooling, equipment, and characterization of sintered compacts.

### 3.2.1 *General:*

**2001 green**—unsintered (not sintered); for example, green compact, green density, green strength.

**2002 preforming**—the initial pressing of a metal powder to form a compact that is subjected to a subsequent pressing operation other than coining or sizing. Also, the preliminary shaping of a refractory metal compact after presintering and before the final sintering.

**2003 blank, n**—a pressed, presintered, or fully sintered compact, usually in the unfinished condition, requiring cutting, machining, or some other operation to give it its final shape.

**2004 briquet, n**—see **compact**.

**2005 compact, n**—an object produced by the compression of metal powder, generally while confined in a die, with or without the inclusion of nonmetallic constituents. Synonymous with **briquet**.

**2006 pressed bar, n**—a compact in the form of a bar; a green compact.

**2007 rolled compact, n**—a compact made by passing metal powder continuously through a rolling mill so as to form relatively long sheets of pressed material.

**2008 composite compact, n**—a metal powder compact consisting of two or more adhering layers, rings, or other shapes of different metals or alloys with each material retaining its original identity.

**2009 compound compact, n**—a metal powder compact consisting of mixed metals, the particles of which are joined by pressing or sintering or both, with each metal particle retaining substantially its original composition.

### 3.2.2 *Processes for Compacting:*

**2101 molding, v**—the pressing of powder to form a compact.

**2102 press, v**—to apply force to a mass of powder, generally while confined in a die or container, to form a compact.

**2103 double press-double sinter, n**—to repress and sinter a previously presintered or sintered compact.

*DISCUSSION*—Used to describe a four-step manufacturing process.

**2104 single-action pressing, n**—a method by which a powder is pressed in a stationary die between one moving and one fixed punch.

*DISCUSSION*—Only during ejection does either the stationary die or punch move.

<sup>3</sup> See Test Method B 331.



**2105 double-action pressing, n**—a method by which a powder is pressed in a die between opposing moving punches.

**2106 withdrawal pressing, n**—a powder consolidation method in which the die moves downward in relation to the lower punch(es) during compaction. It further descends over the fixed lower punch(es) for ejection, so that the compact may then be pushed off the tooling at this point.

**2107 multiple pressing, n**—a method of pressing whereby two or more compacts are produced simultaneously in separate die cavities.

**2108 roll compacting, n**—the progressive compacting of metal powders by the use of a rolling mill. Synonymous with **powder rolling**.

**2109 powder rolling, n**—see **roll compacting**.

**2110 cold pressing, n**—the forming of a compact at room temperature.

### 3.2.3 *Conditions for Compacting:*

**2201 die lubricant, n**—a lubricant applied to the walls of the die and to the punches to facilitate the pressing and ejection of the compact.

DISCUSSION—Contrast with **powder lubricant**. Synonymous with **die-wall lubricant**.

**2202 die-wall lubricant, n**—synonymous with **die lubricant**.

### 3.2.4 *Tools Used for Compacting:*

**2301 compacting tool set, n**—see **die**.

**2302 die, n**—the part or parts making up the confining form in which a powder is pressed. The parts of the die may be some or all of the following: die body, punches, and core rods. Synonymous with **mold**.

**2303 mold, n**—see **die**.

**2304 die body, n**—the stationary or fixed part of a die.

**2305 die set, n**—the parts of a press that hold and locate the die in proper relation to the punches.

**2306 die insert, n**—a removable liner or part of a die body.

**2307 split die, n**—a die made of parts that can be separated for ready removal of the compact.

**2308 segment die, n**—a die fabricated by the assembly of several die sections within a retaining bolster or shrinkage ring.

**2309 punch, n**—part of a die or compacting tool set that is used to transmit pressure to the powder in the die cavity. See **upper punch** and **lower punch**.

**2310 upper punch, n**—the member of the compacting tool set or die that closes the die and forms the top of the part being produced.

**2311 lower punch, n**—the member of the compacting tool set or die that forms the bottom of the part being produced, and the position of which determines the volume of powder fill. Secondary or subdivided lower punches may be necessary to facilitate filling, forming, and ejecting of multiple level parts.

**2312 stripper punch, n**—a punch that, in addition to forming the top or bottom of the die cavity, later moves further into the die to eject the compact.

**2313 core rod, n**—a member of a die used to produce a hole in a compact.

**2314 rotary press, n**—a machine fitted with a rotating table carrying multiple dies in which a material is pressed.

**2315 compacting tool set, n**—an assembly of tooling items

in which powder is pressed.

DISCUSSION—May include a die, punches, and core rods.

**2316 die, n**—a member of the compacting tool set forming the cavity in which the powder is compacted or a P/M compact is repressed.

**2317 core rod, n**—a member of the compacting tool set that forms the inner profile of the P/M compact in the direction of pressing.

### 3.2.5 *Phenomena Resulting from Compaction:*

**2401 bridging, v**—the formation of arched cavities in a powder mass.

**2402 green, adj**—unsintered (not sintered); for example, green compact, green density, green strength.

**2406 springback, n**—see **green expansion**.

**2407 cold welding, n**—cohesion between two surfaces of metal, generally under the influence of externally applied pressure, at room temperature.

DISCUSSION—Often used to describe the mechanism by which powder particles develop initial bonds and a pressed compact develops green strength.

### 3.2.6 *Properties of Compacts:*

**2501 green density, n**—the mass per unit volume of an unsintered compact.

**2502 pressed density, n**—synonymous with **green density**.

**2503 green expansion, n**—the increase in dimensions of an ejected compact relative to the die dimensions, measured at right angles to the direction of pressing. Synonymous with **springback**.

### 3.2.7 *Forging:*

**2601 powder forging, v**—hot densification by forging of an unsintered, presintered, or sintered preform made from powder. Also referred to by the acronyms **P/F**, **P/M forging**, or **P/M hot forming**. There are two basic forms of powder forging: **hot upset powder forging** and **hot repress powder forging**.

DISCUSSION—In the case in which the preform has been sintered, the process is often referred to as “sinter forging.”

**2602 P/F, v**—the acronym for powder forging. See **powder forging**.

**2603 P/M forging, v**—see **powder forging**.

**2604 P/M hot forming, v**—see **powder forging**.

**2605 forging preform, n**—an unsintered, presintered, or fully sintered compact intended to be subjected to hot or cold forming and densification.

**2606 sinter forging, v**—see **powder forging**.

**2607 hot coining, v**—see **powder forging**.

**2608 hot forging, v**—see **powder forging**.

**2609 hot restriking, v**—see **powder forging**.

**2610 hot upset powder forging, v**—hot densification of a P/M preform by forging in which there is a significant amount of lateral material flow.

**2611 hot repress powder forging, v**—hot densification of a P/M preform by forging in which material flow is mainly in the direction of pressing. Also referred to as *hot restriking* or *hot coining*.

### 3.2.8 *Metal Injection Molding:*

**2705 metal injection molding (MIM), n**—a process in which a mixture of metal powders and a binder system is