

SLOVENSKI STANDARD**SIST EN 187-1:1998****01-november-1998**

?YfUa] bYd`cý]W!J`Y YbY_YfUa] bYd`cý]WnjcXcjdc`bcgħt*`i 0901%`i !
g_i d]bU5=V!%`XY

Ceramic tiles - Extruded ceramic tiles with a water absorption of 6%<E<=10% (Group Allb) Part 1

Keramische Fliesen und Platten - Stranggepreßte keramische Fliesen und Platten mit einer Wasseraufnahme von 6%<E<=10% (Gruppe Allb) Teil 1

ITeh STANDARD PREVIEW

(standards.iteh.ai)

Carreaux et dalles céramiques - Carreaux et dalles céramiques étirés a absorption d'eau 6%<E<=10% (Groupe Allb) Partie 1

[SIST EN 187-1:1998](#)

<https://standards.iteh.ai/catalog/standards/sist/71b4aac5-4f00-4e9d-95db-8adc452e3318/sist-en-187-1-1998>

Ta slovenski standard je istoveten z: EN 187-1:1991

ICS:

91.100.23 S^lǣ á } ^Á || z ǣ Ceramic tiles

SIST EN 187-1:1998

en

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 187-1:1998](#)

<https://standards.iteh.ai/catalog/standards/sist/71b4aac5-4f00-4e9d-95db-8adc452e3318/sist-en-187-1-1998>

EUROPEAN STANDARD

EN 187-1:1991

NORME EUROPEENNE

EUROPAISCHE NORM

September 1991

UDC 691.433-413-033.6:666.75-184.2

Supersedes EN 187-1:1985

Descriptors: Tiles, coating slabs, water absorption tests, equipment specification, shape, dimensions, dimensional tolerances, physical properties, mechanical properties, chemical properties, marking

English version

Ceramic tiles -- Extruded ceramic tiles with a water absorption of $6\% \leq E \leq 10\%$ (Group AIIb) Part 1.

Carreaux et dalles céramiques -- Carreaux et dalles céramiques étirés à absorption d'eau $6\% \leq E \leq 10\%$ (Groupe AIIb) Partie 1.

Keramische Fliesen und Platten -- Stranggepreßte keramische Fliesen und Platten mit einer Wasseraufnahme von $6\% \leq E \leq 10\%$ (Gruppe AIIb) Teil 1.

This European Standard was approved by CEN on 1991-09-19. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

8adc452e3318/sist-en-187-1-1998

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.



CEN

REPUBLIKA SLOVENIJA
MINISTRSTVO ZA ZNANOST IN TEHNOLOGIJO
Urad RS za standardizacijo in meroslovje

LJUBLJANA

EN 187-1

PREVZET PO METODI RAZGLASITVE

-11- 1998 Central Secretariat: rue de Stassart 36, B-1050 Brussels

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

(c) CEN 1991 Copyright reserved to all CEN members

Ref. No. EN 187-1:1991 E

Page 2
EN 187-1:1991

Foreword

This European Standard was drawn up by the Technical Committee CEN/TC 67 'Ceramic tiles', the Secretariat of which is held by UNI.

According to the common CEN/CENELEC rules, the following countries are bound to implement this European Standard:

Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 187-1:1998

<https://standards.iteh.ai/catalog/standards/sist/71b4aac5-4f00-4e9d-95db-8adc452e3318/sist-en-187-1-1998>




1 Scope and field of application

This European Standard specifies the sizes, dimensional tolerances, mechanical, physical and chemical requirements, surface quality requirements and marking of ceramic tiles. It is applicable only to extruded ceramic tiles with a water absorption of $6\% < E < 10\%$ according to Group AIIb of EN 87, for interior and exterior use (see clause 7 ordering), mainly on floors and also on walls. The standard applies only to extruded ceramic tiles of first quality.

This standard is divided into two Parts. Part 1 applies to the majority of ceramic tiles in product Group AIIb. Part 2 applies to certain ceramic tiles in product Group AIIb which are produced in individual countries, e.g. terre cuite in France and Belgium, cotto in Italy and baldosin catalan in Spain.

2 References

- EN 87 'Ceramic floor and wall tiles — Definitions, classification, characteristics and marking'
- EN 98 'Ceramic tiles — Determination of dimensions and surface quality'
- EN 99 'Ceramic tiles — Determination of water absorption'
- EN 100 'Ceramic tiles — Determination of modulus of rupture'
- EN 101 'Ceramic tiles — Determination of scratch hardness of surface according to Mohs'
- EN 102 'Ceramic tiles — Determination of resistance to deep abrasion — Unglazed tiles'
- EN 103 'Ceramic tiles — Determination of linear thermal expansion'
<http://standards.itch.ai/mtbpe/standards/sist-en-187-1-1998/8adc452e3318/sist-en-187-1-1998>
- EN 104 'Ceramic tiles — Determination of resistance to thermal shock'



Co-ordinating size (C) = Work size (W) + Joint width (J)
 Work size (W) = Dimensions of the visible face (a) and (b)
 Total width = Work size (W) + projecting edge

NOTE. The form of projecting edging is not specified but the distance between the inner facial edge and the projecting edge shall be a maximum of 2 mm.

- EN 105 'Ceramic tiles — Determination of crazing resistance — Glazed tiles'
- EN 106 'Ceramic tiles — Determination of chemical resistance — Unglazed tiles'
- EN 122 'Ceramic tiles — Determination of chemical resistance — Glazed tiles'
- EN 154 'Ceramic tiles — Determination of resistance to surface abrasion — Glazed tiles'
- EN 155 'Ceramic tiles — Determination of moisture expansion using boiling water — Unglazed tiles'
- EN 163 'Ceramic tiles — Sampling and basis for acceptance'
- EN 202 'Ceramic tiles — Determination of frost resistance'

3 Description

According to EN 87, two types of extruded ceramic tiles are distinguished: split tiles and quarry tiles.

Split tiles are produced as a double tile which is split in two after firing, hence the name 'split tile'. Split tiles are characterized by typical parallel ridges on their reverse. Quarry tiles are shaped by cutting from a single column and are often subsequently die-pressed.

The surface of extruded ceramic tiles can be smooth, profiled, wavy, decorated or finished in some other way; it can be fully or partly glazed (GL) in glossy, matt or semi-matt finish, or unglazed (UGL).

4 Shapes and sizes

4.1 Split tiles (Spaltplatten)

For shapes and sizes see figure 1 and tables 1 and 2.




Figure 1. Split tile

Page 4
EN 187-1:1991

Table 1. Modular preferred sizes for split tiles

Co-ordinating size (C) cm	Work size (W) mm		Thickness mm (d)
	Length (a)	Width (b)	
M 10 x 10			
M 15 x 15			
M 20 x 5			
M 20 x 10			
M 20 x 20			
M 25 x 6,25			
M 25 x 12,5			
M 25 x 25			
M 30 x 7,5			
M 30 x 10			
M 30 x 15			
M 30 x 30			
M 40 x 20			


Table 2. Non-modular sizes for split tiles

The most common sizes are:

Nominal size (N) cm	Work size (W) mm		Thickness mm (d)
	Length (a)	Width (b)	
20 x 20			
21,7 x 10,5			
21,9 x 6,6			
22 x 11			
24 x 7,3			
24 x 11,5			
30 x 30			
40 x 20			

4.2 Quarry tiles

For shapes and sizes see figure 2 and tables 3 and 4.



Co-ordinating size (C) = Work size (W) + Joint width (J)
Work size (W) = Dimensions (a) and (b)

Figure 2. Quarry tile

Table 3. Modular preferred sizes for quarry tiles

Co-ordinating size (C) cm	Work size (W) mm		Thickness mm (d)
	Length (a)	Width (b)	
M 10 x 10			
M 15 x 15			
M 20 x 5			
M 20 x 10			
M 20 x 20			
M 25 x 12,5			
M 25 x 25			
M 30 x 15			

Table 4. Non-modular sizes for quarry tiles

The most common sizes are:

Nominal size (N) cm	Work size (W) mm		Thickness mm (d)
	Length (a)	Width (b)	
10 x 10			
13 x 13			
14 x 14			
15 x 15			
15,2 x 7,6			
15,2 x 15,2			
18 x 18			
20 x 10			
20 x 20			
20,3 x 20,3			
22,9 x 22,9			
26 x 13			
28 x 14			
30 x 30			

4.3 Other sizes

For extruded ceramic tiles with dimensions other than those given in the tables, the work sizes shall be stated by the manufacturer. The relevant requirements for work size and thickness given in the respective tables are applicable.

4.4 Accessories

Dimensions of accessories and their tolerances are not standardized and these shall be stated by the manufacturer where appropriate.

5 Requirements

Dimensional and surface quality requirements and physical and chemical properties shall be as given in table 5.

Sampling and basis for acceptance shall be in accordance with EN 163.

Table 5

	Split tiles	Quarry tiles	Test according to
Dimensions and surface quality			
Length and width			
e The deviation in % of the average size for each tile (2 or 4 sides) from the work size (W)	± 2	± 2	EN 98
f The deviation in % of the average size for each tile (2 or 4 sides) from the average size of the 10 test specimens (20 or 40 sides)	± 1,5	± 1,5	EN 98
Thickness			
The deviation in % of the average thickness of each tile from the work size thickness	± 10	± 10	EN 98
Straightness of sides¹⁾ (facial sides)			
The maximum deviation from straightness, in % related to the corresponding work sizes	± 1,0	± 1,0	EN 98
Rectangularity¹⁾			
The maximum deviation from rectangularity, in % related to the corresponding work sizes	± 1,5	± 1,0	EN 98
Surface flatness	SIST EN 187-1:1998 https://standards.iteh.ai/catalog/standards/sist/71b4aac5-4f00-4e9d-95db-8adc452e3318/sist-en-187-1-1998		
The maximum deviation from flatness, in %			
(a) Centre curvature, related to diagonal calculated from the work sizes	± 0,7	± 1,5	EN 98
(b) Edge curvature, related to the corresponding work size	± 0,7	± 1,5	EN 98
(c) Warpage, related to diagonal calculated from the work sizes	± 1,0	± 1,5	EN 98
Surface quality²⁾	Min. 95 % of the tiles shall be free from visible defects that would impair the appearance of a major area of tiles		
			EN 98
Physical properties			
Water absorption % by weight	Average $6 < E < 10$	Average $6 < E < 10$	EN 99
	Individual max. 11,0	Individual max. 11,0	
Modulus of rupture in N/mm²	Average $> 17,5$	Average $> 17,5$	EN 100
	Individual min. 15	Individual min. 15	
Scratch hardness of surface (Mohs' scale)			
(a) glazed tiles	min. 5	min. 5	EN 101
(b) unglazed tiles	min. 6	min. 6	

1) Not applicable for tiles having curved shapes.

2) Because of firing, slight variations from the standard colour are unavoidable. This does not apply to intentional irregularities of colour variation of the face of extruded tiles (which can be unglazed, glazed or partly glazed) or to the colour variation over a tile area, which is both characteristic for this type of tile and desirable. Spots or coloured dots which are introduced for decorative purposes are not considered a defect.