

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Materials for printed boards and other interconnecting structures –
Part 2-32: Reinforced base materials, clad and unclad – Halogenated modified or
unmodified resin system, woven E-glass laminate sheets of defined relative
permittivity (equal to or less than 3,7 at 1 GHz) and flammability (vertical burning
test), copper-clad**

<https://standards.iteh.ai/catalog/standards/sist/3f96b173-3187-4090-bf63-64b482457c38/iec-61249-2-32-2009>

**Matériaux pour circuits imprimés et autres structures d'interconnexion –
Partie 2-32: Matériaux de base renforcés, plaqués et non plaqués – Feuilles
stratifiées en tissu de verre de type E, en résine isolante halogénée modifiée ou
non, de permittivité relative (inférieure ou égale à 3,7 à 1 GHz) et d'inflammabilité
définies (essai de combustion verticale), plaquées cuivre**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2009 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

[IEC 61249-2-32:2009](tel:+41229190300)

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00



INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Materials for printed boards and other interconnecting structures –
Part 2-32: Reinforced base materials, clad and unclad – Halogenated modified or
unmodified resin system, woven E-glass laminate sheets of defined relative
permittivity (equal to or less than 3,7 at 1 GHz) and flammability (vertical
burning test), copper-clad**

**Matériaux pour circuits imprimés et autres structures d'interconnexion –
Partie 2-32: Matériaux de base renforcés, plaqués et non plaqués – Feuilles
stratifiées en tissu de verre de type E, en résine isolante alogénée modifiée ou
non, de permittivité relative (inférieure ou égale à 3,7 à 1 GHz) et
d'inflammabilité définies (essai de combustion verticale), plaquées cuivre**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

S

CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references.....	6
3 Materials and construction	6
3.1 Resin system.....	6
3.2 Metal foil	7
3.3 Reinforcement.....	7
4 Internal marking.....	7
5 Electrical properties	7
6 Non-electrical properties of the copper-clad laminate	8
6.1 Appearance of the copper-clad sheet.....	8
6.1.1 Indentations (pits and dents).....	8
6.1.2 Wrinkles	8
6.1.3 Scratches	8
6.1.4 Raised areas	9
6.1.5 Surface waviness.....	9
6.2 Appearance of the unclad face.....	9
6.3 Laminate thickness.....	9
6.4 Bow and twist	10
6.5 Properties related to the copper foil bond	11
6.6 Punching and machining	11
6.7 Dimensional stability.....	11
6.8 Sheet sizes.....	12
6.8.1 Typical sheet sizes	12
6.8.2 Tolerances for sheet sizes	12
6.9 Cut panels	12
6.9.1 Cut panel sizes	12
6.9.2 Size tolerances for cut panels	12
6.9.3 Rectangularity of cut panels	12
7 Non-electrical properties of the base material after complete removal of the copper foil.....	13
7.1 Appearance of the dielectric base material.....	13
7.2 Flexural strength.....	13
7.3 Flammability	13
7.4 Water absorption	14
7.5 Measling.....	14
7.6 Glass transition temperature and cure factor	15
8 Quality assurance	15
8.1 Quality system	15
8.2 Responsibility for inspection.....	15
8.3 Qualification inspection.....	15
8.4 Quality conformance inspection	15
8.5 Certificate of conformance	16
8.6 Safety data sheet.....	16
9 Packaging and marking/labelling	16
10 Ordering information	16

ITC STANDARD PREVIEW

(standards.iteh.ai)

IEC 61249-2-32:2009

[https://standards.iteh.ai/catalog/standards/sist/3196b173-3187-4090-b163-](https://standards.iteh.ai/catalog/standards/sist/3196b173-3187-4090-b163-64b482437c38/iec-61249-2-32-2009)

[64b482437c38/iec-61249-2-32-2009](https://standards.iteh.ai/catalog/standards/sist/3196b173-3187-4090-b163-64b482437c38/iec-61249-2-32-2009)

Annex A (informative) Engineering information	17
Annex B (informative) Common laminate constructions.....	19
Annex C (informative) Guideline for qualification and conformance inspection.....	20
Bibliography	21
Table 1 – Electrical properties	7
Table 2 – Nominal thickness and tolerance of metal-clad laminate	10
Table 3 – Bow and twist	10
Table 4 – Pull-off and peel strength	11
Table 5 – Dimensional stability	11
Table 6 – Size tolerances for cut panel	12
Table 7 – Rectangularity of cut panel.....	12
Table 8 – Flexural strength.....	13
Table 9 – Flammability	14
Table 10 – Water absorption	14
Table 11 – Measling	15
Table 12 – Glass transition temperature and cure factor	15

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[IEC 61249-2-32:2009](https://standards.iteh.ai/catalog/standards/sist/3f96b173-3187-4090-bf63-64b482457c38/iec-61249-2-32-2009)

<https://standards.iteh.ai/catalog/standards/sist/3f96b173-3187-4090-bf63-64b482457c38/iec-61249-2-32-2009>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**MATERIALS FOR PRINTED BOARDS AND
OTHER INTERCONNECTING STRUCTURES –**

**Part 2-32: Reinforced base materials, clad and unclad –
Halogenated modified or unmodified resin system, woven E-glass
laminated sheets of defined relative permittivity (equal to or less than 3,7
at 1 GHz) and flammability (vertical burning test), copper-clad**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61249-2-32 has been prepared by IEC technical committee 91: Electronics assembly technology.

The text of this standard is based on the following documents:

FDIS	Report on voting
91/828/FDIS	91/843/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The list of all the parts of the IEC 61249 series, under the general title *Materials for printed boards and other interconnecting structures*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[IEC 61249-2-32:2009](#)

<https://standards.iteh.ai/catalog/standards/sist/3f96b173-3187-4090-bf63-64b482457c38/iec-61249-2-32-2009>

MATERIALS FOR PRINTED BOARDS AND OTHER INTERCONNECTING STRUCTURES –

Part 2-32: Reinforced base materials, clad and unclad – Halogenated modified or unmodified resin system, woven E-glass laminated sheets of defined relative permittivity (equal to or less than 3,7 at 1 GHz) and flammability (vertical burning test), copper-clad

1 Scope

This part of IEC 61249 specifies requirements for properties of modified epoxide woven E-glass laminated sheet of a thickness of 0,05 mm up to 3,2 mm, of defined flammability (vertical burning test), copper-clad. The glass transition temperature is defined to be 150 °C minimum. The relative permittivity is equal to or less than 3,7 and the dissipation factor is equal to or less than 0,007 0 at 1 GHz.

Some property requirements may have several classes of performance. The class desired should be specified in the purchase order; otherwise the default class of material will be supplied.

iTeh STANDARD PREVIEW

2 Normative references (standards.iteh.ai)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61189-2:2006, *Test methods for electrical materials, printed boards and other interconnection structures and assemblies – Part 2: Test methods for materials for interconnection structures*

IEC 61249-5-1:1995, *Materials for interconnection structures – Part 5: Sectional specification set for conductive foils and films with and without coatings – Section 1: Copper foils (for the manufacture of copper-clad base materials)*

ISO 9000, *Quality management systems – Fundamentals and vocabulary*

ISO 11014-1, *Safety data sheet for chemical products – Part 1: Content and order of sections*

ISO 14001, *Environmental management standards – Requirements with guidance for use*

3 Materials and construction

The sheet consists of an insulating base with metal-foil bonded to one side or both.

3.1 Resin system

The resin system is the modified multifunctional epoxide or modified epoxide, with a glass transition temperature of the laminated sheet at 150 °C minimum. The flammability rating is achieved through the use of bromine reacted into the polymer. Inorganic fillers may be used.

Contrast agents may be added to assist processing such as Automated Optical Inspection (AOI).

The resin system should be modified to satisfy the electrical properties requirement of Clause 5.

The flame resistance of the material is defined in terms of the flammability requirements of 7.3.

3.2 Metal foil

The metal foil is made of copper as specified in IEC 61249-5-1, copper foil (for the manufacture of copper-clad materials). The preferred foils are electro-deposited copper of defined ductility.

3.3 Reinforcement

The reinforcement of the laminate shall be woven E-glass fabric (for the manufacture of prepreg and copper clad materials). A woven E-glass fabric exhibiting lower relative permittivity may be utilized.

4 Internal marking

Not specified.

5 Electrical properties

The electrical property requirements are given in Table 1.

Table 1 – Electrical properties
<https://standards.iteh.ai/catalog/standards/sist/61249-2-32-2009/iec-61249-2-32-2009>

Property	Test method IEC 61189-2	Requirement
Resistance of foil	2E12	As specified in IEC 61249-5-1
Surface resistance after damp heat while in the humidity chamber (optional)	2E03	≥10 000 MΩ
Surface resistance after damp heat and recovery	2E03	≥50 000 MΩ
Volume resistivity after damp heat while in the humidity chamber (optional)	2E04	≥5 000 MΩm
Volume resistivity after damp heat and recovery	2E04	≥10 000 MΩm
Relative permittivity after damp heat and recovery (1 MHz)	2E10	≤4,0
Dissipation factor after damp heat and recovery (1 MHz)	2E10	≤0,005 0
Relative permittivity at high frequency (1 GHz)	2E10	≤3,7
Dissipation factor at high frequency (1 GHz)	2E10	≤0,0070
Electric strength (only for material thickness less than 0,5 mm)	2E11	≥30 kV/mm

Property	Test method IEC 61189-2	Requirement
Arc resistance	2E14	≥60 s
Dielectric breakdown (only for material thicknesses ≥0,5 mm)	2E15	≥40 kV
Surface resistance at 125 °C	2E07	≥1 000 MΩ
Volume resistivity at 125 °C	2E07	≥1 000 MΩm

6 Non-electrical properties of the copper-clad laminate

6.1 Appearance of the copper-clad sheet

The copper-clad face shall be substantially free from defects that may have an impact on the fitness of the material for use for the intended purpose.

For the following specific defects, the requirements given shall apply when inspection is made in accordance with IEC 61189-2 method 2M18.

6.1.1 Indentations (pits and dents)

The size of an indentation, usually the length, shall be determined and given a point value to be used as a measure of the quality.

Size mm	Point value for each indentation
0,13 – 0,25	1
0,26 – 0,50	2
0,51 – 0,75	4
0,76 – 1,00	7
Over 1,00	30

The total point count for any 300 mm × 300 mm area laminate shall be calculated to determine the class of the material.

Class A	29 maximum
Class B	17 maximum
Class C	5 maximum
Class D	0
Class X	To be agreed upon by user and supplier

The required class of material shall be specified in the purchase order. Class A applies unless otherwise specified.

6.1.2 Wrinkles

There shall be no wrinkles in the copper surface.

6.1.3 Scratches

Scratches deeper than 20 % of the nominal thickness of the foil thickness are not allowed.

Scratches with a depth less than 5 % of the nominal thickness of the foil shall not be counted unless this depth is 10 µm or more.

Scratches with a depth between 5 % and 20 % of the nominal thickness of the foil are permitted to a total length of 100 mm for a 300 mm × 300 mm area.

6.1.4 Raised areas

Raised areas are usually impressions in the press plates used during manufacture but may also be caused by blisters or inclusions of foreign particles under the foil.

Raised areas caused by blisters or inclusions are not allowed.

Raised areas being impressions of defects in press plates are permitted to the following extent:

Class A and X material	Maximum height of 15 µm and maximum length of 15 mm;
Class B and C material	Maximum height of 8 µm and maximum length of 15 mm;
Class D material	Maximum height of 5 µm and maximum length of 15 mm.

6.1.5 Surface waviness

When examined in accordance with test method 2M12 of IEC 61189-2, the surface waviness in both the machine and cross machine direction shall not exceed 7 µm.

6.2 Appearance of the unclad face

The unclad face of single side clad sheet shall have the natural appearance resulting from the curing process. Small irregularities in colour are allowed. The gloss of the unclad face shall be that given by the press plate or release foil used. Variations of gloss due to the impact of pressure of gases released during the curing are allowed.

6.3 Laminate thickness

The laminate thickness may be ordered to include or exclude the copper foil contribution as specified in the purchase order. As a general rule, laminates less than 0,8 mm are measured excluding copper and laminates greater or equal to 0,8 mm are measured including copper. If the copper-clad laminate is tested in accordance with test method 2D01 of IEC 61189-2, the thickness shall not depart from the nominal thickness by more than the appropriate value given in Table 2. The fine tolerances shall apply unless another tolerance is ordered.

Table 2 – Nominal thickness and tolerance of metal-clad laminate

Nominal thickness excluding metal foil, (material intended for multilayer boards) mm	Nominal thickness including metal foil (material intended for single or double sided boards) mm	Tolerance requirement ±mm		
		Coarse	Fine	Extra Fine
≥0,05 ≤0,10		0,03	0,02	0,01
>0,10 ≤0,15		0,04	0,03	0,02
>0,15 ≤0,30		0,05	0,04	0,03
>0,30 ≤0,50		0,08	0,05	0,04
>0,50 ≤0,80		0,09	0,06	0,05
>0,80 ≤1,00	≥0,80 ≤1,00	0,13	0,09	0,07
>1,00 ≤1,30	>1,00 ≤1,30	0,17	0,11	0,08
	>1,30 ≤1,70	0,20	0,13	0,10
	>1,70 ≤2,10	0,23	0,15	0,12
	>2,10 ≤2,60	0,25	0,18	0,15
	>2,60 ≤3,20	0,30	0,20	0,15

The thickness and tolerances are not applicable to the outer 25 mm of the trimmed master sheet or the outer 13 mm of the cut-to-size panel as manufactured and delivered by the supplier. At no point shall the thickness vary from the nominal by a value greater than 125 % of the specified tolerance.

6.4 Bow and twist

When the copper-clad laminate is tested in accordance with test method 2M01 of IEC 61189-2 the bow and twist shall not exceed the values given in Table 3.

Table 3 – Bow and twist

Property	Test method IEC 61189-2	Nominal thickness mm	Panel dimension longest side mm	Requirement %	
				Copper foil on one side	Copper foil on both sides
Bow and twist	2M01	≥0,8 ≤1,3	≤350	≤2,0	≤1,5
			>350 ≤500	≤1,8	≤1,3
			> 500	≤1,5	≤1,0
		>1,3 <1,7	≤350	≤1,5	≤1,0
			>350 ≤500	≤1,3	≤0,8
			>500	≤1,0	≤0,5
		≥1,7 ≤3,2	≤350	≤1,0	≤0,5
			>350 ≤500	≤0,8	≤0,4
			>500	≤0,5	≤0,3

NOTE The requirements for bow and twist apply only to one sided copper-clad laminates with maximum foil thickness of 105 µm (915 g/m²) and double sided copper-clad laminates with maximum foil thickness difference of 70 µm (610 g/m²).

Requirements for laminates with copper foil configurations beyond these limits are subject to agreement between purchaser and supplier.

6.5 Properties related to the copper foil bond

Pull-off and peel strength requirements are given in Table 4. These requirements apply to copper foil with a normal profile depth. In the case of low or very low profile copper foil, the requirements shall be at least 50 % of that given in Table 4 as a minimum.

Table 4 – Pull-off and peel strength

Property	Test method IEC 61189-2	Requirement			
		Thickness of the copper foil			
		≤12 μm (≤101 g/m ²)	18 μm (152 g/m ²)	35 μm (305 g/m ²)	≥70 μm (≥610 g/m ²)
Peel strength as received	2M14	≥0,50 N/mm	≥0,60 N/mm	≥0,70 N/mm	≥0,80 N/mm
		No blistering nor delamination			
Peel strength after heat shock of 20 s	2M14	≥0,50 N/mm	≥0,60 N/mm	≥0,70 N/mm	≥0,80 N/mm
		No blistering nor delamination			
Blistering after 20 s heat shock	2C05	No blistering nor delamination			

NOTE In case of difficulty due to breakage of the foil or reading range of the force measuring device, the measurement of peel strength at high temperature may be carried out using conductor widths of more than 3 mm.

iTech STANDARD PREVIEW
(standards.itech.ai)

6.6 Punching and machining

Punching is not applicable. The laminate shall, in accordance with the manufacturer's recommendations, be capable of being sheared or drilled. Delamination at the edges due to the shearing process is permissible provided that the depth of delamination is not larger than the thickness of the base material. Delamination at the edges of drilled holes due to the drilling process is not permissible. Drilled holes shall be capable of being through-plated with no interference from any exudations into the hole.

6.7 Dimensional stability

The dimensional stability requirements are given in Table 5. When specimens are tested in accordance with IEC 61189-2 2X02 the observed tolerance shall be as specified in Table 5. The nominal dimensional stability value shall be as agreed upon between user and supplier. The tolerance range agreed upon between user and supplier shall be Class A unless otherwise specified on the purchase order.

The choice of the glass fabrics in the construction of the laminate has a significant impact on dimensional stability. Examples of typical constructions used in printed board applications can be found in Annex B.

Class A performance shall be in effect unless otherwise noted on the purchase order.

Table 5 – Dimensional stability

Property	Test method IEC 61189-2	Class	Requirement ppm
Dimensional stability	2X02	A	±500
		B	±300
		C	±100
		X	As agreed upon between user and supplier