International Standard

8743

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION MEX DYNAPODHAR OPFAHUSALUR ПО СТАНДАРТИЗАЦИИ ORGANISATION INTERNATIONALE DE NORMALISATION

# Grooved pins - Half-length centre grooved

Goupilles cannelées à cannelures centrales constantes sur la moitié de la longueur non débouchantes

First edition — 1986-11-01

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO 8743:1986</u> https://standards.iteh.ai/catalog/standards/sist/d9147438-09ac-490f-bc04f97d77cf0560/iso-8743-1986

## UDC 621.886.12

Ref. No. ISO 8743-1986 (E)

Descriptors : fasteners, pins (mechanics), grooved pins, specifications, dimensions, designation.

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 8743 was prepared by Technical Committee ISO/TC 2, VIEW Fasteners. (standards.iteh.ai)

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated/standards.iteh.ai/catalog/standards/sist/d9147438-09ac-490f-bc04f97d77cf0560/iso-8743-1986

© International Organization for Standardization, 1986

Printed in Switzerland

## INTERNATIONAL STANDARD

## Grooved pins — Half-length centre grooved

# **iTeh STANDARD PREVIEW**

# (standards.iteh.ai) Scope and field of application

### 1

This International Standard specifies the characteristics of half-length centre grooved pins which have three equally spaced grooves impressed longitudinally on their exterior surface, with metric dimensions and nominal diameter, d<sub>1</sub>, from 1,5 to 25 mm inclusive. 50/iso-87

The displaced material to each side of the grooves forming an expanded diameter  $d_2$  which is larger than the nominal diameter  $d_1$  will cause a positive locking fit when these grooved pins are forced into a drilled hole equal to the nominal diameter  $d_1$  (see clause 4).

#### 2 References


ISO 2081, Metallic coatings - Electroplated coatings of zinc on iron or steel.


ISO 3269, Fasteners — Acceptance inspection.

ISO 4520, Chromate conversion coatings on electroplated zinc and cadmium coatings.

ISO 8749, Pins and grooved pins - Shear test.

### **3** Dimensions





									•				Dimen	sions in n	nillimetr
$d_1$		nom.	1,5	2	2,5	3	4	5	6	8	10	12	16	20	25
	tol.		h9							·					
а		~	0,2	0,25	0,3	0,4	0,5	0,63	0,8	1 .	1,2	1,6	2	2,5	3
Minimum shear strength, double <sup>2)</sup> kN		1,6	2,84	4,4	6,4	11,3	17,6	25,4	45,2	70,4	101,8	181	283	444	
	/ <sup>3)</sup>			•			<b></b>	Expande	d diame	ter, $d_2^{4),8}$	5)	<b></b>	ł	1	<b>I</b>
nom.	min.	max.	+ 0,05 0		± 0,05							± 0,10			
8	7,75	8,25	4.00												
10 12	9,75 11,5	10,25 12,5	1,60	iT	eh S	TA		R	PR	FV	FX	<b>7</b>			
14	13,5	14,5			2,60	3,10									
16 18	15,5 17,5	16,5 18,5	1,63	2,10	(	<del>[stai</del>	<b>ida</b> i	<del>ds.</del> i	teh.	ai)					
20	19,5	20,5				3,15	4,15	5,15		·					
22 24	21,5 23,5	22,5 24,5	· .	http://et	2,65	iteh ai/ca	<u>ISO 3</u> talog/stat	3743:198	6,15	138-09a	-490f-b	c04-	· · .	e e la tra	
26	25,5	26,5		2,15	anuarus.	f97(	4.20 177c1056	0/iso-87	43-1986			<u></u>			ъ.
28 30	27,5 29,5	28,5 30,5	$b_{ij} = \frac{1}{2} \left( \frac{1}{2} \right)^{-1}$		4.0	3,20	a ayar a s		6,25	8,20		, * ±	n Saint an		
32 35	31,5 34,5	32,5 35,5				3,20			ta set.	8,25			2		· · ·
40	34,5 39,5	40,5					4,25	E 05			10,20	40.05			
45 50	44,5 49,5	45,5 50,5					l	5,25		8,30		12,25	16,25	20,25	25,2
55	49,5 54,25	50,5 55,75					4,30		6,30	0.05	10,30	12,30	16,30		
60 65	59,25	60,75						5,30		8,35		/		20,30	25,3
65 70	64,25 69,25	65,75 70,75							0.05		10,40				
75 80	74,25 79,25	75,75							6,35			12,40	16,40	20.40	
85	79,25 84,25	80,75 85,75								8,40				20,40	25,4
90 95	89,25 94,25	90,75 95,75									10,45				
95 100	94,25 99,25	95,75 100,75											5		× 1
120 140	119,25 139,25	120,75 140,75										12,50	16,50		_
160	159,25	140,75									10,40			20,50	25,5
180 200	179,25 199,25	180,75													
200	199,25	200,75													

1) The grooving angle 70° applies only to grooved pins made from steel as shown in clause 5. The grooving angle may be modified depending on resilience of material.

2) Applies only to grooved pins made from steel as shown in clause 5.

3) The range of commercial lengths is between the stepped lines.

4) The expanded diameter  $d_2$  applies only to pins made from steel as shown in clause 5. For other materials, for example stainless steel, a reduction amount shall be subtracted from the given values and should be agreed between customer and supplier.

5) For testing  $d_2$ , a GO/NO GO ring gauge should be used.

### Application 4

The bore dimension of the grooved pin hole shall be equal to the nominal diameter,  $d_1$ , of the mating pin, and to tolerance H11.

### Specifications and reference International Standards 5

Material	St = Free-cutting steel, hardness 125 to 245 HV.   Other materials as agreed between customer and supplier.   Form of groove at the discretion of the supplier.							
Grooves								
<u>a fa a de la composition de</u>	Plain, i.e. pins to be supplied in natural finish, treated with a rust-preventative lubricant, unless otherwise specified by agreement between customer and supplier.							
Surface finish	Preferred coatings are black oxide, phosphate coating or zinc plating with chromate conversion coating (see ISO 2081 and ISO 4520). Other coatings as agreed between customer and supplier. All tolerances shall apply prior to the application of a plating or coating.							
Workmanship	Parts shall be uniform in quality and free of irregularities or detrimental defects.							
Shear strength test	The test shall be in accordance with ISO 8749.							
Acceptability	The acceptance procedure is covered in ISO 3269.							

### Designation 6

Example for the designation of a half-length centre grooved steel pin with nominal diameter,  $d_1 = 6$  mm, and nominal length,  $l = 50 \, \text{mm}$  : (standards.iteh.ai)

Grooved pin ISO 8743 - 6  $\times$  50 - St

ISO 8743:1986 https://standards.iteh.ai/catalog/standards/sist/d9147438-09ac-490f-bc04f97d77cf0560/iso-8743-1986