NOTICE: This standard has either been superseded and replaced by a new version or discontinued. Contact ASTM International (www.astm.org) for the latest information.

Designation: C 79/C 79M – 00

Standard Specification for Treated Core and Nontreated Core Gypsum Sheathing Board¹

This standard is issued under the fixed designation C 79/C 79M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This specification covers treated core and nontreated core gypsum sheathing, which is designed to be used as a sheathing on buildings.

1.2 The values stated in either inch-pound or SI (metric) units are to be regarded separately as the standard. Within the text, the SI units are shown in brackets. The values stated in each system shall be used independently of the other. Values from the two systems shall not be combined.

2. Referenced Documents

- 2.1 ASTM Standards:
- C 11 Terminology Relating to Gypsum and Related Building Materials and Systems²
- C 473 Test Methods for Physical Testing of Gypsum Board Products and Gypsum Lath²
- C 645 Specification for Nonstructural Steel Framing Members²
- C 1264/C1264M Specification for Sampling, Inspection, Rejection, Certification, Packaging, Marking, Shipping, Handling, and Storage of Gypsum Board²
- E 119 Test Methods for Fire Tests of Building Construction and Materials³

3. Terminology

3.1 Definitions used in this specification shall be in accordance with Terminology C 11.

4. Materials and Manufacture

4.1 Gypsum sheathing shall consist of a noncombustible core, essentially gypsum, surfaced on both the face and the back with water-repellent paper bonded to the core.

4.1.1 Treated core gypsum sheathing shall have a waterresistant material incorporated into the core.

4.1.2 Nontreated core gypsum sheathing shall not be re-

published as C 79 – 30 T. Last previous edition C 79/C 79M – 97.

² Annual Book of ASTM Standards, Vol 04.01.
³ Annual Book of ASTM Standards, Vol 04.07.

quired to have a water-resistant material incorporated in the core.

4.2 Gypsum Sheathing, Type X (Special Fire-Resistant), designates gypsum sheathing complying with this specification that provides not less than 1-h fire-resistance for boards $\frac{5}{8}$ in. [15.9 mm] thick or $\frac{3}{4}$ -h fire-resistance for boards $\frac{1}{2}$ in. [12.7 mm] thick, applied parallel with and on each side of load bearing 2 by 4 wood studs spaced 16 in. [406 mm] on centers with 6d coated nails, $1\frac{7}{8}$ in. [48 mm] long, 0.0915-in. [2.3-mm] diameter shank, $\frac{1}{4}$ -in. [6.4-mm] diameter heads, spaced 7 in. [178 mm] on center with gypsum sheathing joints staggered 16 in. [406 mm] on each side of the partition and tested in accordance with Test Methods E 119.

NOTE 1—Consult producers for independent test data on assembly details and fire resistance classifications for other types of construction. See official fire test reports for assembly particulars, materials, and classifications.

5. Physical Properties

5.1 Specimens shall be taken from the samples obtained in accordance with 8.1.

1 5.1.1 Specimens shall be tested in accordance with Test Methods C 473.

5.1.2 *Flexural Strength*—The specimens shall be tested face up and face down. The average breaking load shall be not less than the following:

Thickness in. [mm]	Method A Bearing Edges Perp to Panel Length Ibf [N]	Method A Bearing Edges Par to Panel Length Ibf [N]	Method B Bearing Edges Perp to Panel Length Ibf [N]	Method B Bearing Edges Par to Panel Length Ibf [N]
3⁄8 [9.5]	80 [356]	30 [133]	77 [343]	26 [116]
4⁄10 [10.2]	88 [391]	32 [142]	85 [378]	28 [125]
1⁄2 [12.7]	110 [489]	40 [178]	107 [476]	36 [160]
5⁄8 [15.9]	150 [667]	50 [222]	147 [654]	46 [205]

5.1.3 *Humidified Deflection*—The specimens shall have an average deflection of not more than the following:

Thickness in. [mm]	Deflection eighths of an inch [mm]	
³⁄8 [9.5]	15 [48]	
4/10 [10.2]	12 [38]	
1⁄2 [12.7]	10 [32]	
5⁄8 [15.9]	5 [16]	

*A Summary of Changes section appears at the end of this standard.

Copyright © ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States.

¹ This specification is under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.01 on Specifications and Test Methods for Gypsum Products. Current edition approved July 10, 2000. Published September 2000. Originally