



Designation: C 150 – 00

Standard Specification for Portland Cement¹

This standard is issued under the fixed designation C 150; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers eight types of portland cement, as follows (see Note 1):

1.1.1 *Type I*—For use when the special properties specified for any other type are not required.

1.1.2 *Type IA*—Air-entraining cement for the same uses as Type I, where air-entrainment is desired.

1.1.3 *Type II*—For general use, more especially when moderate sulfate resistance or moderate heat of hydration is desired.

1.1.4 *Type IIA*—Air-entraining cement for the same uses as Type II, where air-entrainment is desired.

1.1.5 *Type III*—For use when high early strength is desired.

1.1.6 *Type IIIA*—Air-entraining cement for the same use as Type III, where air-entrainment is desired.

1.1.7 *Type IV*—For use when a low heat of hydration is desired.

1.1.8 *Type V*—For use when high sulfate resistance is desired.

1.2 When both SI and inch-pound units are present, the SI units are the standard. The inch-pound units are approximations listed for information only.

1.3 The text of this standard references notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

2. Referenced Documents

2.1 *ASTM Standards:*

C 33 Specification for Concrete Aggregates²

C 109/C 109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or 50-mm Cube Specimens)³

C 114 Test Methods for Chemical Analysis of Hydraulic Cement³

C 115 Test Method for Fineness of Portland Cement by the Turbidimeter³

C 151 Test Method for Autoclave Expansion of Portland Cement³

C 183 Practice for Sampling and the Amount of Testing of Hydraulic Cement³

C 185 Test Method for Air Content of Hydraulic Cement Mortar³

C 186 Test Method for Heat of Hydration of Hydraulic Cement³

C 191 Test Method for Time of Setting of Hydraulic Cement by Vicat Needle³

C 204 Test Method for Fineness of Hydraulic Cement by Air Permeability Apparatus³

C 226 Specification for Air-Entraining Additions for Use in the Manufacture of Air-Entraining Portland Cement³

C 266 Test Method for Time of Setting of Hydraulic Cement Paste by Gillmore Needles³

C 451 Test Method for Early Stiffening of Hydraulic Cement (Paste Method)³

C 452 Test Method for Potential Expansion of Portland Cement Mortars Exposed to Sulfate³

C 465 Specification for Processing Additions for Use in the Manufacture of Hydraulic Cements³

C 563 Test Method for Optimum SO₃ in Hydraulic Cement Using 24-h Compressive Strength³

C 1038 Test Method for Expansion of Portland Cement Mortar Bars Stored in Water³

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁴

3. Terminology

3.1 *Definitions:*

3.1.1 *portland cement*—a hydraulic cement produced by pulverizing clinker consisting essentially of hydraulic calcium silicates, usually containing one or more of the forms of calcium sulfate as an interground addition.

3.1.2 *air-entraining portland cement*—a hydraulic cement produced by pulverizing clinker consisting essentially of hydraulic calcium silicates, usually containing one or more of the forms of calcium sulfate as an interground addition, and with

¹ This specification is under the jurisdiction of ASTM Committee C01 on Cement and is the direct responsibility of Subcommittee C01.10 on Hydraulic Cements for General Concrete Construction.

Current edition approved Feb. 10, 2000. Published December 2000. Originally published as C 150 – 40 T. Last previous edition C 150 – 99a.

² *Annual Book of ASTM Standards*, Vol 04.02.

³ *Annual Book of ASTM Standards*, Vol 04.01.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

which there has been interground an air-entraining addition.

4. Ordering Information

4.1 Orders for material under this specification shall include the following:

4.1.1 This specification number and date,

4.1.2 Type or types allowable. If no type is specified, Type I shall be supplied,

4.1.3 Any optional chemical requirements from Table 2, if desired,

4.1.4 Type of setting-time test required, Vicat or Gillmore. If not specified, the Vicat shall be used,

4.1.5 Any optional physical requirements from Table 3, if desired.

NOTE 1—Cement conforming to the requirements for all types are not carried in stock in some areas. In advance of specifying the use of cement other than Type I, determine whether the proposed type of cement is, or can be made, available.

5. Additions

5.1 The cement covered by this specification shall contain no addition except as follows:

5.1.1 Water or calcium sulfate, or both, if added, shall be in amounts such that the limits shown in Table 1 for sulfur trioxide and loss-on-ignition are not exceeded.

5.1.2 Processing additions used in the manufacture of the cement shall have been shown to meet the requirements of

Specification C 465 in the amounts used or greater.

5.1.3 Air-entraining portland cement shall contain an inter-ground addition conforming to the requirements of Specification C 226.

6. Chemical Composition

6.1 Portland cement of each of the eight types shown in Section 1 shall conform to the respective standard chemical requirements prescribed in Table 1. In addition, optional chemical requirements are shown in Table 2.

NOTE 2—When comparing oxide analyses and calculated compounds from different sources or from different historic times, be aware that they may not have been reported on exactly the same basis. Chemical data obtained by Reference and Alternate Test Methods of Test Methods C 114 (wet chemistry) may include titania and phosphorus as alumina unless proper correction has been made (see Test Methods C 114), while data obtained by rapid instrumental methods usually do not. This can result in small differences in the calculated compounds. Such differences are usually within the precision of the analytical methods, even when the methods are properly qualified under the requirements of Test Methods C 114.

7. Physical Properties

7.1 Portland cement of each of the eight types shown in Section 1 shall conform to the respective standard physical requirements prescribed in Table 3. In addition, optional physical requirements are shown in Table 4.

TABLE 1 Standard Chemical Requirements

Cement Type ^A	I and IA	II and IIA	III and IIIA	IV	V
Silicon dioxide (SiO ₂), min, %	...	20.0 ^{B,C}
Aluminum oxide (Al ₂ O ₃), max, %	...	6.0
Ferric oxide (Fe ₂ O ₃), max, %	...	6.0 ^{B,C}	...	6.5	...
Magnesium oxide (MgO), max, %	6.0	6.0	6.0	6.0	6.0
Sulfur trioxide (SO ₃), ^D max, %					
When (C ₃ A) ^E is 8 % or less	3.0	3.0	3.5	2.3	2.3
When (C ₃ A) ^E is more than 8 %	3.5	F	4.5	F	F
Loss on ignition, max, %	3.0	3.0	3.0	2.5	3.0
Insoluble residue, max, %	0.75	0.75	0.75	0.75	0.75
Tricalcium silicate (C ₃ S), ^E max, %	35 ^B	...
Dicalcium silicate (C ₂ S), ^E min, %	40 ^B	...
Tricalcium aluminate (C ₃ A) ^E max, %	...	8	15	7 ^B	5 ^C
Tetracalcium aluminoferrite plus twice the tricalcium aluminate ^E (C ₄ AF + 2(C ₃ A)), or solid solution (C ₄ AF + C ₂ F), as applicable, max, %	25 ^C

^A See Note 1.

^B Does not apply when the heat of hydration limit in Table 4 is specified.

^C Does not apply when the sulfate resistance limit in Table 4 is specified.

^D There are cases where optimum SO₃ (using Test Method C 563) for a particular cement is close to or in excess of the limit in this specification. In such cases where properties of a cement can be improved by exceeding the SO₃ limits stated in this table, it is permissible to exceed the values in the table, provided it has been demonstrated by Test Method C 1038 that the cement with the increased SO₃ will not develop expansion in water exceeding 0.020 % at 14 days. When the manufacturer supplies cement under this provision, he shall, upon request, supply supporting data to the purchaser.

^E All values calculated as described in this note shall be rounded according to Practice E 29. When evaluating conformance to a specification, round values to the same number of places as the corresponding table entry before making comparisons. The expressing of chemical limitations by means of calculated assumed compounds does not necessarily mean that the oxides are actually or entirely present as such compounds.

When expressing compounds, C = CaO, S = SiO₂, A = Al₂O₃, F = Fe₂O₃. For example, C₃A = 3CaO·Al₂O₃.

Titanium dioxide and phosphorus pentoxide (TiO₂ and P₂O₅) shall not be included with the Al₂O₃ content. See Note 2.

When the ratio of percentages of aluminum oxide to ferric oxide is 0.64 or more, the percentages of tricalcium silicate, dicalcium silicate, tricalcium aluminate, and tetracalcium aluminoferrite shall be calculated from the chemical analysis as follows:

$$\text{Tricalcium silicate} = (4.071 \times \% \text{CaO}) - (7.600 \times \% \text{SiO}_2) - (6.718 \times \% \text{Al}_2\text{O}_3) - (1.430 \times \% \text{Fe}_2\text{O}_3) - (2.852 \times \% \text{SO}_3)$$

$$\text{Dicalcium silicate} = (2.867 \times \% \text{SiO}_2) - (0.7544 \times \% \text{C}_3\text{S})$$

$$\text{Tricalcium aluminate} = (2.650 \times \% \text{Al}_2\text{O}_3) - (1.692 \times \% \text{Fe}_2\text{O}_3)$$

$$\text{Tetracalcium aluminoferrite} = 3.043 \times \% \text{Fe}_2\text{O}_3$$

When the alumina-ferric oxide ratio is less than 0.64, a calcium aluminoferrite solid solution (expressed as ss(C₄AF + C₂F)) is formed. Contents of this solid solution and of tricalcium silicate shall be calculated by the following formulas:

$$\text{ss}(C_4\text{AF} + C_2\text{F}) = (2.100 \times \% \text{Al}_2\text{O}_3) + (1.702 \times \% \text{Fe}_2\text{O}_3)$$

$$\text{Tricalcium silicate} = (4.071 \times \% \text{CaO}) - (7.600 \times \% \text{SiO}_2) - (4.479 \times \% \text{Al}_2\text{O}_3) - (2.859 \times \% \text{Fe}_2\text{O}_3) - (2.852 \times \% \text{SO}_3)$$

No tricalcium aluminate will be present in cements of this composition. Dicalcium silicate shall be calculated as previously shown.

^F Not applicable.

TABLE 2 Optional Chemical Requirements^A

Cement Type	I and IA	II and IIA	III and IIIA	IV	V	Remarks
Tricalcium aluminate (C ₃ A), ^B max, %	8	for moderate sulfate resistance
Tricalcium aluminate (C ₃ A), ^B max, %	5	for high sulfate resistance
Sum of tricalcium silicate and tricalcium aluminate, ^B max, %	...	58 ^C	for moderate heat of hydration
Equivalent Alkalies (Na ₂ O + 0.658K ₂ O), max, %	0.60 ^D	0.60 ^D	0.60 ^D	0.60 ^D	0.60 ^D	low-alkali cement

^A These optional requirements apply only when specifically requested. Verify availability before ordering. See Note 1 in Section 4.

^B All values calculated as described in this note shall be rounded according to Practice E 29. When evaluating conformance to a specification, round values to the same number of places as the corresponding table entry before making comparisons. The expressing of chemical limitations by means of calculated assumed compounds does not necessarily mean that the oxides are actually or entirely present as such compounds.

When expressing compounds, C = CaO, S = SiO₂, A = Al₂O₃, F = Fe₂O₃. For example, C₃A = 3CaO·Al₂O₃.

Titanium dioxide and phosphorus pentoxide (TiO₂ and P₂O₅) shall not be included with the Al₂O₃ content. See Note 2.

When the ratio of percentages of aluminum oxide to ferric oxide is 0.64 or more, the percentages of tricalcium silicate, dicalcium silicate, tricalcium aluminate, and tetracalcium aluminoferrite shall be calculated from the chemical analysis as follows:

$$\text{Tricalcium silicate} = (4.071 \times \% \text{CaO}) - (7.600 \times \% \text{SiO}_2) - (6.718 \times \% \text{Al}_2\text{O}_3) - (1.430 \times \% \text{Fe}_2\text{O}_3) - (2.852 \times \% \text{SO}_3)$$

$$\text{Dicalcium silicate} = (2.867 \times \% \text{SiO}_2) - (0.7544 \times \% \text{C}_3\text{S})$$

$$\text{Tricalcium aluminate} = (2.650 \times \% \text{Al}_2\text{O}_3) - (1.692 \times \% \text{Fe}_2\text{O}_3)$$

$$\text{Tetracalcium aluminoferrite} = 3.043 \times \% \text{Fe}_2\text{O}_3$$

When the alumina-ferric oxide ratio is less than 0.64, a calcium aluminoferrite solid solution (expressed as ss (C₄AF + C₂F)) is formed. Contents of this solid solution and of tricalcium silicate shall be calculated by the following formulas:

$$\text{ss}(C_4\text{AF} + C_2\text{F}) = (2.100 \times \% \text{Al}_2\text{O}_3) + (1.702 \times \% \text{Fe}_2\text{O}_3)$$

$$\text{Tricalcium silicate} = (4.071 \times \% \text{CaO}) - (7.600 \times \% \text{SiO}_2) - (4.479 \times \% \text{Al}_2\text{O}_3) - (2.859 \times \% \text{Fe}_2\text{O}_3) - (2.852 \times \% \text{SO}_3)$$

No tricalcium aluminate will be present in cements of this composition. Dicalcium silicate shall be calculated as previously shown.

^C The optional limit for heat of hydration in Table 4 shall not be requested when this optional limit is requested.

^D Specify this limit when the cement is to be used in concrete with aggregates that are potentially reactive and no other provisions have been made to protect the concrete from deleteriously reactive aggregates. Refer to Specification C 33 for information on potential reactivity of aggregates.

TABLE 3 Standard Physical Requirements

Cement Type ^A	I	IA	II	IIA	III	IIIA	IV	V
Air content of mortar, ^B volume %:								
max	12	22	12	22	12	22	12	12
min	...	16	...	16	...	16
Fineness, ^C specific surface, m ² /kg (alternative methods):								
Turbidimeter test, min	160	160	160	160	160	160
Air permeability test, min	280	280	280	280	280	280
Autoclave expansion, max, %	0.80	0.80	0.80	0.80	0.80	0.80	0.80	0.80
Strength, not less than the values shown for the ages indicated as follows: ^D								
Compressive strength, MPa (psi):								
1 day	12.0 (1740)	10.0 (1450)
3 days	12.0 (1740)	10.0 (1450)	10.0 (1450)	8.0 (1160)	24.0 (3480)	19.0 (2760)	...	8.0 (1160)
7 days	19.0 (2760)	16.0 (2320)	17.0 (2470)	14.0 (2030)	7.0 (1020)	15.0 (2180)
28 days	17.0 (2470)	21.0 (3050)
Time of setting (alternative methods): ^F								
Gillmore test:								
Initial set, min, not less than	60	60	60	60	60	60	60	60
Final set, min, not more than	600	600	600	600	600	600	600	600
Vicat test: ^G								
Time of setting, min, not less than	45	45	45	45	45	45	45	45
Time of setting, min, not more than	375	375	375	375	375	375	375	375

^A See Note 1.

^B Compliance with the requirements of this specification does not necessarily ensure that the desired air content will be obtained in concrete.

^C The testing laboratory shall select the fineness method to be used. However, when the sample fails to meet the requirements of the air-permeability test, the turbidimeter test shall be used, and the requirements in this table for the turbidimetric method shall govern.

^D The strength at any specified test age shall be not less than that attained at any previous specified test age.

^E When the optional heat of hydration or the chemical limit on the sum of the tricalcium silicate and tricalcium aluminate is specified.

^F The time-of-setting test required shall be specified by the purchaser. In case he does not so specify, the requirements of the Vicat test only shall govern.

^G The time of setting is that described as initial setting time in Test Method C 191.

8. Sampling

8.1 When the purchaser desires that the cement be sampled and tested to verify compliance with this specification, perform sampling and testing in accordance with Practice C 183.

8.2 Practice C 183 is not designed for manufacturing quality control and is not required for manufacturer's certification.