



**SLOVENSKI STANDARD
SIST EN 2622:2002**

01-januar-2002

Aerospace series - Circular tubes, for fluids in heat resisting alloys-Diameter 3,2 mm <= D <= 100 mm - Dimensions

Aerospace series - Circular tubes, for fluids in heat resisting alloys-Diameter 3,2 mm <= D <= 100 mm - Dimensions

Luft- und Raumfahrt - Runde Leitungsrohre aus hochwarmfesten Legierungen - Durchmesser 3,2 mm # D # 100 mm - Maße

Série aérospatiale - Tubes circulaires, pour canalisations en alliages résistant a chaud - Diametres 3,2 mm <= D <= 100 mm - Dimensions

<https://standards.iteh.ai/catalog/standards/sist/95ee166e-3e9e-4554-83d7-c925d92043a3/sist-en-2622-2002>

Ta slovenski standard je istoveten z: EN 2622:2001

ICS:

49.080 Številni sistemi za prenos tekočin in plinov v letalstvu
Aerospace fluid systems and components

SIST EN 2622:2002

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2622:2002

<https://standards.iteh.ai/catalog/standards/sist/95eeff6e-3e9e-4554-83d7-c925d92043a3/sist-en-2622-2002>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 2622

September 2001

ICS 49.080

English version

Aerospace series - Circular tubes, for fluids in heat resisting alloys - Diameter $3,2 \text{ mm} \leq D \leq 100 \text{ mm}$ - Dimensions

Série aérospatiale - Tubes circulaires, pour canalisations en alliages résistant à chaud - Diamètres $3,2 \text{ mm} \leq D \leq 100 \text{ mm}$ - Dimensions

Luft- und Raumfahrt - Runde Leitungsrohre aus hochwarmfesten Legierungen - Durchmesser $3,2 \text{ mm} \leq D \leq 100 \text{ mm}$ - Maße

This European Standard was approved by CEN on 2 May 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

SIST EN 2622:2002

<https://standards.iteh.ai/catalog/standards/sist/95eef66e-3e9e-4554-83d7-c925d92043a3/sist-en-2622-2002>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This European Standard has been prepared by the European Association of Aerospace Manufacturers (AECMA).

After inquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2002, and conflicting national standards shall be withdrawn at the latest by March 2002.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

0 Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

1 Scope

This standard specifies the dimensions and tolerances of:

Circular tubes, for fluids
in heat resisting alloys
Diameter $3,2 \text{ mm} \leq D \leq 100 \text{ mm}$

for aerospace applications.

2 Normative references

This European Standard incorporates by dated or undated reference provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 3848 Aerospace series - Semi-finished metallic products - Method of measuring form deviations.

EN 4258 Aerospace series - Metallic materials - General organization of standardization - Links between types of EN standards and their use

3 Form

See figure 1.




Figure 1

4 Recommended dimensions and mass

4.1 Diameter, thickness and mass

See table 1.

Table 1

Nominal D mm	Linear mass ^a in kg/m for nominal a in mm:									
	0,32	0,40	0,50	0,60	0,80	1,00	1,20	1,60	2,00	2,50
3,2	0,023	0,029	0,034	–	–	–	–	–	–	–
4,0	0,030	0,037	0,045	0,052	–	–	–	–	–	–
5,0	–	0,047	0,057	0,067	0,086	–	–	–	–	–
6,0	–	0,057	0,070	0,082	0,106	–	–	–	–	–
8,0	–	0,077	0,095	0,113	0,147	–	–	–	–	–
10,0	–	0,098	0,121	0,144	0,187	0,229	–	–	–	–
12,0	–	0,118	0,146	0,174	0,228	0,280	–	–	–	–
16,0	–	0,159	0,197	0,235	0,309	0,382	0,452	0,586	–	–
20,0	–	–	–	0,296	0,391	0,483	0,574	0,749	–	–
25,0	–	–	–	0,373	0,493	0,611	0,727	0,953	1,171	1,431
32,0	–	–	–	–	0,635	0,789	0,941	1,238	1,527	1,877
40,0	–	–	–	–	0,798	0,992	1,185	1,563	1,934	2,386
50,0	–	–	–	–	1,002	1,247	1,490	1,971	2,443	3,022
63,0	–	–	–	–	1,266	1,578	1,887	2,5	3,105	3,849
80,0	–	–	–	–	–	2,010	2,406	3,192	3,970	4,930
100,0	–	–	–	–	–	–	–	4,006	4,988	6,203

^a For information, calculated with a density of $8,1 \text{ kg/dm}^3$

4.2 Length

The order shall specify if tubes are to be supplied in fixed or in random lengths. In the event of a supply of random lengths the minimum and maximum values for the lengths shall be specified on the order.

5 Tolerances

5.1 Dimensional tolerances

5.1.1 Diameter

See table 2.

Table 2

Dimensions in millimetres

Diameter	Tolerances
$3,2 \leq D \leq 32$	$\pm 0,08$
$32 < D \leq 50$	$\pm 0,10$
$50 < D \leq 63$	$\pm 0,13$
$63 < D \leq 80$	$\pm 0,18$
$80 < D \leq 100$	$\pm 0,20$

5.1.2 Thickness

See table 3.

Table 3

Dimensions in millimetres

Thickness	Tolerances
0,32 $\leq a \leq 0,5$	$\pm 0,04$
0,5 $< a \leq 1,2$	$\pm 0,05$
1,2 $< a \leq 1,6$	$\pm 0,06$
1,6 $< a \leq 2,0$	$\pm 0,08$
2,0 $< a \leq 2,5$	$\pm 0,10$

5.1.3 Length

See table 4, only applicable to tubes supplied in fixed lengths.

Table 4

Dimensions in millimetres

Length	Tolerances
$l \leq 1\,000$	$+0,05 \times l$ 0
$l > 1\,000$	$+0,1 \times l$ 0

5.2 Geometric tolerances

5.2.1 Straightness

5.2.1.1 Method of measurement and symbols

See EN 3848.

5.2.1.2 Tolerances

See table 5.

Table 5

Dimensions in millimetres

Diameter	Straightness deviation Y_1 per metre
$3,2 \leq D \leq 100$	≤ 2

EN 2622:2001 (E)

5.2.2 Roundness

5.2.2.1 Method of measurement and symbol

See EN 3848.

5.2.2.2 Tolerances

Roundness deviation shall be contained within the outside diameter tolerances.

5.2.3 Eccentricity

5.2.3.1 Method of measurement and symbol

See EN 3848.

5.2.3.2 Tolerances

Eccentricity shall be contained within the thickness tolerances.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 2622:2002](https://standards.iteh.ai/catalog/standards/sist/95eeff6e-3e9e-4554-83d7-c925d92043a3/sist-en-2622-2002)

<https://standards.iteh.ai/catalog/standards/sist/95eeff6e-3e9e-4554-83d7-c925d92043a3/sist-en-2622-2002>