
Aerospace series - Aluminium alloy AL-P7009-T74511 - Extruded bars and sections a or D $\leq$ 125 mm with peripheral coarse grain control

Aerospace series - Aluminium alloy AL-P7009-T74511 - Extruded bars and sections a or D $\leq$ 125 mm with peripheral coarse grain control

Luft- und Raumfahrt - Aluminiumlegierung AL-P7009-T74511 - Stranggepreßte Stangen und Profile a oder D $\leq$ 125 mm mit Kontrolle der Grobkorndrandzone

Série aérospatiale - Alliage d'aluminium AL-P7009-T74511 - Barres et profilés filés a ou D $\leq$ 125 mm avec contrôle de la zone périphérique a gros grains

<https://standards.iteh.ai/catalog/standards/sist/1332c7d3-8f85-4473-864b-845d9d5938bb/sist-en-2630-2001>

Ta slovenski standard je istoveten z: EN 2630:1993

ICS:

49.025.20

Aluminij

Aluminium

SIST EN 2630:2001

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2630:2001

<https://standards.iteh.ai/catalog/standards/sist/1332c7d3-8f85-4473-864b-845d9d5938bb/sist-en-2630-2001>

EUROPEAN STANDARD

EN 2630

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 1993

UDC 669.715-422:620.1:629.7

Descriptors: Aircraft industry, aluminium, aluminium alloys, metal bars, metal sections, extruded products

English version

**Aerospace series - Aluminium alloy
AL-P7009-T74511 - Extruded bars and sections a
or $D \leq 125$ mm with peripheral coarse grain
control**

Série aérospatiale - Alliage d'aluminium
AL-P7009-T74511 - Barres et profilés filés a ou
 $D \leq 125$ mm avec contrôle de la zone
périphérique à gros grains

Luft- und Raumfahrt - Aluminiumlegierung
AL-P7009-T74511 - Stranggeprägte Stangen und
Profile a oder $D \leq 125$ mm mit Kontrolle der
Grobkornrandzone

(standards.iteh.ai)

[SIST EN 2630:2001](https://standards.iteh.ai/catalog/standards/sist/1332c7d3-8f85-4473-864b-845d9d5938bb/sist-en-2630-2001)

<https://standards.iteh.ai/catalog/standards/sist/1332c7d3-8f85-4473-864b-845d9d5938bb/sist-en-2630-2001>

This European Standard was approved by CEN on 1993-12-06. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

.....T010
INTERNATIONAL JOURNAL OF TRAVEL

0 Introduction

For the use of this standard, see EN 2500-2.

1 Scope

This standard specifies the requirements relating to extruded bars and sections in aluminium alloy AL-P7009-, for use in the T74511 condition ¹⁾, a or D ≤ 125 mm, with peripheral coarse grain control, for aerospace applications.

This standard may also be used to supply material in the T74510 condition, if the purchaser specifies this condition on the order. In this case the designation of line 97 shall not be used.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

- | | |
|-----------|--|
| EN 2004-1 | Aerospace series - Test methods for aluminium and aluminium alloy products - Part 1: Determination of electrical conductivity of wrought aluminium alloys |
| EN 2047 | Beaded L- section aluminium alloy extrusions - Dimensions - Aerospace series ²⁾ |
| EN 2048 | L- section aluminium alloy extrusions - Dimensions - Aerospace series ²⁾ |
| EN 2049 | Channel section aluminium alloy extrusions - Dimensions - Aerospace series ²⁾ |
| EN 2050 | T- section aluminium alloy extrusions - Dimensions - Aerospace series ²⁾ |
| EN 2070-3 | Aerospace series - Aluminium and aluminium alloy wrought products - Technical specification - Part 3: Bar and section |
| EN 2134 | Round aluminium alloy bars - Extruded - Dimensions - Aerospace series ²⁾ |
| EN 2341 | Aluminium and aluminium alloy square and rectangular extruded bars - Dimensions - Aerospace series ²⁾ |
| EN 2500-2 | Aerospace series - Instructions for the drafting and use of metallic material standards - Part 2: Specific requirements for aluminium, aluminium alloys and magnesium alloys ³⁾ |
| EN 2600 | Aerospace series - Designation of metallic semi-finished products - Rules ³⁾ |

1) Formerly incompletely designated as T73651

2) Published as AECMA Standard at the date of publication of this standard

3) Published as AECMA Prestandard at the date of publication of this standard

6	6.1 Delivery condition and heat treatment	T74511 $460^{\circ}\text{C} \leq \theta \leq 470^{\circ}\text{C} / \text{WQ } \theta \leq 40^{\circ}\text{C}$ + 1 % $\leq$ stretched $\leq$ 3 % and minor straightening allowable + $115^{\circ}\text{C} \leq \theta \leq 125^{\circ}\text{C} / 20 \text{ h} \leq t \leq 24 \text{ h}$ + $167^{\circ}\text{C} \leq \theta \leq 173^{\circ}\text{C} / 4 \text{ h} \leq t \leq 12 \text{ h}$
	6.2 Delivery condition code	U
7	Use condition and heat treatment	T74511 Delivery condition

8				SIST EN 2630:2001 https://standards.iteh.ai/catalog/standards/sist/1332c7d3-8f85-4473-864b-845d9d5938bb/sist-en-2630-2001							
Sample											
Test piece											
Heat treatment				Use condition: T74511							
9		Dimensions concerned		mm	a or D ≤ 50		50 < a or D ≤ 100		100 < a or D ≤ 125		
10		Thickness of cladding on each face		%	-						
11				Direction of test piece		L	LT	L	LT	L	LT
12		Temperature		θ	°C		Ambient				
13		Proof stress		R _{p0.2}	MPa	≥ 450	≥ 390	≥ 480	≥ 400	≥ 450	≥ 390
14		Strength		R _m	MPa	≥ 510	≥ 460	≥ 530	≥ 470	≥ 510	≥ 460
15		Elongation		A	%	≥ 7 1)	≥ 4 2)	≥ 7	≥ 4	≥ 7	≥ 4
16		Reduction of area		Z	%	-					
17				Hardness		-					
18		Shear strength		R _c	MPa	-					
19		Bending		k	-	-					
20				Impact strength		-					
21		Temperature		θ	°C		-				
22		Time			h		-				
23		Stress		σ _a	MPa	-					
24		Elongation		a	%	-					
25		Rupture stress		σ _R	MPa	-					
26		Elongation at rupture		A	%	-					
27				Notes (see line 98)		1), 2)					

32	Electrical conductivity	1	See EN 2004-1		
		6	Measurement on specimen for tensile test (flat machined surface if necessary)		
		7	$\gamma \geq 22,0 \text{ MS/m}$	Acceptable	
			$21,5 \text{ MS/m} \leq \gamma < 22,0 \text{ MS/m}$	Not acceptable unless a stress corrosion test gives satisfactory results	
			$\gamma < 21,5 \text{ MS/m}$	Not acceptable	
39	Stress corrosion	2	In case of dispute or if $21,5 \text{ MS/m} \leq \gamma < 22,0 \text{ MS/m}$		
		3	$a \text{ or } D \geq 20 \text{ mm}$		
		6	$\sigma = 60\% R_{p0,2} \text{ min. } L / t = 20 \text{ d}$		
44	External defects	-	See EN 2070-3		
51	Macrostructure	7	Back end defects: See EN 2070-3		
			Peripheral coarse grain: level A		
61	Internal defects	-	See EN 2070-3		
82	Batch uniformity	1	See EN 2070-3		
		7	Electrical conductivity	See EN 2070-3	
			or		
		7	Hardness	150 HB (typical value)	
				$\delta \leq 20 \text{ HB per product}$	$\Delta \leq 30 \text{ HB per batch}$
			SIST EN 2630:2001 https://standards.iteh.ai/catalog/standards/sist/1332c7d3-8f85-4473-864b-845d9d5938bb/sist-en-2630-2001		
97	Designation	-	For extruded bars, see EN 2600. For extruded sections, see relevant drawing		
98	Notes	-	1) $A_{50 \text{ mm}} \geq 6\%$ for $a \leq 10 \text{ mm}$ 2) $A_{50 \text{ mm}} \geq 3,5\%$ for $a \leq 10 \text{ mm}$		
99	Typical use	-			