



**SLOVENSKI STANDARD**  
**SIST EN 2638:2019**

**01-september-2019**

---

**Aeronavtika - Aluminijeva zlitina 2024 - T3 - Ekstrudirane palice in profili - 1,2 mm ≤ (a ali D) ≤ 150 mm z nadzorom hrapavosti zunanjih zrn**

Aerospace series - Aluminium alloy 2024-T3 - Extruded bar and section - 1,2 mm ≤ (a or D) ≤ 150 mm with coarse peripheral grain control

Luft- und Raumfahrt - Aluminiumlegierung 2024-T3 - Stranggepresste Stangen und Profile 1,2 mm ≤ (a or D) ≤ 150 mm mit Kontrolle der Grobkornrandzone

Série aérospatiale - Alliage d'aluminium 2024-T3 - Barres et profilés filés - 1,2 mm ≤ (a or D) ≤ 150 mm avec contrôle de la zone périphérique à gros grains

<https://standards.iteh.ai/catalog/standards/sist/7280fc4b-d8fc-4594-be2c-0e774e5bcf71/en-sist-en-2638-2019>

**Ta slovenski standard je istoveten z: EN 2638:2019**

---

**ICS:**

49.025.20      Aluminij                                      Aluminium

**SIST EN 2638:2019**                                      **en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 2638:2019

<https://standards.iteh.ai/catalog/standards/sist/7280fc4b-d8fc-4594-be2c-0c774a5bcf71/sist-en-2638-2019>

EUROPEAN STANDARD

EN 2638

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2019

ICS 49.025.20

English Version

## Aerospace series - Aluminium alloy 2024- - T3 - Extruded bar and section - $1,2 \text{ mm} \leq (a \text{ or } D) \leq 150 \text{ mm}$ with coarse peripheral grain control

Série aérospatiale - Alliage d'aluminium 2024- - T3 -  
Barres et profilés filés -  $1,2 \text{ mm} \leq (a \text{ or } D) \leq 150 \text{ mm}$   
avec contrôle de la zone périphérique à gros grains

Luft- und Raumfahrt - Aluminiumlegierung 2024- - T3 -  
Stranggepresste Stangen und Profile -  $1,2 \text{ mm} \leq (a \text{ or } D) \leq 150 \text{ mm}$  mit Kontrolle der Grobkornrandzone

This European Standard was approved by CEN on 20 August 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

**iTeh STANDARD PREVIEW**

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

<b>Contents</b>	<b>Page</b>
<b>European foreword</b> .....	<b>3</b>
<b>Introduction</b> .....	<b>4</b>
<b>1 Scope</b> .....	<b>5</b>
<b>2 Normative references</b> .....	<b>5</b>
<b>3 Terms and definitions</b> .....	<b>5</b>
<b>4 Requirements</b> .....	<b>6</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 2638:2019](https://standards.iteh.ai/catalog/standards/sist/7280fc4b-d8fc-4594-be2c-0c774a5bcf71/sist-en-2638-2019)

<https://standards.iteh.ai/catalog/standards/sist/7280fc4b-d8fc-4594-be2c-0c774a5bcf71/sist-en-2638-2019>

## European foreword

This document (EN 2638:2019) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2019, and conflicting national standards shall be withdrawn at the latest by November 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/7280fc4b-d8fc-4594-be2c-0c774a5bcf71/sist-en-2638-2019>

EN 2638:2019 (E)

## Introduction

This document is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This document has been prepared in accordance with EN 4500-2.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 2638:2019

<https://standards.iteh.ai/catalog/standards/sist/7280fc4b-d8fc-4594-be2c-0c774a5bcf71/sist-en-2638-2019>

## 1 Scope

This document specifies the requirements relating to:

Aluminium alloy 2024-T3  
Extruded bar and section  
 $1,2 \text{ mm} \leq (a \text{ or } D) \leq 150 \text{ mm}$   
with coarse peripheral grain control

for aerospace applications.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2004-1, *Aerospace series — Test methods for aluminium and aluminium alloy products — Part 1: Determination of electrical conductivity of wrought aluminium alloy products*

EN 2047, *Aerospace series — Beaded L-section extruded, in aluminium alloys — Dimensions*

EN 2048, *Aerospace series — Extruded L-section, in aluminium alloys — Dimensions*

EN 2049, *Aerospace series — Extruded channel section, in aluminium alloys — Dimensions*

EN 2050, *Aerospace series — Extruded T-section, in aluminium alloys — Dimensions*

EN 2070-1, *Aerospace series — Aluminium and aluminium alloy wrought products — Technical specification — Part 1: General requirements*

EN 2070-3, *Aerospace series — Aluminium and aluminium alloy wrought products — Technical specification — Part 3: Bar and section*

EN 2134, *Aerospace series — Round bars, extruded in aluminium and aluminium alloys — Diameter  $10 \text{ mm} \leq D \leq 220 \text{ mm}$  — Dimensions*

EN 2341, *Aerospace series — Aluminium and aluminium alloy — Square and rectangular extruded bars — Dimensions*

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use*

EN 4500-2, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 2: Specific rules for aluminium, aluminium alloys and magnesium alloys*<sup>1</sup>

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>

<sup>1</sup> Published as ASD-STAN Prestandard at the date of publication of this standard by AeroSpace and Defence industries Association of Europe — Standardization (ASD-STAN), <http://www.asd-stan.org/>.

**EN 2638:2019 (E)**

- ISO Online browsing platform: available at <http://www.iso.org/obp>

**4 Requirements**

Table 1 shows the requirements for aluminium alloy 2024-T3 — Extruded bars and sections.

**iTeh STANDARD PREVIEW  
(standards.iteh.ai)**

SIST EN 2638:2019

<https://standards.iteh.ai/catalog/standards/sist/7280fc4b-d8fc-4594-be2c-0c774a5bcf71/sist-en-2638-2019>



**Table 1 — Requirements for aluminium alloy 2024-T3 — Extruded bars and sections**

1	Material designation	Aluminium alloy 2024-T3														
2	Chemical composition %	Element	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ti+Zr	Others		Al Rem.	
		min.	-	-	3,8	0,30	1,2	-	-	-	-	-	-	-		-
		max.	0,50	0,50	4,9	0,9	1,8	0,10	-	0,25	0,15	0,20	0,05	0,15		
3	Method of melting	-														
4.1	Form	Bar and section														
4.2	Method of production	Extruded														
4.3	Limit dimension(s)	mm	$1,2 \leq (a \text{ or } D) \leq 150$													
5	Technical specification	EN 2070-1 and EN 2070-3 EN 2047 to EN 2050 EN 2134 and 2341														

6.1	Delivery condition	T3													
	Heat treatment	Solution treated ( $495 \pm 5$ ) °C/WQ $\theta \leq 40$ °C + cold worked + naturally aged $t \geq 5$ d													
6.2	Delivery condition code	U													
7	Use condition	T3													
	Heat treatment	Delivery condition													

**iTeh STANDARD PREVIEW** Characteristics

8.1	Test sample(s)	-													
8.2	Test piece(s)	-													
8.3	Heat treatment	T3													
9	Dimensions concerned	$a$ or $D$	mm	$\geq 1,2$	$\geq 10$	$\geq 25$	$\geq 75$	$\geq 100$	-						
10	Thickness of cladding on each face	%	-												
11	Direction of test piece	L			L			L			L			L	
12	Temperature	$\theta$	°C	Ambient											
13	Proof stress	$R_{p0,2}$	MPa*	$\geq 330$	$\geq 330$	$\geq 340$	$\geq 330$	$\geq 320$	-						
14	Strength	$R_m$	MPa*	$\geq 440$	$\geq 440$	$\geq 470$	$\geq 460$	$\geq 450$	-						
15	Elongation	A	%	$\geq 12^a$	$\geq 11$	$\geq 10$	$\geq 10$	$\geq 9$	-						
16	Reduction of area	Z	%	-											
17	Hardness	120 HB (for information)													
18	Shear strength	$R_c$	MPa*	-											
19	Bending	k	-	-											
20	Impact strength	-													
21	Temperature	$\theta$	°C	-											
22	Time	h		-											
23	Stress	$\sigma_a$	MPa*	-											
24	Elongation	a	%	-											
25	Rupture stress	$\sigma_R$	MPa*	-											
26	Elongation at rupture	A	%	-											
27	Notes (see line 98)	*, a													