



Standard Specification for Self-Adhering Polymer Modified Bituminous Sheet Materials Used as Steep Roofing Underlayment for Ice Dam Protection¹

This standard is issued under the fixed designation D 1970; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers polymer modified bituminous sheet materials intended for use as underlayment on roof eaves, or valleys, or both, to prevent leakage of shingle, tile, or metal roofs from water back-up due to ice dams.

1.2 These underlayment sheets have a sticky adhesive layer which is exposed by removal of a protective sheet. The top surface is suitable to work on during the application of the exposed roofing.

1.3 The values stated in SI units are to be regarded as standard.

1.4 The following safety hazards caveat pertains to the test methods portion, Section 7, of this standard. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 228 Test Methods for Asphalt Roll Roofing, Cap Sheets, and Shingles²

D 903 Test Method for Peel or Stripping Strength of Adhesive Bonds³

D 1079 Terminology Relating to Roofing, Waterproofing, and Bituminous Materials²

D 1204 Test Method for Linear Dimensional Changes of Nonrigid Thermoplastic Sheeting or Film at Elevated Temperature⁴

D 2523 Practice for Testing Load-Strain Properties of Roofing Membranes²

D 4073 Test Method for Tensile-Tear Strength of Bituminous Roofing Membranes²

D 5147 Test Methods for Sampling and Testing Modified

Bituminous Sheet Material²

E 96 Test Methods for Water Vapor Transmission of Materials⁵

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminology D 1079.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *lot*—for the purpose of sampling, a lot shall consist of all material manufactured in one production run (not to exceed 24 h) using the same source of raw materials.

4. Workmanship, Finish, and Appearance

4.1 The underlayment sheet shall be supplied in roll form.

4.2 The underlayment sheet shall be substantially uniform in thickness and appearance. It shall be free of visible defects such as holes, ragged or untrue edges, breaks, cracks, tears, protuberances, and indentations, except for those perforations or protuberances which are intentional.

4.3 The surface of the underlayment sheet shall be designed to provide traction and slip resistance to the applicator.

NOTE 1—The intent of 4.3 is to recognize that surface slipperiness is important when working on a roof and, while no test method is specified in this standard, several methods for assessing the relative slipperiness of surfaces are available. It is the further intent of this paragraph to ensure that, whatever method is used, the friction coefficient or resistance to slipping of the surface of these products should be at least as great as asphalt-saturated felt shingle underlayment tested under the same conditions of temperature and wetness as agreed between purchaser and seller.

4.4 Sheet sections shall be suitable for joining by the manufacturer's recommended procedure. The entire lower surface of the underlayment sheet shall be capable of being fully adhered to the roof deck.

5. Physical Requirements

5.1 The underlayment sheet shall conform to the physical requirements prescribed in Table 1.

5.2 The underlayment sheet shall not crack nor be so sticky as to cause tearing or other damage upon being unrolled at material temperatures between 4.4 and 60°C (40 and 140°F).

¹ This specification is under the jurisdiction of ASTM Committee D-8 on Roofing, Waterproofing, and Bituminous Materials and is the direct responsibility of Subcommittee D08.02 on Prepared Roofings, Shingles, and Siding Materials.

Current edition approved Jan. 10, 2000. Published March 2000. Originally published as D 1970 – 90. Last previous edition D 1970 – 97.

² Annual Book of ASTM Standards, Vol 04.04.

³ Annual Book of ASTM Standards, Vol 15.06.

⁴ Annual Book of ASTM Standards, Vol 08.01.

⁵ Annual Book of ASTM Standards, Vol 04.06.

TABLE 1 Physical Requirements of Polymer Modified Bitumen Sheets Used as Steep Roofing Underlayment

Property	Inch-Pound	Metric
Thickness, min	40 mils	1.0 mm
Maximum load, min		
Longitudinal	25 lbf/in.	4.4 kN/m
Transverse	25 lbf/in.	4.4 kN/m
Elongation at break, min of modified bitumen portion	10 %	
Adhesion to plywood, min at 40°F	2.0 lbf/ft width	0.92 kgf/30.5 cm
Adhesion to plywood, min at 75°F	12.0 lbf/ft width	5.44 kgf/30.5 cm
Water absorption, max	0.1 %	
Thermal stability, max	0.1 in.	3 mm
Flexibility temperature	-20°F	-29°C
Tear resistance		
Longitudinal, min	20 lbf	89 N
Transverse, min	20 lbf	89 N
Moisture vapor permeability, max	0.1 U.S. Perms	5.7 ng/Pa.S.M. ²
Sealability around nail	pass	
Waterproof integrity after low temperature flexibility	pass	
Waterproof integrity of lap seam	pass	
Slip resistance	Greater than asphalt saturated felt when tested under the same conditions of temperature and wetness (see Note 1)	

6. Sampling

6.1 From each lot of underlayment sheet, select sample rolls in accordance with Test Methods D 228.

6.2 The rolls so selected shall constitute the representative sample used for all subsequent observations and tests pertaining to the lot of material being examined.

7. Test Methods

7.1 *Conditioning*—Unless otherwise specified, condition test specimens for at least 4 h at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5 % relative humidity prior to testing.

7.2 Thickness:

7.2.1 Measure the thickness of the shingle underlayment in accordance with Test Methods D 5147.

7.2.2 Report the number of measurements, the average and standard deviation across the sheet.

7.3 *Maximum Load and Elongation at Break*—This test method covers the determination of the maximum load and elongation at break of the underlayment sheets, as set forth in Practice D 2523 except as noted below.

7.3.1 Specimens:

7.3.1.1 Prepare five specimens from each sample roll in both the longitudinal and transverse directions. Specimens shall be 25 mm (1 in.) ± 5 % wide by a minimum of 150 mm (6 in.) ± 5 % long. For materials with high elongation the length of the sample may be reduced to 100 mm (4 in.) ± 5 % if necessary to avoid limitations imposed by dimensions of the test machine.

7.3.2 Procedure:

7.3.2.1 Condition each specimen at least 2 h at 23 ± 2°C (73.4 ± 3.6°F).

7.3.2.2 Use a constant rate of elongation (CRE) tension testing machine, preferably with automatic load and strain recording equipment and clamps that permit a uniform clamping pressure on the specimen without slipping. The initial clamp separation shall be a minimum of 75 mm (3 in.) ± 5 %

for sheets having an ultimate elongation of 75 % or less at 23.9°C (75°F) and 50 mm (2 in.) ± 5 % for sheets having an ultimate elongation greater than 75 % at 23.9°C (75°F).

7.3.2.3 Maintain a rate of separation of 50 mm (2 in.) ± 3 % per min.

7.3.2.4 Record the percent elongation of each specimen at the visual break of the modified bitumen portion using an extensometer, or mark the extension at visual break of the modified bitumen portion from the chart of the stress versus time (knowing the speed of the chart drive and the jaw separation rate).

7.3.2.5 Record the maximum load attained by each specimen.

7.3.3 Calculation:

7.3.3.1 Determine the percent elongation at break of the modified bitumen portion obtained from the extensometer in accordance with the manufacturer's instructions, or read directly. Calculate the percent elongation from the chart as follows:

$$\% \text{ Elongation} = \frac{a}{b} \times 100 \% \quad (1)$$

where:

a = extension at modified bitumen break (extension at break on chart × jaw separation rate divided by chart speed), and

b = initial jaw separation.

7.3.3.2 Determine the average percent elongation at break of the modified bitumen portion in each direction.

7.3.3.3 Calculate the average *maximum load* in each direction.

7.3.4 *Report*—For each set of five specimens in each direction report the individual measurements, the average and standard deviation for the size of specimen (initial length between jaws), maximum load in kN/m (lbf/in.), percent elongation at modified bitumen break, and method of determining elongation.

7.4 *Adhesion to Plywood*—This test method covers the determination of the adhesive properties of the underlayment sheets to plywood, as set forth in Test Method D 903 except as noted below.

7.4.1 Specimen Preparation:

7.4.1.1 The test specimen shall consist of one piece of underlayment sheet, 75 ± 2 by 200 ± 2 mm (3 ± 0.125 by 8 ± 0.125 in.), bonded for 15 in.² (75 × 125 mm) (3 by 5 in.) to one piece of 6 mm (¼ in.) minimum thick plywood, APA Grade, Exposure 1, 75 by 150 mm (3 by 6 in.). The plywood must not be reused for testing.

7.4.1.2 Roll test specimen three times back and forth with a roller which has a mass of 11.8 kg (26 lb) ± 0.5 %, diameter of 125 mm (5 in.) ± 5 %, and width of 125 mm (5 in.) ± 5 % (2 to 3 s per cycle).

7.4.1.3 At least five specimens shall be tested for each test temperature.

7.4.1.4 It is recommended that specimens be assembled individually. Cutting specimens to size after assembly may influence the test results.

7.4.2 *Conditioning*—Testing is to be performed at two temperatures, 23.9 ± 1.1°C (75 ± 2°F) and 4.4 ± 1.1°C (40 ±