
**Ophthalmic optics — Uncut finished
spectacle lenses —**

Part 3:

Transmittance specifications and test methods

*Optique ophtalmique — Verres de lunettes finis non détournés —
Partie 3: Spécifications relatives au facteur de transmission et méthodes
d'essai*

ISO 8980-3:1999

<https://standards.iteh.ai/catalog/standards/sist/147c81b7-2dfb-4192-82f6-ec69fe245bcc/iso-8980-3-1999>



Contents

1 Scope 1

2 Normative references 1

3 Terms and definitions 1

4 Classification..... 2

5 Requirements 2

6 Testing 4

7 Information to be supplied..... 8

Annex A (normative) Spectral weighting functions for calculating relative visual attenuation quotients 9

Annex B (normative) Calculation of solar UV transmittance values..... 11

Annex C (informative) Spectral radiation risks 13

Bibliography 14

iteh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/147c81b7-2dfb-4192-82f6-ec69fe245bcc/iso-8980-3-1999>

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet iso@iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 8980-3 was prepared by ISO/TC 172, *Optics and optical instruments*, Subcommittee SC 7, *Ophthalmic optics and instruments*.

ISO 8980 consists of the following parts, under the general title *Ophthalmic optics — Uncut finished spectacle lenses*:

— Part 1: *Specifications for single-vision and multifocal lenses*

— Part 2: *Specifications for progressive power lenses*

— Part 3: *Transmittance specifications and test methods*

— Part 4: *Specifications and test methods for anti-reflection coatings*

Annexes A and B form a normative part of this part of ISO 8980. Annex C is for information only.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 8980-3:1999

<https://standards.iteh.ai/catalog/standards/sist/147c81b7-2dfb-4192-82f6-ec69fe245bcc/iso-8980-3-1999>

Ophthalmic optics — Uncut finished spectacle lenses —

Part 3:

Transmittance specifications and test methods

1 Scope

This part of ISO 8980 specifies requirements for the transmittance properties of uncut finished spectacle lenses.

This part of ISO 8980 is not applicable to:

- spectacle lenses having particular transmittance or absorption characteristics prescribed for medical reasons;
- products where specific personal protective equipment transmittance standards apply.

NOTE Optical and geometric requirements for uncut finished spectacle lenses are specified in ISO 8980-1 and ISO 8980-2.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 8980-3:1999

2 Normative references

<https://standards.iteh.ai/catalog/standards/sist/147c81b7-2dfb-4192-82f6-ec69fe245bcc/iso-8980-3-1999>

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 8980. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 8980 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 13666:1998, *Ophthalmic optics — Spectacle lenses — Vocabulary*.

ISO 14889:1997, *Ophthalmic optics — Fundamental requirements for uncut finished spectacle lenses*.

ISO/CIE¹⁾ 10526:1991, *CIE standard colorimetric illuminants*.

ISO/CIE 10527:1991, *CIE standard colorimetric observers*.

3 Terms and definitions

For the purposes of this part of ISO 8980, the terms and definitions given in ISO 13666 apply.

1) International Commission on Illumination, Kegelgasse 27, A-1030 Vienna.

4 Classification

Spectacle lenses are classified with respect to transmittance as follows:

- a) clear spectacle lenses;
- b) uniformly tinted spectacle lenses;
- c) gradient-tinted spectacle lenses;
- d) photochromic spectacle lenses;
- e) polarizing spectacle lenses.

NOTE Two or more of the above classifications may be combined.

5 Requirements

5.1 General

The requirements shall apply at a temperature of 23 °C ± 5 °C, and shall apply to the design reference point, unless specified otherwise. Measurements shall be made with a test beam having a minimum width of 5 mm in any direction.

5.2 General transmittance requirements

The general transmittance requirements specified in ISO 14889 shall apply.

Spectacle lenses shall be attributed to one of five luminous transmittance categories as specified in Table 1, and shall be tested as described in clause 6.

NOTE Table 1 also includes the UV requirements for spectacle lenses, but those spectacle lenses of category 0 for which no specific claim is made as to UV transmittance performance are excluded from the UV requirements of Table 1.

Table 1 — Categories for luminous transmittance and the related permissible transmittance in the ultraviolet solar spectral range

Categories	Visible spectral range		Ultraviolet spectral range	
	Range of luminous transmittance τ_V		Maximum value of solar UV-A transmittance τ_{SUA}	Maximum value of solar UV-B transmittance τ_{SUVB}
	from over %	to %	over 315 nm to 380 nm UV-A	over 280 nm to 315 nm UV-B
0	80,0	100	τ_V	τ_V
1	43,0	80,0		0,125 τ_V
2	18,0	43,0		
3	8,0	18,0		0,5 τ_V
4	3,0	8,0		1,0 % absolute

NOTE 1 Photochromic spectacle lenses are usually attributed to two categories, corresponding respectively to the faded state and to the darkened state.

NOTE 2 The UV requirements of photochromic spectacle lenses in the darkened state may be checked in the faded state, if the UV requirements for the darkened state are met in the faded state.

NOTE 3 It is recommended that uniform or gradient tints should be ordered by reference to a manufacturer's identification code, name or reference number.

For categories 0, 1, 2 and 3, the luminous transmittance τ_v of the spectacle lens at the design reference point shall not lie outside the limits of the stated category by more than 2 % absolute.

For category 4, the luminous transmittance τ_v of the spectacle lens at the design reference point shall not lie outside the limits of that category by more than 20 % relative to the stated luminous transmittance.

5.3 Requirements for driving

Spectacle lenses to be used by vehicle drivers shall conform to the specific requirements for transmittance specified in ISO 14889.

5.4 Transmittance requirements for special types of spectacle lenses

5.4.1 Photochromic spectacle lenses

5.4.1.1 General

When tested by the methods described in 6.5, the luminous transmittance values of a photochromic spectacle lens in its faded and in its darkened states shall be used to identify the appropriate categories in accordance with Table 1.

5.4.1.2 Photochromic response

When tested by the methods described in 6.5.3.1 to 6.5.3.3, the ratio of the luminous transmittance of a photochromic specimen (see 6.5.1) in its faded state $\tau_v(0)$ and, after 15 min irradiation, in its darkened state $\tau_v(15)$ shall be at least 1,25. That is:

$$\frac{\tau_v(0)}{\tau_v(15)} \geq 1,25 \quad (1)$$

5.4.1.3 Photochromic response at various temperatures (optional)

If photochromic temperature sensitivity is stated, it shall be determined by measuring the luminous transmittance of the specimen (see 6.5.1) in the darkened state $\tau_v(15)$ using the procedure described in 6.5.3.6 at 5 °C, 23 °C and 35 °C.

NOTE The manufacturer may use additional temperatures, provided this information is given.

5.4.1.4 Photochromic response at moderate light levels (optional)

If the photochromic response at moderate light levels is stated, it shall be determined by measuring the luminous transmittance of the specimen (see 6.5.1) in the darkened state $\tau_v(15)$ using the procedure described in 6.5.3.4 after exposure to the illumination specified in 6.5.2.1 attenuated to an intensity of 30 %.

5.4.2 Polarizing spectacle lenses

When tested by the method described in 6.6, the ratio of the luminous transmittance values of a polarizing spectacle lens measured parallel and perpendicular to the plane of polarization shall be greater than 8:1 for categories 2, 3, 4 and shall be greater than 4:1 for category 1.

If there is a marking on the spectacle lens indicating the plane of polarization, then the actual plane of polarization shall not deviate from this marking by more than $\pm 3^\circ$.

5.4.3 Gradient-tinted spectacle lenses

The stated category for gradient-tinted spectacle lenses shall be determined at the design reference point of the spectacle lens.

NOTE It is recommended that gradient tints be ordered by reference to a manufacturer's identification code, name or reference number.

5.5 Resistance to radiation

Following irradiation as specified in 6.7, the relative change in the luminous transmittance τ_v at the design reference point (for photochromic lenses: in the faded state when tested by the methods described in 6.5.3.1 and 6.5.3.2) shall be less than

$\pm 10\%$ for spectacle lenses of categories 0 and 1 and

$\pm 20\%$ for spectacle lenses of categories 2, 3 and 4.

For photochromic spectacle lenses, the photochromic response $\frac{\tau_v(0)}{\tau_v(15)}$ following irradiation additionally shall be maintained at $\geq 1,25$ (regardless of the category).

6 Testing

6.1 General

This clause specifies type-test methods for transmittance properties of spectacle lenses.

NOTE For purposes of quality control, etc., alternative test methods may be used if shown to be equivalent.

6.2 Spectral transmittance

iTeh STANDARD PREVIEW
(standards.iteh.ai)

The uncertainties of the test methods determining transmittance values shall be

2 % absolute, for transmittance $> 20\%$; [ISO 8980-3:1999](https://standards.iteh.ai/catalog/standards/sist/147c81b7-2dfb-4192-82fb-269fe245bcc/iso-8980-3-1999)
10 % relative, for transmittance $\leq 20\%$

These measurement uncertainties shall be based on a confidence level of 95 %.

6.3 Luminous transmittance and relative visual attenuation quotient

The spectral distribution of standard illuminant D 65 as specified in ISO/CIE 10526 and the luminous efficiency of the average human eye for daylight vision as specified in ISO/CIE 10527 shall be used to determine the luminous transmittance τ_v . When calculating the luminous transmittance τ_v from the spectral transmittance $\tau(\lambda)$, the step width shall not exceed 10 nm.

NOTE 1 The product of the spectral distribution of radiation of the standard illuminant D 65 and the luminous efficiency of the average human eye for daylight vision is given in annex A. Linear interpolation of these values for steps smaller than 10 nm is permissible.

When calculating the relative visual attenuation quotient Q for signal lights from the spectral transmittance $\tau(\lambda)$, the step width shall not exceed 10 nm.

NOTE 2 The products of the spectral distribution of radiation of the signal lights and of standard illuminant D 65 and the spectral luminous efficiency function for daylight vision are given in annex A. Linear interpolation of these values for steps smaller than 10 nm is permissible. Requirements for the relative visual attenuation quotient Q for signal lights are given in ISO 14889.

6.4 Ultraviolet transmittance

The ultraviolet transmittance in the spectral range from 280 nm to 380 nm of the uncut finished spectacle lens shall be determined using a spectrophotometer.

The spectrophotometer shall:

- a) operate over the wavelength range from 280 nm to 380 nm;
- b) have a spectral bandwidth (full width at half-maximum, FWHM) not exceeding 5 nm;
- c) be capable of measuring spectral data at wavelength intervals not greater than 5 nm;
- d) be capable of determining spectral transmittance to within 2,0 % absolute for transmittance > 20 %, and to within 10 % relative for transmittance \leq 20 %.

When calculating bioactinically-weighted solar UV transmittance values τ_{SUVB} from 280 nm to 315 nm and τ_{SUVA} from 315 nm to 380 nm, the step width shall not exceed 5 nm and shall be equal to the spectral bandwidth used for the spectral transmittance measurements.

NOTE The spectral functions for the calculation of the bioactinically-weighted solar ultraviolet transmittance values τ_{SUVA} and τ_{SUVB} defined in ISO 13666 are given in annex B. Linear interpolation of these values for steps smaller than 5 nm is permissible.

6.5 Transmittance properties of photochromic spectacle lenses and photochromic specimens

6.5.1 Test specimens

The test specimens shall be plano spectacle lenses, normally with a reference thickness of 2,0 mm \pm 0,1 mm. If a thickness outside this range is used, the thickness shall be stated. After having undergone careful cleaning, each specimen shall be conditioned as described in 6.5.3.1.

NOTE The base curve is not specified, but should be recorded.

6.5.2 Apparatus

6.5.2.1 Irradiation source, used to darken photochromic spectacle lens.

The irradiation source (solar simulator) shall approximate as closely as practical the spectral power distribution of solar radiation defined as Air Mass (AM) $m = 2$ (see [3] or [11]) at an illuminance of 50 000 lx \pm 3 000 lx and a UV-A Irradiance between 6,5 W/m² and 11 W/m² spectrally integrated over the 315 nm to 380 nm UV range, at the specimen's position. The intensity of the solar simulator shall be monitored to correct for drifts in the output of the source.

See annex C for details of risks associated with solar radiation.

NOTE 1 Care should be taken to ensure the light from the source does not interfere with the transmittance measurements.

NOTE 2 To attenuate the intensity of the light source (solar simulator) for the measurement of the sensitivity of a photochromic spectacle lens at moderate light levels (see 5.4.1.4), a neutral density filter may be used, suitably positioned in the beam.

6.5.2.2 Specimen chamber, to maintain the specimen at the required temperature, 5 °C, 23 °C or 35 °C, to within \pm 2 °C during exposure to the solar simulator.

NOTE 1 A water bath may be used to achieve temperature control. Since immersion of the specimen(s) in water reduces the reflectivity of the surfaces, the transmittance values determined using water immersion may require correction to yield the equivalent "air" values. Calibration of the equipment may be checked using a non-photochromic test sample with refractive index within \pm 0,01 of the refractive index of the specimen.

NOTE 2 If a water bath is used, in order to avoid modifying the photochromic performance due to water absorption into the lens, care should be taken not to immerse specimens longer than necessary.

NOTE 3 Photochromic lenses with comparatively high temperature gradients (e.g. 2 % change of absolute transmission per degree Celsius of temperature variation) may impose the necessity to observe a narrower temperature tolerance than \pm 2 °C while determining the luminous transmittance as described in 6.5.3.

6.5.2.3 Spectrophotometer, capable of recording spectral transmittance data from 280 nm to 780 nm within a time span that does not affect the results.

For determining transmittance properties in the darkened state, the spectrophotometer shall:

- a) have a spectral bandwidth not greater than 5 nm;
- b) be capable of measuring spectral data at wavelength intervals not greater than 5 nm;
- c) be capable of determining spectral transmittance to within 2,0 % absolute for transmittance > 20 %, and to within 10 % relative for transmittance ≤ 20 %.

6.5.3 Determination of luminous transmittance

6.5.3.1 Conditioning

Use the procedure specified by the manufacturer in their product technical information to attain the faded state of the lens. If no procedure is specified by the manufacturer, store the specimen(s) in the dark at $65\text{ °C} \pm 5\text{ °C}$ for 2,0 h $\pm 0,2$ h. Then store the specimen in the dark at $23\text{ °C} \pm 5\text{ °C}$ until required for testing.

6.5.3.2 Luminous transmittance in the faded state

After conditioning and before exposing the specimen to any irradiation source, determine the luminous transmittance $\tau_v(0)$ of the specimen in its faded state, using the apparatus described in 6.5.2 with the specimen at a temperature of $23\text{ °C} \pm 2\text{ °C}$.

6.5.3.3 Luminous transmittance in the darkened state

While maintaining the specimen temperature at $23\text{ °C} \pm 2\text{ °C}$, illuminate the specimen with the irradiation source for $15\text{ min} \pm 0,1\text{ min}$ and determine the luminous transmittance $\tau_v(15)$ of the specimen in the darkened state using the apparatus described in 6.5.2.

6.5.3.4 Luminous transmittance at moderate light levels

When determining the photochromic response at moderate light levels, repeat the procedure described in 6.5.3.1 to 6.5.3.3 at $23\text{ °C} \pm 2\text{ °C}$ with the radiation from the solar simulator specified in 6.5.2.1 attenuated to an intensity of 30 %.

6.5.3.5 Luminous transmittance for driving at night

After conditioning as described in 6.5.3.1 and while maintaining the specimen temperature at $23\text{ °C} \pm 2\text{ °C}$, illuminate the specimen under the conditions described in 6.5.3.4 for $15\text{ min} \pm 1\text{ min}$. Afterwards, depending on the manufacturer's specification, store the specimen at $23\text{ °C} \pm 2\text{ °C}$ for $60\text{ min} \pm 1\text{ min}$ either in the dark or under reduced illumination. Achieve this illumination by using a $15\,000\text{ lx} \pm 750\text{ lx}$ light source to which a cut-off filter passing wavelengths longer than 500 nm has been added. Then determine the luminous transmittance τ_v of the specimen using the apparatus described in 6.5.2.

6.5.3.6 Luminous transmittance at various temperatures

When determining the temperature sensitivity of the specimen(s), repeat the procedure described in 6.5.3.1 to 6.5.3.3 at $5\text{ °C} \pm 2\text{ °C}$ and $35\text{ °C} \pm 2\text{ °C}$.

6.6 Test methods for polarizing spectacle lenses

6.6.1 Mean luminous transmittance

The luminous transmittance value of polarizing lenses shall be determined using unpolarized light or shall be calculated as a mean value of the transmittance values determined for two mutually perpendicular orientations of the polarization plane of the filter.

6.6.2 Ratio of luminous transmittance values

The ratio of the luminous transmittance values parallel and perpendicular to the plane of polarization is determined with radiation polarized parallel and perpendicular to the plane of polarization. For the measurements, a spectrophotometer shall be used in combination with a polarizing medium of known plane of polarization in the ray path.

Before measuring the sample, the spectrophotometer beam should be essentially 100 % linearly polarized by introduction of a suitable polarizing medium and calibrated to 100 %.

6.6.3 Plane of polarization

For the determination of the plane of polarization, a polarizer of known plane of polarization in the light path shall be used, e. g. by the method given in 6.6.3.1 and 6.6.3.2.

6.6.3.1 Apparatus (see Figure 1)

A split-field polarizer, cut to give a $+3^\circ$ to -3° angle about the horizontal. The top and bottom halves of the polarizer shall then be jointed together and glass-mounted. The polarizer shall be capable of being rotated by means of a lever carrying a corresponding pointer. The pointer transverses a scale calibrated in degrees to the left or right of zero. The split fields shall be illuminated from behind by a diffused light source.




Figure 1 — Principle of apparatus for determination of plane of polarization

6.6.3.2 Procedure

Mount the polarizing spectacle lens on the apparatus and orientate the marking vertically for the plane of polarization, i. e. the front towards the split fields on a horizontal register bar, and ensure that the split field appears in the centre of the polarizing spectacle lens by means of vertical adjusters. Move the lever from side to side until the top and bottom halves of the illuminated split-field polarizer appear of equal density when viewed through the lens.

Read off the pointer position to give the deviation in degrees (plus or minus) of the polarizing axis of the lens from the marking direction.