



## Standard Test Method for Determination of Glass Fiber Content in Glass Fiber Reinforced Concrete (GFRC) (Wash-Out Test)<sup>1</sup>

This standard is issued under the fixed designation C 1229; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers determination of the fiber content in an uncured, glass fiber reinforced concrete (GFRC) sample panel.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information only.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

C 1228 Practice for Preparing Coupons for Flexural and Washout Tests on Glass Fiber Reinforced Concrete<sup>2</sup>

### 3. Terminology

#### 3.1 Definition:

3.1.1 *glass fiber reinforced concrete (GFRC)*—a composition of cementitious material, aggregates, water, admixtures, and alkali-resistant glass fiber.

### 4. Significance and Use

4.1 Glass fiber contents, determined by this test method, are useful for quality control of GFRC products to ensure that manufacturing equipment has been set up to deliver the correct proportions of glass fiber reinforcement in a GFRC composite.

### 5. Apparatus

5.1 *Balance*, 2 kg capacity, sensitive to the nearest 0.1 g.

5.2 *Mesh Basket or Strainer*, approximately 30 in.<sup>3</sup> (493 cm<sup>3</sup>) capacity of woven stainless steel wire and mesh size between  $\frac{3}{16}$  (4.5 mm) and  $\frac{1}{16}$  (1.5 mm). Overall dimensions must totally accept the test sample without any overhang, and depth should be approximately twice the thickness of the test

sample. Gage and construction must be such that mesh dimension cannot easily enlarge, allowing glass reinforcement to escape.

5.3 *Drying Chamber*, an oven that can be set at 230°F  $\pm$  10° (110°C  $\pm$  10°), or a muffle furnace set at 900°F  $\pm$  10° (482°C  $\pm$  10°).

5.4 *Razor Knife*, capable of 6 in. blade extension.

5.5 *Splitting Jig*, see Fig. 1.

### 6. Sampling

6.1 Sampling should be in accordance with governing specifications.

### 7. Test Specimens

7.1 Cut the coupons with a razor knife from a freshly cast, damp, uncured sample panel. When cutting out the test coupon, the sample panel shall have sufficient cohesiveness such that: (a) a clean cut can be made without pulling out fibers from the test coupon or the adjacent material, and (b) that material is not lost from the test coupon prior to determining mass.

7.2 The test specimen shall be between 12 in.<sup>2</sup> (78 cm<sup>2</sup>) and 16 in.<sup>2</sup> (103 cm<sup>2</sup>).

### 8. Procedure

8.1 Cut two test coupons with a razor knife from a freshly produced, damp, uncured sample panel as done in Practice C 1228. Place the coupons in a mesh basket of known mass ( $W_1$ ) and record the total mass ( $W_2$ ). The basket and contents are held under a stream of running water and the composite is worked with fingers to break it up. Take care to ensure that no glass is lost. See Fig. 2.

8.2 When all the cement and fine aggregate (if any) are washed away, dry the basket and contents in an oven at 230°F  $\pm$  10° (110°C  $\pm$  10°), (or muffle furnace at 900°F  $\pm$  10° (483°C  $\pm$  10°C) to a constant mass, as determined by taking three measurements at 10 min intervals. After drying, tap the basket of dried glass against the countertop to dislodge adhered sand particles that would induce an error in the glass content measurement. Be careful not to lose any glass particles. The last value of mass is recorded as  $W_3$ , provided it differs from the previous value by less than 0.1 %.

NOTE 1—Microwave ovens should not be used to dry glass fiber.

NOTE 2—If desired or required, a measure of the glass fiber distribution through the thickness of the coupon can be obtained by repeating the

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C-27 on Precast Concrete Products and is the direct responsibility of Subcommittee C27.40 on Glass Fiber Reinforced Concrete Made by the Spray-Up Process.

Current edition approved Oct. 15, 1994. Published December 1994. Originally published as C 1229 – 93. Last previous edition C 1229 – 93.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 04.05.