



Designation: C 297 – 94 (Reapproved 1999)

## Standard Test Method for Flatwise Tensile Strength of Sandwich Constructions<sup>1</sup>

This standard is issued under the fixed designation C 297; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This test method covers the determination of the core flatwise tension strength or the bond between core and facings of an assembled sandwich panel. The test consists of subjecting a sandwich construction to a tensile load normal to the plane of the sandwich, such load being transmitted to the sandwich through thick loading blocks bonded to the sandwich facings or directly to the core.

1.2 The values stated in SI units are to be regarded as the standard. The inch-pound units given may be approximate.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*

E 4 Practices for Force Verification of Testing Machines<sup>2</sup>

### 3. Significance and Use

3.1 For a sandwich panel to function properly, the facings must have a sufficient bond to the core.

3.2 This test method provides information on how well the facings are bonded to the core or the flatwise tensile strength of the core. It is mainly used as a quality control test for bonded sandwich panels.

### 4. Apparatus

4.1 *Test machine*, capable of maintaining a controlled loading rate and indicating the load with an accuracy of  $\pm 1\%$  of the indicated value. The accuracy of the test machine shall be verified in accordance with Practices E 4.

4.2 *Loading fixtures*, the loading fixtures shall be self-aligning and shall not apply eccentric loads. A satisfactory type

of apparatus is shown in Fig. 1. The loading blocks shall be sufficiently stiff to keep the bonded facings essentially flat under load. Loading blocks 40 to 50 mm (1.5 to 2.0 in.) thick have been found to perform satisfactorily.

4.3 *Micrometer, gage, or caliper*, capable of measuring accurately to 0.025 mm (0.001 in.).

### 5. Test Specimens

5.1 Test specimens shall be square or round and equal in thickness to the sandwich panel thickness. All dimensions shall be measured to the nearest 0.25 mm (0.01 in.). Minimum areas for various types of core materials are given below:

5.1.1 For continuous cores, such as balsa wood and foams, the minimum facing area of the specimen shall be 625 mm<sup>2</sup> (1 in.<sup>2</sup>).

5.1.2 For open-celled cores, such as honeycomb, having cells less than 6 mm (0.5 in.), the minimum area shall be 2600 mm<sup>2</sup> (4 in.<sup>2</sup>), and for cells 6 mm (0.5 in.) or greater, the minimum area shall be 5800 mm<sup>2</sup> (9 in.<sup>2</sup>).

5.2 The loading blocks shall be bonded to the facings of the test specimen using a suitable adhesive. Ideally, the bonding temperature and pressure shall not appreciably affect the existing bond between facing and core. The bonding pressure shall not be greater than the original facing to core bonding pressure. If possible, the assembly temperature shall be room temperature or at least 28°C (50°F) lower than that at which the sandwich was originally bonded.

5.3 The number of test specimens and the method of their selection depend on the purpose of the particular test under consideration, and no general rule can be given to cover all cases. However, when specimens are to be used for acceptance tests, at least five specimens shall be tested.

### 6. Conditioning

6.1 When the physical properties of the component materials are affected by moisture, bring the test specimens to constant weight ( $\pm 1\%$ ) before testing, preferably in a conditioning room with temperature and humidity control, and make the tests, preferably, in a room under the same conditions. A temperature of  $23 \pm 3^\circ\text{C}$  ( $73 \pm 5^\circ\text{F}$ ) and a relative humidity of  $50 \pm 5\%$  are recommended.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-30 on Composite Materials and is the direct responsibility of Subcommittee D30.09 on Sandwich Construction.

Current edition approved Nov. 15, 1994. Published January 1995. Originally published as C 297 – 52T. Last previous edition C 297 – 61(1988) <sup>$\epsilon$ 1</sup>.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 03.01.