



Standard Specification for Preformed Flexible Elastomeric Cellular Thermal Insulation in Sheet and Tubular Form¹

This standard is issued under the fixed designation C 534; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers preformed flexible elastomeric cellular thermal insulation in sheet and tubular form. This specification covers materials to be used on commercial or industrial systems with operating temperatures from -57 to 104°C (-70 to 220°F).

1.2 The values stated in SI units are to be regarded as the standard. The inch-pound equivalents of SI units, given in parentheses, may be approximate.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- C 168 Terminology Relating to Thermal Insulating Materials²
- C 177 Test Method for Steady-State Heat Measurements and Thermal Transmission Properties by Means of the Guarded Hot Plate Apparatus²
- C 209 Test Methods for Cellulosic Fiber Insulation Board²
- C 390 Criteria for Sampling and Acceptance of Preformed Thermal Insulation Lots²
- C 335 Test Method for Steady-State Heat Transfer Properties of Horizontal Pipe Insulation²
- C 411 Test Method for Hot-Surface Performance of High-Temperature Thermal Insulation²
- C 447 Practice for Estimating the Maximum Use Temperature of Thermal Insulations²
- C 518 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus²
- C 585 Practice for Inner and Outer Diameters of Rigid Thermal Insulation for Nominal Sizes of Pipe and Tubing²
- C 692 Test Method for Evaluating the Influence of Thermal Insulations on the External Stress Corrosion Cracking

Tendency of Austenitic Steel²

- C 795 Specification for Thermal Insulation for use in Contact with Austenitic Stainless Steel²
- C 871 Test Methods for Chemical Analysis of Thermal Insulation Materials for Leachable Chloride, Fluoride, Silicate, and Sodium Ions²
- C 1045 Practice for Calculating Thermal Properties from Steady-State Heat Flux Measurements²
- C 1058 Practice for Selecting Temperatures for Evaluating and Reporting Thermal Properties of Thermal Insulation²
- C 1114 Test Method for Steady-State Thermal Transmission Properties by Means of the Thin-Heater Apparatus²
- C 1304 Test Method for Assessing the Odor Emissions of Thermal Insulation Materials²
- D 883 Terminology Relating to Plastics³
- D 1622 Test Method for Apparent Density of Rigid Cellular Plastics³
- D 1667 Specification for Flexible Cellular Materials-Vinyl Chloride Polymers and Copolymers (Closed-Cell Foam)³
- E 84 Test Method for Surface Burning Characteristics of Building Materials⁴
- E 96 Test Methods for Water Vapor Transmission of Materials²

3. Terminology

3.1 *Definitions*—Terms used in this specification are defined in Terminology C 168 and in Terminology D 883.

3.2 Definition of Term Specific to This Standard:

3.2.1 *cellular elastomeric foam*—a closed-cell foam made of natural or synthetic rubber, or a mixture of the two, and containing other polymers, other chemicals, or both, which may be modified by organic or inorganic additives. These foams have properties similar to those of vulcanized rubber, namely, (1) the ability to be converted from a thermoplastic to a thermosetting state by cross-linking (vulcanization) and (2) the ability to recover substantially its original shape when strained or elongated.

4. Classification

4.1 The types of preformed flexible elastomeric cellular thermal insulation are designated as follows:

¹ This specification is under the jurisdiction of ASTM Committee C-16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.22 on Organic and Nonhomogeneous Inorganic Thermal Insulation.

Current edition approved March 10, 1999. Published May 1999. Originally published as C 534 - 64T. Last previous edition C 534 - 94.

² *Annual Book of ASTM Standards*, Vol 04.06.

³ *Annual Book of ASTM Standards*, Vol 08.01.

⁴ *Annual Book of ASTM Standards*, Vol 04.07.

4.1.1 *Type I*—Tubular, and

4.1.2 *Type II*—Sheet.

4.2 Use temperature for Type I and Type II is -57 to 104°C (-70 to 220°F).

NOTE 1—Continuous long-term exposure at or above the upper use temperature may cause degradation in the form of loss of flexibility (see 11.1.3).

5. Materials

5.1 These products shall be made of a homogeneous blend of natural or synthetic rubber that may be modified with various thermoplastic or thermosetting resins, plasticizers, modifiers, antioxidants, curatives, blowing agents and other additives. These products are thermoset and not thermoplastic in nature.

5.2 These products are expanded with chemical blowing agents that decompose with the application of heat. The gases produced by these blowing agents are similar to those found in the atmosphere and thus the diffusion rate is not significant. These gases do not change over time and the thermal conductivity of the insulation is stable over time.

5.3 Flexible, elastomeric, cellular thermal insulations shall be of uniform core density and have closed cells. Even though these insulation materials may have a smooth skin surface on one or both sides, they are to be considered homogeneous for the purposes of determining thermal performance.

6. Physical Requirements

6.1 *Qualification Requirements*—Thermal conductivity, water vapor permeability and dimensional stability physical properties listed in Table 1, are defined as qualification requirements (refer to C 390, Section 5, Classification of Requirements and Section 6, Acceptance for Qualification Requirements).

6.2 *Inspection Requirements:*

6.2.1 The requirements for water absorption and flexibility physical properties listed in Table 1 are defined as inspection requirements (refer to C 390, Section 5, Classification of Requirements, and Section 7, Acceptance for Inspection Requirements).

6.2.2 All dimensional requirements are as described in Section 6 and Table 2.

6.2.3 All workmanship, finish and appearance requirements are as described in Section 9.

6.2.4 Compliance with inspection requirements shall be in accordance with Criteria C 390.

6.3 Both Type I and Type II insulations shall conform to the physical property requirements listed in Table 1.

6.4 The material shall be free of objectionable odors at all temperatures within the recommended use range when tested according to Test Method C 1304.

6.5 *Surface Burning Characteristics*—Surface burning characteristics are to be tested for the thickness supplied in accordance with Test Method E 84 and the results are to be reported.

NOTE 2—This test method does not always define the hazard that may be presented by preformed flexible elastomeric cellular thermal insulation under actual fire conditions. It is retained for reference in this standard as lab test data required by some building codes.

NOTE 3—Preformed flexible cellular elastomeric thermal insulation is an organic material and is combustible. It should not be exposed to flames or other ignition sources. The fire performance of the material should be addressed through fire test requirements established by the appropriate governing documents.

7. Standard Shapes, Sizes and Dimensions

7.1 *Type I*—Tubular materials are typically available in 1.52- or 1.83-m (60- or 72-in.) standard lengths, as well as in continuous lengths (see Note 1). Insulation is typically available for diameters up to 200 mm (8 in. nominal pipe size (NPS)) with wall thickness up to 25.4 mm (1 in.).

7.2 *Type II*—Sheet material is available in thicknesses up to 50 mm (2 in.). Sheets are typically available from one or more manufacturers in sizes up to 1.22 m (48 in.) in width and in continuous lengths. Other sizes are available upon request. Individual dimensions shall conform to those specified by the manufacturer.

7.3 Actual dimensions shall be agreed upon between the manufacturer and the purchaser. The procedure section and the pipe and tubing diameter information of Practice C 585 may be beneficial in determining these actual dimensions.

7.4 The insulation tolerances shall conform to Table 2.

8. Surface

8.1 *Type I*—All surfaces (except ends and slits that are mechanically cut) shall have natural skins.

8.2 *Type II*—Sheet material is available either without skins, with skin on one side or with skin on two sides. The surface

TABLE 1 Physical Requirements for Type I (Tubular) and Type II (Sheet)^A

Property	Unit	Type I and Type II
Apparent thermal conductivity, max., at a mean temperature of:	W/m·K (Btu-in./h·ft ² ·°F)	
-29°C (-20°F)		0.0395 (0.27)
-18°C (0°F)		0.0403 (0.28)
24°C (75°F)		0.0432 (0.30)
50°C (120°F)		0.0461 (0.32)
66°C (150°F)		0.0478 (0.33)
Water absorption, max.	% by volume	0.2
Water-vapor permeability, max.	g/Pa·s·m (perm-in.)	4.35× 10 ⁻¹⁰ (0.30)
Flexibility (mandrel bend):		
at 23°C (73.4°F)		Shall not crack
at 0°C (32°F)		
Dimensional stability, max.	% linear change	7.0

^ATable 1 describes two types of flexible elastomeric cellular thermal insulation. The values stated in Table 1 may not always be appropriate as design values. For specific design recommendations using a particular product and for supporting documentation, consult the manufacturer.