

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving –
Sheet 282: Heat-shrinkable, polyolefin sleeving – Stress control

Gaines isolantes souples –
Partie 3: Spécifications pour types particuliers de gaines –
Feuille 282: Gaines thermorétractables en polyoléfine – Contrôle de fatigue



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2010 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

[IEC 60684-3-282:2010](mailto:IEC.60684-3-282:2010)

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00



IEC 60684-3-282

Edition 1.0 2010-06

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving –
Sheet 282: Heat-shrinkable, polyolefin sleeving – Stress control**

**Gaines isolantes souples –
Partie 3: Spécifications pour types particuliers de gaines –
Feuille 282: Gaines thermorétractables en polyoléfine – Contrôle de fatigue**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

J

ICS 29.035.20

ISBN 978-2-88910-962-3

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Designation.....	7
4 Conditions of test.....	7
5 Requirements.....	7
6 Sleeving conformance.....	7
Annex A (informative) Guidance on the available sizes and wall thicknesses.....	9
Table 1 – Property requirements.....	7
Table 2 – Resistance to selected fluids.....	8
Table A.1 – Type A, medium wall.....	9
Table A.2 – Type B, thick wall.....	9

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[IEC 60684-3-282:2010](#)

<https://standards.iteh.ai/catalog/standards/sist/09c8bf8a-491b-4f9c-8515-d17382b3e531/iec-60684-3-282-2010>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FLEXIBLE INSULATING SLEEVING –

**Part 3: Specifications for individual types of sleeving –
Sheet 282: Heat-shrinkable, polyolefin sleeving –
Stress control**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60684-3-282 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

The text of this standard is based on the following documents:

FDIS	Report on voting
15/564/FDIS	15/587/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60684 series, under the general title *Flexible insulating sleeving*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 60684-3-282:2010](#)

<https://standards.iteh.ai/catalog/standards/sist/09cdbf8a-491b-4f9c-8515-d17382b3e531/iec-60684-3-282-2010>

INTRODUCTION

This International Standard is one of a series which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

Part 1: Definitions and general requirements (IEC 60684-1)

Part 2: Methods of test (IEC 60684-2)

Part 3: Specifications for individual types of sleeving (IEC 60684-3)

This standard comprises one of the sheets of Part 3 as follows:

Sheet 282: Heat-shrinkable, polyolefin sleeving – Stress control

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[IEC 60684-3-282:2010](https://standards.iteh.ai/catalog/standards/sist/09c8bf8a-491b-4f9c-8515-d17382b3e531/iec-60684-3-282-2010)

<https://standards.iteh.ai/catalog/standards/sist/09c8bf8a-491b-4f9c-8515-d17382b3e531/iec-60684-3-282-2010>

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 282: Heat-shrinkable, polyolefin sleeving – Stress control

1 Scope

This part of IEC 60684 gives the requirements for two types of heat-shrinkable, polyolefin sleeving, stress control, not flame retarded, with a nominal shrink ratio up to 3:1.

This sleeving has been found suitable for use up to temperatures of 100 °C.

- Type A : Medium wall Internal diameter up to 65,0 mm typically
- Type B : Thick wall Internal diameter up to 95,0 mm typically

These sleeveings are normally supplied in colour black.

Since these types of sleeveings cover a significantly large range of sizes and wall thicknesses, Tables A.1 and A.2 in this standard provides guidance to the range of sizes available. The actual size shall be agreed between the user and the supplier.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application should be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

This sleeving is designed to be used in MV cable accessories and as such electrical performance must be proven as part of the assembly. Examples of this are described in HD 629 and the IEC 60502 series.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60296:2003, *Fluids for electrotechnical applications – Unused mineral insulating oils for transformers and switchgear*

IEC 60502 (all parts), *Power cables with extruded insulation and their accessories for rated voltages from 1 kV ($U_m = 1,2$ kV) up to 30 kV ($U_m = 36$ kV)*

IEC 60684-1:2003, *Flexible insulating sleeving – Part 1: Definitions and general requirements*

IEC 60684-2:1997, *Flexible insulating sleeving – Part 2: Methods of test*
Amendment 1 (2003)
Amendment 2 (2005)

IEC 60757:1983, *Code for designation of colours*

HD 629, *Test requirements on accessories for use on power cables of rated voltages from 3,6/6(7,2)KV up to 20,8/36 (42)KV– Part 1: Cables with extruded insulation*

3 Designation

The sleeving shall be identified by the following designation:

Description	IEC publication number	IEC part number	IEC sheet number	Type	Size (expanded and recovered internal diameter in millimetres)	Colour
↓	↓	↓	↓	↓	↓	↓
Sleeving	IEC 60684	- 3	-282	- A	- 45,0/20,0	- BK

Colour abbreviation shall comply with IEC 60757.

NOTE This information is for labelling only in accordance with IEC 60684-1.

4 Conditions of test

Unless otherwise specified, the sleeving shall be shrunk in a forced air circulation oven for (10 ± 1) min at $200 \text{ °C} \pm 3 \text{ K}$ prior to testing.

5 Requirements

ITeH STANDARD PREVIEW
(standards.iteh.ai)

In addition to the general requirements given in IEC 60684-1, the sleeving shall comply with the requirements of Tables 1 and 2.

<https://standards.iteh.ai/catalog/standards/sist/09cdeb8a-491b-4f9c-8515-d17382b3e531/iec-60684-3-282-2010>

6 Sleeving conformance

Conformance to the requirements of this specification shall normally be based on the results from typical sizes.

- Type A : Recovered ID 25 mm - 30 mm
- Type B : Recovered ID 25 mm - 30 mm

Table 1 – Property requirements

Property	IEC 60684-2 clause or subclause	Units	Max. or min.	Requirements	Remarks
Dimensions – Internal diameter – Wall thickness – Concentricity – expanded – recovered	3 3.1.2 3.3.2 3.3.3	mm mm %	Min. Min.	To be agreed between the purchaser and the supplier 60 85	
Heat shock Tensile strength Elongation at break	6 19.1 and 19.2 19.1 and 19.2	MPa %	Min. Min.	8 175	Heat at $150 \text{ °C} \pm 5 \text{ K}$.
Longitudinal change	9	%	Max.	+5 -10	
Bending at low temperature	14	–	–	No cracking shall be visible.	Test at -40 °C . For strips, the mandrel shall be between 20

Property	IEC 60684-2 clause or subclause	Units	Max. or min.	Requirements	Remarks
					and 22 times the wall thickness. Full section sleeving is tested unfilled and the mandrel shall be between 20 and 22 times the outer diameter.
Dimensional stability on storage	16	-	-	The dimensions shall remain as agreed.	See Clause 1 Scope.
Tensile strength	19.1 and 19.2	MPa	Min.	10	Use a jaw separation rate of 100 mm/min Below 6,5 mm Ø as sleeving. At 6,5 mm Ø and above as dumbbells.
Elongation at break	19.1 and 19.2	%	Min.	200	
Secant modulus at 2 % elongation	19.4	MPa	Max.	100	
Resistance to selected fluids	36				Use the fluids and test temperatures specified in Table 2.
Tensile strength	19.1 and 19.2	MPa	Min.	4	
Elongation at break	19.1 and 19.2	%	Min.	150	
Heat ageing	39				Heat at 135 °C ± 3 K.
Tensile strength	19.1 and 19.2	MPa	Min.	5	
Elongation at break	19.1 and 19.2	%	Min.	200	
Relative permittivity	24		Min.	5 or as agreed between user and supplier	See note.
Volume resistivity at room temperature	23 23.4.2	Ω.m	Min.	10 ⁸ or as agreed between user and supplier	
Long term ageing	50				The ageing temperature shall be 100 °C ± 3 K.
Elongation at break	19.2	%	Min.	100	

NOTE These values are set so as to define the tube as stress controlling and do not indicate any guarantee of suitable performance in an accessory. Further testing by the supplier will be needed to prove this. Note also that the values may change with applied voltage.

Table 2 – Resistance to selected fluids

Test fluid No.	Fluids	Type	Standard or symbol	Immersion temperature °C ± 2 K
1	Insulating oil	Mineral based	IEC 60296	23
2			Isopropyl alcohol	23
3	-	Water	De-ionized	85

Other fluids and/or temperatures may be specified for customers with specific needs. These additional fluids and/or temperatures shall be applicable when incorporated into agreements between the supplier and the customer.

Annex A (informative)

Guidance on the available sizes and wall thicknesses

Table A.1 – Type A, medium wall

Internal diameter		Wall
Expanded Min. mm	Recovered Max. mm	Recovered wall thickness mm
16,0	8,0	1,8
20,0	10,0	1,8
26,0	12,0	2,5
30,0	15,0	2,9
45,0	20,0	3,0
50,0	25,0	3,3
65,0	30,0	3,3

iTeh STANDARD PREVIEW

Table A.2 – Type B, thick wall
(standards.iteh.ai)

Internal diameter		Wall
Expanded Min. mm	Recovered Max. mm	Recovered wall thickness mm
30,0	10,0	2,5
36,0	12,0	3,0
45,0	15,0	3,0
55,0	22,0	3,0
66,0	22,0	3,0
75,0	28,0	3,0
85,0	28,0	3,0
95,0	45,0	3,6