

# SLOVENSKI STANDARD

## SIST EN 2845:2014

01-februar-2014

---

**Aeronautika - Akrilonitril-butadien kavčuk (NBR) - Odporen proti gorivom in sintetičnim oljem - Trdota 50 IRHD**

Aerospace series - Acrylonitrile-butadiene rubber (NBR) - Fuel and synthetic oil resistant  
- Hardness 50 IRHD

Luft- und Raumfahrt - Brennstoff und synthetisches Öl resistente acrylonitrile-butadien Elastomere (NBR) - Härte 50 - Eigenschaften

**ITEH STANDARD PREVIEW**

**(standards.iteh.ai)**

Caoutchouc acrylonitrile-butadiène résistant à l'huile synthétique et au combustible (NBR) - Degré de dureté 50 - Caractéristiques

SIST EN 2845:2014

<https://standards.iteh.ai/catalog/standards/sist/cacf138b-c62d-443d-853e-99eeb1b34515/sist-en-2845-2014>

**Ta slovenski standard je istoveten z: EN 2845:2013**

---

**ICS:**

49.025.40      Guma in polimerni materiali      Rubber and plastics

**SIST EN 2845:2014**

**en**

**iTeh STANDARD PREVIEW  
(standards.iteh.ai)**

SIST EN 2845:2014

<https://standards.iteh.ai/catalog/standards/sist/cafc138b-c62d-443d-853e-99eeb1b34515/sist-en-2845-2014>

**EUROPEAN STANDARD**  
**NORME EUROPÉENNE**  
**EUROPÄISCHE NORM**

**EN 2845**

February 2013

ICS 49.025.40

English Version

**Aerospace series - Acrylonitrile-butadiene rubber (NBR) - Fuel  
and synthetic oil resistant - Hardness 50 IRHD**

Série aérospatiale - Élastomère acrylonitrile butadiène  
(NBR) - Résistant aux carburants et aux huiles  
synthétiques - Dureté 50 DIDE

Luft- und Raumfahrt - Acrylnitril-Butadien-Elastomer (NBR)  
- Beständig gegen Brennstoffe und synthetische Öle -  
Härte 50 IRHD

This European Standard was approved by CEN on 3 November 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

**STANDARD PREVIEW**  
**(standards.iteh.ai)**  
<https://standards.iteh.ai/catalog/standards/sist/cafc138b-c62d-443d-853e-99eeb1b34515/sist-en-2845-2014>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
 COMITÉ EUROPÉEN DE NORMALISATION  
 EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

## Contents

	Page
<b>Foreword</b> .....	<b>3</b>
<b>1 Scope</b> .....	<b>4</b>
<b>2 Normative references</b> .....	<b>4</b>
<b>3 Application of the material</b> .....	<b>4</b>
<b>3.1 General</b> .....	<b>4</b>
<b>3.2 Typical use</b> .....	<b>4</b>
<b>3.3 Temperature range</b> .....	<b>4</b>
<b>4 Properties</b> .....	<b>4</b>
<b>5 Designation</b> .....	<b>6</b>
<b>6 Technical specification</b> .....	<b>6</b>
<b>Bibliography</b> .....	<b>7</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 2845:2014

<https://standards.iteh.ai/catalog/standards/sist/cafc138b-c62d-443d-853e-99eeb1b34515/sist-en-2845-2014>

## Foreword

This document (EN 2845:2013) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2013, and conflicting national standards shall be withdrawn at the latest by August 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 2845:2014

<https://standards.iteh.ai/catalog/standards/sist/cafc138b-c62d-443d-853e-99eeb1b34515/sist-en-2845-2014>

## 1 Scope

This European Standard specifies the properties of acrylonitrile-butadiene rubber (NBR) <sup>1)</sup>, fuel and synthetic oil resistant, hardness 50 IRHD, for aerospace applications.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 3207, *Aerospace series — Rubber compounds — Technical specification*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

## 3 Application of the material

### 3.1 General

The suitability of the material for a specific application shall be determined by complementary tests carried out on the finished product as the properties specified in this standard are obtained from standard test specimens.

### 3.2 Typical use

For applications where resistance to petroleum-based fuels and diester-based lubricants is required.

### 3.3 Temperature range

**iTech STANDARD PREVIEW**  
**(standards.itech.ai)**

- Continuous service : from – 40 °C to 120 °C; [SIST EN 2845:2014](#)  
<https://standards.itech.ai/catalog/standards/sist/cacf138b-c62d-443d-853e-99cc81834515/sist-en-2845-2014>
- Intermittent service : from – 40 °C to 150 °C

## 4 Properties

See Table 1 and Table 2 according to EN 3207.

For qualification, all tests shall be performed.

For batch acceptance, the tests identified with footnote "a" in Table 1 and Table 2 shall be performed.

---

1) Symbol as per ISO 1629.

Table 1 — Test methods

Line	Column		
	1	2	3
	Properties	Units	Requirements
1	Hardness	IRHD	50 <sup>+ 5</sup> <sub>- 4</sub> a
2	—	—	—
3	Density	Mg/m <sup>3</sup>	a, b
4	—	—	—
5	Tensile strength	MPa	10 min. a
6	—	—	—
7	Elongation at break	%	400 min. a
8	—	—	—
9	Modulus at ... % strain	MPa	—
10	—	—	—
11	Tear strength	N/mm	—
12	—	—	—
13	Resistance to low temperatures TR 10	°C	– 25 max.
14	Crystallization	Point	—
15	Compression set		—
15.1	After 24 h to 125 °C	%	35 max. a
15.2	After 70 h to 125 °C		40 max.
16	(standards.iteh.ai)	—	—
17	Ozone resistance Ozone concentration : SIST EN 2845:2014 (4 ± 2) ppbm Elongation of test piece : % Time : h Temperature : ... °C	—	—
18	—	—	—
19	Corrosion and adhesion on metals Time : 168 h Temperature : 100 °C	—	no corrosion no adhesion
20	Corrosion and adhesion on metals		
20.1	Time : ... h Temperature : ... °C Humidity : ... %	—	—
20.2	Time : ... h Temperature : ... °C Humidity : ... %	—	—
21	—	—	—
22	—	—	—
23	—	—	—
24	—	—	—
25	—	—	—
26	—	—	—
27	—	—	—
28	—	—	—
29	—	—	—
30	—	—	—

a Test for batch accepted.

b The value determined for each batch shall not differ from that determined at qualification by more than 0,02 Mg/m<sup>3</sup>.

**Table 2 — Tests**

Line	Column				
	1	2	3	4	5
1	Test media	–	Air	Liquid B, see ISO 1817	Liquid No. 1, see ISO 1817
2	Conditions of exposure in test media	Units	70 h/125 °C	48 h/40 °C	70 h/125 °C
3	Permitted variation of the properties compared to the initial value	Volume	%	–	+ 30 a + 10 0 a
4		Mass	%	–	–
5		Tensile strength	%	– 10 a	–
6		Elongation at break	%	– 45 a	–
7		Hardness	IRHD	+ 12 0 a	0 – 12 a
8		–	–	–	–

a Test for batch acceptance.

# iTeh STANDARD PREVIEW

## (standards.iteh.ai)

## 5 Designation

## EXAMPLE

SIST EN 2845:2014

<https://standards.iteh.ai/catalog/standards/sist/cafc138b-c62d-443d-853e-2845-2014> Identity block

## RUBBER

EN2845

### Number of this standard -

## 6 Technical specification

See EN 3207.