

SLOVENSKI STANDARD
SIST EN 2939:2001**01-januar-2001**

Aerospace series - Screws, 100° countersunk head, offset cruciform recess, threaded to head, in heat resisting steel FE-PA92HT (A286) - Classification: 900 MPa (at ambient temperature) / 650 °C

Aerospace series - Screws, 100° countersunk head, offset cruciform recess, threaded to head, in heat resisting steel FE-PA92HT (A286) - Classification: 900 MPa (at ambient temperature) / 650 °C

Luft- und Raumfahrt - 100° Senkschrauben, Flügelkreuzschlitz, Gewinde bis Kopf, aus hochwarmfestem Stahl FE-PA92HT (A286) - Klasse: 900 MPa (bei Raumtemperatur) / 650 °C

[SIST EN 2939:2001](https://standards.iteh.ai/catalog/standards/sist/0d9678c5-26db-4273-9eb8-3e01b2c61201)

Série aérospatiale - Vis à tête fraisée 100°, empreinte cruciforme déportée, filetées sous tête, en acier résistant à chaud FE-PA92HT (A286) - Classification: 900 MPa (à température ambiante) / 650 °C

Ta slovenski standard je istoveten z: EN 2939:1994

ICS:

49.030.20 Sorniki, vijaki, stebelni vijaki Bolts, screws, studs

SIST EN 2939:2001**en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2939:2001

<https://standards.iteh.ai/catalog/standards/sist/0d9678c5-26db-4273-9eb8-ac576fa84cdc/sist-en-2939-2001>

EUROPEAN STANDARD

EN 2939

NORME EUROPÉENNE

EUROPÄISCHE NORM

August 1994

UDC 621.882.2.091.6-034.018.44:629.7

Descriptors: Aircraft industry, fastener, screw, countersunk head screw, cross recessed screw, heat resistant steel, classification, characteristic, dimension, screw thread, code, designation, marking

English version

Aerospace series - Screws, 100° countersunk head, offset cruciform recess, threaded to head, in heat resisting steel FE-PA92HT (A286) - Classification: 900 MPa (at ambient temperature)/650°C

Série aérospatiale - Vis à tête fraisée 100°, empreinte cruciforme déportée, filetées sous tête, en acier résistant à chaud FE-PA92HT (A286) - Classification: 900 MPa (à température ambiante)/650°C

Luft- und Raumfahrt - 100° Senkschrauben, Flügelkreuzschlitz, Gewinde bis Kopf, aus hochwarmfestem Stahl FE-PA92HT (A286) - Klasse: 900 MPa (bei Raumtemperatur)/650°C

SIST EN 2939:2001

<https://standards.iteh.ai/catalog/standards/sist/0d9678c5-26db-4273-9eb8-ac576fa84cdc/sist-en-2939-2001>

This European Standard was approved by CEN on 1994-08-17. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Foreword

This European Standard has been prepared by the European Association of Aerospace Manufacturers (AECMA).

After inquiries and votes carried out in accordance with the rules of this Association, this Standard has successively received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This standard was submitted for Formal Vote, and the result was positive.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 1995, and conflicting national standards shall be withdrawn at the latest by February 1995.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, United Kingdom.

SIST EN 2939:2001
<https://standards.iteh.ai/catalog/standards/sist/019678c5-2fdb-4273-9eb8-170464710000/standards/en-2939-1994>
AECMA
EUROPEAN ASSOCIATION OF AEROSPACE MANUFACTURERS
1994

1 Scope

This standard specifies the characteristics of screws with 100° countersunk head with offset cruciform recess, threaded to head, in FE-PA92HT, for aerospace applications.

Classification : 900 MPa ¹⁾ / 650 °C ²⁾

2 Normative references

This European Standard incorporates by dated or undated reference provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

- ISO 3353 Aerospace - Rolled threads for bolts - Lead and runout requirements
- ISO 5855-2 Aerospace - MJ threads - Part 2 : Limit dimensions for bolts and nuts
- ISO 7994 Aerospace - Internal drive, offset cruciform recess (Torq-Set [®]) for rotary fastening devices - Metric series
- EN 2398 Heat resisting steel FE-PA92-HT - $R_m \geq 900$ MPa - Bars for machined bolts - $D \leq 25$ mm - Aerospace series ³⁾
- EN 2399 Heat resisting steel FE-PA92-HT - $R_m \geq 900$ MPa - Bars for forged bolts - $D \leq 25$ mm - Aerospace series ³⁾
- EN 2424 Aerospace series - Marking of aerospace products ³⁾
- EN 3043 Aerospace series - Fasteners, externally threaded, in heat resisting steel FE-PA92HT (A286) - Classification : 900 MPa / 650 °C - Manufacturing method optional - Technical specification ⁴⁾

3 Required characteristics

3.1 Configuration - Dimensions - Tolerances - Masses

See figure 1 and tables 1 and 2. Dimensions and tolerances are in millimetres.

3.2 Materials

EN 2398 or EN 2399

-
- 1) Minimum tensile strength of the material at ambient temperature
 2) Maximum test temperature of the parts
 3) Published as AECMA Standard at the date of publication of this standard
 4) Published as AECMA Prestandard at the date of publication of this standard




Figure 1

Table 1

| Code | Thread ¹⁾ Designation | D ± 0,13 | E ²⁾ min. | F min. | G | H ²⁾ min. | K min. | P - 0,08 | Q | | R | | W | | Recess number ISO 7994 |
|------|-------------------------------------|-------------|-------------------------|-----------|------|-------------------------|-----------|-------------|------|-------|------|------|------|------|------------------------------|
| | | | | | | | | | nom. | Tol. | max. | min. | max. | min. | |
| 030 | MJ3x0,5-4h6h | 2,68 | 6 | 5,4 | 4,5 | 1,4 | 0,06 | 0,63 | 2,3 | 0 | 0,4 | 0,2 | 2,4 | 2,15 | R3 |
| 040 | MJ4x0,7-4h6h | 3,55 | 8 | 7,2 | 5,78 | 1,9 | 0,08 | 0,93 | 3 | - 0,5 | 0,4 | 0,2 | 3,27 | 2,92 | R4 |
| 050 | MJ5x0,8-4h6h | 4,48 | 10 | 9 | 7,71 | 2,4 | 0,1 | 0,96 | 3,4 | ± 0,5 | 0,5 | 0,3 | 3,98 | 3,58 | R5 |

1) In accordance with ISO 5855-2
2) Corresponds to maximum condition.


Table 2

| Length code | N ± 0,3 | Thread code | | |
|-------------|------------|--------------------|--------------------|--------------------|
| | | 030 | 040 | 050 |
| | | Mass ¹⁾ | Mass ¹⁾ | Mass ¹⁾ |
| 006 | 6 | 0,43 | 0,84 | |
| 008 | 8 | 0,51 | 0,99 | 1,75 |
| 010 | 10 | 0,60 | 1,15 | 2,00 |
| 012 | 12 | 0,69 | 1,31 | 2,25 |
| 014 | 14 | 0,78 | 1,46 | 2,50 |
| 016 | 16 | 0,87 | 1,62 | 2,75 |
| 018 | 18 | 0,96 | 1,77 | 3,00 |
| 020 | 20 | 1,05 | 1,93 | 3,25 |
| 022 | 22 | 1,14 | 2,08 | 3,50 |
| 024 | 24 | 1,22 | 2,24 | 3,75 |
| 026 | 26 | 1,31 | 2,40 | 4,00 |
| 028 | 28 | 1,40 | 2,55 | 4,25 |
| 030 | 30 | 1,49 | 2,71 | 4,50 |
| 032 | 32 | 1,58 | 2,86 | 4,75 |
| 034 | 34 | 1,67 | 3,02 | 5,00 |
| 036 | 36 | 1,76 | 3,18 | 5,25 |
| 038 | 38 | 1,84 | 3,33 | 5,50 |
| 040 | 40 | 1,93 | 3,49 | 5,75 |
| 042 | 42 | 2,02 | 3,64 | 6,00 |
| 044 | 44 | 2,11 | 3,80 | 6,25 |
| 046 | 46 | 2,20 | 3,96 | 6,50 |
| 048 | 48 | | 4,11 | 6,75 |
| 050 | 50 | | 4,27 | 7,00 |
| 052 | 52 | | 4,42 | 7,25 |
| 054 | 54 | | 4,58 | 7,50 |
| 056 | 56 | | 4,74 | 7,75 |
| 058 | 58 | | | 8,00 |
| 060 | 60 | | | 8,25 |
| 062 | 62 | | | 8,50 |
| 064 | 64 | | | 8,75 |
| 066 | 66 | | | 9,00 |
| 068 | 68 | | | 9,25 |
| 070 | 70 | | | 9,50 |

1) Mass ≈ quoted in kg/1 000 parts

4 Designation

EXAMPLE :



NOTE : If necessary, the code I9005 shall be placed between the description block and the identity block.

5 Marking

EN 2424, style see table 3 and as indicated on figure 1.

iTeh STANDARD PREVIEW
Table 3
(standards.iteh.ai)

| Thread code | Style |
|-------------|-------|
| 030 and 040 | F |
| 050 | C |

6 Technical specification

EN 3043