
Aeronavtika - Toplotno odporna zlitina NI-PH1302 (NiCr20Co13Mo4Ti3Al) - Topilno žarjena in hladno preoblikovana - Palice za kovane vezne elemente - $3 \text{ mm} \leq D \leq 30 \text{ mm}$

Aerospace series - Heat resisting alloy NI-PH1302 (NiCr20Co13Mo4Ti3Al) - Solution treated and cold worked - Bar for forged fasteners - $3 \text{ mm} \leq D \leq 30 \text{ mm}$

Luft- und Raumfahrt - Hochwarmfeste Legierung - NI-PH1302 (NiCr20Co13Mo4Ti3Al) - Lösungsgeglüht und kaltverfestigt - Stangen zum Warmstauchschmieden für Verbindungselemente - $3 \text{ mm} \leq D \leq 30 \text{ mm}$

Série aérospatiale - Alliage résistant à chaud - NI-PH1302 (NiCr20Co13Mo4Ti3Al) - Mis en solution et écroui - Barres pour éléments de fixations forgés - $3 \text{ mm} \leq D \leq 30 \text{ mm}$

Ta slovenski standard je istoveten z: EN 2959:2019

ICS:

49.025.15	Neželezove zlitine na splošno	Non-ferrous alloys in general
-----------	-------------------------------	-------------------------------

SIST EN 2959:2019

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2959:2019

<https://standards.iteh.ai/catalog/standards/sist/d0949e60-1abb-44d5-8335-5eccb1e031c/sist-en-2959-2019>

EUROPEAN STANDARD

EN 2959

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2019

ICS 49.025.15; 49.025.99

English Version

**Aerospace series - Heat resisting alloy NI-PH1302
(NiCr20Co13Mo4Ti3Al) - Solution treated and cold
worked - Bar for forged fasteners - $3 \text{ mm} \leq D \leq 30 \text{ mm}$**

Série aérospatiale - Alliage résistant à chaud - NI-
PH1302 (NiCr20Co13Mo4Ti3Al) - Mis en solution et
écroui - Barres pour éléments de fixations forgés - 3
 $\text{mm} \leq D \leq 30 \text{ mm}$

Luft- und Raumfahrt - Hochwarmfeste Legierung - NI-
PH1302 (NiCr20Co13Mo4Ti3Al) - Lösungsgeglüht und
kaltverfestigt - Stangen zum Warmstauchschmieden
für Verbindungselemente - $3 \text{ mm} \leq D \leq 30 \text{ mm}$

This European Standard was approved by CEN on 6 January 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Requirements	5

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2959:2019

<https://standards.iteh.ai/catalog/standards/sist/d0949e60-1abb-44d5-8335-5eccc1e031c/sist-en-2959-2019>

European foreword

This document (EN 2959:2019) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2019, and conflicting national standards shall be withdrawn at the latest by December 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2959:2019

<https://standards.iteh.ai/catalog/standards/sist/d0949e60-1abb-44d5-8335-5eccc1e031c/sist-en-2959-2019>

Introduction

This document is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This document has been prepared in accordance with EN 4500-003.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 2959:2019](https://standards.iteh.ai/catalog/standards/sist/d0949e60-1abb-44d5-8335-5eccc1e031c/sist-en-2959-2019)

<https://standards.iteh.ai/catalog/standards/sist/d0949e60-1abb-44d5-8335-5eccc1e031c/sist-en-2959-2019>

1 Scope

This document specifies the requirements relating to:

Heat resisting alloy NI-PH1302 (NiCr20Co13Mo4Ti3Al)
Solution treated and cold worked
Bar for forged fasteners
 $3 \text{ mm} \leq D \leq 30 \text{ mm}$

for aerospace applications.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2043, *Aerospace series — Metallic materials — General requirements for semi-finished product qualification (excluding forgings and castings)*

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use*

EN 4500-003, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 003: Specific rules for heat resisting alloys*

EN 4700-002, *Aerospace series — Steel and heat resisting alloys — Wrought products — Technical specification — Part 002 : bar and section¹⁾*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Requirements

See Table 1.

¹⁾ Published as ASD-STAN Prestandard at the date of publication of this standard by AeroSpace and Defence industries Association of Europe — Standardization (ASD-STAN) (<http://www.asd-stan.org/>)

EN 2959:2019 (E)

Table 1 — Requirements for heat resisting alloy NI-PH1302 (NiCr20Co13Mo4Ti3Al)

1	Material designation	Heat resisting alloy NI-PH1302 (NiCr20Co13Mo4Ti3Al)										
2	Chemical composition	Element	C	Si	Mn	P	S	Al	B	Co	Cr	Fe
		min.	0,02	–	–	–	–	1,20	0,003	12,0	18,0	–
	%	max.	0,10	0,15	0,10	0,015	0,008	1,60	0,010	15,0	21,0	2,0
	Element	Mo	Ti	Zr	Ag	Bi	Ca	Cu	Pb	Mg	Ni	
	min.	3,50	2,80	0,02	–	–	–	–	–	–	Base	
max.	5,00	3,30	0,08	5*)	1*)	0,01	0,10	10*)	0,01			
3	Method of melting	Vacuum melted and consumable electrode remelted										
4.1	Form	Bar for forged fasteners										
4.2	Method of production	Wrought										
4.3	Limit dimension(s)	mm	$3 \leq D \leq 30$									
5	Technical specification	See EN 4700-002.										

6.1	Delivery condition	Solution treated, cold worked, straightened and ground										
	Heat treatment	$1\ 010\ ^\circ\text{C} \leq \theta \leq 1\ 080\ ^\circ\text{C} / t \geq 1\ \text{h} / \text{AC}$ or faster + 10 % ≤ cold worked ≤ 30 % at $\theta \leq 870\ ^\circ\text{C}$ + straightened + ground										
6.2	Delivery condition code	U										
7	Use condition	Delivery condition										
	Heat treatment	iTech STANDARD PREVIEW (standards.itech.ai)										

Characteristics

8.1	Test sample(s)	See EN 4700-002.2959:2019										See EN 4700-002.
8.2	Test piece(s)	See EN 4700-002.										See EN 4700-002.
8.3	Heat treatment	Delivery condition										See line 29
9	Dimensions concerned	mm	$3 \leq D \leq 30$									$3 \leq D \leq 30$
10	Thickness of cladding on each face	%	–									–
11	Direction of test piece	–										–
12	Temperature	θ	°C	–								Ambient
13	Proof stress	$R_{p0,2}$	MPa	–								≥ 800
14	T Strength	R_m	MPa	–								≥ 1 210
15	Elongation	A	%	–								≥ 13
16	Reduction of area	Z	%	–								≥ 18
17	Hardness	≤ 385 HV										$320 \leq \text{HV} \leq 410$
18	Shear strength	R_c	MPa	–								–
19	Bending	k	–	–								–
20	Impact strength	–										–
21	Temperature	θ	–	–								730
22	Time		h	–								$t_R \geq 23$
23	Stress	σ_a	–	–								–
24	Elongation	a	–	–								–
25	Rupture stress	σ_R	MPa	–								520
26	Elongation at rupture	A	%	–								≥ 5
27	Notes (see line 98)	*)										

29	Reference heat treatment	-	Delivery condition + 850 °C / t = 4 h / AC or faster + 760 °C / t = 16 h / AC or faster	
34	Grain size	-	See EN 4700-002.	
		7	Grain size number	% of area
			≥ 3	≥ 95
			2 ≤ G < 3	≤ 5
< 2	Not acceptable			
44	External defects	-	See EN 4700-002.	
		1	Visual inspection	
<p>iTeh STANDARD PREVIEW (standards.iteh.ai)</p> <p>SIST EN 2959:2019 https://standards.iteh.ai/catalog/standards/sist/d0949e60-1abb-44d5-8335-5ecccb1e031c/sist-en-2959-2019</p>				
95	Marking inspection	-	See EN 4700-002.	
96	Dimensional inspection	-	See EN 4700-002.	
98	Notes	-	*) p.p.m	
99	Typical use	-	-	