

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE

GROUP SAFETY PUBLICATION  
PUBLICATION GROUPEE DE SÉCURITÉ

Test on gases evolved during combustion of materials from cables –  
Part 2: Determination of acidity (by pH measurement) and conductivity  
(standards.iteh.ai)

Essai sur les gaz émis lors de la combustion des matériaux prélevés sur  
câbles –  
Partie 2: Détermination de la conductivité et de l'acidité (par mesure du pH)



**THIS PUBLICATION IS COPYRIGHT PROTECTED**  
**Copyright © 2011 IEC, Geneva, Switzerland**

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland  
Email: [inmail@iec.ch](mailto:inmail@iec.ch)  
Web: [www.iec.ch](http://www.iec.ch)

## About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

## About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

■ Catalogue of IEC publications: [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

■ IEC Just Published: [www.iec.ch/online\\_news/justpub](http://www.iec.ch/online_news/justpub)

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

■ Electropedia: [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

■ Customer Service Centre: [www.iec.ch/webstore/custserv](http://www.iec.ch/webstore/custserv)

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: [csc@iec.ch](mailto:csc@iec.ch)

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

---

## A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

## A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

■ Catalogue des publications de la CEI: [www.iec.ch/searchpub/cur\\_fut-f.htm](http://www.iec.ch/searchpub/cur_fut-f.htm)

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

■ Just Published CEI: [www.iec.ch/online\\_news/justpub](http://www.iec.ch/online_news/justpub)

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

■ Electropedia: [www.electropedia.org](http://www.electropedia.org)

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

■ Service Clients: [www.iec.ch/webstore/custserv/custserv\\_entry-f.htm](http://www.iec.ch/webstore/custserv/custserv_entry-f.htm)

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: [csc@iec.ch](mailto:csc@iec.ch)

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE

GROUP SAFETY PUBLICATION  
PUBLICATION GROUPEE DE SÉCURITÉ

**Test on gases evolved during combustion of materials from cables –  
Part 2: Determination of acidity (by pH measurement) and conductivity**  
(standards.iteh.ai)

**Essai sur les gaz émis lors de la combustion des matériaux prélevés sur  
câbles –**  
<https://standards.iteh.ai/catalog/standards/sist/7ed836bb-b293-40f6-b43d-51c0e1d1c004/iec-60754-2>  
**Partie 2: Détermination de la conductivité et de l'acidité (par mesure du pH)**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

PRICE CODE  
CODE PRIX

R

ICS 13.220.40; 29.020; 29.060.20

ISBN 978-2-88912-716-0

## CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references.....	7
3 Terms and definitions.....	7
4 Test method principle.....	8
5 Test apparatus.....	8
5.1 General.....	8
5.2 Tube furnace.....	8
5.3 Quartz glass tube.....	8
5.4 Combustion boats.....	8
5.5 Bubbling devices for gases.....	9
5.6 Air supply system.....	9
5.7 Analytical balance.....	10
5.8 Laboratory glassware.....	10
5.9 pH meter.....	10
5.10 Conductivity measuring device.....	10
6 Test specimen.....	10
6.1 General.....	10
6.2 Conditioning of specimen.....	10
6.3 Mass of specimen.....	10
7 Test procedure.....	11
7.1 General.....	11
7.2 Test apparatus and arrangement.....	11
7.3 Heating procedure.....	11
7.4 Washing procedure.....	11
7.5 Determination of the pH value and conductivity.....	11
8 Evaluation of the test results.....	12
8.1 General method.....	12
8.2 Simplified method.....	12
8.3 Weighted values.....	12
8.3.1 Value of pH.....	12
8.3.2 Conductivity.....	13
9 Performance requirement.....	13
10 Test report.....	13
Annex A (informative) Recommended performance requirements.....	19
Bibliography.....	20
Figure 1 – Device for inserting combustion boat and test specimen.....	14
Figure 2 – Example of a gas washing bottle.....	15
Figure 3 – Test apparatus: method 1 – Use of synthetic or compressed air from a bottle.....	16
Figure 4 – Test apparatus: method 2 – Use of laboratory compressed air supply.....	17

Figure 5 – Test apparatus: method 3 – Use of ambient air sucked by means of a suction pump ..... 18

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 60754-2:2011](https://standards.iteh.ai/catalog/standards/sist/7ed836bb-b293-40f6-b43d-5b1c0ca16b5d/iec-60754-2-2011)

<https://standards.iteh.ai/catalog/standards/sist/7ed836bb-b293-40f6-b43d-5b1c0ca16b5d/iec-60754-2-2011>

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

**TEST ON GASES EVOLVED DURING  
COMBUSTION OF MATERIALS FROM CABLES –****Part 2: Determination of acidity  
(by pH measurement) and conductivity**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60754-2 has been prepared by IEC technical committee 20: Electric cables.

It has the status of a group safety publication in accordance with IEC Guide 104.

This second edition of IEC 60754-2 cancels and replaces the first edition, published in 1991, Amendment 1 (1997), and constitutes a technical revision.

The significant technical changes with respect to the previous edition are as follows:

- improved definition of safety requirements relating to capture of gases;
- introduction of guidance on the preparation of test specimens for more even combustion;
- better expression of tolerances and precision;
- clarification of the conductivity and acidity functions;

- improved definition of the heating procedure;
- greater precision in the definition of the test temperature for the determination of pH value and conductivity;
- correction of the formulae for the calculation of the test results.

The text of this standard is based on the following documents:

FDIS	Report on voting
20/1265/FDIS	20/1275/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60754 series, published under the general title *Test on gases evolved during combustion of materials from cables*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**  
<https://standards.iteh.ai/catalog/standards/sist/7ed836bb-b293-40f6-b43d-5b1c0ca16b5d/iec-60754-2-2011>

## INTRODUCTION

IEC 60754 consists of the following parts, under the general title *Test on gases evolved during combustion of materials from cables*:

- Part 1: *Determination of the halogen acid gas content*
- Part 2: *Determination of acidity (by pH measurement) and conductivity.*

IEC 60754-2 was originally developed due to concerns expressed by cable users over the amount of acid gas evolved when some cable insulating, sheathing and other materials are burned, as such corrosive effluent can cause extensive damage to electrical and electronic equipment not involved in the fire itself.

NOTE Guidance on the corrosivity of fire effluent is given in IEC 60695-5-1.

This standard provides a method for determining the acidity (by pH measurement) and conductivity of an aqueous solution of gases evolved during the combustion of materials so that limits can be agreed for cable specifications. As the test is not carried out on a complete cable test piece, for a hazard assessment the actual material volumes of the cable components should be taken into consideration.

The method provides an indirect assessment of corrosivity. However, the recommended limits of pH and conductivity can only be regarded as an indication, as the relationship between corrosion and these two parameters does not necessarily embrace all materials.

This part of IEC 60754 is linked with IEC 60754-1, but the test procedure differs considerably.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 60754-2:2011](https://standards.iteh.ai/catalog/standards/sist/7ed836bb-b293-40f6-b43d-5b1c0ca16b5d/iec-60754-2-2011)

<https://standards.iteh.ai/catalog/standards/sist/7ed836bb-b293-40f6-b43d-5b1c0ca16b5d/iec-60754-2-2011>



# TEST ON GASES EVOLVED DURING COMBUSTION OF MATERIALS FROM CABLES –

## Part 2: Determination of acidity (by pH measurement) and conductivity

### 1 Scope

This part of IEC 60754 specifies the apparatus and procedure for the determination of the potential corrosivity of gases evolved during the combustion of materials taken from electric or optical fibre cable constructions by measuring the acidity (pH) and conductivity of an aqueous solution resulting from the gases evolved during the combustion.

The general method specified in this standard is intended for the testing of individual components used in a cable construction. Formulae are given for the calculation of a weighted value for a combination of materials found in a specified cable. The use of this method will enable the verification of relevant requirements for either individual components or combined components of a cable construction stated in the appropriate cable specification.

A simplified method is included for the testing of individual components where it is required only to demonstrate compliance with a stated performance requirement for quality control purposes.

NOTE 1 The relevant cable standard should indicate which components of the cable should be tested, and which method of calculation (see Clause 8) should be used in the case of dispute.

NOTE 2 This test method may be used to test materials to be used in cable manufacture, but a declaration of cable performance should not be made based on such a test.

NOTE 3 For the purposes of this standard, the term “electric cable” covers all insulated metallic conductor cables used for the conveyance of energy or signals.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1042, *Laboratory glassware – One-mark volumetric flasks*  
(available only in French)

ISO 3696, *Water for analytical laboratory use – Specification and test methods*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1

##### pH value

pH of an aqueous solution resulting from the gases evolved during the combustion of the material under the conditions given in this standard

### 3.2 conductivity value

conductivity of an aqueous solution resulting from the gases evolved during the combustion of the material under the conditions given in this standard

## 4 Test method principle

The material under test shall be heated in a stream of dry air. The evolved gases shall be trapped by bubbling through wash bottles filled with distilled or demineralized water.

The acidity of the resulting solution shall be assessed by determination of its pH value. The conductivity of the solution shall also be determined.

## 5 Test apparatus

### 5.1 General

The apparatus is shown in Figures 1 to 5.

The assembly of the components which constitute the test apparatus shall be leak-tight. The connecting distances between the quartz glass tube and the first bottle and between subsequent bottles shall be as short as possible. Glass or silicone rubber tubing shall be used for these connections.

NOTE 1 At the exit side of the quartz glass tube, as close to the end as possible, it is permitted to place a plug of silica wool to aid collection of condensates.

NOTE 2 A third empty bottle, of the same size as the gas washing bottles, placed before the gas washing bottles may be used to improve safety, i.e. to prevent suck back of water into the quartz glass tube.

### 5.2 Tube furnace

The length of the heating zone of the furnace shall be within the range 480 mm to 620 mm and its inside diameter shall be within the range 38 mm to 62 mm. It shall be equipped with an adjustable electrical heating system.

### 5.3 Quartz glass tube

For the test, a quartz glass tube shall be introduced into the tube furnace. The tube shall be approximately concentric to the furnace. It shall be resistant to the action of corrosive gases.

The inside diameter of the tube shall be within the range 30 mm to 46 mm. The tube shall protrude on the entrance side of the furnace by a length of between 60 mm to 200 mm, and on the exit side by between 60 mm to 100 mm. The initial clearance shall allow for thermal expansion. For the purposes of measurement of the protrusion distances, the tube shall be regarded as that part of essentially constant diameter.

NOTE The outer diameter of the tube should be chosen with due regard to the inside diameter of the tube furnace.

Prior to each test the tube shall be cleaned throughout its length by being calcined at approximately 950 °C.

### 5.4 Combustion boats

The combustion boat shall be made of porcelain, fused quartz or soapstone and shall have the following dimensions:

- external length: within the range 45 mm to 100 mm;

- external width: within the range 12 mm to 30 mm;
- internal depth: within the range 5 mm to 10 mm.

NOTE The dimensions of the boat should be chosen with due regard to the inside diameter of the quartz tube.

The preferred method for insertion of the combustion boat into the quartz glass tube is shown in Figure 1.

Prior to each test, the combustion boat shall be washed and calcined in a muffle furnace at approximately 950 °C for 4 h after which it shall be introduced into a desiccator and cooled to ambient temperature. The combustion boat shall then be weighed to an accuracy of 0,1 mg until two identical consecutive weights are obtained. This weight  $m_1$  shall be recorded.

### 5.5 Bubbling devices for gases

At the exit of the quartz glass tube, the evolved gases shall be trapped by bubbling through two wash bottles (see Figure 2), each containing approximately 450 ml of distilled or demineralized water of a purity at least Grade 3 in accordance with ISO 3696.

The pH value of the water shall be between 5,5 and 7,5, and the conductivity less than 0,5 µS/mm.

A magnetic stirrer shall be introduced in the first gas washing bottle to get a good swirling motion and an effective absorption of the combustion gases. The tubes into the wash bottles shall have a maximum internal diameter at their tip of 5 mm in order to aid absorption.

The height of the liquid above the end of the tube shall be  $(110 \pm 10)$  mm in each bottle.

NOTE Use of a standard laboratory glass bottle of internal diameter approximately 75 mm will enable this requirement to be met.

### 5.6 Air supply system

The gas used for combustion shall be air.

The flow rate of air introduced into the quartz tube shall be adjusted according to the actual internal cross-sectional area of the tube, such that the speed of air flowing across the sample is approximately 20 ml/mm<sup>2</sup>/h.

The speed of air shall be regulated by reference to the flow rate of air. The flow rate of air shall be  $(0,0157 \times D^2)$  l/h with a tolerance of  $\pm 10$  %.

NOTE The derivation of the flow rate of air from the speed of air is:

$$\rho = V \times \frac{\pi D^2}{4}$$

where

$D$  is the internal diameter of the tube (mm);

$\rho$  is the flow rate of air (ml/h);

$V$  is the speed of air (ml/mm<sup>2</sup>/h).

The air supply shall be adjusted and controlled by a needle valve, and the flow rate monitored by a flowmeter of the appropriate range.

The air supplied shall be selected from one of the following methods:

### Method 1

This method uses synthetic air or compressed air from a bottle. The air shall be introduced on the inlet side of the quartz glass tube (see Figure 3).

### Method 2

This method uses a laboratory compressed air supply. Air shall be introduced on the inlet side of the quartz glass tube and shall be filtered and dried (see Figure 4).

### Method 3

This method uses the ambient air of the laboratory. The air shall be filtered and dried. In this case, the mixture of air and combustion gas shall be sucked by a pump (see Figure 5).

## 5.7 Analytical balance

The balance shall have a precision of  $\pm 0,1$  mg.

## 5.8 Laboratory glassware

For pH and conductivity determination, the following laboratory glassware shall be available:

- one mark volumetric flask in accordance of ISO 1042 with 1 000 ml capacity.

## 5.9 pH meter

The pH meter shall have a precision of  $\pm 0,02$  and shall be equipped with a pH electrode.

[IEC 60754-2:2011](https://standards.iteh.ai/catalog/standards/sist/7ed836bb-b293-40f6-b43d-5b1c0ca16b5d/iec-60754-2-2011)

## 5.10 Conductivity measuring device

The conductivity measuring device shall have a range of  $10^{-1}$   $\mu\text{S}/\text{mm}$  to  $10^{+2}$   $\mu\text{S}/\text{mm}$  and shall be equipped with an electrode.

# 6 Test specimen

## 6.1 General

Three test specimens for the general method, or two for the simplified method, each consisting of  $(1\,000 \pm 5)$  mg of the material to be tested, shall be prepared. Each test specimen shall be taken from a sample representative of the material. Each test specimen shall be cut into a number of smaller pieces.

NOTE Pieces with a maximum dimension of 3 mm have been found to be suitable.

## 6.2 Conditioning of specimen

The prepared test specimens shall be stored for at least 16 h at a temperature of  $(23 \pm 2)$  °C and a relative humidity of  $(50 \pm 5)$  %.

## 6.3 Mass of specimen

Weigh the combustion boat ( $m_1$ ) with a precision of 0,1 mg (see 5.4). After conditioning, the test specimen shall be put into the combustion boat and evenly distributed on the bottom of the boat, which shall be weighed to an accuracy of 0,1 mg. The weight ( $m_2$ ) shall be recorded.

The mass  $m$  of the test specimen shall be calculated as follows:

$$m = m_2 - m_1$$

where

$m$  is the mass of the test specimen in grams;

$m_1$  is the mass of the combustion boat in grams;

$m_2$  is the mass of the combustion boat with the test specimen, in grams.

## 7 Test procedure

### 7.1 General

The test procedure and determination of pH value and conductivity value shall be carried out on each test specimen.

### 7.2 Test apparatus and arrangement

The test procedure defined in this clause shall be carried out using the apparatus detailed in Clause 5.

### 7.3 Heating procedure

The air flow shall be adjusted by means of a needle valve to the value specified in 5.6 and shall be kept constant during the test.

The temperature shall be measured by a thermocouple suitably protected against corrosion and placed inside the quartz glass tube. The heating system shall be adjusted such that the temperature at the designated position for the boat shall be not less than 935 °C and not more than 965 °C. The temperature at a position 300 mm from the designated position in the direction of the air flow shall be not less than 900 °C.

The boat containing the test specimen shall be quickly inserted into the heating zone of the tube to the designated position determined by the thermocouple measurement and the timer shall be started. The combustion boat shall be placed in such a way that the distance between the boat and the exit end of the effective heating zone is at least 300 mm. The effective heating zone is that zone where a temperature of not less than 900 °C has been determined by the thermocouple measurement.

The combustion procedure, under the air flow condition, shall be continued for (30 ± 1) min in the furnace.

**WARNING** The operator should take precautions, e.g. the wearing of eye protection and suitable protective clothing, because certain materials ignite quickly, and can cause "blow back" of hot gases. Care should also be taken to avoid over-pressurization of the system, and to allow for venting of exhaust gases. Guidance on the avoidance of "blow back" is given in NOTE 2 of 5.1.

### 7.4 Washing procedure

Following the heating procedure, all the bottles used shall be disconnected, and the contents washed into a 1 000 ml volumetric flask. Using water with the properties given in 5.5, the bottles, the connecting links and, after cooling, the end of the quartz glass tube including the silica wool (if used) shall also be washed into the flask, and the contents made up to 1 000 ml.

### 7.5 Determination of the pH value and conductivity

The pH shall be measured using a pH meter calibrated as proposed by the instrument supplier.