
Aeronavtika - Titanova zlitina TI-P64003 - Hladno preoblikovana in s popuščeni napetostmi - Nevarjena cev za tlačne sisteme - $4 \text{ mm} \leq D \leq 51 \text{ mm}$ - $690 \text{ MPa} \leq R_m \leq 1030 \text{ MPa}$

Aerospace series - Titanium alloy TI-P64003 - Cold worked and stress relieved - Seamless tube for pressure systems - $4 \text{ mm} \leq D \leq 51 \text{ mm}$ - $690 \text{ MPa} \leq R_m \leq 1030 \text{ MPa}$

Luft- und Raumfahrt - Titanlegierung TI-P64003 - Kaltverformt und spannungsarm gegläht - nahtlose Innendruckrohre - $4 \text{ mm} \leq D \leq 51 \text{ mm}$ - $690 \text{ MPa} \leq R_m \leq 1030 \text{ MPa}$

Série aérospatiale - Alliage de titane TI-P64003 - Étiré à froid et détensionné - Tube hydraulique sans soudure pour applications sous pression - $4 \text{ mm} \leq D \leq 51 \text{ mm}$ - $690 \text{ MPa} \leq R_m \leq 1030 \text{ MPa}$

Ta slovenski standard je istoveten z: EN 3120:2012

ICS:

49.025.30 Titan Titanium

SIST EN 3120:2012

en,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 3120:2012

<https://standards.iteh.ai/catalog/standards/sist/7a387770-1c22-4097-a12b-5fb562b18102/sist-en-3120-2012>

EUROPEAN STANDARD

EN 3120

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2012

ICS 49.025.30

English Version

Aerospace series - Titanium alloy TI-P64003 - Cold worked and stress relieved - Seamless tube for pressure systems - $4 \text{ mm} \leq D \leq 51 \text{ mm}$ - $690 \text{ MPa} \leq R_m \leq 1\,030 \text{ MPa}$

Série aéronautique - Alliage de titane TI-P64003 - Étiré à froid et détensionné - Tube hydraulique sans soudure pour applications sous pression - $4 \text{ mm} \leq D \leq 51 \text{ mm}$ - $690 \text{ MPa} \leq R_m \leq 1\,030 \text{ MPa}$

Luft- und Raumfahrt - Titanlegierung TI-P64003 - Kaltverformt und spannungsarm gegläht - Nahtlose Innendruckrohre - $4 \text{ mm} \leq D \leq 51 \text{ mm}$ - $690 \text{ MPa} \leq R_m \leq 1\,030 \text{ MPa}$

This European Standard was approved by CEN on 27 August 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents		Page
Foreword.....		3
Introduction		4
1	Scope	4
2	Normative references	4

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 3120:2012

<https://standards.iteh.ai/catalog/standards/sist/7a387770-1c22-4097-a12b-5fb562b18102/sist-en-3120-2012>

Foreword

This document (EN 3120:2012) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2012, and conflicting national standards shall be withdrawn at the latest by August 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 3120:2012](https://standards.iteh.ai/catalog/standards/sist/7a387770-1c22-4097-a12b-5fb562b18102/sist-en-3120-2012)

<https://standards.iteh.ai/catalog/standards/sist/7a387770-1c22-4097-a12b-5fb562b18102/sist-en-3120-2012>

Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-4.

1 Scope

This European Standard specifies the requirements relating to:

Titanium alloy TI-P64003
Cold worked and stress relieved
Seamless tube for pressure systems
 $4 \text{ mm} \leq D \leq 51 \text{ mm}$
 $690 \text{ MPa} \leq R_m \leq 1\,030 \text{ MPa}$

for aerospace applications.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2043, *Aerospace series — Metallic materials — General requirements for semi-finished product qualification (excluding forgings and castings)*.¹⁾
SIST EN 3120:2012
<https://standards.iteh.ai/catalog/standards/sist/7a387770-1c22-4097-a12b-51b562b18102/sist-en-3120-2012>

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use*.

EN 4500-4, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 4: Specific rules for titanium and titanium alloys*.

EN 4800-003, *Aerospace series — Titanium and titanium alloys — Technical specification — Part 3: Tube*.

ISO 4288:1996, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Rules and procedures for the assessment of surface texture*.

ISO 6772:1988, *Aerospace — Fluid systems — Impulse testing of hydraulic hose, tubing and fitting assemblies*.

SAE AS4076, *Contractile strain ratio testing of titanium hydraulic tubing*.²⁾

1) Published as ASD-STAN Prestandard at the date of publication of this standard.

2) Published by: Department of Defense (DOD), the Pentagon, Washington, DC 20301, USA.

1	Material designation		Titanium alloy TI-P64003									
2	Chemical composition %	Element	Al	V	O ₂	N ₂	H ₂	Fe	C	Others ^a		Ti
		min.	2,5	2,0	–	–	–	–	–	–	–	Base
		max.	3,5	3,0	0,120	0,020	0,0150	0,30	0,05	0,10	0,40	
3	Method of melting		See EN 4800-3.									
4.1	Form		Seamless tube									
4.2	Method of production		–									
4.3	Limit dimension(s)	mm	$4 \leq D \leq 51$									
5	Technical specification		EN 4800-003									

6.1	Delivery condition		Cold worked and stress relieved								
	Heat treatment		$380 \text{ °C} \pm 10 \text{ °C} / t \geq 30 \text{ min} / \text{AC}$ or inert atmosphere								
6.2	Delivery condition code		U								
7	Use condition		Delivery condition								
	Heat treatment		–								

iTeh STANDARD PREVIEW
Characteristics
(standards.iteh.ai)

8.1	Test sample(s)		See EN 4800-003.										
8.2	Test piece(s)		See EN 4800-003.										
8.3	Heat treatment		Use condition										
9	Dimensions concerned	mm	$4 \leq D \leq 7$			$7 < D \leq 12$			$12 < D \leq 51$				
10	Thickness of cladding on each face	%	–			–			–				
11	Direction of test piece		L			L			L				
12	T	Temperature	θ	°C	Ambient			Ambient			Ambient		
13		Proof stress	R _{p0.2}	MPa	≥ 650			≥ 730			≥ 730		
14		Strength	R _m	MPa	$690 \leq R_m \leq 920$			$870 \leq R_m \leq 1\ 030$			$870 \leq R_m \leq 1\ 030$		
15		Elongation	A	%	$A_{50\text{ mm}} \geq 14$			$A_{50\text{ mm}} \geq 14$			$A_{50\text{ mm}} \geq 16$		
16	Reduction of area	Z	%	–			–			–			
17	Hardness		–										
18	Shear strength	R _c	MPa	–									
19	Bending	k	–	–									
20	Impact strength		–										
21	C	Temperature	θ	°C	–								
22		Time		h	–								
23		Stress	σ_a	MPa	–								
24		Elongation	a	%	–								
25		Rupture stress	σ_R	MPa	–								
26		Elongation at rupture	A	%	–								
27	Notes (see line 98)		A										

EN 3120:2012 (E)

30	Microstructure	–	See EN 4800-003.	
		7	The microstructure shall consist of an elongated globular, wrought, alpha and beta structure. Evidence of Widmannstätten structure is not acceptable.	
33	Flattening of tubes	–	See EN 4800-003.	
		6	D/a	Z
			≤ 10	8 a
			$10 < D/a \leq 16$	12 a
			$16 < D/a \leq 30$	15 a
	$30 < D/a \leq 50$	17 a		
34	Grain size	–	See EN 4800-003.	
		3	Transverse	
		7	$G \geq 8$	
37	Bending of tubes ^b	–	See EN 4800-003.	
		2	Two samples per batch	
		6	$\alpha = 180^\circ$; $r = 2,5 D$	
		7	No visible defects	
44	External defects	–	See EN 4800-003.	
55	Deformation under pressure of tubes (Hydraulic distention test)	–	See EN 4800-003.	
		6	$P = 0,95 R_{p0,2}$	
61	Internal defects (Ultrasonics)	–	See EN 4800-003.	
		7	Nominal wall thickness (mm)	Class
			$a \leq 1,14$	5
			$1,14 < a \leq 1,52$	4
			$1,52 < a \leq 2,03$ $2,03 < a \leq 2,54$	3 2
64	Surface condition roughness	–	See EN 4800-003.	
		1	One per batch	
		2	One per batch	
		7	$R_a \leq 0,8 \mu\text{m}$ for external surface $R_a \leq 0,8 \mu\text{m}$ for internal surface $R_t \leq 8,0 \mu\text{m}$ for internal surface	
67	Contractile strain ratio (C.S.R.) ^{b c}	–	See EN 4800-003	
		1	SAE AS4076	
		2	2 per batch	
		7	$1.5 \leq \text{CSR} \leq 2.5$	
74	Surface contamination	–	See EN 4800-003.	
75	Internal pressure test of tubes	–	See EN 4800-003.	
		1	On straight tubes, straight tube length = 300 mm. Two per size batch for qualification and lot. One per size and lot. Pressure value formula: $P = 0,95 = R_{p0,95} = (D_N^2 - d^2 / D_N^2 + d^2)$ where D_N = Tube outside diameter. d = Tube inside diameter.	
75	Impulse fatigue test of tubes ^{b c}	–	See EN 4800-003.	
		1	See ISO 6772.	
		4	On $\pm 90^\circ$ bend tube at a bending radius of $3 D$	
95	Marking inspection	–	See EN 4800-003.	
96	Dimensional inspection	–	See EN 4800-003.	
98	Notes	–	^a Determination not required for routine acceptance ^b 2 additional bend tests required if $2,5 < \text{CSR} \leq 2,8$ ^c 2 pressure impulse fatigue tests per batch required only if $1,3 \leq \text{CSR} < 1,5$	
99	Typical use	–	Pressure systems	