



Edition 2.0 2010-04

INTERNATIONAL STANDARD



Fibre optic interconnecting devices and passive components – Basic test and measurement procedures – Part 2-24: Tests – Screen testing of ceramic alignment split sleeve by stress application

IEC 61300-2-24:2010

https://standards.iteh.ai/catalog/standards/iec/83347259-21a8-424f-9420-c00b17206ca8/iec-61300-2-24-2010





THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2010 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office 3, rue de Varembé CH-1211 Geneva 20 Switzerland Email: inmail@iec.ch Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

Catalogue of IEC publications: <u>www.iec.ch/searchpub</u>

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

IEC Just Published: <u>www.iec.ch/online_news/justpub</u>

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

Customer Service Centre: <u>www.iec.ch/webstore/custserv</u>
If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11 talog/standards/iec/83347259-21 a8-424f-9420-c00b17206ca8/iec-61300-2-24-2010 Fax: +41 22 919 03 00





Edition 2.0 2010-04

INTERNATIONAL STANDARD



Fibre optic interconnecting devices and passive components – Basic test and measurement procedures – Part 2-24: Tests – Screen testing of ceramic alignment split sleeve by stress application

IEC 61300-2-24:2010

https://standards.iteh.ai/catalog/standards/iec/83347259-21a8-424f-9420-c00b17206ca8/iec-61300-2-24-2010

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PRICE CODE

Ρ

ICS 33.180.20

ISBN 978-2-88910-492-5

CONTENTS

FOREWORD	3
1 Scope	5
2 General description	5
3 Apparatus	5
4 Procedure	7
5 Details to be specified	7
Annex A (informative) Static fatigue for zirconia alignment sleeve	8
Bibliography1	5
Figure 1 – Apparatus used for screen testing of a ceramic alignment sleeve	6
Figure A.1 – Model of time-varying proof stress for a zirconia sleeve	0
Figure A.2 – Calculated contour lines of gauge retention force and working stress along with inner and outer diameter of a zirconia sleeve	1
Figure A.3 – Calculated general relationship between σ_p/σ_a and t_e , satisfying 0,1 FIT for 20 years use	2
Figure A.4 – Calculated failure probability of screened zirconia sleeves along with working time	2
Figure A.5 – Measured and calculated strength distribution of 2,5 mm zirconia sleeves (comparison between sleeves, extended proof tested or not)	3
Figure A.6 – Measured strength distribution of 1,25 mm zirconia sleeves (comparison between sleeves, extended proof tested or not)14	4
Table 1 – Dimension example of the reference gauge and the plate for the ceramic	
sleeve	6
Table 2 – Dimension example of a commonly used ceramic alignment sleeve	7-20
Table A.1 – Measured static fatigue parameters for zirconia sleeves	1

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FIBRE OPTIC INTERCONNECTING DEVICES AND PASSIVE COMPONENTS – BASIC TEST AND MEASUREMENT PROCEDURES –

Part 2-24: Tests – Screen testing of ceramic alignment split sleeve by stress application

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committee; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
 - 6) All users should ensure that they have the latest edition of this publication.
 - 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
 - 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
 - 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61300-2-24 has been prepared by subcommittee 86B: Fibre optic interconnecting devices and passive components, of IEC technical committee 86: Fibre optics.

This second edition replaces the first edition published in 1999. This second edition constitutes a technical revision. Specific technical changes involve the addition of a dimension example of the reference gauge and the plate for the ceramic sleeve and a commonly used ceramic alignment sleeve for the 1,25 mm ceramic sleeve.

The text of this standard is based on the following documents:

FDIS	Report on voting
86B/2967/FDIS	86B/3014/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of IEC 61300 series, published under the general title, *Fibre optic interconnecting and passive components – Basic test and measurement procedures*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

http

FIBRE OPTIC INTERCONNECTING DEVICES AND PASSIVE COMPONENTS – BASIC TEST AND MEASUREMENT PROCEDURES –

Part 2-24: Tests – Screen testing of ceramic alignment split sleeve by stress application

1 Scope

The purpose of this part of IEC 61300 is to identify weaknesses in a ceramic alignment split sleeve which could lead to early failure of the component.

2 General description

Ceramic alignment sleeves are important components often used in the adaptor of plugadaptor-plug optical connector sets. By using the method described, the component is subjected to a proof stress greater than would be experienced under normal service conditions. This enables weak products to be screened out.

3 Apparatus (https://standards.iteh.ai)

The apparatus and arrangement necessary to perform this screening procedure are shown in Figure 1. The material needed consists of the following:

a) a reference gauge made of ceramic with a sleeve-holding section, a tapered section and a

stress-applying section. The diameter of each section is dependent on the dimensions of the product being screened. The length of the sleeve-holding section and the stress-2010 applying section should be greater than the component being tested;

b) plates A and B, each having a clearance hole in the centre to allow the plate to move a sample of a ceramic alignment split sleeve on the reference gauge.





ttps://standards.iteh.ai/catalog/standards/iec/83347259-21a8-424F9420-c00b17206ca8/iec-61300-2-24-2010 Table 1 shows the dimension of the reference gauge and the plate for the ceramic split sleeve. A dimension of the stress-applying section diameter (E) is shown for a commonly used ceramic alignment sleeve in Table 2.

Reference	For 1,25 mm gauge	For 2,5 mm gauge	Notes
	Dimension mm	Dimension mm	
A	9	14	NOTE 2
В	5	5	
С	9	14	NOTE 2
D	-	_	NOTE 1
E	$1,259\ 0\pm0,000\ 5$	2,515	
F	-	-	NOTE 3
G	20	20	
н	2	2	
NOTE 1 This diameter sh	ould be less than the inner	diameter of the split sleev	/e.
NOTE 2 Surface finish in	this area Ra = 0,2 μm.		
NOTE 3 Dimension F sh	ould be greater than dime	nsion E, and less than sl	eeve ØD.

Table 1 – Dimension example of the reference gauge and the plate for the ceramic sleeve

Items	For 1,25 mm	For 2,5 mm
	Dimension mm	Dimension mm
Length	6,8	10,1
Outer diameter	1,62	3,2
Inner diameter (ref.)	1,246	2,49
Split section width	6,8	10,1

Table 2 – Dimension example of a commonly used ceramic alignment sleeve

4 Procedure

This test should be carried out under a 23 $^{\circ}C \pm 2 ^{\circ}C$ environmental temperature condition.

The procedure is as follows.

- a) Insert plate A into the reference gauge and set it at the fixed end of the reference gauge.
- b) Moisten the inside surface of a ceramic split sleeve sample with distilled water (for example using a cotton bud). Only touch the sleeve with suitable tools.
- c) The sample sleeve is inserted onto the sleeve-holding part and set just in front of the tapered part of the reference gauge.
- d) Insert plate B into the left-hand side of the sample sleeve and move the sample sleeve onto the stress-applying part until the sample sleeve touches plate A (within approximately 1 s).
- e) The sample sleeve should be held for 3 s under the stressed state.
- f) After 3 s, stress applied to the sample sleeve is removed by moving plate A to the lefthand side (within approximately 1 s).

g) In the course of the procedure from d) to f), samples without damage (breakage or crack) should be selected as acceptable sleeves.

5 Details to be specified

The following details shall be specified depending on the sample sleeve size in the detail specification:

- diameter of sleeve-holding part of reference gauge (ØD);
- diameter of stress-applying part of reference gauge (ØE);
- length of sleeve-holding part (A) and stress-applying part (C);
- diameter of the center hole of plates A and B (ØF);
- deviations from test procedure.

Annex A

(informative)

Static fatigue for zirconia alignment sleeve

A.1 Prediction of failure probability by static fatigue

This annex applies primarily to 2,5 mm zirconia alignment sleeves supported by references [1] to [5]¹⁾. For 1,25 mm zirconia sleeves, a comprehensive analysis is referenced [6] and the strength distribution is shown in Figure A.6. Micro-cracks essentially exist on the surface or inside of ceramics. Therefore, fracture due to static fatigue occurs in ceramics under lower stress than the characteristic strength of the materials because of crack propagation in ceramic materials [1] [2].

Assurance of reliable optical fibre connections requires the prediction of failure probability of the zirconia sleeves under working stress needed to align the ferrules.

Assuming aligned ferrules of optical connectors, the zirconia sleeves are allowed to stand under a constant stress, as working stress σ_a . Based on the theories of Weibull statistics and slow crack growth for brittle materials, cumulative failure probability F of the zirconia sleeves suffering from working stress is given by the following equation:

with

$$\begin{array}{l}
 \text{(https:} \ln \frac{1}{1-F} = \frac{m}{N-1} \ln \sigma_a^N t_a + \ln \gamma \quad \text{(A.1)} \\
 \text{(A.1)}$$

$$\beta \equiv \frac{1}{(N-2) \operatorname{AY}^2 K_{IC}^{(N-2)}}$$

where

t _a	is the working time during which the working stress σ_{a} is applied;
m, V _e and σ_0	are the Weibull modulus, effective volume, and normalization constant to express the failure probability by the Weibull statistics theory, respectively;
Y	is the geometry constant;
K _{IC}	is the critical stress intensity factor;

A and *N* are crack propagation constants of the brittle materials [2].

¹⁾ Figures in square brackets refer to the Bibliography.