

---

**Aeronavtika - Jeklo FE-PM1503 (X3CrNiMoAl13-8-2) - Materiali za kovanje a ali D ≤ 300 mm, mehl'ani, taljeni z vakuumsko indukcijo in pretaljeni s talilno elektrodo**

Aerospace series - Steel FE-PM1503 (X3CrNiMoAl13-8-2) - Vacuum induction melted and consumable electrode remelted, softened, forging stock a or D ≤ 300 mm

Luft- und Raumfahrt - Stahl FE-PM1503 (X3CrNiMoAl 13-8-2) - Vakuuminduktionserschmolzen und mit selbstverzehrender Elektrode umgeschmolzen, weichgegl'ht, Schmiedevormaterial a oder D ≤ 300 mm

S°rie a°rospatiale - Acier FE-PM1503 (X3CrNiMoAl13-8-2) - a°labor° sous vide par induction et refondu ©l°lectrode consommable, adouci, produits destin°s ©la forge a ou D ≤ 300 mm

**Ta slovenski standard je istoveten z: EN 3359:2007**

---

**ICS:**

49.025.10      Jekla      Steels

**SIST EN 3359:2009**

**en,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 3359:2009

<https://standards.iteh.ai/catalog/standards/sist/95a91884-19e2-4a85-ab96-386c2846b62a/sist-en-3359-2009>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 3359**

July 2007

ICS 49.025.10

English Version

**Aerospace series - Steel FE-PM1503 (X3CrNiMoAl13-8-2) -  
Vacuum induction melted and consumable electrode remelted,  
softened, forging stock a or D  $\leq$  300 mm**

Série aérospatiale - Acier FE-PM1503 (X3CrNiMoAl13-8-2)  
- Élaboré sous vide par induction et refondu à l'électrode  
consommable, adouci, produits destinés à la forge a ou D  $\leq$   
300 mm

Luft- und Raumfahrt - Stahl FE-PM1503 (X3CrNiMoAl13-8-  
2) - Vakuuminduktionserschmolzen und mit  
selbstverzehrender Elektrode umgeschmolzen, gegläht,  
Schmiedevormaterial a oder D  $\leq$  300 mm

This European Standard was approved by CEN on 15 February 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

**Contents**

Page

|                                     |   |
|-------------------------------------|---|
| Foreword.....                       | 3 |
| Introduction .....                  | 4 |
| 1 <b>Scope</b> .....                | 4 |
| 2 <b>Normative references</b> ..... | 4 |

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 3359:2009

<https://standards.iteh.ai/catalog/standards/sist/95a91884-19e2-4a85-ab96-386c2846b62a/sist-en-3359-2009>

## Foreword

This document (EN 3359:2007) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2008, and conflicting national standards shall be withdrawn at the latest by January 2008.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

ITEH STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN 3359:2009

<https://standards.iteh.ai/catalog/standards/sist/95a91884-19e2-4a85-ab96-386c2846b62a/sist-en-3359-2009>

## EN 3359:2007 (E)

## Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-5.

## 1 Scope

This standard specifies the requirements relating to:

Steel FE-PM1503 (X3CrNiMoAl13-8-2) — Vacuum induction melted and consumable electrode remelted, softened, forging stock  $a$  or  $D \leq 300$  mm

for aerospace applications.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2003-7, *Aerospace series — Steel — Test methods — Part 7: Macrographic test*<sup>1)</sup>

EN 2043, *Aerospace series — Metallic materials — General requirements for semi-finished product qualification (excluding forgings and castings)*<sup>1)</sup>

EN 2157-2, *Aerospace series — Steel-forging stock and forgings — Technical specification — Part 2: Forging stock*

EN 4050-1, *Aerospace series — Test method for metallic materials — Ultrasonic inspection of bars, plates, forging stock and forgings — Part 1: General requirements*<sup>1)</sup>

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use*

EN 4436, *Aerospace series — Steel — Test methods — Determination of  $\delta$ -Ferrite*<sup>1)</sup>

EN 4500-5, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 5: Specific rules for steels*<sup>1)</sup>

---

1) Published as AECMA Prestandard at the date of publication of this standard.

| 1   | Material designation    |         | Steel FE-PM1503 (X3CrNiMoAl13-8-2)                        |      |      |       |       |       |      |      |      |       |      |
|-----|-------------------------|---------|-----------------------------------------------------------|------|------|-------|-------|-------|------|------|------|-------|------|
| 2   | Chemical composition %  | Element | C                                                         | Si   | Mn   | P     | S     | Cr    | Mo   | Ni   | Al   | N2    | Fe   |
|     |                         | min.    | –                                                         | –    | –    | –     | –     | 12,25 | 2,00 | 7,50 | 0,90 | –     | Base |
|     |                         | max.    | 0,05                                                      | 0,10 | 0,10 | 0,010 | 0,008 | 13,25 | 2,50 | 8,50 | 1,35 | 0,010 |      |
| 3   | Method of melting       |         | Vacuum induction melted and consumable electrode remelted |      |      |       |       |       |      |      |      |       |      |
| 4.1 | Form                    |         | Forging stock                                             |      |      |       |       |       |      |      |      |       |      |
| 4.2 | Method of production    |         | –                                                         |      |      |       |       |       |      |      |      |       |      |
| 4.3 | Limit dimension(s)      | mm      | $a$ or $D \leq 300$                                       |      |      |       |       |       |      |      |      |       |      |
| 5   | Technical specification |         | EN 2157-2                                                 |      |      |       |       |       |      |      |      |       |      |

|     |                         |  |                    |  |  |  |  |  |  |  |  |  |  |
|-----|-------------------------|--|--------------------|--|--|--|--|--|--|--|--|--|--|
| 6.1 | Delivery condition      |  | Softened           |  |  |  |  |  |  |  |  |  |  |
|     | Heat treatment          |  | –                  |  |  |  |  |  |  |  |  |  |  |
| 6.2 | Delivery condition code |  | U                  |  |  |  |  |  |  |  |  |  |  |
| 7   | Use condition           |  | Delivery condition |  |  |  |  |  |  |  |  |  |  |
|     | Heat treatment          |  | –                  |  |  |  |  |  |  |  |  |  |  |

## Characteristics

|     |                                    |                   |            |     |                     |   |                                                               |  |                              |  |
|-----|------------------------------------|-------------------|------------|-----|---------------------|---|---------------------------------------------------------------|--|------------------------------|--|
| 8.1 | Test sample(s)                     |                   |            |     | See EN 2157-2       |   | Forged or machined                                            |  |                              |  |
| 8.2 | Test piece(s)                      |                   |            |     | See EN 2157-2       |   | See EN 2157-2                                                 |  |                              |  |
| 8.3 | Heat treatment                     |                   |            |     | Delivery condition  |   | See line 29                                                   |  |                              |  |
| 9   | Dimensions concerned               |                   | mm         |     | $a$ or $D \leq 300$ |   | $a$ or $D < 150$                                              |  | $150 \leq a$ or $D \leq 300$ |  |
| 10  | Thickness of cladding on each face |                   | %          |     | —                   |   | —                                                             |  | —                            |  |
| 11  | Direction of test piece            |                   |            |     | L                   |   | T                                                             |  | T                            |  |
| 12  | T                                  | Temperature       | $\theta$   | °C  | —                   |   | Ambient                                                       |  | Ambient                      |  |
| 13  |                                    | Proof stress      | $R_{p0,2}$ | MPa | —                   |   | $\geq 1\,310$                                                 |  | $\geq 1\,310$                |  |
| 14  |                                    | Strength          | $R_m$      | MPa | —                   |   | $\geq 1\,400$                                                 |  | $\geq 1\,400$                |  |
| 15  |                                    | Elongation        | $A$        | %   | —                   |   | $\geq 9$                                                      |  | $\geq 9$                     |  |
| 16  |                                    | Reduction of area | $Z$        | %   | —                   |   | $\geq 50$                                                     |  | $\geq 45$                    |  |
| 17  | Hardness                           |                   |            |     | $\leq 363$ HB       |   | $43 \leq \text{HRC} \leq 47$ or $400 \leq \text{HB} \leq 460$ |  |                              |  |
| 18  | Shear strength                     |                   | $R_c$      | MPa | —                   |   |                                                               |  |                              |  |
| 19  | Bending                            |                   | $k$        | —   | —                   |   |                                                               |  |                              |  |
| 20  | Impact strength                    |                   |            |     | —                   |   |                                                               |  |                              |  |
| 21  | C                                  | Temperature       | $\theta$   | °C  | —                   |   |                                                               |  |                              |  |
| 22  |                                    | Time              |            |     | h                   | — |                                                               |  |                              |  |
| 23  |                                    | Stress            | $\sigma_a$ | MPa | —                   |   |                                                               |  |                              |  |
| 24  |                                    | Elongation        | $a$        | %   | —                   |   |                                                               |  |                              |  |
| 25  |                                    | Rupture stress    | $\sigma_R$ | MPa | —                   |   |                                                               |  |                              |  |
| 26  | Elongation at rupture              |                   | $A$        | %   | —                   |   |                                                               |  |                              |  |
| 27  | Notes (see line 98)                |                   |            |     | —                   |   |                                                               |  |                              |  |

## EN 3359:2007 (E)

|    |                                                 |   |                                                                                                                                                                                                                                                               |                    |          |
|----|-------------------------------------------------|---|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------|----------|
| 29 | Reference heat treatment                        | – | Precipitation treated<br>900 °C ≤ $\theta$ ≤ 950 °C / $t \geq 30$ min / AC or OQ<br>+ 530 °C ≤ $\theta$ ≤ 550 °C / $t = 4$ h / AC                                                                                                                             |                    |          |
| 30 | Microstructure                                  | 1 | EN 4436                                                                                                                                                                                                                                                       |                    |          |
|    |                                                 | 2 | One per cast                                                                                                                                                                                                                                                  |                    |          |
|    |                                                 | 3 | Corresponding to the top of ingot                                                                                                                                                                                                                             |                    |          |
|    |                                                 | 5 | See line 29                                                                                                                                                                                                                                                   |                    |          |
|    |                                                 | 7 | The $\delta$ -ferrite content shall not exceed 2 %                                                                                                                                                                                                            |                    |          |
| 44 | External defects                                | – | See EN 2157-2                                                                                                                                                                                                                                                 |                    |          |
| 50 | Cleanliness/inclusion content (micro-cleanness) | – | See EN 2157-2                                                                                                                                                                                                                                                 |                    |          |
|    |                                                 | 7 | Category 5                                                                                                                                                                                                                                                    |                    |          |
| 51 | Macrostructure                                  | – | See EN 2157-2                                                                                                                                                                                                                                                 |                    |          |
|    |                                                 | 1 | EN 2003-7                                                                                                                                                                                                                                                     |                    |          |
|    |                                                 | 7 | Class                                                                                                                                                                                                                                                         | Condition          | Severity |
|    |                                                 |   | 1                                                                                                                                                                                                                                                             | Freckles           | A        |
|    |                                                 |   | 2                                                                                                                                                                                                                                                             | White spots        | A        |
|    |                                                 |   | 3                                                                                                                                                                                                                                                             | Radial segregation | A        |
|    |                                                 |   | 4                                                                                                                                                                                                                                                             | Ring pattern       | B        |
| 61 | Internal defects                                | – | See EN 2157-2                                                                                                                                                                                                                                                 |                    |          |
|    |                                                 | 1 | EN 4050-1                                                                                                                                                                                                                                                     |                    |          |
|    |                                                 | 7 | Class 3                                                                                                                                                                                                                                                       |                    |          |
|    |                                                 |   | <p>SIST EN 3359:2009</p> <p><a href="https://standards.iteh.ai/catalog/standards/sist/95a91884-19e2-4a85-ab96-386c2846b62a/sist-en-3359-2009">https://standards.iteh.ai/catalog/standards/sist/95a91884-19e2-4a85-ab96-386c2846b62a/sist-en-3359-2009</a></p> |                    |          |
| 95 | Marking inspection                              | – | See EN 2157-2                                                                                                                                                                                                                                                 |                    |          |
| 96 | Dimensional inspection                          | – | See EN 2157-2                                                                                                                                                                                                                                                 |                    |          |
| 98 | Notes                                           | – | –                                                                                                                                                                                                                                                             |                    |          |
| 99 | Typical use                                     | – | –                                                                                                                                                                                                                                                             |                    |          |