

---

---

**Thermoplastics valves — Pressure test  
methods and requirements —**

**Part 2:**

Test conditions and basic requirements for PE,  
PP, PVC-U and PVDF valves

iTeh STANDARD PREVIEW

*Robinets en matériaux thermoplastiques — Méthodes d'essai et exigences —  
(standards.iteh.ai)*

*Partie 2: Conditions d'essai et exigences de base pour les robinets en PE,  
PP, PVC-U et PVDF*

[https://standards.iteh.ai/catalog/standards/sist/34516541-29ac-4a32-a2b3-  
c3f9659125a9/iso-9393-2-1997](https://standards.iteh.ai/catalog/standards/sist/34516541-29ac-4a32-a2b3-c3f9659125a9/iso-9393-2-1997)



## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 9393-2 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 7, *Valves and auxiliary equipment of plastics materials*.

ISO 9393 consists of the following parts, under the general title *Thermoplastics valves — Pressure test methods and requirements*:

- Part 1: *General*
- Part 2: *Test conditions and basic requirements for PE, PP, PVC-U and PVDF valves*

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case postale 56 • CH-1211 Genève 20 • Switzerland  
Internet central@iso.ch  
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

# Thermoplastics valves — Pressure test methods and requirements —

## Part 2:

### Test conditions and basic requirements for PE, PP, PVC-U and PVDF valves

#### 1 Scope

This part of ISO 9393 specifies the test parameters and conditions for hydrostatic-pressure tests on valves made of the following thermoplastic materials:

— **polyethylene (PE)**

PE 100, PE 80, as defined in ISO 12162

— **polypropylene (PP)**

homopolymer (PP-H)  
block copolymer (PP-B)  
random copolymer (PP-R)  
glass-reinforced polypropylene (PP-R-GR)

— **unplasticized poly(vinyl chloride) (PVC-U)**

material having an MRS equal to or greater than 25 MPa as defined in ISO 12162 (PVC-UH) (see ISO 4422-3)

— **poly(vinylidene fluoride) (PVDF) homopolymer** as defined in ISO 12162

The tests cover the following aspects:

- the material used for manufacturing valves;
- the pressurized valve components;
- the complete valve.

#### 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 9393. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 9393 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 4422-3:1996, *Pipes and fittings made of unplasticized poly(vinyl chloride) (PVC-U) for water supply — Specifications — Part 3: Fittings and joints.*

ISO/TR 9080:1992, *Thermoplastics pipes for the transport of fluids — Methods of extrapolation of hydrostatic stress rupture data to determine the long-term hydrostatic strength of thermoplastics pipe materials.*

ISO 9393-1:1994, *Thermoplastics valves — Pressure test methods and requirements — Part 1: General.*

ISO 12162:1995, *Thermoplastics materials for pipes and fittings for pressure applications — Classification and designation — Overall service (design) coefficient.*

### 3 Material test

3.1 The material shall be tested in accordance with the conditions and requirements given in ISO/TR 9080 or equivalent and classified in accordance with ISO 12162.

3.2 It is not necessary to retest material which has already been tested by the material supplier.

### 4 Shell test

#### 4.1 Test conditions

The test specimen described in 5.2 of ISO 9393-1:1994 shall be subjected to the applicable test conditions given in table 1.

**Table 1 — Conditions for shell test**

Material	Minimum test time h	Test pressure <sup>1)</sup> bar	$\sigma_s$ <sup>2)</sup>	Temperature °C	Test fluid	
					Inside	Outside
PE 100	100	1,55 × PN	8	20 ± 2	Water	Water
	165	0,69 × PN		80 ± 2	Water	Water
	1 000	0,62 × PN		80 ± 2	Water	Water
PE 80	100	1,59 × PN	6,3	20 ± 2	Water	Water
	165	0,73 × PN		80 ± 2	Water	Water
	1 000	0,63 × PN		80 ± 2	Water	Water
PP-H and PP-R-GR	1	4,2 × PN	5	20 ± 2	Water	Water
	1 000	0,7 × PN		95 ± 2	Water	Water or air
PP-B	1	3,2 × PN	5	20 ± 2	Water	Water
	1 000	0,52 × PN		95 ± 2	Water	Water or air
PP-R	1	3,2 × PN	5	20 ± 2	Water	Water
	1 000	0,7 × PN		95 ± 2	Water	Water or air
PVC-U	1	4,2 × PN	10	20 ± 2	Water	Water
	1 000	3,2 × PN		20 ± 2	Water	Water
PVC-UH $d_n < 160$	1	4,2 × PN	10	20 ± 2	Water	Water
	1 000	3,2 × PN		20 ± 2	Water	Water
$d_n \geq 160$	1	3,36 × PN	12,5	20 ± 2	Water	Water
	1 000	2,56 × PN		20 ± 2	Water	Water
PVDF	200	0,72 × PN	16	95 ± 2	Water	Water or air

1) The test pressures  $p_{test}$  were calculated from the following equation:

$$p_{test} = PN \times \frac{\sigma_t}{\sigma_s}$$

where

- $\sigma_t$  is the induced stress under the test conditions;
- $\sigma_s$  is the design stress in megapascals.

2)  $\sigma_s$  = design stress in megapascals.

1 bar = 0,1 MPa = 0,1 N/mm<sup>2</sup> = 10<sup>5</sup> N/m<sup>2</sup>

## 4.2 Requirements

The test specimen shall be considered satisfactory if no leakage from the valve is noted, and no rupture or other visible failure occurs during the test period. The test specimen be regarded as unsatisfactory if the valve body bursts before the end of the test period.

If a pipe or a connection fails, the test shall be considered null and void and shall be repeated using a different specimen.

## 5 Long-term behaviour test on the complete valve

### 5.1 Test conditions

The test specimen described in 5.3 of ISO 9393-1:1994 shall be subjected to the applicable test conditions given in table 2.

**Table 2 — Conditions for long-term behaviour test**

Material	Minimum test time h	Test pressure <sup>1)</sup> bar	Temperature °C	Test fluid	
				Inside	Outside
PE 100, PE 80	1 000	1,5 × PN	20 ± 2	Water	Water
PP-H	1 000	2,24 × PN	20 ± 2	Water	Water
PP-B, PP-R and PP-R-GR	1 000	1,6 × PN	20 ± 2	Water	Water
PVC-U and PVC-UH	1 000	1,3 × PN	40 ± 2	Water	Water
PVDF	1 000	1,45 × PN	20 ± 2	Water	Water

1) The test pressures  $p_{\text{test}}$  were calculated from the following equation:

$$p_{\text{test}} = \text{PN} \times \frac{\sigma_t}{\sigma_s}$$

where

$\sigma_t$  is the induced stress under the test conditions

$\sigma_s$  is the design stress in megapascals.

For diaphragm valves, the test pressure shall be 1,5 × PN bar for all materials except for PVC-U and PVC-UH (1,3 × PN bar) and PVDF (1,45 × PN bar).

### 5.2 Requirements

The test specimen shall be considered satisfactory if no leakage from the valve is noted, and no rupture or other visible failure occurs during the test period. The test specimen shall be regarded as unsatisfactory if the valve assembly bursts before the end of the test period.

If a pipe or a connection fails, the test shall be considered null and void and shall be repeated using a different specimen.

## 6 Seat and packing tests

### 6.1 Test conditions

The test conditions<sup>1)</sup> shall be the same for all the different valve materials. Test specimens (complete valves) shall be subjected to the tests described in 7.4.1 and 7.4.2 of ISO 9393-1:1994 using the test conditions given in table 3, as applicable.

1) The general criteria for seat and packing tests are taken from ISO 5208:1993, *Industrial valves — Pressure testing of valves*.

Table 3 — Conditions for seat and packing tests

Test	Minimum test time s	Test pressure bar	Temperature °C	Test fluid	
				Inside	Outside
Seat test (valve closed) <sup>1)</sup>	60	0,5 <sup>2)</sup>	20 ± 2	Air	Water
	<sup>5)</sup>	1,1 × PN <sup>3)</sup>	20 ± 2	Water <sup>4)</sup>	Air
Packing test (valve opened)	<sup>6)</sup>	1,5 × PN <sup>3)</sup>	20 ± 2	Water <sup>4)</sup>	Air

1) The valve shall be opened/closed with the torque specified in the relevant product standard.

2) This is a low-pressure test at 0,5 bar.

3) Maximum test pressure (PN + 5) bar.

4) Or air inside at (6 ± 1) bar and water outside.

5) Nominal valve size      DN ≤ 200: minimum test time 15 s  
                                    DN ≥ 250: minimum test time 30 s

6) Nominal valve size      DN ≤ 50: minimum test time 15 s  
                                    DN ≥ 65: minimum test time 30 s

## 6.2 Requirements

The test specimen shall be considered satisfactory if no leakage occurs through the valve seat and packing during the test period.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 9393-2:1997

<https://standards.iteh.ai/catalog/standards/sist/34516541-29ac-4a32-a2b3-c3f9659125a9/iso-9393-2-1997>

**iTeh STANDARD PREVIEW**  
This page intentionally left blank  
**(standards.iteh.ai)**

ISO 9393-2:1997

<https://standards.iteh.ai/catalog/standards/sist/34516541-29ac-4a32-a2b3-c3f9659125a9/iso-9393-2-1997>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 9393-2:1997

<https://standards.iteh.ai/catalog/standards/sist/34516541-29ac-4a32-a2b3-c3f9659125a9/iso-9393-2-1997>

---

---

**ICS 23.060.01; 83.140.30**

**Descriptors:** plastics products, thermoplastic resins, polyethylene, polypropylene, unplasticized polyvinyl chloride, polyvinylidene fluoride, valves and fittings, cocks, valves, specifications, tests, pressure tests, determination, leaktightness, testing conditions.

Price based on 4 pages

---

---