



SLOVENSKI STANDARD
SIST ISO 9416:2004
01-marec-2004

Določa metode za določanje koeficientov razpršitve svetlobe in absorpcije svetlobe (z uporabo Kubelka-Munk teorije).

Paper -- Determination of light scattering and absorption coefficients (using Kubelka-Munk theory)

STANDARD PREVIEW

Papier -- Détermination des coefficients de diffusion et d'absorption de la lumière (utilisation de la théorie de Kubelka-Munk)

[SIST ISO 9416:2004](https://standards.iteh.ai/catalog/standards/sist/521e3d8b-a20c-46ea-b181-5c18dc2acb9d/sist-iso-9416-2004)

Ta slovenski standard je istoveten z: **ISO 9416:1998**

ICS:

85.060 Papir, karton in lepenka Paper and board

SIST ISO 9416:2004 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 9416:2004

<https://standards.iteh.ai/catalog/standards/sist/521e3d8b-a20c-46ea-b181-5c18de2acb9d/sist-iso-9416-2004>

INTERNATIONAL STANDARD

ISO
9416

First edition
1998-02-15

Paper — Determination of light scattering and absorption coefficients (using Kubelka-Munk theory)

*Papier — Détermination des coefficients de diffusion et d'absorption de la
lumière (utilisation de la théorie de Kubelka-Munk)*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 9416:2004](https://standards.iteh.ai/catalog/standards/sist/521e3d8b-a20c-46ea-b181-5c18de2acb9d/sist-iso-9416-2004)

[https://standards.iteh.ai/catalog/standards/sist/521e3d8b-a20c-46ea-b181-
5c18de2acb9d/sist-iso-9416-2004](https://standards.iteh.ai/catalog/standards/sist/521e3d8b-a20c-46ea-b181-5c18de2acb9d/sist-iso-9416-2004)



Reference number
ISO 9416:1998(E)

ISO 9416:1998(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 9416 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

Annex A forms an integral part of this International Standard. Annex B is for information only.

<https://standards.iteh.ai/catalog/standards/sist/521e3d8b-a20c-46ea-b181-5c18de2acb9d/sist-iso-9416-2004>

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Introduction

The opacity of a paper is dependent on its grammage, but it is also intrinsically dependent on the light absorption and light scattering coefficients of the material. These coefficients are calculated from the values of the reflectance factor over a black backing, the intrinsic reflectance factor and the grammage of the sheet.

The calculation of these coefficients requires luminous-reflectance-factor data obtained by measurement under specified conditions. The reflectance factor depends on the conditions of measurement and particularly on the spectral and geometric characteristics of the instrument used for its determination. This International Standard should therefore be read in conjunction with ISO 2469 and ISO 2471.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

NOTE — This method is based on a theory developed by Kubelka and Munk. This theory describes scattering and absorption processes with certain approximations and simplifications and may therefore yield questionable results in extreme cases. However, the Kubelka-Munk theory offers a simple method for determining these coefficients with the instrument used for the determination of optical properties of paper and pulps. Moreover, the method based on this theory has been successfully used in practical applications.

<https://standards.iteh.ai/catalog/standards/sist/521e3d8b-a20c-46ca-b181-5c18de2acb9d/sist-iso-9416-2004>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 9416:2004

<https://standards.iteh.ai/catalog/standards/sist/521e3d8b-a20c-46ea-b181-5c18de2acb9d/sist-iso-9416-2004>

Paper — Determination of light scattering and absorption coefficients (using Kubelka-Munk theory)

1 Scope

This International Standard specifies a method for the calculation of light scattering and light absorption coefficients based upon diffuse reflectance measurements.

The use of the method is restricted to white and near-white uncoated papers with an opacity less than about 95 %. Paper that has been treated with a fluorescent dyestuff or exhibits significant fluorescence can only be dealt with if a filter with a cut-off wavelength of 420 nm is used to eliminate all the fluorescence effect.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 186:1994, *Paper and board — Sampling to determine average quality*.

ISO 187:1990, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*.

ISO 536:1995, *Paper and board — Determination of grammage*.

ISO 2469:1994, *Paper, board and pulps — Measurement of diffuse reflectance factor*.

ISO 2471:1998, *Paper and board — Determination of opacity (paper backing) — Diffuse reflectance method*.

ASTM E 308-96, *Computing the Colors of Objects by Using the CIE System*.

CIE Publication No. 38:1977, *Radiometric and photometric characteristics of materials and their measurement*.

3 Definitions

For the purposes of this International Standard, the following definitions apply.

3.1 reflectance factor, R : The ratio, expressed as a percentage, of the radiation reflected by a body to that reflected by the perfect reflecting diffuser under the same conditions.

3.2 luminous reflectance factor, R_y : The reflectance factor defined with reference to the CIE illuminant C and the CIE 1931 colour matching function $\bar{y}(\lambda)$, and corresponding to the attribute of visual perception of the reflecting surface.

3.3 single-sheet luminous reflectance factor, R_0 : The luminous reflectance factor of a single sheet of paper with a black cavity as backing.

3.4 intrinsic luminous reflectance factor, R_∞ : The luminous reflectance factor of a layer or pad of material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured reflectance factor.

3.5 opacity (paper backing): The ratio, expressed as a percentage, of the single-sheet luminous reflectance factor, R_0 , to the intrinsic luminous reflectance factor, R_∞ , of the same sample.

3.6 light scattering coefficient (Kubelka-Munk), s : The fraction of the diffuse light flux that is reflected on its passage through an infinitesimally thin layer of material. This may be related to the light reflected by a finite layer using the Kubelka-Munk theory which takes into account the grammage of the material, so that s has the units m^2/kg .

3.7 light absorption coefficient (Kubelka-Munk), k : The fraction of the diffuse light flux that is absorbed on its passage through an infinitesimally thin layer of material. This may be related to the light absorbed by a finite layer using the Kubelka-Munk theory which takes into account the grammage of the material, so that k has the units m^2/kg .

iTeh STANDARD PREVIEW

(standards.iteh.ai)

NOTE 1 Definitions 3.6 and 3.7 are strictly applicable to monochromatic light but for the purpose of this International Standard they apply to broad-band radiation. In research work, s and k can and should be determined at the relevant wavelength for the study concerned. As general descriptions of a given paper, they are defined here in relation to the C illuminant and the $\bar{y}(\lambda)$ function.

NOTE 2 More exact definitions of the Kubelka-Munk coefficients can be found in CIE Publication No. 38, Section 11.

4 Principle

The luminous reflectance factor of a single sheet of the paper over a black cavity and the intrinsic luminous reflectance factor of the paper are determined by measurement according to ISO 2471, and the grammage is determined according to ISO 536.

The light absorption and light scattering coefficients are then calculated from these data using the Kubelka-Munk theory.

NOTE — These measurements are the same as those required for the determination of opacity (ISO 2471).

5 Apparatus

5.1 Reflectometer, having the geometric, spectral and photometric characteristics described in ISO 2469, Annex A, equipped for the measurement of luminous reflectance factor, and calibrated in accordance with the provisions of ISO 2469, Annex B.

5.2 Filter-function. In the case of a filter reflectometer, a filter that in conjunction with the optical characteristics of the basic instrument gives an overall response equivalent to the CIE tristimulus value Y of the CIE 1931 standard colorimetric system of the test piece evaluated for the CIE standard illuminant C.

In the case of an abridged spectrophotometer, a function that permits calculation of the CIE tristimulus value Y of the CIE 1931 standard colorimetric system of the test piece evaluated for the CIE standard illuminant C using the weighting functions given in Annex A.

5.3 UV-cut-off filter. To eliminate any fluorescence effect, the instrument shall be equipped with a sharp cut-off, UV-absorbing filter having a transmittance not exceeding 0,5 % at and below a wavelength of 410 nm and not exceeding 50 % at a wavelength of 420 nm.

5.4 Two working standards, calibrated in the apparatus concerned against ISO reference standards of level 3 supplied by an authorized laboratory (see ISO 2469). Calibrate the working standards sufficiently frequently to ensure that satisfactory calibration is maintained.

Use new reference standards sufficiently frequently to ensure that the reflectometer is maintained in agreement with the reference instrument.

5.5 Black cavity, having a reflectance factor which does not differ from its nominal value by more than 0,2 %, at all wavelengths. The black cavity should be stored upside down in a dust-free environment or with a protective cover.

NOTE — The condition of the black cavity should be checked by reference to the instrument maker.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

6 Sampling

SIST ISO 9416:2004

<https://standards.iteh.ai/catalog/standards/sist/521e3d8b-a20c-46ea-b181-482a1e000000>

If the tests are being made to evaluate a lot, the sample should be selected in accordance with ISO 186. If the tests are made on another type of sample, make sure that the test pieces taken are representative of the sample received.

7 Preparation of test pieces

Avoiding watermarks, dirt and obvious defects, cut rectangular test pieces approximately 75 mm x 150 mm. Assemble at least ten of the test pieces in a pad with their top sides uppermost; the number of test pieces should be such that doubling the number does not alter the reflectance factor. Protect the pad by placing an additional sheet on both the top and bottom of the pad; avoid contamination and unnecessary exposure to light or heat.

Mark the top test piece in one corner to identify the sample and its top side.

NOTE — If the top side can be distinguished from the wire side, it shall be uppermost; if not, as may be the case for papers manufactured on double-wire machines, ensure that the same side of the sheet is uppermost.

8 Procedure

8.1 Remove the protecting sheets from the test-piece pad. Without touching the test area, use the procedure appropriate to the instrument, and the working standard, to measure the intrinsic reflectance factor R_{∞} of the top side of the test-piece pad. Read and record the value to the nearest 0,05 % of the reflectance factor.