



Designation: A 709/A 709M – 01b^{€3}

Standard Specification for Carbon and High-Strength Low-Alloy Structural Steel Shapes, Plates, and Bars and Quenched-and-Tempered Alloy Structural Steel Plates for Bridges¹

This standard is issued under the fixed designation A 709/A 709M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

^{€1} NOTE—An editorial change was made in Table 7 in March 2002.

^{€2} NOTE—An editorial change was made in Table 3 in May 2002.

^{€3} NOTE—An editorial change was made in Table S1.3 in July 2002.

1. Scope

1.1 This specification covers carbon and high-strength low-alloy steel structural shapes, plates, and bars and quenched and tempered alloy steel for structural plates intended for use in bridges. Eight grades are available in four yield strength levels as follows:

Grade U.S. [SI]	Yield Strength, ksi [MPa]
36 [250]	36 [250]
50 [345]	50 [345]
50S [345S]	50 [345]
50W [345W]	50 [345]
HPS 50W [HPS 345W]	50 [345]
HPS 70W [HPS 485W]	70 [485]
100 [690]	100 [690]
100W [690W]	100 [690]

1.1.1 Grades 36 [250], 50 [345], 50S [345S], 50W [345W], 100 [690], and 100W [690W] are also included in Specifications A 36/A 36M, A 572/A 572M, A 992/A 992M, A 588/A 588M, and A 514/A 514M, respectively. When the supplementary requirements of this specification are specified, they exceed the requirements of Specifications A 36/A 36M, A 572/A 572M, A 992/A 992M, A 588/A 588M, and A 514/A 514M.

1.1.2 Grades 50W [345W], HPS 50W [HPS 345], HPS 70W [HPS 485W], and 100W [690W] have enhanced atmospheric corrosion resistance (see 11.1.2). Product availability is shown in Table 1.

1.2 Grade HPS 70W [HPS 485W], 100 [690], or 100W [690W] shall not be substituted for Grades 36 [250], 50 [345], 50S [345S], 50W [345W], or HPS 50W [HPS 345W]. Grade 50W [345W], or HPS 50W [HPS 345W] shall not be substituted for Grades 36 [250], 50 [345] or 50S [345S] without agreement between the purchaser and the supplier.

1.3 When the steel is to be welded, it is presupposed that a welding procedure suitable for the grade of steel and intended use or service will be utilized. See Appendix X3 of Specification A 6/A 6M for information on weldability.

1.4 Supplementary requirements are available but shall apply only when specified by the purchaser at the time of ordering.

1.5 The values stated in either inch-pound units or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with this specification.

1.6 For structural products cut from coiled product, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification A 6/A 6M apply.

2. Referenced Documents

2.1 ASTM Standards:

- A 6/A 6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling²
- A 36/A 36M Specification for Carbon Structural Steel²
- A 370 Test Methods and Definitions for Mechanical Testing of Steel Products³
- A 435/A 435M Specification for Straight-Beam Ultrasonic Examination of Steel Plates²
- A 514/A 514M Specification for High-Yield-Strength, Quenched and Tempered Alloy Steel Plate, Suitable for Welding²
- A 572/A 572M Specification for High-Strength Low-Alloy Columbium-Vanadium Structural Steel²
- A 588/A 588M Specification for High-Strength Low-Alloy Structural Steel with 50 ksi (345 MPa) Minimum Yield

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock, and Ships.

Current edition approved Oct. 10, 2001. Published January 2002. Originally published as A 709 – 74. Last previous edition A 709/A 709M – 01a.

² Annual Book of ASTM Standards, Vol 01.04.

³ Annual Book of ASTM Standards, Vol 01.03.

 **A 709/A 709M – 01b^{ε3}**

TABLE 1 Tensile and Hardness Requirements^A

NOTE 1— Where “. . .” appears in this table, there is no requirement.

Grade	Plate Thickness, in. [mm]	Structural Shapes Groups	Yield Point or Yield Strength, ^B ksi [MPa]	Tensile Strength, ksi [MPa]	Minimum Elongation, %				Reduction of Area ^{C,D} min, %	Brinell Hard- ness Number
					Plates and Bars ^{E,C}		Shapes ^E			
					8 in. or 200 mm	2 in. or 50 mm	8 in. or 200 mm	2 in. or 50 mm		
36 [250]	to 4 [100], incl	to 426 lb/ft (634 kg/m) over 426 lb/ft (634 kg/m)	36 [250] min 36 [250] min	58–80 [400–550] 58 [400] min	20 ...	23 ...	20 20	21 ^F 19	...	G G
50 [345]	to 4 [100], incl	all	50 [345] min	65 [450] min	18	21	18	21 ^F	...	G
50S [345S]	^H	all	50–65 [345–450] ^I	65 [450] ^I min	18	21	...	G
50W [345W] and HPS 50W [HPS 345W]	to 4 [100], incl	all	50 [345] min	70 [485] min	18	21	18	21 ^J	...	G
HPS 70W [HPS 485 W]	to 4 [100], incl	^H	70 [485] min ^B	85–110 [585–760]	...	19	G
100 [690] and 100W [690W]	to 2½ [65], incl	^H	100 [690] min ^B	110–130 [760–895]	...	18 ^K	40 ^L –50 ^M	235–293 ^G
100 [690] and 100W [690 W]	over 2½ to 4 [65 to 100]	^H	90 [620] min ^B	100–130 [690–895]	...	16 ^K	40 ^L –50 ^M	G

^ASee specimen orientation and preparation subsection in the Tension Tests section of Specification A 6/A 6M.

^BMeasured at 0.2 % offset or 0.5 % extension under load as described in Section 13 of Test Methods A 370.

^CElongation and reduction of area not required to be determined for floor plates.

^DFor plates wider than 24 in. [600 mm], the reduction of area requirement, where applicable, is reduced by five percentage points.

^EFor plates wider than 24 in. [600 mm], the elongation requirement is reduced two percentage points. See elongation requirement adjustments in the Tension Tests section of Specification A 6/A 6M.

^FElongation in 2 in. or 50 mm: 19 % for shapes over 426 lb/ft [634 kg/m].

^GBrinell requirements apply only to material ⅜ in. [10 mm] and thinner for Grades 100 and 100W.

^HNot applicable.

^IThe yield to tensile ratio shall be 0.85 or less.

^JFor wide flange shapes over 426 lb/ft [634 kg/m], elongation in 2 in. of 18 % minimum applies.

^KWhen measured on the Fig. 3 (Test Methods A 370) 1½ -in. [40-mm] wide specimen the elongation is determined in a 2-in. or 50-mm gage length which includes the fracture and shows the greatest elongation.

^LWhen measured on the Fig. 3 (Test Methods A 370) 1½ -in. [40-mm] wide specimen.

^MWhen measured on the Fig. 4 (Test Methods A 370) ½ -in. [12.5-mm] round specimen.

- Point to 4 in. (100 mm) Thick²
- A 673/A 673M Specification for Sampling Procedure for Impact Testing of Structural Steel²
- A 992/A 992M Specification for Steel for Structural Shapes for Use in Building Framing²
- E 112 Test Methods for Determining Average Grain Size⁴
- G 101 Guide for Estimating the Atmospheric Corrosion Resistance of Low-Alloy Steels⁵

3. General Requirements for Delivery

3.1 Material furnished under this specification shall conform to the requirements of the current edition of Specification A 6/A 6M, for the ordered material, unless a conflict exists in which case this specification shall prevail.

3.1.1 Coiled product is excluded from qualification to this specification until leveled and cut to length. Structural products produced from coil means structural products that have been cut to individual lengths from a coiled product and are furnished without heat treatment. The processor decoils, levels, cuts to length, and marks the product. The processor is responsible for performing and certifying all tests, inspections, and operations not intended to affect the properties of the material. For structural products produced from coils, two tests shall be reported for each qualifying coil. See Note 1.

NOTE 1—Additional requirements regarding structural products from coil are described in Specification A 6/A 6M.

4. Materials and Manufacture

4.1 For Grades 36 [250] and 50 [345], the steel shall be semi-killed or killed.

4.2 For Grades 50W [345W], HPS 50W [HPS 345W], and HPS 70W [HPS 485W], the steel shall be made to fine grain practice.

4.3 For Grade 50S [345S], the steel shall be killed. Killed steel is confirmed by a statement of killed steel on the test report or by reporting strong deoxidizers, such as 0.10% or more for silicon or 0.015% or more for aluminum.

4.4 For Grade 50S [345S], the steel shall be made using a practice producing nitrogen not greater than 0.012%; or the steel for Grade 50S shall be made using a practice producing nitrogen not greater than 0.015% and one or more nitrogen-binding elements shall be added.

4.5 Grades HPS 50W [HPS 345W] and HPS 70W [HPS 485W], the steel shall be made using a low-hydrogen practice, such as vacuum degassing during steel making; controlled soaking of the ingots, slabs; controlled slow cooling of the ingots, slabs, or plates, or a combination thereof.

4.6 For Grades 100 [690] and 100W [690W], the requirements for fine austenitic grain size in Specification A 6/A 6M shall be met.

4.7 Grades HPS 50W [HPS 345W] and HPS 70W [HPS 485W] shall be furnished in one of the following conditions:

⁴ Annual Book of ASTM Standards, Vol 03.01.

⁵ Annual Book of ASTM Standards, Vol 03.02.

 **A 709/A 709M – 01b^{e3}**

as-rolled, control-rolled, thermo-mechanical control processed (TMCP) with or without accelerated cooling, or quenched and tempered.

5. Heat Treatment

5.1 For quenched and tempered Grades HPS 50W [HPS 345W] and HPS 70W [HPS 485W], the heat treatment shall be performed by the manufacturer and shall consist of heating the steel to not less than 1650°F [900°C], quenching it in water or oil, and tempering it at not less than 1100°F [590°C]. The heat-treating temperatures shall be reported on the test certificates.

5.2 For Grades 100 [690] and 100W [690W], the heat treatment shall be performed by the manufacturer and shall consist of heating the steel to not less than 1650°F [900°C], quenching it in water or oil, and tempering it at not less than 1150°F [620°C]. The heat-treating temperatures shall be reported on the test certificates.

6. Chemical Requirements

6.1 The heat analysis shall conform to the requirements for the specified grade in Tables 2-7.

6.2 For Grade 50S, in addition to the elements listed in Table 7, test reports shall include, for information, the chemical analysis for tin. Where the amount of tin is less than 0.02%, it shall be permissible for the analysis to be reported as < 0.02%.

6.3 The maximum permissible carbon equivalent value shall be 0.47% for structural shapes in Groups 4 and 5, and 0.45%

for other structural shapes. The carbon equivalent shall be based on heat analysis. The required chemical analysis as well as the carbon equivalent shall be reported. The carbon equivalent shall be calculated using the following formula:

$$CE = C + \frac{Mn}{6} + \frac{(Cr + Mo + V)}{5} + \frac{(Ni + Cu)}{15} \quad (1)$$

7. Tensile Requirements

7.1 The material as represented by test specimens, except as specified in 7.2, shall conform to the requirements for tensile properties prescribed in Table 1.

7.2 For Grade 36 [250] shapes less than 1 in. ²[645 mm²] in cross section and bars, other than flats, less than ½ in. [12.5 mm] in thickness or diameter need not be subjected to tension tests by the manufacturer.

8. Brinell Hardness Requirements for Grades 100 [690] and 100W [690W]

8.1 For plates ¾ in. [10 mm] and under in thickness, a Brinell hardness test may be used instead of tension testing each plate, in which case a tension test specimen shall be taken from a corner of each of two plates per lot. A lot shall consist of plates from the same heat and thickness, same prior condition and scheduled heat treatment and shall not exceed 15 tons [15 Mg] in weight. A Brinell hardness test shall be made on each plate not tension tested and shall meet the requirements shown in Table 1.

TABLE 2 Grade 36 [250] Chemical Requirements (Heat Analysis)

NOTE 1— Where “. . .” appears in this table there is no requirement. The heat analysis for manganese shall be determined and reported as described in the Heat Analysis section of Specification A 6/A 6M.

Product Thickness, in. (mm)	Shapes ^A All	Plates ^B				Bars		
		To ¾ [20], incl	Over ¾ to 1½ [20 to 40], incl	Over 1½ to 2½ [40 to 65], incl	Over 2½ to 4 [65 to 100], incl	To ¾ [20], incl	Over ¾ to 1½ [20 to 40], incl	Over 1½ to 4 [100], incl
Carbon, max, %	0.26	0.25	0.25	0.26	0.27	0.26	0.27	0.28
Manganese, %	0.80–1.20	0.80–1.20	0.85–1.20	...	0.60–0.90	0.60–0.90
Phosphorus, max, %	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04
Sulfur, max, %	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05
Silicon, %	0.40 max	0.40 max	0.40 max	0.15–0.40	0.15–0.40	0.40 max	0.40 max	0.40 max
Copper, min, % when copper steel is specified	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20

^A Manganese content of 0.85 to 1.35 % and silicon content of 0.15 to 0.40 % is required for shapes over 426 lb/ft [634 kg/m].

^BFor each reduction of 0.01 % below the specified carbon maximum, an increase of 0.06 % manganese above the specified maximum will be permitted up to the maximum of 1.35 %.

 **A 709/A 709M – 01b^{ε3}**

TABLE 3 Grade 50 [345] Chemical Requirements^A(Heat Analysis)

Maximum Diameter, Thickness, or Distance Between Parallel Faces, in. [mm]	Carbon, max, %	Manganese, ^B max, %	Phosphorus, max, %	Sulfur, max, %	Silicon ^C		Columbium, Vanadium and Nitrogen
					Plates to 1½ -in. [40-mm] Thick, Shapes to 426 lb/ft [634 kg/m], Bars, Zees and Rolled Tees, max, % ^D	Plates Over 1½ [40-mm] Thick and Shapes Over 426 lb/ft [634 kg/m], %	
4 [100]	0.23	1.35	0.04	0.05	0.40	0.15–0.40	see Footnote ^E

^ACopper when specified shall have a minimum content of 0.20 % by heat analysis (0.18 % product analysis).
^BManganese, minimum by heat analysis of 0.80 % (0.75 % product analysis) shall be required for all plates over ¾ in. [10 mm] in thickness; a minimum of 0.50 % (0.45 % product analysis) shall be required for plates ¾ in. [10 mm] and less in thickness, and for all other products. The manganese to carbon ratio shall not be less than 2 to 1. A maximum of manganese of 1.50 % is permissible, with an associated reduction of the carbon maximum of 0.03 %.
^CSilicon content in excess of 0.40 % by heat analysis must be negotiated.
^DBars over 1½ in. [40 mm] in diameter, thickness, or distance between parallel faces, shall be made by a killed steel practice.
^EAlloy content shall be in accordance with Type 1, 2, 3, 4, or 5 and the contents of the applicable elements shall be reported on the test report.

Type	Elements	Heat Analysis, %
1	Columbium ^A	0.005–0.05 ^B
2	Vanadium	0.01–0.15
3	Columbium ^A Vanadium	0.005–0.05 ^B 0.01–0.15
4	Columbium plus vanadium Vanadium Nitrogen	0.02–0.15 ^C 0.01–0.15 ^D 0.015 max ^D
5	Titanium Nitrogen Vanadium	0.006–0.04 0.003–0.015 0.06 max

^AColumbium shall be restricted to Grade 50 [345] plate, bar, zee, and rolled tee thickness of ¾ in. [20 mm] max, and to shapes of Groups 1 and 2 (see Table A of Specification A6/A6M) unless killed steel if furnished. Killed steel shall be confirmed by a statement of killed steel on the test report, or by a report of the presence of a sufficient quantity of a strong deoxidizing element, such as silicon at 0.10 % or higher, or aluminum at 0.015 % or higher.
^BProduct analysis limits = 0.004 to 0.06 %.
^CProduct analysis limits = 0.01 to 0.16 %
^DThe vanadium to nitrogen ratio shall be 4 to 1 or greater.

TABLE 4 Grade 50W [345 W] Chemical Requirements (Heat Analysis)

NOTE 1—Types A, B, and C are equivalent to Specification A 588/A 588M Grades A, B, and C, respectively.

Element	Composition, % ^A		
	Type A	Type B	Type C
Carbon	0.19 max	0.20 max	0.15 max
Manganese	0.80–1.25	0.75–1.35	0.80–1.35
Phosphorus	0.04 max	0.04 max	0.04 max
Sulfur	0.05 max	0.05 max	0.05 max
Silicon	0.30–0.65	0.15–0.50	0.15–0.40
Nickel	0.40 max	0.50 max	0.25–0.50
Chromium	0.40–0.65	0.40–0.70	0.30–0.50
Copper	0.25–0.40	0.20–0.40	0.20–0.50
Vanadium	0.02–0.10	0.01–0.10	0.01–0.10

^AWeldability data for these types have been qualified by FHWA for use in bridge construction.

9. Test Specimens and Number of Tension Tests

9.1 For Grades 36 [250], 50 [345], and 50W [345W], and non-quenched and tempered Grades HPS 50W [HPS 345W]

and HPS 70W [HPS 485W], location and condition, number of tests, and preparation of test specimens shall meet the requirements of Specification A 6/A 6M.

9.2 The following requirements, which are in addition to those of Specification A 6/A 6M, shall apply only to Grades 100 [690] and 100W [690W] and quenched and tempered Grades HPS 50W [HPS 345W] and HPS 70W [HPS 485 W].

9.2.1 When possible, all test specimens shall be cut from the plate in its heat-treated condition. If it is necessary to prepare test specimens from separate pieces, all of these pieces shall be full thickness, and shall be similarly and simultaneously heat treated with the material. All such separate pieces shall be of such size that the prepared test specimens are free of any variation in properties due to edge effects.

9.2.2 After final heat treatment of the plates, one tension test specimen shall be taken from a corner of each plate as heat treated (except as specified in 8.1).

NOTE 2—The term “plate” identifies the “plate as heat treated.”