

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Plastic films for electrical purposes –
Part 3: Specifications for individual materials – Sheet 8: Balanced biaxially
oriented polyethylene naphthalate (PEN) films used for electrical insulation**

**Films plastiques à usages électriques –
Partie 3: Spécifications pour matériaux particuliers – Feuille 8: Films de
polynaphtalate d'éthylène (PEN), à orientation bi-axiale équilibrée, utilisés
dans l'isolation électrique**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2011 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

[IEC 60674-3-8:2011](mailto:IEC.60674-3-8:2011)

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Plastic films for electrical purposes –
Part 3: Specifications for individual materials – Sheet 8: Balanced biaxially
oriented polyethylene naphthalate (PEN) films used for electrical insulation**

**Films plastiques à usages électriques –
Partie 3: Spécifications pour matériaux particuliers – Feuille 8: Films de
polynaphtalate d'éthylène (PEN), à orientation bi-axiale équilibrée, utilisés
dans l'isolation électrique**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

M

ICS 29.035.20

ISBN 978-2-88912-587-6

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Classification.....	6
4 Designation.....	6
5 General requirements.....	7
6 Dimensions.....	7
6.1 Thickness.....	7
6.2 Width.....	7
7 Properties.....	8
7.1 Properties not dependent on thickness.....	8
7.2 Properties dependent on thickness.....	9
7.3 Other properties.....	10
7.3.1 Thermal endurance.....	10
7.3.2 Burning characteristics.....	10
8 Roll characteristics for all types.....	11
8.1 Roll diameter/film length.....	11
8.2 Windability/sag.....	11
8.2.1 General.....	11
8.2.2 For films of width less than 150 mm.....	11
8.2.3 For films of width 150 mm and above.....	11
8.3 Joins.....	11
8.4 Roll width.....	12
8.5 Cores.....	12
Table 1 – Properties not dependent on thickness.....	8
Table 2 – Properties dependent on thickness.....	9
Table 3 – Electric strength (a.c. test) for all types.....	10
Table 4 – Electric strength (d.c. test) type 2 only.....	10
Table 5 – Windability.....	11
Table 6 – Maximum permissible number of joins or breaks per roll.....	11
Table 7 – Film width.....	12

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PLASTIC FILMS FOR ELECTRICAL PURPOSES –

**Part 3: Specifications for individual materials –
Sheet 8: Balanced biaxially oriented polyethylene
naphthalate (PEN) films used for electrical insulation**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60674-3-8 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

The text of this standard is based on the following documents:

FDIS	Report on voting
15/631/FDIS	15/643/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60674 series, under the general title *Plastic films for electrical purposes*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 60674-3-8:2011](#)

<https://standards.iteh.ai/catalog/standards/sist/9b5ce44c-3002-48ec-b4ee-4c21d8b6aebf/iec-60674-3-8-2011>

INTRODUCTION

This International Standard is one of a series which deals with plastic films for electrical purposes.

The series consists of three parts:

Part 1: Definitions and general requirements (IEC 60674-1).

Part 2: Methods of test (IEC 60674-2).

Part 3: Specifications for individual materials (IEC 60674-3).

This standard contains one of the sheets comprising part 3, as follows:

Sheet 8: Balanced biaxially oriented polyethylene naphthalate (PEN) films used for electrical insulation.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[IEC 60674-3-8:2011](https://standards.iteh.ai/catalog/standards/sist/9b5ce44c-3002-48ec-b4ee-4c21d8b6aebf/iec-60674-3-8-2011)

<https://standards.iteh.ai/catalog/standards/sist/9b5ce44c-3002-48ec-b4ee-4c21d8b6aebf/iec-60674-3-8-2011>

PLASTIC FILMS FOR ELECTRICAL PURPOSES –

Part 3: Specifications for individual materials – Sheet 8: Balanced biaxially oriented polyethylene naphthalate (PEN) films used for electrical insulation

1 Scope

This International Standard gives the requirements for balanced biaxially oriented polyethylene naphthalate (PEN) films for use as electrical insulation.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application should be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

Safety warning: it is the responsibility of the user of the methods contained or referred to in this document to ensure that they are used in a safe manner.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[https://standards.iteh.ai/catalog/standards/sist/9b5ce44c-3002-48ec-b4ee-](https://standards.iteh.ai/catalog/standards/sist/9b5ce44c-3002-48ec-b4ee-421d9b6ebf7a-60674-3-8-2011)

IEC 60674-1:1980, *Specification for plastic films for electrical purposes – Part 1: Definitions and general requirements*

IEC 60674-2:1988, *Specification for plastic films for electrical purposes – Part 2: Methods of test*

IEC60068-2-66:1994, *Environmental testing – Part 2: Test methods – Test Cx: Damp heat, steady state (unsaturated pressurized vapour)*

IEC 60216-5:2008, *Electrical insulating materials – Thermal endurance properties – Part 5: Determination of relative thermal endurance index (RTE) of an insulating material*

ISO11357-3:1999, *Plastics – Differential scanning calorimetry (DSC) – Part 3: Determination of temperature and enthalpy of melting and crystallization*

3 Classification

The PEN film shall be of the following types:

- Type 1a: General purpose, high hydrolytic stability grade.
- Type 1b: General purpose, standard grade.
- Type 2: Capacitor grade.

4 Designation

The plastic film shall be identified by the following designation:

Designation of the film - IEC 60674-3-8 - PEN - type - thickness in micrometres - width in millimetres - length in metres - colour.

Example:

Polyethylene naphthalate - IEC 60674-3-8 - PEN - type 1b - 100 - 20 - 200 – nc
(nc = natural colour; other colours according to IEC 60757).

5 General requirements

The material shall be made from polyethylene naphthalate; it shall be biaxially oriented with an approximately balanced orientation and shall conform to the requirements laid down in IEC 60674-1.

For certain applications additives to the base material may be present (e.g. pigments, dyes). Where such additives are included, they shall not affect the requirements for any of the properties listed for that type unless otherwise specified.

6 Dimensions

6.1 Thickness

The film thickness shall be measured by a gravimetric method in accordance with the requirements of Subclause 3.3 of IEC 60674-2.

NOTE There are no requirements for thickness in this standard but preferred thicknesses in μm are as follows:

1,2; 1,3; 1,5; 1,8; 1,9; 2; 2,1; 2,3; 3; 3,5; 4; 5; 6; 8; 9; 12; 16; 19; 20; 25; 38; 45; 50; 75; 89; 100; 125; 188; 200; 250.

[IEC 60674-3-8:2011](https://standards.iteh.ai/catalog/standards/sist/9b5ce44c-3002-48ec-b4ee-4c2fd8b6aebf/iec-60674-3-8-2011)

The thickness tolerance shall comply with the requirements in Subclause 4.1 of IEC 60674-1 unless otherwise specified in the purchase contract.

6.2 Width

The film width shall be measured in accordance with the requirements of Clause 5 of IEC 60674-2.

Preferred widths cannot be given on account of the great variety of applications.

The tolerance on the width shall comply with the requirements of Subclause 4.2 of IEC 60674-1 except for slot closure applications where on a width of less than 25 mm a tolerance of $x_{-0,3}^{0,0}$ mm is specified as an alternative.

7 Properties

7.1 Properties not dependent on thickness

Table 1 – Properties not dependent on thickness

Property	Requirements	Units	IEC 60674- 2 Test method Subclause	Type
Density - normal	1 350 ± 20	kg/m ³	4, Method D	1a,1b and 2
Melting- point	270 ± 5 ^a	°C	–	1a,1b and 2
Permittivity	2,6 ± 0,5	–	16.1 (23 °C, 1 kHz) ^b	1a,1b and 2
Dissipation factor	<5 × 10 ⁻³	–	16.1 (23 °C, 48 Hz – 62 Hz) ^b	1a,1b and 2
	<9 × 10 ⁻³	–	16.1 (23 °C, 1 kHz) ^b	1a and 1b
Volume resistivity	>10 ¹⁶	Ω × m	15 ^c	1a and 1b
	>10 ¹⁶			2
Surface resistivity	>10 ¹⁴	Ω	14 ^c	1a and 1b
	>10 ¹⁵			2
<p>^a DSC method according to ISO 11357-3.</p> <p>^b Use non-contacting electrodes or evaporated metal electrodes.</p> <p>^c Measurement conditions shall be 23 °C and 50 % r.h. after 24 h exposure. The test voltages are 100 V ± 10 V for thicknesses > 10 µm and 10 V for thicknesses ≤ 10 µm.</p>				

7.2 Properties dependent on thickness

Table 2 – Properties dependent on thickness

Property	Requirements			Units	IEC 60674- 2 Test method Subclause	Type
	≤15 μm	>15 μm up to 100 μm	>100 μm up to 250 μm			
Tensile strength (either direction) Minimum value						
- Initial value	180 ^a	120	95	MPa	10 ^b	1a, 1b and 2
- After exposure to unsaturated damp heat for 96 h ^c	130 ^a	100	90			1a
	110 ^a	90	85			1b and 2
Elongation at break (either direction) Minimum value						
- Initial value	35 ^a	40	40	%	10 ^b	1a, 1b and 2
- After exposure to unsaturated damp heat for 96 h ^c	20 ^a	20	20			1a
	10 ^a	10	10			1b and 2
Dimensional change (shrinkage either direction)						
	1,3	1,0	0,8	%	23 (150 °C, 15 min)	1a, 1b and 2
	6,5	3,5	1,6		23 (200 °C, 10 min)	1a, 1b and 2
Electric strength	See Tables 3 and 4				18.1, a.c. ^d	1a, 1b and 2
					18.2, d.c.	2
^a No requirement for film thicknesses below 5 μm. ^b Rate of extension 100 mm/min, reference lines 100 mm apart. ^c Exposure to unsaturated damp heat (unsaturated pressurized vapour), 120 °C, 85 % r.h. according to Clauses 3 to 9 in IEC 60068-2-66. ^d Method to use 6 mm diameter electrodes. For materials of thicknesses 100 μm or less, tests shall be made in air using a rate of rise of voltage of 500 V/s. For materials thicker than 100 μm, tests shall be made in transformer oil in accordance with IEC60243-1.						