SLOVENSKI STANDARD
SIST EN 3469:2009

01-november-2009

Aeronavtika - Jeklo FE-PM1802 (X5CrNiCu15-5) - Pretaljeno s talilno elektrodo - Ģarjeno v topilu in utrjeno - Izkovki - a ali D Ò200 mm - Rm Ó1310 MPa

Aerospace series - Steel FE-PM1802 (X5CrNiCu15-5) - Consumable electrode remelted - Solution treated and precipitation treated - Forgings - a or D Ò200 mm - Rm Ó1 310 MPa

Luft- und Raumfahrt - Stahl FE-PM1802 (X5CrNiCu15-5) - Mit selbstverzehrender Elektrode umgeschmolzen - Lºsungsgegl¿ht und ausgelagert - Schmiedest¿cke - a oder D Ò200 mm - Rm Ó1310 MPa

S®rie a®rospatiale - Acier FE-PM1802 (X5CrNiCu15-5) - Refondu ¨ l'®lectrode consommable - Mis en solution et vieilli - Pi¯ces forg®es et pi¯ces matric®es - a ou D Ò 200 mm - Rm Ó1310 MPa

Ta slovenski standard je istoveten z: **EN 3469:2009**

ICS:

49.025.10 Jekla Steels

SIST EN 3469:2009 **en,de**

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

EN 3469

September 2009

ICS 49.025.10

English Version

Aerospace series - Steel FE-PM1802 (X5CrNiCu15-5) - Consumable electrode remelted - Solution treated and precipitation treated - Forgings - a or D ≤ 200 mm - Rm ≥ 1 310 MPa

Série aérospatiale - Acier FE-PM1802 (X5CrNiCu15-5) - Refondu à l'électrode consommable - Mis en solution et vieilli - Pièces forgées et pièces matricées - a ou D ≤ 200 mm - Rm ≥ 1 310 MPa

Luft- und Raumfahrt - Stahl FE-PM1802 (X5CrNiCu15-5) - Mit selbstverzehrender Elektrode umgeschmolzen - Lösungsgeglüht und ausgelagert - Schmiedestücke - a oder D ≤ 200 mm - Rm ≥ 1 310 MPa

This European Standard was approved by CEN on 8 August 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Ref. No. EN 3469:2009: E

Foreword

This document (EN 3469:2009) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2010, and conflicting national standards shall be withdrawn at the latest by March 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-5.

1 Scope

This standard specifies the requirements relating to:

Steel FE-PM1802 (X5CrNiCu15-5)
Consumable electrode remelted
Solution treated and precipitation treated
Forgings
a or *D* ≤ 200 mm
R_m ≥ 1 310 MPa

for aerospace applications.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2043, *Aerospace series — Metallic materials — General requirements for semi-finished product qualification (excluding forgings and castings).* [1)]

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use.*

EN 4500-5, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 5: Specific rules for steels.* [1)]

EN 4700-006, *Aerospace series — Steel and heat resisting alloy — Wrought products — Technical specification — Part 006: Pre-production and production forgings.* [1)]

1) Published as ASD Prestandard at the date of publication of this standard.

			C	Si	Mn	P	S	Cr	Mo	Ni	Cu	Nb + Ta	Fe
1	Material designation		Steel FE-PM1802 (X5CrNiCu15-5)										
2	Chemical composition %	Element	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	Nb + Ta	Fe
		min.	–	–	–	–	–	14,0	–	3,5	2,5	5 × C	Base
		max.	0,07	1,00	1,00	0,030	0,015	15,5	0,50	5,5	4,5	0,45	
3	Method of melting		Consumable electrode remelted										
4.1	Form		Forgings										
4.2	Method of production		Forged from forging stock										
4.3	Limit dimension(s)	mm	*a* or *D* ≤ 200										
5	Technical specification		EN 4700-006										

6.1	Delivery condition	Solution treated	Solution treated and precipitation treated
	Heat treatment	1 025 °C ≤ θ ≤ 1 055 °C / t ≥ 30 min / AC or OQ + cool to θ ≤ 30 °C	1 025 °C ≤ θ ≤ 1 055 °C / t ≥ 30 min / AC or OQ + cool to θ ≤ 30 °C + 465 °C ≤ θ ≤ 495 °C / t ≥ 1 h / AC
6.2	Delivery condition code	W	U
7	Use condition	Solution treated and precipitation treated	Delivery condition
	Heat treatment	Delivery condition + 465 °C ≤ θ ≤ 495 °C / t ≥ 1 h / AC	–

Characteristics

8.1	Test sample(s)				See EN 4700-006.			
8.2	Test piece(s)				See EN 4700-006.			
8.3	Heat treatment				Solution treated	Use condition		
9	Dimensions concerned			mm	*a* or *D* ≤ 200	*a* or *D* ≤ 75	75 < *a* or *D* ≤ 200	
10	Thickness of cladding on each face			%	–	–	–	
11	Direction of test piece				–	L	L	T
12	T	Temperature	θ	°C	–	Ambient	Ambient	Ambient
13	T	Proof stress	$R_{p0,2}$	MPa	–	≥ 1 170	≥ 1 170	≥ 1 170
14	T	Strength	R_m	MPa	–	≥ 1 310	≥ 1 310	≥ 1 310
15	T	Elongation	A	%	–	≥ 9	≥ 7	≥ 5
16	T	Reduction of area	Z	%	–	≥ 35	≥ 25	≥ 15
17	Hardness				≤ 363 HB	388 ≤ HB ≤ 444	388 ≤ HB ≤ 444	388 ≤ HB ≤ 444
18	Shear strength		R_c	MPa	–			
19	Bending		k	–	–			
20	Impact strength				–			
21	C	Temperature	θ	°C	–			
22	C	Time		h	–			
23	C	Stress	σ_a	MPa	–			
24	C	Elongation	a	%	–			
25	C	Rupture stress	σ_R	MPa	–			
26	C	Elongation at rupture	A	%	–			
27	Notes (see line 98)				–			

34	Grain size	–	See EN 4700-006.
		7	G ≥ 5
44	External defects	–	See EN 4700-006.
		1	Visual
50	Cleanliness/inclusion content (micro-cleanness)	–	See EN 4700-006.
		7	Category 4
61	Internal defects	–	See EN 4700-006.
		6	*a* or *D* ≤ 100 mm may be tested either on the product or at an earlier stage of manufacturing.
		7	Class 3
82	Batch uniformity	–	See EN 4700-006.
95	Marking inspection	–	See EN 4700-006.
96	Dimensional inspection	–	See EN 4700-006.
98	Notes	–	–
99	Typical use	–	–

100	–	Product qualification	–	See EN 2043.
				Qualification programme to be agreed between manufacturer and purchaser.