



Designation: A 139 – 00

## Standard Specification for Electric-Fusion (Arc)-Welded Steel Pipe (NPS 4 and Over)<sup>1</sup>

This standard is issued under the fixed designation A 139; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification covers five grades of electric-fusion (arc)-welded straight-seam or helical-seam steel pipe. Pipe of NPS 4 (Note 1) and larger with nominal (average) wall thickness of 1.0 in. (25.4 mm) and less are covered. Listing of standardized dimensions are for reference (Note 2). The grades of steel are pipe mill grades having mechanical properties which differ from standard plate grades. The pipe is intended for conveying liquid, gas, or vapor.

NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size.”

NOTE 2—A comprehensive listing of standardized pipe dimensions is contained in ANSI B 36.10.<sup>2</sup>

NOTE 3—The suitability of pipe for various purposes is somewhat dependent on its dimensions, properties, and conditions of service. For example, for high-temperature service see applicable codes and Specification A 691.

1.2 The values stated in inch-pound units are to be regarded as the standard.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products<sup>2</sup>

A 691 Specification for Carbon and Alloy Steel Pipe, Electric Fusion-Welded for High-Pressure Service at High Temperatures<sup>2</sup>

A 751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products<sup>2</sup>

E 59 Practice for Sampling Steel and Iron for Determination of Chemical Composition<sup>3</sup>

#### 2.2 American Welding Society Standard:<sup>4</sup>

ANSI/AWS B2.1 Standard for Welding Procedure and Performance Qualifications Welding Handbook, Vol 1, 8th ed

2.3 ASME Standard:<sup>5</sup>

ASME Boiler and Pressure Vessel Code: Section IX, Welding Qualifications

### 3. Ordering Information

3.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

3.1.1 Quantity (feet or number of lengths),

3.1.2 Name of material (electric-fusion-(arc) welded steel pipe),

3.1.3 Grade (Table 1),

3.1.4 Size (NPS, or outside diameter, and nominal wall thickness, or schedule number),

3.1.5 Lengths (specific or random, Section 17),

3.1.6 End finish (Section 18),

3.1.7 Hydrostatic test pressure (Section 16, Note 8, and Note 9),

3.1.8 ASTM specification designation, and

3.1.9 End use of material.

### 4. Process

4.1 The steel shall be made by one or more of the following processes: open-hearth, basic-oxygen, or electric-furnace.

4.2 Steel may be cast in ingots or may be strand cast. When steels of different grades are sequentially strand cast, identification of the resultant transition material is required. The producer shall remove the transition material by any established procedure that positively separates the grades.

NOTE 4—The term “basic-oxygen steelmaking” is used generically to describe processes in which molten iron is refined to steel under a basic slag in a cylindrical furnace lined with basic refractories, by directing a jet of high-purity gaseous oxygen onto the surface of the hot metal bath.

### 5. Manufacture

5.1 The longitudinal edges of the steel shall be shaped to give the most satisfactory results by the particular welding

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys, and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved March 10, 2000. Published June 2000. Originally published as A 139 – 32 T. Last previous edition A 139 – 96<sup>ε</sup>.

<sup>2</sup> Annual Book of ASTM Standards, Vol 01.01.

<sup>3</sup> Discontinued 1996; see 1995 Annual Book of ASTM Standards, Vol 03.05.

<sup>4</sup> Available from American Welding Society, 550 NW LeJeune Rd., Miami, FL 33135.

<sup>5</sup> Available from American Society of Mechanical Engineers, Three Park Ave., New York, NY 10016-5990.

**TABLE 1 Chemical Requirements**

Element	Composition, max, %				
	Grade A	Grade B	Grade C	Grade D	Grade E
Carbon	0.25	0.26	0.28	0.30	0.30
Manganese	1.00	1.00	1.20	1.30	1.40
Phosphorus	0.035	0.035	0.035	0.035	0.035
Sulfur	0.035	0.035	0.035	0.035	0.035

process employed. The weld shall be made by automatic (Note 5) means (except tack welds if used) and shall be of reasonably uniform width and height for the entire length of the pipe.

NOTE 5—Upon agreement between the purchaser and the manufacturer, manual welding by qualified procedure and welders may be used as an equal alternative under these specifications.

5.2 All weld seams made in manufacturing pipe shall be made using complete joint penetration groove welds.

**6. Chemical Composition**

6.1 The steel shall conform to the chemical requirements prescribed in Table 1 and the chemical analysis shall be in accordance with Test Methods, Practices, and Terminology A 751.

**7. Tensile Requirements for the Steel**

7.1 Longitudinal tension test specimens taken from the steel shall conform to the requirements as to tensile properties prescribed in Table 2. At the manufacturer’s option, the tension test specimen for sizes 8 5/8 in. (219.1 mm) in outside diameter and larger may be taken transversely as described in 19.4.

7.2 The yield point shall be determined by the drop of the beam, by the halt in the gage of the testing machine, by the use of dividers, or by other approved methods. The yield strength corresponding to a permanent offset of 0.2 % of the gage length of the specimen, or to a total extension of 0.5 % of the gage length under load shall be determined.

**8. Tensile Requirements of Production Welds**

8.1 Reduced-section tension test specimens taken perpendicularly across the weld in the pipe, with the weld reinforcement removed, shall show a tensile strength not less than 95 % of the minimum specified in Section 7. At the manufacturer’s option, the test may be made without removing the weld reinforcement, in which case the tensile strength shall be not less than that specified in Section 7.

**TABLE 2 Tensile Requirements**

	Grade A	Grade B	Grade C	Grade D	Grade E
Tensile strength, min, ksi (MPa)	48 (330)	60 (415)	60 (415)	60 (415)	66 (455)
Yield strength, min, ksi (MPa)	30 (205)	35 (240)	42 (290)	46 (315)	52 (360)
Elongation in 2 in. or 50 mm, min, %:					
Basic minimum elongation for walls 5/16 in. (7.9 mm) and over in thickness, longitudinal strip tests	35	30	25	23	22
For longitudinal strips tests, a deduction for each 1/32-in. (0.8-mm) decrease in wall thickness below 5/16 in. (7.9 mm) from the basic minimum elongation of the following percentage <sup>A</sup>	1.75 <sup>A</sup>	1.50 <sup>A</sup>	1.25	1.50	2.0
Elongation in 8 in. (203.2 mm), in min, % <sup>B,C</sup>	1 500 000 specified tensile strength (psi)				

<sup>A</sup> The table below gives the computed minimum values.

<sup>B</sup> For wall thicknesses 1/2 in. (12.7 mm) and greater, the elongation may be taken in 8 in. (203.2 mm).

<sup>C</sup> The elongation in 8 in. (203.2 mm) need not exceed 30 %.

Wall Thickness		Elongation in 2 in. or 50 mm, min, %	
in.	mm	Grade A	Grade B
5/16 (0.312)	7.94	35.00	30.00
9/32 (0.281)	7.14	33.25	28.50
1/4 (0.250)	6.35	31.50	27.00
7/32 (0.219)	5.56	29.75	25.50
3/16 (0.188)	4.76	28.00	24.00
5/32 (0.156)	3.97	26.25	22.50
1/8 (0.125)	3.68	24.50	21.00
3/32 (0.094)	2.38	22.75	19.50
1/16 (0.062)	1.59	21.00	18.00

Note—The above table gives the computed minimum elongation values for each 1/32-in. (0.79-mm) decrease in wall thickness. Where the wall thickness lies between two values shown above, the minimum elongation value shall be determined by the following equation:

Grade	Equation
A	$E = 56t + 17.50$
B	$E = 48t + 15.00$
C	$E = 40t + 12.50$
D	$E = 48t + 8$
E	$E = 64t + 2$

where:

- $E$  = elongation in 2 in., %, and
- $t$  = actual thickness of specimen, in.

## 9. Heat Analysis

9.1 An analysis of each heat of steel shall be made by the manufacturer to determine the percentages of the elements specified in Section 6. This analysis shall be made from a test ingot taken during the pouring of the heat. When requested by the purchaser, the chemical composition thus determined shall be reported to the purchaser or his representative, and shall conform to the requirements specified in Section 6.

## 10. Product Analysis

10.1 An analysis may be made by the purchaser on samples of pipe selected at random and shall conform to the requirements specified in Section 6. Samples for chemical analysis, except for spectrochemical analysis, shall be taken in accordance with Method E 59. The number of samples shall be determined as follows:

NPS	Number of Samples Selected
Under 14	2 for each lot of 200 pipes or fraction thereof
14 to 36, incl	2 for each lot of 100 pipes or fraction thereof
Over 36	2 for each 3000 ft or fraction thereof

10.2 *Retests*—If the analysis of either length of pipe or length of skelp does not conform to the requirements specified in Section 6, analyses of two additional lengths from the same lot shall be made, each of which shall conform to the requirements specified.

## 11. Dimensions, Weight, and Permissible Variations

11.1 *Weight*—The specified weight per unit length shall be calculated using the following equation:

$$W = C(D - t)t \quad (1)$$

where:

$C$  = 10.69 (0.02466),

$W$  = weight per unit length, lb/ft (kg/m),

$D$  = outside diameter, in. (mm), specified or calculated (from inside diameter and wall thickness), and

$t$  = specified wall thickness, in. (to 3 decimal places) (mm) (to 2 decimal places)

NOTE 6—The weights given in the American National Standards and the calculated weights given by the equation of 11.1 are based on the weights for carbon steel pipe. The weight of pipe made of ferritic stainless steels may be about 5 % less, and that made of austenitic stainless steel about 2 % greater than the values given. The specified weight of an individual pipe length shall be calculated as its specified weight per unit length times its length.

11.1.1 The weight of any length of pipe shall not vary more than 10 % over the specified weight.

11.1.2 The weight of any length of pipe shall not vary more than 5 % under the specified weight when the specified wall thickness is 0.188 in. (4.78 mm) or less or more than 5.5 % under when the specified wall thickness is greater than 0.188 in. (4.78 mm).

11.1.3 The weight of a carload lot shall not vary more than 1¾ % under the specified weight. A carload lot is considered to be a minimum of 40 000 lb (18 144 kg) shipped on a conveyance.

11.2 *Thickness*—The minimum wall thickness at any point shall be not more than 12.5 % under the nominal wall thickness specified.

11.3 *Circumference*—The pipe shall be substantially round. The outside circumference of the pipe shall not vary more than ±1.0 %, but not exceeding ±¾ in. (19.0 mm), from the nominal outside circumference based upon the diameter specified, except that the circumference at ends shall be sized, if necessary, to meet the requirements of Section 18.

11.4 *Straightness*—Finished pipe shall be commercially straight. When specific straightness requirements are desired, the order should so state, and the tolerance shall be a matter of agreement between the purchaser and the manufacturer.

11.5 *Ovality (Out-of-Roundness)*—The pipe diameter, within 4.0 in. (100 mm) of ends, shall not vary more than 1 % from the specified diameter as measured across any single plane with a bar gage, caliper, or other instrument capable of measuring actual diameter.

## 12. Finish

12.1 *Repair by Welding*—The manual, or automatic arc, welding of injurious defects in the pipe wall, provided their depth does not exceed one third the specified wall thickness, will be permitted. Defects in the welds, such as sweats or leaks, shall be repaired or the piece rejected at the option of the manufacturer. Repairs of this nature shall be made by completely removing the defect, cleaning the cavity, and then welding.

12.2 All repaired pipe shall be tested hydrostatically in accordance with Section 16.

## 13. Retests

13.1 If any specimen tested under Sections 8 or 15 fails to meet the requirements, retests of two additional specimens from the same lot of pipe shall be made, all of which shall meet the specified requirements. If any of the retests fail to conform to the requirements, test specimens may be taken from each untested pipe length, at the manufacturer's option, and each specimen shall meet the requirements specified, or that pipe shall be rejected.

## 14. Number of Production Test Specimens

14.1 One longitudinal tension test specimen specified in 19.2 shall be made from the steel of each heat, or fraction thereof, used in the manufacture of the pipe.

14.2 One reduced-section production weld test specimen specified in 19.5 shall be taken from a length of pipe from each lot of 3000 ft (914 m) of pipe, or fraction thereof, of each size and wall thickness.

14.3 If any test specimen shows defective machining or develops flaws not associated with the quality of the steel or the welding, it may be discarded and another specimen substituted.

14.4 Each length of pipe shall be subjected to the hydrostatic test specified in Section 16.

## 15. Qualification of Welding Procedure

15.1 Welding procedures shall be qualified in accordance with the requirements of ANSI/AWS B2.1; ASME Boiler and Pressure Vessel Code, Section IX; or other qualification procedures as noted in the American Welding Society Welding Handbook. Tests and test values shall be as specified in 15.2 and 15.3.