



Designation: C 406 – 00

Standard Specification for Roofing Slate¹

This standard is issued under the fixed designation C 406; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the material characteristics, physical requirements, and sampling appropriate to the selection of slate for use as roof shingles.

1.2 Slates not included in this specification are those containing soft carbonaceous ribbons. The wide variation in physical properties and composition of such ribbon slates render their service life uncertain under some conditions of use.

2. Referenced Documents

2.1 ASTM Standards:

- C 119 Terminology Relating to Dimension Stone²
- C 120 Methods of Flexure Testing of Slate (Modulus of Rupture, Modulus of Elasticity)²
- C 121 Test Method for Water Absorption of Slate²
- C 217 Test Method for Weather Resistance of Slate²

3. Terminology

3.1 *Definitions*—Definitions shall be in accordance with Terminology C 119.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *service life*—a period of time over which the slate material is expected to require no repair or replacement due to weathering.

3.2.2 *ribbons*—narrow bands of carbonaceous material, darker in color than the surrounding slate. These ribbons are inclusions of the original beds and are softer and less durable than the surrounding material.

4. Classification

4.1 Roofing slate shall be classified by grade in accordance with the physical requirements of Table 1.

4.2 Expected service life of the various grades, depending on geographic location and environmental exposure, is as follows:

Grade	Service Life (years)
Grade S ₁	over 75
Grade S ₂	40 to 75
Grade S ₃	20 to 40

TABLE 1 Physical Requirements

Classification	Modulus of Rupture Across the Grain, min, psi (MPa) ^A	Absorption, max, % ^B	Depth of Softening, max, in. (mm) ^C
Grade S ₁	9000 (62)	0.25	0.002 (0.05)
Grade S ₂	9000 (62)	0.36	0.008 (0.20)
Grade S ₃	9000 (62)	0.45	0.014 (0.36)

^A See Methods C 120.

^B See Test Method C 121.

^C See Test Method C 217.

5. Ordering Information

5.1 *Color*—The following color nomenclature is commonly used:

Black	Mottled purple and green
Blue black	Green
Gray	Purple variegated
Blue gray	Red
Purple	Weathering green (changes to buff or brown)

5.2 *Standard Roofs*—Sloping roofs utilizing a nominal thickness of 3/16 to 1/4 in. (4.8 to 6.4 mm), are known as standard roofs. These shingles shall be rectangular unless otherwise specified. These shingles shall be machine punched or drilled for two nails located for proper headlap.

5.3 *Textural Roofs*—Sloping roofs utilizing various sizes, thicknesses, textures, and colors for architectural effects, are known as textural roofs. These shingles shall be machine punched or drilled for two nails located for proper headlap.

5.4 *Graduated Roofs*—Sloping roofs utilizing a greater range of sizes, thicknesses, and exposed lengths of shingles, are known as graduated roofs. The slates are arranged on the roof so that the thickest and longest occur at the eaves and gradually diminish in size and thickness toward the ridges. These shingles shall be machine punched or drilled for two nails located for proper headlap.

6. Physical Requirements

6.1 Slate supplied under this specification shall conform to the physical requirements listed in Table 1.

¹ This specification is under the jurisdiction of ASTM Committee C-18 on Dimension Stone and is the direct responsibility of Subcommittee C18.03 on Material Specifications.

Current edition approved April 10, 2000. Published June 2000. Originally published as C 406 – 57 T. Last previous edition C 406 – 89 (1996).

² *Annual Book of ASTM Standards*, Vol 04.07.