



## Standard Test Method for Volatile Content of Coatings<sup>1</sup>

This standard is issued under the fixed designation D 2369; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This test method describes a procedure for the determination of the weight percent volatile content of solventborne and waterborne coatings. Test specimens are heated at  $110 \pm 5^\circ\text{C}$  for 60 min.

NOTE 1—The coatings used in these round-robin studies represented air-dried, air-dried oxidizing, heat-cured baking systems, and also included multicomponent paint systems.

1.2 Sixty minutes at  $110 \pm 5^\circ\text{C}$  is a general purpose test method based on the precision obtained with both solventborne and waterborne coatings (see Section 9). These coatings (single package, heat cured) are commonly applied in factories to automobiles, metal containers, flat (coil) metal and large appliances, and many other metal parts.

1.3 This test method is viable for coatings wherein one or more parts may, at ambient conditions, contain liquid coreactants that are volatile until a chemical reaction has occurred with another component of the multi-package system.

NOTE 2—Committee D-1 has run round-robin studies on volatiles of multicomponent paint systems. The only change in procedure is to premix the weighed components in the correct proportions and allow the specimens to stand at room temperature for 1 h prior to placing them into the oven.

1.4 This test method may not be applicable to all types of coatings. Other procedures may be substituted with mutual agreement between the producer and the user.

NOTE 3—If unusual decomposition or degradation of the specimen occurs during heating, the actual time and temperature used to cure the coating in practice may be substituted for the time and temperature specified in this test method, subject to mutual agreement between the producer and the user. The U.S. EPA Reference Method 24 specifies  $110 \pm 5^\circ\text{C}$  for 1 h for coatings.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For a specific hazard statement see 7.4.1.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Paint Materials.

Current edition approved Jan. 10, 2001. Published March 2001. Originally published as D 2369 – 65 T. Last previous edition D 2369 – 98.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

- D 1193 Specification for Reagent Water<sup>2</sup>
- D 3925 Practice for Sampling Liquid Paints and Related Pigmented Coatings<sup>3</sup>
- E 145 Specification for Gravity-Convection and Forced-Ventilation Ovens<sup>4</sup>
- E 180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals<sup>5</sup>

#### 2.2 Other Standards:

- EPA Reference Method 24—Determination of Volatile Matter Content, Density, Volume Solids, and Weight Solids of Surface Coatings<sup>6</sup>

### 3. Summary of Test Method

3.1 A designated quantity of coating specimen is weighed into an aluminum foil dish containing 3 mL of an appropriate solvent, dispersed, and heated in an oven at  $110 \pm 5^\circ\text{C}$  for 60 min. The percent volatile is calculated from the loss in weight.

### 4. Significance and Use

4.1 This test method is the procedure of choice for determining volatiles in coatings for the purpose of calculating the volatile organic content in coatings under specified test conditions. The weight percent solids content (nonvolatile matter) may be determined by difference. This information is useful to the paint producer and user and to environmental interests for determining the volatiles emitted by coatings.

### 5. Apparatus

5.1 *Analytical Balance*, capable of weighing  $\pm 0.1$  g.

5.2 *Aluminum Foil Dishes*, 58 mm in diameter by 18 mm high with a smooth (planar) bottom surface. Precondition the dishes for 30 min in an oven at  $110 \pm 5^\circ\text{C}$  and store in a desiccator prior to use. Use tongs or rubber gloves, or both, to handle the dishes.

5.3 *Forced Draft Oven*, Type IIA or Type IIB as specified in

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 11.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 06.01.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 14.04.

<sup>5</sup> *Annual Book of ASTM Standards*, Vol 15.05.

<sup>6</sup> Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.