NOTICE: This standard has either been superseded and replaced by a new version or discontinued. Contact ASTM International (www.astm.org) for the latest information.



AMERICAN SOCIETY FOR TESTING AND MATERIALS 100 Barr Harbor Dr., West Conshohocken, PA 19428 Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Practice for Determining the Effect of Overbaking on Organic Coatings¹

This standard is issued under the fixed designation D 2454; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the determination of the timetemperature effect of overbaking on the physical and chemical properties of organic coatings.

1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of whoever uses this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. Specific hazard statements are given in Section 7.

2. Referenced Documents

- 2.1 ASTM Standards:
- D 522 Test Method for Mandrel Bend Test of Attached Organic Coatings²
- D 523 Test Method for Specular Gloss²
- D 609 Practice for Preparation of Cold-Rolled Steel Panels for Testing Paint, Varnish, Conversion Coatings, and Related Coating Products²
- D 823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels²
- D 1005 Test Methods for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers²
- D 1186 Test Methods for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to a Ferrous Base²
- D 1308 Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes³
- D 1400 Test Method for Nondestructive Measurement of Dry Film Thickness of Nonconductive Coatings Applied to a Nonferrous Metal Base²
- D 1640 Test Methods for Drying, Curing, or Film Formation of Organic Coatings at Room Temperature²
- D 1729 Practice for Visual Evaluation of Color Differences of Opaque Materials²
- D 1730 Practices for Preparation of Aluminum and Aluminum-Alloy Surfaces for Painting⁴

- D 1731 Practices for Preparation of Hot-Dip Aluminum Surfaces for Painting⁴
- D 2092 Guide for Preparation of Zinc-Coated (Galvanized) Steel Surfaces for Painting³
- D 2197 Test Method for Adhesion of Organic Coatings by Scrape Adhesion²
- D 2201 Practice for Preparation of Zinc-Coated and Zinc-Alloy-Coated Steel Panels for Testing Paint, and Related Coating Products²
- D 2244 Test Method for Calculation of Color Differences From Instrumentally Measured Color Coordinates²
- D 2794 Test Method for Resistance of Organic Coatings to the Effects of Rapid Deformation (Impact)²
- D 3359 Test Methods for Measuring Adhesion by Tape Test²
- D 3363 Test Method for Film Hardness by Pencil Test²

E 805 Practice for Identification of Instrumental Methods of Color or Color-Difference, Measurement of Materials²

3. Terminology

3.1 Definition:

3.1.1 *overbaking*—an exposure of the coating to a moderately higher temperature or to a longer period of baking, or both, than recommended by the manufacturer of the coating for normal curing. This condition is in contrast to "heat resistance" which is a parameter relating to the service life of a coating.

4. Summary of Practice

4.1 Four panels are prepared and baked at the schedule normally recommended for the coating. Two of the panels are then removed and the remaining two are subjected to an additional overbake in which the time and temperature are mutually agreed upon between the purchaser and the seller. The sets of panels, after a suitable conditioning interval, are then evaluated for the properties that are compatible with the substrate. Among these are gloss, color, flexibility, adhesion, impact resistance, and resistance to reagents. Note that glass substrates should not be tested for impact, and zinc-coated substrates can influence both flexibility and impact.

5. Significance and Use

5.1 Most coatings are designed for a specific baking time and temperature. For a variety of reasons (line stoppages, rerouting back through ovens, oven overheating, etc.) the prescribed time or temperature, or both, of the bake is often

¹ This practice is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.27 on Accelerated Testing.

Current edition approved Nov. 10, 1995. Published January 1996. Originally published as D 2454 – 66 T. Last previous edition D 2454 – 91.

² Annual Book of ASTM Standards, Vol 06.01.

³ Annual Book of ASTM Standards, Vol 06.02.

⁴ Annual Book of ASTM Standards, Vol 02.05.