



Designation: D 1978 – 91 (Reapproved 1996)

AMERICAN SOCIETY FOR TESTING AND MATERIALS  
100 Barr Harbor Dr., West Conshohocken, PA 19428  
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

## Standard Guide for Analysis of Electrocoat Bath Samples<sup>1</sup>

This standard is issued under the fixed designation D 1978; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This guide covers the selection of test methods for determination of the important parameters that affect the performance of electrocoating paints.

1.2 The test methods involved are D 4370, D 4399, D 4584, and D 5145.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 4370 Test Methods for Acid and Base Milliequivalent Content of Electrocoat Bath Samples<sup>2</sup>

D 4399 Test Method for Measuring Electrical Conductivity of Electrocoat Baths<sup>2</sup>

D 4584 Test Method for Measuring Apparent pH of Electrocoat Baths<sup>2</sup>

D 5145 Test Method for Nonvolatile and Pigment Content of Electrocoat Baths<sup>2</sup>

### 3. Significance and Use

3.1 This guide indicates test procedures recommended for the maintenance of acceptable performance of the paint in an electrocoating bath. Several critical parameters must be determined throughout the operation of the bath. These parameters

must be adjusted when deviations from the norm occur.

3.2 The test methods for electrocoat baths are unique, as the aqueous samples have a nonvolatile content between 8 and 25 %. Constant agitation must be present when the samples are taken and during the measurement of some of the parameters.

### 4. Test Methods

4.1 *Acid and Base Content*—Test Methods D 4370 covers the determination of acid and base milliequivalent content of electrocoat baths.

4.2 *Electrical Conductivity*—Test Method D 4399 describes the determination of the electrical conductivity of electrocoat baths.

4.3 *pH Determination*—Test Method D 4584 describes the measurement of the apparent pH of paints and ultrafiltrates of electrocoat baths.

4.4 *Nonvolatile and Pigment Content*—Test Method D 5145 covers the determination of nonvolatile and inorganic pigment content of electrocoat baths.

### 5. Precision

5.1 The referenced test methods have precision limits listed. Reference to the individual standards for precision statements is recommended.

### 6. Keywords

6.1 electrical conductivity; nonvolatile content; electrocoat baths; pH; pigment content

<sup>1</sup> This guide is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Materials.

Current edition approved Feb. 22, 1991. Published April 1991.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 06.01.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*