

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE



**Electric and optical fibre cables – Test methods for non-metallic materials –  
Part 501: Mechanical tests – Tests for determining the mechanical properties of  
insulating and sheathing compounds**

**Câbles électriques et à fibres optiques – Méthodes d'essai pour les matériaux  
non-métalliques –**

**Partie 501: Essais mécaniques – Détermination des propriétés mécaniques des  
mélanges pour les enveloppes isolantes et les gaines**





## THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2018 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

#### IEC Catalogue - [webstore.iec.ch/catalogue](http://webstore.iec.ch/catalogue)

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

#### IEC publications search - [webstore.iec.ch/advsearchform](http://webstore.iec.ch/advsearchform)

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

#### IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

#### Electropedia - [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing 21 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

#### IEC Glossary - [std.iec.ch/glossary](http://std.iec.ch/glossary)

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

#### IEC Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [sales@iec.ch](mailto:sales@iec.ch).

### A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

### A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

#### Catalogue IEC - [webstore.iec.ch/catalogue](http://webstore.iec.ch/catalogue)

Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

#### Recherche de publications IEC - [webstore.iec.ch/advsearchform](http://webstore.iec.ch/advsearchform)

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

#### IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

#### Electropedia - [www.electropedia.org](http://www.electropedia.org)

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient 21 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 16 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

#### Glossaire IEC - [std.iec.ch/glossary](http://std.iec.ch/glossary)

67 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

#### Service Clients - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: [sales@iec.ch](mailto:sales@iec.ch).



IEC 60811-501

Edition 1.1 2018-06  
CONSOLIDATED VERSION

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE



**Electric and optical fibre cables – Test methods for non-metallic materials –  
Part 501: Mechanical tests – Tests for determining the mechanical properties of  
insulating and sheathing compounds**

**Câbles électriques et à fibres optiques – Méthodes d'essai pour les matériaux  
non-métalliques –  
Partie 501: Essais mécaniques – Détermination des propriétés mécaniques des  
mélanges pour les enveloppes isolantes et les gaines**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

ICS 29.035.01; 29.060.20

ISBN 978-2-8322-5825-5

**Warning! Make sure that you obtained this publication from an authorized distributor.  
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**



## REDLINE VERSION

## VERSION REDLINE



**Electric and optical fibre cables – Test methods for non-metallic materials –  
Part 501: Mechanical tests – Tests for determining the mechanical properties of  
insulating and sheathing compounds**

**Câbles électriques et à fibres optiques – Méthodes d'essai pour les matériaux  
non-métalliques –**

**Partie 501: Essais mécaniques – Détermination des propriétés mécaniques des  
mélanges pour les enveloppes isolantes et les gaines**



## CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references .....	6
3 Terms and definitions .....	6
4 Test method .....	7
4.1 General.....	7
4.2 Insulation .....	7
4.2.1 General .....	7
4.2.2 Sampling .....	7
4.2.3 Preparation and conditioning of test pieces .....	7
4.2.4 Determination of cross-sectional area.....	10
4.2.5 Ageing treatment .....	11
4.2.6 Tensile testing procedure .....	11
4.2.7 Expression of results .....	12
4.3 Sheath .....	12
4.3.1 General .....	12
4.3.2 Sampling .....	12
4.3.3 Preparation and conditioning of test pieces .....	12
4.3.4 Determination of cross-sectional area.....	12
4.3.5 Ageing treatment .....	13
4.3.6 Tensile testing procedure .....	13
4.3.7 Expression of results .....	13
5 Test report.....	13
Annex A (informative) Principle of operation of a typical machine for preparing test pieces.....	16
Bibliography.....	17
Figure 1 – Dumb-bell test piece .....	14
Figure 2 – Small dumb-bell test piece .....	14
Figure 3 – Punch end showing groove .....	14
Figure 4 – Test pieces cut by grooved punch.....	15
Figure A.1 – Machine for preparing test pieces .....	16

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**ELECTRIC AND OPTICAL FIBRE CABLES –  
TEST METHODS FOR NON-METALLIC MATERIALS –**

**Part 501: Mechanical tests –  
Tests for determining the mechanical properties  
of insulating and sheathing compounds**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

**This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.**

**IEC 60811-501 edition 1.1 contains the first edition (2012-03) [documents 20/1297/FDIS and 20/1346/RVD] and its amendment 1 (2018-06) [documents 20/1795/FDIS and 20/1809/RVD].**

**In this Redline version, a vertical line in the margin shows where the technical content is modified by amendment 1. Additions are in green text, deletions are in strikethrough red text. A separate Final version with all changes accepted is available in this publication.**

International Standard IEC 60811-501 has been prepared by IEC technical committee 20: Electric cables.

This Part 501 of IEC 60811 cancels and replaces Clause 9 of IEC 60811-1-1:1993, which is withdrawn. Full details of the replacements are shown in Annex A of IEC 60811-100:2012.

There is one significant technical change with respect to the previous edition:

- the requirements for the (minimum) thickness of dumb-bell test pieces have changed.

See also the Foreword to IEC 60811-100.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

This part of IEC 60811 shall be used in conjunction with IEC 60811-100.

A list of all the parts in the IEC 60811 series, published under the general title *Electric and optical fibre cables – Test methods for non-metallic materials*, can be found on the IEC website.

The committee has decided that the contents of the base publication and its amendment will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or [IEC 60811-501:2012](https://standards.iteh.ai/catalog/standards/iec/b58f1ec4-160c-4b90-828a-5613a201cd44/iec-60811-501-2012)
- amended.

**IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.**



## INTRODUCTION

The IEC 60811 series specifies the test methods to be used for testing non-metallic materials of all types of cables. These test methods are intended to be referenced in standards for cable construction and for cable materials.

NOTE 1 Non-metallic materials are typically used for insulating, sheathing, bedding, filling or taping within cables.

NOTE 2 These test methods are accepted as basic and fundamental and have been developed and used over many years principally for the materials in all energy cables. They have also been widely accepted and used for other cables, in particular optical fibre cables, communication and control cables and cables for ships and offshore applications.

**iTeh Standards**  
**(<https://standards.itih.ai>)**  
**Document Preview**

[IEC 60811-501:2012](#)

<https://standards.itih.ai/catalog/standards/iec/b58f1ec4-160c-4b90-828a-5613a201cd44/iec-60811-501-2012>

# ELECTRIC AND OPTICAL FIBRE CABLES – TEST METHODS FOR NON-METALLIC MATERIALS –

## Part 501: Mechanical tests – Tests for determining the mechanical properties of insulating and sheathing compounds

### 1 Scope

This Part 501 of IEC 60811 gives the procedure for determining the mechanical properties, which typically applies to cross-linked and thermoplastic compounds used for insulating and sheathing materials.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60811-100:2012, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 100: General*

IEC 60811-201, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 201: General tests – Measurement of insulation thickness*

IEC 60811-202, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 202: General tests – Measurement of thickness of non-metallic sheaths*

IEC 60811-203, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 203: General tests – Measurement of overall dimensions*

IEC 60811-401, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 401: Miscellaneous tests – Thermal ageing methods – Ageing in an air oven*

IEC 60811-404, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 404: Miscellaneous tests – Mineral oil immersion tests for sheaths made with cross-linked compounds*

IEC 60811-606, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 606: Physical tests – Methods for determining the density*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60811-100, together with the following, apply.

#### 3.1

##### **maximum tensile force**

highest value reached by the load during the test

### 3.2

#### **tensile stress**

tensile force per unit of the cross-sectional area of the unstretched test piece

### 3.3

#### **tensile strength**

maximum tensile stress recorded in extending the test piece to breaking point

### 3.4

#### **elongation at break**

increase of the length between the reference marks of the test piece, expressed as the percentage of the length between the reference marks of the unstretched test piece at breaking point

## 4 Test method

### 4.1 General

This part of IEC 60811 shall be used in conjunction with IEC 60811-100.

Unless otherwise specified, before any test, all test pieces, aged and unaged, shall be kept for at least 3 h at a temperature of  $(23 \pm 5)$  °C.

### 4.2 Insulation

#### 4.2.1 General

These tests are to determine the tensile strength and elongation at break of the insulating material (exclusive of any semi-conducting layers) of the cable in the condition as manufactured (i.e. without any ageing treatment) and, when required, after one or more accelerated ageing treatment(s), which are prescribed in the relevant cable standard.

<https://standards.iteh.ai/> When the ageing treatment is to be carried out on prepared test pieces (in accordance with IEC 60811-401), the test pieces for the ageing treatment shall be from positions adjacent to the test pieces used for the test without ageing and the tensile tests on the aged and unaged test pieces shall be made in immediate succession. Preparation and conditioning of test pieces for ageing treatment and test pieces without ageing shall be the same.

NOTE Where further increased test reliability is necessary, it is recommended that the tests on aged and unaged test pieces are performed by the same person using the same testing method and the same apparatus, in the same laboratory.

#### 4.2.2 Sampling

One sample of each core to be tested (or of the insulation from each core to be tested) shall be taken of sufficient size to provide a minimum of five test pieces each for the tensile tests without ageing and the tensile tests after each of the required ageing treatments, bearing in mind that a 100 mm length is needed for the preparation of each test piece.

The cores of unsheathed flat cables shall not be separated.

Any sample that shows signs of mechanical damage shall not be used for the test.

#### 4.2.3 Preparation and conditioning of test pieces

a) Conditioning of test pieces shall be carried out as follows:

1) Elevated temperature conditioning

NOTE 1 Elevated temperature conditioning is not an ageing treatment. It is used as a means of ensuring stable and consistent test pieces when required. ~~It is used a) when called for in the relevant cable~~

~~standard, or b) if there is a doubt or disagreement about a result and the test needs to be repeated. In either case, the conditioning applies only to the test piece as taken from the cable before any subsequent treatment (ageing, compatibility test, oil immersion etc).~~ Initial mechanical values can show significant variation due to extrusion and cooling conditions, and can change over time and with thermal history.

Elevated temperature conditioning is used:

- when called for in the relevant cable standard; or
- if there is a doubt or disagreement about a result and the test needs to be repeated.

In either case, the conditioning applies only to the test piece as taken from the cable before any subsequent treatment (ageing, compatibility test, oil immersion, etc.).

Where conditioning at elevated temperature is used, such conditioning shall be carried out as follows:

- for dumb-bells,
  - (A) after the removal of the insulation from the cable and removal of semi-conducting layers (if any) but before the cutting of strips;
  - (B) after grinding (or cutting) to obtain parallel surfaces.Where grinding (or cutting) is not needed, the conditioning shall be performed at the point in the test protocol according to (A);
- for tubular test pieces, such conditioning shall be carried out after removal of the conductor, and any separator, but before applying the reference marks, if any, for measurement of the extension.

Where the relevant cable standard calls for conditioning at elevated temperature, it shall be for the time and temperature given in that standard. Where, in case of doubt, the test has to be repeated, the conditioning shall be 24 h ~~at  $(70 \pm 2)^\circ\text{C}$ , or a lower temperature corresponding to the maximum operating temperature of the conductor~~ at the maximum rating temperature for the cable or the continuous maximum rated conductor temperature, as specified in the cable standard.

Conditioning of test pieces at elevated temperature does not modify the required ageing period.

## 2) Room temperature conditioning

Before determination of the cross-sectional area, all test pieces shall be protected from direct sunlight and maintained for at least 3 h at a temperature of  $(23 \pm 5)^\circ\text{C}$ , except for thermoplastic insulating materials which shall be kept at  $(23 \pm 2)^\circ\text{C}$ .

### b) Dumb-bell test pieces

Dumb-bell test pieces shall be used whenever possible. They shall be prepared from samples of insulation removed from the conductor, cut open in the direction of the axis of the core.

Semi-conducting layers, if any, inside and/or outside the insulation, shall be removed mechanically, i.e. without using a solvent.

Each sample of insulation shall be cut into strips of an appropriate length. The strips shall be marked to identify the sample from which they are cut and their positions relative to each other in the original sample.

The strips of insulation shall be ground or cut, so as to obtain two parallel smooth surfaces between the reference marks mentioned below, care being taken to avoid undue heating. An example of a cutting machine is given in Annex A. For polyethylene (PE) and polypropylene (PP) insulation, cutting only, not grinding, shall be employed. After cutting or grinding, including any removal of burrs, the thickness of the strips shall not be less than 0,8 mm and not more than 2,0 mm. If it is not possible to prepare dumb-bell test pieces that comply with the minimum thickness of 0,8 mm, then tubular test pieces shall be used. If tubular test pieces cannot be prepared, then dumb-bells thinner than 0,8 mm may be used, but the rate of separation shall be 25 mm/min.

NOTE 2 The test report should also include the fact that non-compliant dumb-bells were used and that the result is indicative.

NOTE 3 For certain tests, a minimum thickness may be required, for instance for the ozone resistance test (IEC 60811-403) and the mineral oil immersion test (IEC 60811-404).

A dumb-bell test piece, in accordance with Figure 1, shall then be punched from each prepared strip of insulation, or if possible, two dumb-bell test pieces shall be punched side by side.

In order to improve the reliability of the results, the following is recommended:

- the punch shall be very sharp to minimize imperfections in the test piece;
- a cardboard or other suitable support shall be placed between the strip and the base plate. This support shall be marked during punching, but not completely cut through by the punch;
- burrs on the sides of the test piece shall be avoided.

For materials where punching results in burrs, the following method may be used:

- 1) each end of the punch shall have a groove approximately 2,5 mm wide and 2,5 mm high (see Figure 3);
- 2) the cut dumb-bell test pieces shall remain attached at both ends with the strip previously prepared according to the requirements of 4.2.3 b) (see Figure 4);
- 3) with the machine given in Annex A, an additional 0,10 mm to 0,15 mm thickness can be cut away to remove possible burrs resulting from the dumb-bell punch. When this operation is completed, the dumb-bell test pieces shall be cut through at their ends in order to remove them from the strip.

When the diameter of the core is too small to allow the dumb-bell to be cut in accordance with Figure 1, then a smaller dumb bell test piece in accordance with Figure 2, shall be punched from each prepared strip.

The central 20 mm for the larger dumb-bells or 10 mm for the smaller dumb-bells shall be marked on each test piece, immediately before the tensile test.

NOTE 4 Where a contact extensometer is used, the pre set grips at the required spacing are deemed to constitute a mark.

Dumb-bell test pieces with incomplete ends are permitted, provided that the breaking point occurs between the reference marks.

#### c) Tubular test pieces

Tubular test pieces shall be used only when the dimensions of the core are such that it is not possible to prepare dumb-bell test pieces.

The samples of core shall be cut into pieces approximately 100 mm long and the conductor and any outer coverings removed, care being taken not to damage the insulation. The tubes shall be marked to identify the sample from which they were prepared and their relative positions in the sample.

Careful removal of the conductor can be facilitated by the use of one or more of the following operations:

- 1) by elongation of the rigid conductors;
- 2) by careful rolling of the core under low mechanical force;
- 3) in the case of stranded or flexible conductors, by first removing one or more of the central strands or wires.

After removal of the conductor, the separators, if any, are removed. In case of difficulty, one of the following operations may be used:

- immersion in water, in the case of paper separators;
- immersion in ethyl alcohol, in the case of polyethylene terephthalate separators;
- rolling of the insulation on a smooth surface.

The central 20 mm shall be marked immediately before the tensile test.

NOTE 5 Where a contact extensometer is used, the pre set grips at the required spacing are deemed to constitute a mark.

The presence of pieces of separator remaining inside the test piece can be observed during the tensile tests by formation of irregularities in the test piece during elongation.

In such cases, the result shall be rejected.

#### 4.2.4 Determination of cross-sectional area

##### a) Dumb-bell test piece

The cross-sectional area of each test piece is the product of the common width and the measured individual minimum thickness which shall be determined as follows.

For the width:

- the common width is the minimum width of three, randomly selected test pieces;
- if there is doubt about the uniformity of the width, this shall be measured at three positions on the top and the bottom side of the three test pieces. The mean of the top and bottom side measurements shall be calculated for each position. The common width shall be the minimum of the nine mean values determined on the three test pieces;
- in the case of further doubt, the width is measured on each individual test piece.

For the thickness:

- the thickness of each test piece is the minimum of three thickness measurements carried out in the area to be stretched.

The measurements shall be carried out by an optical instrument or by a dial gauge giving a contact pressure not exceeding 0,07 N/mm<sup>2</sup>.

The instrument shall be capable of measuring the thickness with an error of not more than 0,01 mm and the width with an error of not more than 0,04 mm.

In case of doubt, where technically possible, an optical instrument shall be used. Alternatively, a dial gauge with a maximum contact pressure of 0,02 N/mm<sup>2</sup> may be used.

NOTE An appropriate curved foot of the dial gauge should be used if the central part of the dumb-bell is still curved.

##### b) Tubular test piece

In the middle of the sample being used to prepare the test pieces, a piece shall be taken to determine the cross-sectional area,  $A$ , in square millimetres, of the test piece, using one of the following methods. In case of doubt, the second method b2) shall be used.

b1) From the dimensions, using the formula:

$$A = \pi (D - \delta) \delta$$

where

$\delta$  is the mean value of the thickness of the insulation, in millimetres, determined as specified in IEC 60811-201 and rounded off to two decimal places;

$D$  is the mean value of the outer diameter of the test piece, in millimetres, determined as specified in test method of IEC 60811-203 and rounded off to two decimal places.

b2) From the density, the mass and the length, using the formula:

$$A = \frac{1\,000\,m}{d \times l}$$

where