NOTICE: This standard has either been superseded and replaced by a new version or discontinued. Contact ASTM International (www.astm.org) for the latest information.



AMERICAN SOCIETY FOR TESTING AND MATERIALS 100 Barr Harbor Dr., West Conshohocken, PA 19428 Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Test Method for Chemical Resistance of Coatings Used in Light-Water Nuclear Power Plants¹

This standard is issued under the fixed designation D 3912; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method establishes procedures for the evaluation of the chemical resistance of coatings used in light-water nuclear power plants.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:

- D 714 Test Method for Evaluating Degree of Blistering of Paints²
- D 1193 Specification for Reagent Water³
- D 5139 Specification for Sample Preparation for Qualification Testing of Coatings to be Used in Nuclear Power Plants⁴

2.2 NACE Standard:

NACE TM-01-74–91 Laboratory Methods for the Evaluation of Protective Coatings Used as Lining Materials in Immersion Service⁵

3. Significance and Use

3.1 The specific chemical resistance tests to be performed are dependent upon the relative severity of the service conditions. Fig. 1 lists some chemical solutions that may be applicable to nuclear power plants and may be considered for use in testing chemical resistance of coatings when applicable. Testing these, or other chemical solutions should not be construed as mandatory, but may be specified by the owner when desired. 3.2 The lining test may be used to evaluate the resistance characteristics of coating systems for lining surfaces of tanks, vessels and similar facilities used in a light-water nuclear power plant.

4. Sampling

4.1 Prepare individual specimens for testing in each of the pertinent solutions.

4.2 Prepare one additional specimen as a control. Multiple tests may be performed.

5. Preparation of Test Specimens

5.1 Steel Panels:

5.1.1 Prepare steel panels in accordance with Specification D 5139.

5.1.2 Use carbon steel panels in lining tests at least 7 by 7 by ¹/₄ in. (178 by 178 by 6.4 mm) thick for Procedure A only. 5.2 *Concrete Blocks*—Prepare blocks in accordance with Specification D 5139 with the exception that the top and bottom ends of the block shall be coated.

6. Procedure

6.1 Test in accordance with NACE TM-01-74–91, Procedure B, Immersion Testing, except use Procedure A, One-Side Testing (cold wall) when a significant temperature differential is anticipated across the coating film as for tank linings.

6.2 Lining Test:

6.2.1 Immerse lining test specimens in the appropriate test solutions listed in Fig. 1 or as otherwise specified for a minimum of 180 days.

6.2.2 Maintain a temperature of $72 \pm 5^{\circ}F(22 \pm 3^{\circ}C)$ unless otherwise specified by the owner.

6.2.3 Use deionized water with an initial resistivity of not less than 2.5 m Ω /in. at 77°F (1 M Ω /cm at 25°C) and with a total solids of no more than 0.5 ppm, no more than 0.15 ppm of chloride or no more than 0.15 ppm of fluoride. Maintain the pH range from 6.0 to 8.0.

6.2.4 Change the deionized water daily during the first week and weekly thereafter. Measure any constituents leached out before the water is changed.

6.3 Chemical Exposure Tests:

6.3.1 Test the chemical resistance properties of the coatings by immersion in the appropriate test solutions with duration as required.

¹ This test method is under the jurisdiction of ASTM Committee D-33 on Protective Coating and Lining Work for Power Generation Facilities and is the direct responsibility of Subcommittee D33.02 on Service and Material Parameters.

Current edition approved Oct 10, 1995. Published December 1995. Originally published as D 3912 – 80. Last previous edition D 3912 – 80 (1989).

² Annual Book of ASTM Standards, Vol 06.01.

³ Annual Book of ASTM Standards, Vol 11.01.

⁴ Annual Book of ASTM Standards, Vol 06.02.

⁵ Available from the National Association of Corrosion Engineers, P.O. Box 218340, Houston, TX 77218.

備) D 3912

CHEMICAL-EXPOSURE TEST RESULTS

pecimen No.		Date		
	DFT	··· · · · · · · · · · · · · · · · · ·		
diate	DFT			
	DFT			······
Method of Application			***···	
°F, Relative Humidity	%, Curing Time		at	°F.
			• · · · · · · · · · · · · · · · · · · ·	
Chemical	Concentration, weight %	8 h	24 h	5 days
2 ^{O)}	5 5 5 1.03 11.5			
	diate Method of Application °F, Relative Humidity Chemical	DFT DFT DFT Method of Application °F, Relative Humidity %, Curing Time °F, Relative Humidity %, Curing Time Chemical Concentration, weight % 5 5 5 5 5 5 5 5 5 5 5 5 5		Date

6.3.2 Maintain a temperature of $72 \pm 5^{\circ}$ F (22 to 3° C) unless the service conditions require a higher temperature.

97.2.2 Evaluate the condition of the specimens within 1 h after removal from the test solutions.

6.3.3 Use reagent grade chemicals and water conforming to 7.2.3 Evaluate the test specimens at each inspection as in J/Star 7.1.3. Specification D 1193, Type III, for all solutions.

7. Examination and Evaluation

7.1 Lining Test:

7.1.1 Examine the test specimens weekly for the first month and then monthly thereafter.

7.1.2 Inspect specimens immediately upon completion of the test period. Make a final inspection not later than 24 h after removal from the test solution.

7.1.3 Evaluate the test specimens at each inspection for peeling, delamination, blistering (Test Method D 714), discoloration, and softening.

7.2 Chemical Exposure Tests:

7.2.1 Examine the test specimens at the end of the test period or every 24 h, whichever is the shorter time.

8. Documentation and Report

8.1 Report all procedures and conditions relating to the test specimen preparation.

8.2 Document the testing procedure and test results. A suggested format is illustrated by Fig. 1.912-95

9. Precision and Bias

9.1 These tests are qualitative in nature. Precision and bias are not definable.

10. Keywords

10.1 chemical resistance; coatings and linings; nuclear

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.