

INTERNATIONAL STANDARD

**Optical fibres –
Part 1-44: Measurement methods and test procedures – Cut-off wavelength**

iTech Standards
(<https://standards.iteh.ai>)
Document Preview

IEC 60793-1-44:2011

<https://standards.iteh.ai/catalog/standards/iec/77/775195-8141-45ac-91bb-ca65b15cec21/iec-60793-1-44-2011>

WITHDRAWN



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2011 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/customerserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

IEC 60793-1-44:2011

<https://standards.iteh.ai/document/iec/793-1-44-2011>

INTERNATIONAL STANDARD

Optical fibres –
Part 1-44: Measurement methods and test procedures – Cut-off wavelength

<https://standards.iteh.ai/standards/iec/77/75195-8141-45ac-91bb-ca65b15cec21/iec-60793-1-44-2011>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE

S

ICS 33.180.10

ISBN 978-2-88912-451-0

CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references	6
3 Background	6
4 Overview of methods	7
5 Mapping functions	7
6 Reference test method	8
7 Apparatus.....	8
7.1 Light source	8
7.2 Modulation	8
7.3 Launch optics	8
7.4 Support and positioning apparatus	8
7.5 Cladding mode stripper	8
7.6 Deployment mandrel	9
7.6.1 General	9
7.6.2 Cable cut-off wavelength, Method A	9
7.6.3 Cable cut-off wavelength, Method B	9
7.6.4 Fibre cut-off wavelength, Method C	9
7.7 Detection optics	11
7.8 Detector assembly and signal detection electronics.....	11
8 Sampling and specimens.....	11
8.1 Specimen length.....	11
8.2 Specimen end face.....	12
9 Procedure	12
9.1 Positioning of specimen in apparatus	12
9.1.1 General requirements for all methods	12
9.1.2 Deployment requirements for each method	12
9.2 Measurement of output power	12
9.2.1 Overview	12
9.2.2 Bend-reference technique.....	13
9.2.3 Multimode-reference technique.....	13
10 Calculations	13
10.1 Bend-reference technique	13
10.2 Multimode-reference technique	14
10.3 Curve-fitting technique for improved precision (optional)	14
10.3.1 General	14
10.3.2 Step 1, define the upper-wavelength region	15
10.3.3 Step 2, characterize the attenuation curve	15
10.3.4 Step 3, determine the upper wavelength of the transition region	16
10.3.5 Step 4, determine the lower wavelength of the transition region.....	16
10.3.6 Step 5, characterize the transition region with the theoretical model.....	16
10.3.7 Step 6, compute the cut-off wavelength, λ_c	17
11 Results.....	17
11.1 Report the following information with each measurement:	17
11.2 The following information shall be available upon request:	17

12 Specification information	18
Annex A (normative) Requirements specific to method A – Cable cut-off wavelength, λ_{CC} , using uncabled fibre	19
Annex B (normative) Requirements specific to method B – Cable cut-off wavelength, λ_{CC} , using cabled fibre	20
Annex C (normative) Requirements specific to method C – Fibre cut-off wavelength, λ_c	21
Bibliography.....	22
Figure 1 – Deployment configuration for cable cut-off wavelength, method A	9
Figure 2 – Deployment configuration for cable cut-off wavelength, method B	10
Figure 3 – Default configuration to measure λ_c	10
Figure 4 – Deployment configurations for fibre cut-off measurement	11
Figure 5 – Cut-off wavelength using the bend-reference technique	12
Figure 6 – Cut-off wavelength using the multimode-reference technique	13

iTech Standards
(<https://standards.iteh.ai>)
Document Preview

IEC 60793-1-44:2011

<https://standards.iteh.ai/coupling-standards/iec/75195-8141-45ac-91bb-ca65b15ccc21/iec-60793-1-44-2011>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

**Part 1-44: Measurement methods and test procedures –
Cut-off wavelength**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60793-1-44 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This second edition cancels and replaces the first edition published in 2001. This edition constitutes a technical revision.

The main change with respect to the previous edition is the withdrawal of annex D.

Annexes A, B and C form an integral part of this standard.

This standard should be read in conjunction with IEC 60793-1-1.

The text of this standard is based on the following documents:

FDIS	Report on voting
86A/1369/FDIS	86A/1385/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 60793-1-4x series, published under the general title *Optical fibres – measurement methods and test procedures*, can be found on the IEC website

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

OPTICAL FIBRES –

Part 1-44: Measurement methods and test procedures – Cut-off wavelength

1 Scope

This part of IEC 60793 establishes uniform requirements for measuring the cut-off wavelength of single-mode optical fibre, thereby assisting in the inspection of fibres and cables for commercial purposes.

This standard gives the methods for measuring the cut-off wavelength of fibre and cable

There are two methods for measuring cable cut-off wavelength, λ_{cc} :

- Method A: using uncabled fibre;
- Method B: using cabled fibre.

There is only one method (Method C) for measuring fibre cut-off wavelength, λ_c .

The test method in this standard describes procedures for determining the cut-off wavelength of a sample fibre in either an uncabled condition (λ_c) or in a cable (λ_{cc}). Three default configurations are given here: any different configuration will be given in a detail specification. These procedures apply to all category B and C fibre types (see Normative references).

All methods require a reference measurement. There are two reference-scan techniques, either or both of which may be used with all methods:

- bend-reference technique;
- multimode-reference technique using category A1 multimode fibre.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-1, *Optical fibres – Part 1-1: Measurement methods and test procedures – General and guidance*

IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

3 Background

Theoretical cut-off wavelength is the shortest wavelength at which only the fundamental mode can propagate in a single-mode fibre, as computed from the refractive index profile of the fibre.

In optical fibres, the change from multimode to single-mode behaviour does not occur at an isolated wavelength, but rather smoothly over a range of wavelengths. For purposes of

determining fibre performance in a telecommunications network, theoretical cut-off wavelength is less useful than the lower value actually measured when the fibre is deployed.

Measured cut-off wavelength is defined as the wavelength greater than which the ratio between the total power, including launched higher-order modes, and the fundamental mode power has decreased to less than 0,1 dB. According to this definition, the second-order (LP_{11}) mode undergoes 19,3 dB more attenuation than the fundamental (LP_{01}) mode at the cut-off wavelength.

Because measured cut-off wavelength depends on the length and bends of the fibre, the resulting value of cut-off wavelength depends on whether the measured fibre is configured in a deployed, cabled condition, or it is short and uncabled. Consequently, there are two overall types of cut-off wavelength:

- Cable cut-off wavelength, measured in an uncabled fibre deployment condition (method A), or in a cabled condition (method B);
- Fibre cut-off wavelength, measured on a short length of uncabled, primary-coated fibre.

Cable cut-off wavelength is the preferred attribute to be specified and measured.

4 Overview of methods

All of the methods shall use the transmitted-power technique, which measures the variation with wavelength of the transmitted power of a fibre under test compared to a reference transmitted-power wavelength scan. The reference scan normalizes wavelength-dependent fluctuations in the measurement equipment so that the attenuation of the LP_{11} mode in the specimen can be properly characterized and the cut-off wavelength precisely determined.

The reference scan uses one of the following two techniques:

- the specimen with an additional, smaller-radius fibre bend;
- a (separate) category A1 multimode fibre.

This procedure can determine the cut-off wavelength of a fibre specimen in either a cabled or uncabled condition. Each method has its own default configurations; the detail specification will give any different configuration required.

The fibre cut-off wavelength, (λ_c), measured under the standard length and bend conditions described in this standard, will generally exhibit a value larger than λ_{cc} . For normal installed cable spans, it is common for the measured λ_c value to exceed the system transmission wavelength. Thus cable cut-off wavelength is the more useful description of system performance and capability.

For short cables, e.g. a pigtail with a length shorter (and possibly a bending radius larger) than described in this method, the cable may introduce modal noise near the cut-off wavelength when lossy splices are present (>0.5 dB).

5 Mapping functions

A mapping function is a formula by which the measured results of one type of cut-off wavelength are used to predict the results that one would obtain from another type.

An empirical mapping function is specific to a particular fibre type and design. Generate mapping functions by doing an experiment in which samples of fibre are chosen to represent the spectrum of cut-off wavelength values for the fibre type, then measure the values using

the two methods to be mapped. Linear regression of the respective values will often produce a satisfactory mapping function. When establishing criteria for fibre selection, residual errors in the regression shall be taken into account.

The customer and the supplier shall agree to the confidence level of each mapping function established.

6 Reference test method

Method A of cable cut-off wavelength, using uncabled fibre, is the reference test method (RTM), which shall be the one used to settle disputes.

The apparatus for each method is described in Clause 7.

7 Apparatus

7.1 Light source

Provide a filtered white light source, with line width not greater than 10 nm, stable in position and intensity. The light source should be capable of operating over the wavelength range 1 000 nm to 1 600 nm for most category B fibres. An operating range of 800 nm to 1 700 nm may be necessary for some B4 fibres, B5 fibres or some category C fibres.

7.2 Modulation

Modulate the light source to prevent ambient light affecting the results, and to aid signal recovery. A mechanical chopper with a reference output is a suitable arrangement.

7.3 Launch optics

Provide launch optics, such as a lens system or a multimode fibre, to overfill the test fibre over the full range of measurement wavelengths. This launch is relatively insensitive to the input end face position of the single-mode fibre, and is sufficient to excite the fundamental and any higher-order modes in the specimen. If using a butt splice, provide means of avoiding interference effects.

When using a multimode fibre, overfilling the reference fibre can produce an undesired ripple effect in the power transmission spectrum. Restrict the launch sufficiently to eliminate the ripple effect. One example of restricted launch is in method A, attenuation by cut-back of IEC 60793-1-40. Another example of restricted launch is a mandrel-wrap mode filter with sufficient (approximately 4 dB) insertion loss.

7.4 Support and positioning apparatus

Provide a means to stably support the input and output ends of the specimen for the duration of the test; vacuum chucks, magnetic chucks, or connectors may be used for this purpose. Support the fibre ends such that they can be repeatedly positioned in the launch and detection optics. When measuring λ_{cc} in method B, provide a means to suitably support the cable ends.

7.5 Cladding mode stripper

Provide a means to remove cladding-mode power from the specimen. Under some circumstances, the fibre coating will perform this function; otherwise, provide methods or devices that extract cladding-mode power at the input and output ends of the specimen.