AMERICAN SOCIETY FOR TESTING AND MATERIALS 100 Barr Harbor Dr., West Conshohocken, PA 19428 Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

# Standard Specification for Dehydrated Castor Oil<sup>1</sup>

This standard is issued under the fixed designation D 961; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon  $(\epsilon)$  indicates an editorial change since the last revision or reapproval.

 $\epsilon^1$  Note—Keywords were added editorially in May 1995.

## 1. Scope

1.1 This specification covers a drying oil made from castor oil that has been treated to remove the elements of water. Two types of dehydrated castor oil are covered: unbodied and Z-3 bodied.

Note 1—Other types of bodied dehydrated castor oil are commercially available but are not covered by this specification.

#### 2. Referenced Documents

- 2.1 ASTM Standards:
- D 445 Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and the Calculation of Dynamic Viscosity)<sup>2</sup>
- D 555 Guide for Testing Drying Oils<sup>3</sup>
- D 1475 Test Method for Density of Paint, Varnish, Lacquer, and Related Products<sup>4</sup>
- D 1544 Test Method for Color of Transparent Liquids (Gardner Color Scale)<sup>4</sup>
- D 1545 Test Method for Viscosity of Transparent Liquids by Bubble Time Method<sup>3</sup>
- D 1639 Test Method for Acid Value of Organic Coating Materials<sup>3</sup>
- D 1640 Test Methods for Drying, Curing, or Film Formation of Organic Coatings at Room Temperature<sup>3</sup>
- D 1955 Test Method for Gel Time of Drying Oils<sup>3</sup>
- D 1959 Test Method for Iodine Value of Drying Oils and Fatty Acids<sup>3</sup>

- D 1962 Test Method for Saponification Value of Drying Oils, Fatty Acids, and Polymerized Fatty Acids<sup>3</sup>
- D 1963 Test Method for Specific Gravity of Drying Oils, Varnishes, Resins, and Related Materials at 25/25°C<sup>3</sup>
- D 2090 Test Method for Clarity and Cleanness of Paint and Ink Liquids<sup>3</sup>
- E 1 Specification for ASTM Thermometers<sup>5</sup>

## 3. Properties

3.1 Dehydrated castor oil shall conform to the requirements prescribed in Table 1.

# 4. Test Methods

- 4.1 The properties enumerated in this specification shall be determined in accordance with the appropriate methods given in Table 1 with the following exceptions:
- 4.1.1 *Gel Time*—Determine the gel time in accordance with Test Method D 1955 but with the following changes:
- 4.1.1.1 Use an ASTM Partial Immersion Thermometer having a range from 20 to 760°F and conforming to the requirements for Thermometer 3F as prescribed in Specification E 1.
- 4.1.1.2 Heat the bath to  $600 \pm 1^{\circ}F$  (315  $\pm 0.5^{\circ}C$ ), insert the tubes containing the oil in the bath, maintain the bath at  $600 \pm 1^{\circ}F$  for the duration of the test, and
- 4.1.1.3 Raise the glass rods a fraction of an inch at 1-min intervals after 125 min in the case of the unbodied oil or after 25 min in the case of the bodied oil.
- 4.1.2 *Iodine Value*—Use the procedure described in Method D 1959, to determine the iodine value, except that the specimen weights shall be 0.11 to 0.13 g of oil.
- 4.2 The significance of and comments on the referenced methods are discussed in Guide D 555.

### 5. Keywords

5.1 castor oil; dehydrated; dehydrated castor oil

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications, and is the direct responsibility of Subcommittee D 01.32 on Drying Oils.

Current edition approved March 27, 1986. Published May 1986. Originally published as D 961 – 48 T. Last previous edition D 961 – 80.

<sup>&</sup>lt;sup>2</sup> Annual Book of ASTM Standards, Vol 05.01.

<sup>&</sup>lt;sup>3</sup> Annual Book of ASTM Standards, Vol 06.03.

<sup>&</sup>lt;sup>4</sup> Annual Book of ASTM Standards, Vol 06.01.

<sup>&</sup>lt;sup>5</sup> Annual Book of ASTM Standards, Vol 14.03.