

# INTERNATIONAL STANDARD

**ISO  
9722**

First edition  
1992-11-01

---

## Nickel and nickel alloys — Composition and forms of wrought products

iTeh STANDARD PREVIEW  
Nickel et alliages de nickel — Composition chimique et formes des  
produits corroyés  
(standards.iteh.ai)

[ISO 9722:1992](#)

[https://standards.iteh.ai/catalog/standards/sist/c0265155-4159-407f-87c7-  
e1e7ac36c974/iso-9722-1992](https://standards.iteh.ai/catalog/standards/sist/c0265155-4159-407f-87c7-e1e7ac36c974/iso-9722-1992)



Reference number  
ISO 9722:1992(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 9722 was prepared by Technical Committee ISO/TC 155, *Nickel and nickel alloys*, Sub-Committee SC 2, *Wrought and cast nickel and nickel alloys*.

[ISO 9722:1992](#)

Annex A forms an integral part of this International Standard.  
<https://standards.iteh.ai/catalog/standards/sist/c0265155-4159-407f-87c7-1107ac30c974/iso-9722-1992>

© ISO 1992

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

# Nickel and nickel alloys — Composition and forms of wrought products

## 1 Scope

This International Standard lists the chemical composition of wrought nickel and nickel alloys and the forms of wrought products in which they are commercially available.

## 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 6207:1992, *Seamless nickel and nickel alloy tube*.

ISO 6208:1992, *Nickel and nickel alloy plate, sheet and strip*.

ISO 6372-1:1989, *Nickel and nickel alloys — Terms and definitions — Part 1: Materials*.

ISO 6372-3:1989, *Nickel and nickel alloys — Terms and definitions — Part 3: Wrought products and castings*.

ISO/TR 7003:1990, *Unified format for the designation of metals*.

ISO/TR 9721-<sup>1)</sup>, *Nickel and nickel alloys — Code of designation based on chemical symbols*.

ISO 9723:1992, *Nickel and nickel alloy bars*.

ISO 9724:1992, *Nickel and nickel alloy wire and drawing stock*.

ISO 9725:1992, *Nickel and nickel alloy forgings*.

## 3 Definitions

For the purposes of this International Standard, the definitions for nickel and nickel alloys in ISO 6372-1 and for wrought products in ISO 6372-3 apply.

## 4 Alloy identification

For the purposes of this International Standard, the principles for alloy identification in ISO/TR 7003 and ISO/TR 9721 apply.

1) To be published.

## 5 Composition

### 5.1 The compositions of nickel and nickel alloys are shown in table 1.

The composition limits do not preclude the possible presence of other elements that are not specified. If the purchaser's requirements necessitate limits for any other element that is not specified, these shall be agreed upon between the purchaser and the supplier. The percentage content of elements shown

as "remainder" shall be calculated by difference from 100 %.

### 5.2 For a list of ISO analytical standards, see annex A.

## 6 Forms of wrought products

The forms of wrought products in which nickel and nickel alloys are available are indicated in table 2 by an "X" in the appropriate column.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 9722:1992](#)

<https://standards.iteh.ai/catalog/standards/sist/c0265155-4159-407f-87c7-e1e7ac36c974/iso-9722-1992>

**Table 1 — Composition and density of wrought nickel and nickel alloys**

Alloy identification <sup>1)</sup> Number	Description	Al	B	C	Co <sup>4)</sup>	Cr	Cu	Fe	Mn	Mo	Composition % (m/m) <sup>2)</sup>				Density <sup>3)</sup> g/cm <sup>3</sup>	
											Ni	P	S	Si	Ti	
NW2200	Ni99.0			0.15		0.2	0.4	0.3			99.0		0.010	0.3		8.9
NW2201	Ni98.0-LC										99.0		0.010	0.3		8.9
NW3021	NiCo20Cr15Mo5Al4Ti https://std.nist.gov/tiers/1/standards/itech.aij	4.5 4.9	0.003 0.010	0.2 0.17	18.0 22.0	14.0 15.7	0.2 0.2	0.4 1.0	0.3 1.0	0.4 5.5	Remainder		0.9 1.5		Ag: 0.0005(5) Bi: 0.0001(1) Pb: 0.0015(15)	8.4
NW7263	NiCo20Cr20Mo5Ti2Al https://std.nist.gov/tiers/1/standards/itech.aij	0.3	0.04	19.0 0.08	19.0 21.0	19.0 21.0	0.2 0.2	0.7 0.7	0.6 0.6	5.6 5.6	Remainder		1.9 2.4		Ag: 0.0005(5) Bi: 0.0001(1) Pb: 0.0020(20) Ti+Al: 2.4 to 2.8	8.4
NW7001	NiCr20Co13Mo4Ti3Al	1.2 1.6	0.003 0.010	0.02 0.10	12.0 15.0	18.0 21.0	0.10 0.21	2.0 1.0	1.0 1.0	3.5 5.0	Remainder	0.015	0.1 0.1	2.8 3.3	Ag: 0.0005(5) Bi: 0.0005(0.5) Pb: 0.0010(10) Zr: 0.02 to 0.08	8.4
NW7090	NiCr20Co18Ti3	1.0 2.0	0.020	0.13	15.0 21.0	18.0 21.0	0.2 0.2	1.5 1.5	1.0 1.0		Remainder	0.015	1.0 3.0	2.0 3.0	Zr: 0.15	8.2
NW8617	NiCr22Co12Mo9	0.8 1.5	0.006	0.15	10.0 15.0	20.0 24.0	0.5 0.5	3.0 3.0	1.0 1.0	3.0 10.0	Remainder	0.015	1.0 0.5	0.6 2.2	Nb+Ta: 0.7 to 1.2	8.4
NW7750	NiCr15Fe7Ti2Al	0.4 1.0	0.08		14.0 17.0	5.0 9.0	0.5 1.0			70.0		0.015	0.5 0.5	2.2 2.8	Nb+Ta: 0.7 to 1.2	8.3
NW8600	NiCr15Fe8			0.15	14.0 17.0	6.0 10.0	0.5 1.0				72.0		0.015	0.5		8.4
NW8602	NiCr15Fe8-LC			0.02	17.0 17.0	6.0 10.0	0.5 1.0				72.0		0.015	0.5		8.4
NW7718	NiCr19Fe18Nb5Mo3	0.2 0.3	0.006	0.08	17.0 21.0	1.5 2.5	0.3 0.3	Remainder	0.4 3.3	2.8 55.0	Remainder	0.015	0.4 0.4	0.6 1.2	Nb+Ta: 4.7 to 5.5	8.0
NW8002	NiCr21Fe18Mo9		0.010	0.15	20.5 23.0	17.0 20.0	0.5 1.0		8.0 10.0		Remainder	0.040	0.030	1.0 1.0		8.2
NW8007	NiCr22Fe20Mo6Cu2Nb		0.05	2.5	21.0 23.5	1.5 2.5	0.5 0.5	Remainder	2.0 2.0	5.5 7.5	Remainder	0.040	0.030	1.0	Nb+Ta: 1.7 to 2.5	8.3
NW8985	NiCr22Fe20Mo7Cu2		0.015	5.0	21.0 23.5	1.5 2.5	0.5 0.5	18.0 21.0	6.0 8.0	Remainder	0.040	0.030	1.0 1.5	Nb+Ta: 0.5	8.3	
NW8601	NiCr23Fe15Al	1.0 1.7	0.10		21.0 25.0	1.0		Remainder	1.0	58.0 63.0		0.015	0.5			8.0
NW6333	NiCr26Fe20Mo3Nb3		0.10	4.0	24.0 27.0	4.0		Remainder	2.0 4.0	44.0 48.0		0.030	1.5 4.0	2.5 4.0		
NW6690	NiCr29Fe9		0.05		27.0 31.0	0.5 0.5		7.0 11.0	0.5	Remainder	0.015	0.5			8.2	

Number	Description	Al	B	C	Co4)	Cr	Cu	Fe	Composition % (m/m)2)						Density3) g/cm <sup>3</sup>		
									Mn	Mo	Ni	P	S	Si	Ti		
NW6455	NiCr16Mo16Ti			0,015	2,0	14,0	18,0	3,0	1,0	14,0	Remainder	0,040	0,030	0,08	0,7	8,6	
NW6922	NiCr21Mo13Fe4W3			0,015	2,5	20,0	22,5	2,0	0,5	12,5	Remainder	0,025	0,020	0,08	2,5 2,5	8,7	
NW6625	NiCr22Mo9Nb					20,0	23,0	5,0	5,0	8,0	58,0	0,015	0,015	0,50	Nb+Ta: 3,15 to 4,15	8,5	
NW6621	NiCr20Ti1	0,40 0,08	0,09 0,15	0,0	0,0	0,0	0,0	5,0	1,0	1,0	Remainder	0,020	1,0	0,20 0,60	Pb: 0,0060(50)	8,4	
NW7080	NiCr20Ti2Al	1,0 1,8	0,008 0,10	0,04 2,0	0,10 21,0	18,0 0,2	21,0 0,2	1,5 1,0	1,0	1,5	Remainder	0,015	1,0	1,8 2,7	Ag: 0,0005(5) Bi: 0,0001(1) Pb: 0,0020(20)	8,2	
NW4400	NiCu30-LC					28,0 34,0	36,0 2,5	2,5 2,0		63,0		0,025	0,5			8,8	
NW5500	NiCu30Al3Ti	2,2 3,2	0,25			27,0 34,0	2,0	1,5			Remainder	0,020	0,015	0,5 0,85		8,8	
NW8825	NiFe30Cr21Mo3	0,2	0,05			19,5 23,5	1,5 3,0	Remainder	1,0	2,5 3,5	38,0 46,0	0,015	0,5	0,6 1,2		8,5	
NW8911	NiFe36Cr12Mo6Ti3	0,35	0,010 0,020	0,02 0,06		11,0 14,0	0,2	Remainder	0,5	5,0 6,5	40,0 45,0	0,020	0,020	0,4 3,1		8,1	
NW0276	NiMo16Cr15Fe6W4					14,5	16,5	4,0 7,0	1,0	15,0 17,0	Remainder	0,040	0,030	0,08 4,5		8,2	
NW0665	NiMo28					0,010	2,5	1,0	2,0	1,0	26,0 30,0	Remainder	0,040	0,030	0,1		8,9
NW0001	NiMo30Fe5			0,02	1,0			6,0	4,0	26,0 1,0	Remainder	0,040	0,030	1,0	V: 0,2 to 0,4	9,2	
NW6028	FeNi31Cr27Mo4Cu1			0,030		26,0 28,0	0,6 1,4	Remainder	2,5	3,0 4,0	30,0 34,0	0,030	0,030	1,0		8,0	
NW8800	FeNi32Cr21AlTi	0,15 0,60	0,10			19,0 23,0	0,7	Remainder	1,5	30,0 35,0	0,05 1,0	0,15 0,60			8,0		

# iTeh STANDARD REVIEW (standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/c0265155-4159-407f-87c7-e1eac36c974/iso-9-722-t992>

Alloy identification <sup>1)</sup> Number	Description	Al	B	C	Co <sup>4)</sup>	Cr	Cu	Fe	Composition % (m/m) <sup>2)</sup>				P	S	Si	Ti	W	Others <sup>5)</sup>	Density <sup>3)</sup> g/cm <sup>3</sup>
									Mn	Mo	Ni								
NW8810	FeNi32Cr21AlTi-HC	0,15 0,60		0,05 0,10		19,0 23,0	0,7	Remainder	1,5		30,0 35,0		0,015	1,0	0,15 0,60			3,0	
NW8811	FeNi32Cr21AlTi-HT	0,25 0,60		0,06 0,10		19,0 23,0	0,7	Remainder	1,5		30,0 35,0		0,015	1,0	0,25 0,60		Al+Ti: 0,85 to 1,2	8,0	
NW8801	FeNi32Cr21Ti			0,10		19,0 22,0	0,5	Remainder	1,5		30,0 34,0		0,015	1,0	0,7 1,5			8,0	
NW8820	FeNi35Cr20Cu4Mo2			0,07		19,0 21,0	3,0 4,0	Remainder	2,0	2,0 3,0	32,0 38,0		0,040	0,030	1,0		Nb+Ta: 8 x C to 1,0	8,1	

- 1) For alloy identification either the number or the description may be used.
- 2) Single values are maximum limits, except for nickel where single values are minimum.
- 3) Density values are average values and are given for information only.
- 4) Where no limits are specified, cobalt up to a maximum of 1,5 % is allowed and counted as nickel. In this case, an indication of cobalt content is not required.
- 5) Values for Ag, Bi and Pb may be expressed in mass percentage [% (m/m)] or in parts per million (ppm).

**Table 2 — Forms of wrought products in which nickel and nickel alloys are available**

Alloy identification <sup>1)</sup>		Plate Sheet Strip ISO 6208	Tubes ISO 6207	Rod Bar ISO 9723	Wire ISO 9724	Forgings ISO 9725
Number	Description					
NW2200	Ni99,0	X	X	X	X	X
NW2201	Ni99,0-LC	X	X	X	X	X
NW3021	NiCo20Cr15Mo5Al4Ti			X		X
NW7263	NiCo20Cr20Mo5Ti2Al	X	X	X		X
NW7001	NiCr20Co13Mo4Ti3Al			X	X	X
NW7090	NiCr20C018Ti3	X		X	X	X
NW6617	NiCr22Co12Mo9	X	X		X	
NW7750	NiCr15Fe7Ti2Al	X		X	X	X
NW6600	NiCr15Fe8	X	X	X	X	X
NW6602	NiCr15Fe8-LC	X	X	X		X
NW7718	NiCr19Fe19Nb5Mo3	X		X	X	X
NW6002	NiCr21Fe18Mo9	X	X	X	X	X
NW6007	NiCr22Fe20Mo6Cu2Nb	X	X		X	
NW6985	NiCr22Fe20Mo7Cu2	X	X		X	
NW6601	NiCr23Fe15Al	X	X	X	X	X
NW6333	NiCr26Fe20Co3Mo3W3	X	X	X	X	
NW6690	NiCr29Fe9	X	X	X	X	
NW6455	NiCr16Mo16Ti	X	X	X	X	X
NW6022	NiCr21Mo13Fe4W3	X	X	X	X	
NW6625	NiCr22Mo9Nb	X	X	X	X	X
NW6621	NiCr20Ti	X	X	X	X	X
NW7080	NiCr20Ti2Al	X		X	X	X
NW4400	NiCu30	X	X	X	X	X
NW4402	NiCu30-LC	X	X	X		X
NW5500	NiCu30Al3Ti	X		X	X	X
NW8825	NiFe30Cr21Mo3	X	X	X	X	X
NW9911	NiFe36Cr12Mo6Ti3			X		X
NW0276	NiMo16Cr15WFe6W4	X	X	X	X	X
NW0665	NiMo28	X	X	X	X	X
NW0001	NiMo30Fe5	X	X	X	X	X
NW8028	FeNi31Cr27Mo4Cu1	X	X		X	

iTeh STANDARD PREVIEW  
(standards.itech.ai)

ISO 9722:1992

<http://standards.itech.ai/catalog/standards/sist/cx265155-4159-x07f87d7-01e7ac36c974/iso-9722:1992>

Alloy identification <sup>1)</sup>		Plate Sheet Strip ISO 6208	Tubes ISO 6207	Rod Bar ISO 9723	Wire ISO 9724	Forgings ISO 9725
Number	Description					
NW8800	FeNi32Cr21AlTi	X	X	X	X	X
NW8810	FeNi32Cr21AlTi-HC	X	X	X		X
NW8811	FeNi32Cr21AlTi-HT	X	X	X		X
NW8801	FeNi32Cr20Ti	X	X	X		X
NW8802	FeNi35Cr20Cu4Mo2	X	X	X	X	X

1) For the identification of the alloy, either the number or the description may be used.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 9722:1992](#)

<https://standards.iteh.ai/catalog/standards/sist/c0265155-4159-407f-87c7-e1e7ac36c974/iso-9722-1992>