



SLOVENSKI STANDARD
SIST ISO 9725:1996
01-avgust-1996

Izkovki iz niklja in nikljevih zlitin

Nickel and nickel alloy forgings

Pièces forgées en nickel et alliages de nickel

Ta slovenski standard je istoveten z: ISO 9725:1992

[SIST ISO 9725:1996
https://standards.iteh.ai/catalog/standards/sist/913d8b78-1acb-4045-9ecd-958b42c50749/sist-iso-9725-1996](https://standards.iteh.ai/catalog/standards/sist/913d8b78-1acb-4045-9ecd-958b42c50749/sist-iso-9725-1996)

ICS:

| | | |
|-----------|-----------------------------|------------------------------|
| 77.150.40 | Nikljevi in kromovi izdelki | Nickel and chromium products |
|-----------|-----------------------------|------------------------------|

SIST ISO 9725:1996

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 9725:1996

<https://standards.iteh.ai/catalog/standards/sist/913d8b78-1acb-4045-9ecd-958b42c50749/sist-iso-9725-1996>

INTERNATIONAL STANDARD

**ISO
9725**

First edition
1992-12-01

Nickel and nickel alloy forgings

Pièces forgées en nickel et alliages de nickel

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 9725:1996](https://standards.iteh.ai/catalog/standards/sist/913d8b78-1acb-4045-9ecd-958b42c50749/sist-iso-9725-1996)

<https://standards.iteh.ai/catalog/standards/sist/913d8b78-1acb-4045-9ecd-958b42c50749/sist-iso-9725-1996>



Reference number
ISO 9725:1992(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 9725 was prepared by Technical Committee ISO/TC 155, *Nickel and nickel alloys*, Sub-Committee SC 2, *Wrought and cast nickel and nickel alloys*.

[SIST ISO 9725:1996](https://standards.iteh.ai/catalog/standards/sist/913d8b78-1acb-4045-9ecd-958642c50749/sist-iso-9725-1996)

Annex A forms an integral part of this International Standard.

<https://standards.iteh.ai/catalog/standards/sist/913d8b78-1acb-4045-9ecd-958642c50749/sist-iso-9725-1996>

© ISO 1992

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Nickel and nickel alloy forgings

1 Scope

This International Standard specifies requirements for nickel and nickel alloy forgings for general purposes.

NOTE 1 Bars used for the manufacture of forgings should conform to the requirements for bars to be further worked by the purchaser, specified in subclause 5.2 of ISO 9723:1992.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO/R 204:1961, *Non-interrupted creep testing of steel at elevated temperatures*.

ISO/R 206:1961, *Creep stress rupture testing of steel at elevated temperatures*.

ISO 6372-1:1989, *Nickel and nickel alloys — Terms and definitions — Part 1: Materials*.

ISO 6372-3:1989, *Nickel and nickel alloys — Terms and definitions — Part 3: Wrought products and castings*.

ISO 6892:1984, *Metallic materials — Tensile testing*.

ISO/TR 7003:1990, *Unified format for the designation of metals*.

ISO/TR 9721:1992, *Nickel and nickel alloys — Rules for material description based on chemical symbols*.

ISO 9722:1992, *Nickel and nickel alloys — Composition and forms of wrought products*.

ISO 9723:1992, *Nickel and nickel alloy bars*.

ASTM E 112:1988, *Standard methods for determining average grain size*.

3 Definitions

For the purposes of this International Standard, the following definitions and those for nickel and nickel alloys in ISO 6372-1 and for forgings in 6372-3 apply.

3.1 heat: The product of a furnace melt or a number of melts that are mixed prior to casting.

3.2 lot: Forgings of the same cross-sectional dimensions, from the same heat, heat treated together or sequentially heat treated in a continuous furnace, but in no case for longer than 16 h of production. For forgings not identified by heat, the lot shall be either one piece of the forging or 500 kg, whichever is larger.

4 Alloy identification

For the purposes of this International Standard, the principles for alloy identification in ISO/TR 7003 and ISO/TR 9721 apply.

ISO 9725:1992(E)

5 Ordering information

Orders for forgings according to this International Standard shall include the following information.

5.1 The number of this International Standard.

5.2 Quantity (mass or number of pieces).

5.3 Alloy identification (see table 1).

NOTE 2 For alloy identification, either the number or the description may be used.

5.4 Alloy temper (see table 2).

5.5 Dimensions and tolerances: marked on the sketch or drawing.

5.6 Specify if purchaser will heat treat the product.

5.7 Optional requirements:

- a) samples for product analysis (see 7.1.2);
- b) type of test sample (see 7.2);
- c) determination of 1 % proof stress, (see 9.2.3);
- d) hardness as acceptance test (see 6.1.6);
- e) individual forging marking (see 10.2);
- f) purchaser or third party inspection (see clause 11);
- g) declaration of conformity (see clause 12).

6 Requirements

6.1 Requirements for forgings heat treated by the manufacturer

Unless required in the hot-finished temper, forgings shall be supplied in the annealed, solution treated or solution and precipitation treated temper.

Unless otherwise specified, precipitation-hardenable alloy forgings shall be supplied in the solution treated temper.

6.1.1 Composition

Heat analysis shall meet the composition limits specified in table 1.

The composition limits do not preclude the possible presence of other elements that are not specified. If the purchaser's requirements necessitate limits for any other element that is not specified, these shall

be agreed between the purchaser and the supplier. The percentage content of elements shown as "remainder" shall be calculated by difference from 100 %.

6.1.2 Tensile properties

Forgings shall have the tensile properties specified in table 2.

6.1.3 Heat treatment

Precipitation-hardenable alloy forgings shall be heat treated in accordance with table 3 to the condition as ordered.

6.1.4 Grain size

Forgings of alloys NW8810 (FeNi32Cr21AlTi-HC) and NW8811 (FeNi32Cr21AlTi-HT) shall have a grain size ASTM No. 5 or coarser (average diameter 0,06 mm or greater).

6.1.5 Creep or stress rupture properties

Where applicable, forgings of precipitation-hardenable alloys shall meet the creep or stress rupture requirements of table 4.

6.1.6 Hardness

If it is required that qualification and acceptance of forgings be based on hardness instead of tensile properties, the hardness values to be met and the method of hardness test to be used shall be specified on the order form or drawing.

6.1.7 Dimensional tolerances

Dimensions and tolerances shall be as specified on the order form or drawing.

6.1.8 Surface condition

Forgings shall be clean and free from detrimental surface imperfections.

NOTE 3 Where appropriate, the acceptance criteria should be agreed between the purchaser and the supplier.

6.2 Requirements for forgings to be heat treated by the purchaser

6.2.1 Composition

Heat analysis shall meet the composition limits specified in table 1.

The composition limits do not preclude the possible presence of other elements that are not specified. If the purchaser's requirements necessitate limits for

any other element that is not specified, these shall be agreed between the purchaser and the supplier. The percentage content of elements shown as "remainder" shall be calculated by difference from 100 %.

6.2.2 Temper

Unless otherwise specified, forgings to be heat treated by the purchaser shall be supplied in the hot-worked temper.

6.2.3 Precipitation-hardenable alloys

The supplier of precipitation-hardenable alloy forgings shall demonstrate the capability of meeting the requirements specified in table 2 and/or table 4, by testing samples heat treated in accordance with table 3.

6.2.4 Dimensional tolerances

Dimensional tolerances shall conform to the requirements specified on the order form or drawing.

6.2.5 Surface condition

Forgings shall be clean and free from detrimental surface imperfections.

NOTE 4 Where appropriate, the acceptance criteria should be agreed between the purchaser and the supplier.

7 Sampling

7.1 Chemical analysis

7.1.1 Representative heat analysis samples shall be taken during pouring or subsequent processing.

7.1.2 Product analysis samples shall be taken from the finished product.

7.2 Tensile, creep or stress rupture test

Test specimens shall be taken either as separate test samples (see 7.2.1), as integral test samples (see 7.2.2) or as test samples machined from the body of the forgings.

Unless otherwise specified, the sampling procedure and the location of samples representing the lot shall be at the option of the supplier.

7.2.1 Separate test samples shall be prepared from the same heat from which the forgings are made and forged to obtain samples. Separate test samples shall be identifiable to the forgings they represent.

7.2.2 Integral test samples shall be provided by extensions or prolongations on one or both ends of the forgings; they shall not be separated from the forgings until all heat treatment has been completed.

If the forgings are to be supplied in other than the fully heat-treated condition, the test samples shall be separated from the forgings only if required by the purchaser.

7.2.3 Test samples machined from the body of the forgings shall be taken in the final heat-treated condition.

7.3 Heat treatment of test samples

7.3.1 Forgings supplied in hot-worked temper

If appropriate, test samples selected in accordance with 7.2 shall be annealed or solution and precipitation treated in accordance with table 3 prior to testing.

7.3.2 Forgings supplied in heat-treated temper

Test samples selected in accordance with 7.2 shall be heat treated with the forging they represent.

8 Number of tests

8.1 Chemical analysis, one test per heat.

8.2 Forgings heat treated by the manufacturer

Tensile strength and creep or stress rupture and grain size shall be tested at a frequency of one test per lot.

8.3 Forgings to be heat treated by the purchaser

Capability tests for tensile strength, creep or stress rupture shall be tested at a frequency of one test per lot.

9 Test procedures

9.1 Chemical analysis

9.1.1 The method of chemical analysis shall be at the option of the supplier, however, in cases of dispute the method specified in the relevant International Standard shall be used.

If no International Standard exists, an analytical method that can be calibrated to a reference standard agreed upon by the purchaser and the supplier shall be used.

9.1.2 For a list of ISO analytical standards, see annex A.

ISO 9725:1992(E)

9.2 Tensile testing

9.2.1 Tensile testing shall be carried out in accordance with ISO 6892.

9.2.2 The largest possible round specimen, not exceeding 15 mm in diameter on the gauge length, shall be used. (See annexes C and D of ISO 6892).

9.2.3 The offset method shall be used for the determination of proof stress. An offset of 0,2 % ($R_{p0,2}$) shall be standard. However, a 1 % proof stress ($R_{p1,0}$) shall be determined and reported for information when requested by the purchaser.

9.3 Creep and stress rupture testing

9.3.1 Creep tests shall be carried out in accordance with ISO/R 204, except that only the final total plastic strain need be reported.

9.3.2 Stress rupture tests shall be carried out in accordance with ISO/R 206.

9.4 Grain size determination

A sample in the final heat-treated condition shall be examined in accordance with ASTM E 112, on a section transverse to the greatest metal flow.

9.5 Rounding-off

For the purpose of determining compliance with the specified limits of the properties listed below, an observed value or calculated value shall be rounded as follows.

When the figure immediately after the last figure to be retained is lower than 5, the last figure to be retained remains unchanged.

When the figure immediately after the last figure to be retained is 5 or greater, the last figure to be retained is increased by one.

| | |
|---|---|
| Composition, creep, stress rupture, grain size, hardness and dimensions | Nearest unit to the last right-hand place of figures of the specified limit |
| Tensile strength (R_m) | Nearest 10 N/mm ² |
| Proof stress ($R_{p0,2}$) | Nearest 5 N/mm ² |
| Elongation (A) | Nearest 1 % |

9.6 Retests

If any one of the test pieces first selected fails to pass the specified tests, two further samples from the same lot shall be selected for testing, one of which shall be from the original forging tested, unless that forging has been withdrawn by the supplier. If the test pieces from both these additional samples pass, the lot represented by the test samples shall be deemed to comply with the requirements of this International Standard. If the test pieces from either of these additional samples fail, the lot represented by these samples shall be deemed not to comply with the requirements of this International Standard.

10 Marking

10.1 Each shipping container shall be marked with the number of this International Standard, the alloy identification (either the number or the description), heat-treated condition, drawing number, the gross, tare and net weight, the consigner and consignee address, contract or order number, and any other information requested in the contract or order.

10.2 If agreed between the purchaser and supplier, the supplier shall mark each forging with the number of this International Standard, the alloy identification (either the designation or the UNS-Number), the heat number and the manufacturer's name. The method of marking will be at the option of the supplier, unless otherwise agreed. Marking shall not result in harmful contamination.

11 Purchaser or third party inspection

On-site inspection of forgings by the purchaser or third parties shall be in accordance with agreements made between the purchaser and the supplier as part of the purchase contract.

12 Declaration of conformity

When requested by the purchaser in the contract or order, the supplier shall certify that the forgings were manufactured and tested in accordance with this International Standard. The declaration of conformity shall detail the heat treatment applied to the forgings and/or the test samples and the results of all tests required by this International Standard and the order.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 9725:1996
<https://standards.iteh.ai/catalog/standards/sist/913d8b78-1acb-4045-9ecd-959b42c50749/sist-iso-9725-1996>

Table 1 — Composition and density of wrought nickel and nickel alloys (selected from table 1 of ISO 9722:1992)

| Alloy identification ¹⁾ Number | Description | Composition % (wt/m ²) | | | | | | | | | | | Density ²⁾ g/cm ³ | | | | | | | | | | | | | | | | |
|--|--------------------|------------------------------------|----------------|--------------|------------------|--------------|------|------|--------------|--------------|-------|------|--|---|----|----|---|----------------------|--|-------|------|--|--|--|--|--|--|--|-----|
| | | Al | B | C | Co ⁴⁾ | Cr | Cu | Fe | Mn | Mo | Ni | P | | S | Si | Ti | W | Others ⁵⁾ | | | | | | | | | | | |
| NW2200 | Ni99,0 | | | 0,15 | | | | | | 0,2 | 0,4 | 0,3 | | | | | | 99,0 | | 0,010 | 0,3 | | | | | | | | 8,9 |
| NW2201 | Ni99,0-LC | | | 0,02 | | | | | | 0,2 | 0,4 | 0,3 | | | | | | 99,0 | | 0,010 | 0,3 | | | | | | | | 8,9 |
| NW3021 | NiCo20Cr13Mo5Al4Ti | 4,5 4,9 | 0,003 0,010 | 0,12 0,17 | 18,0 22,0 | 14,0 15,7 | 0,2 | 1,0 | 4,5 5,5 | Remainder | 0,015 | 1,0 | 0,9 1,5 | | | | | Remainder | | 0,015 | 1,0 | 0,0005(5) Bi: 0,0001(1) Pb: 0,0015(15) | | | | | | | 8,4 |
| NW7263 | NiCo20Cr20Mo5Ti2Al | 0,3 0,6 | 0,005 | 0,04 0,08 | 19,0 21,0 | 19,0 21,0 | 0,2 | 0,6 | 5,6 6,1 | Remainder | 0,007 | 0,4 | 1,9 2,4 | | | | | Remainder | | 0,007 | 0,4 | Ag: 0,0005(5) Bi: 0,0001(1) Pb: 0,0020(20) Ti+Al: 2,4 to 2,8 | | | | | | | 8,4 |
| NW7001 | NiCr20Co13Mo4Ti3Al | 1,2 1,6 | 0,003 0,010 | 0,02 0,10 | 12,0 15,0 | 18,0 21,0 | 0,10 | 1,0 | 3,5 5,0 | Remainder | 2,0 | 0,1 | 2,8 3,3 | | | | | Remainder | | 0,015 | 0,1 | Ag: 0,0005(5) Bi: 0,0005(0,5) Pb: 0,0010(10) Zr: 0,02 to 0,08 | | | | | | | 8,4 |
| NW7090 | NiCr20Co18Ti3 | 1,0 2,0 | 0,020 | 0,13 | 15,0 21,0 | 18,0 21,0 | 0,2 | 1,0 | Remainder | Remainder | 0,015 | 1,0 | 2,0 3,0 | | | | | Remainder | | 0,015 | 1,0 | Zr: 0,15 | | | | | | | 8,2 |
| NW7750 | NiCr15Fe7Ti2Al | 0,4 1,0 | | 0,08 | | 14,0 17,0 | 0,5 | 1,0 | 70,0 | 5,0 9,0 | 0,015 | 0,5 | 2,2 2,8 | | | | | 70,0 | | 0,015 | 0,5 | Nb+Ta: 0,7 to 1,2 | | | | | | | 8,3 |
| NW6600 | NiCr15Fe8 | | | 0,15 | | 14,0 17,0 | 0,5 | 1,0 | 72,0 | 6,0 10,0 | 0,015 | 0,5 | | | | | | 72,0 | | 0,015 | 0,5 | | | | | | | | 8,4 |
| NW6602 | NiCr15Fe8-LC | | | 0,02 | | 14,0 17,0 | 0,5 | 1,0 | 72,0 | 6,0 10,0 | 0,015 | 0,5 | | | | | | 72,0 | | 0,015 | 0,5 | | | | | | | | 8,4 |
| NW7718 | NiCr19Fe19Nb5Mo3 | 0,2 0,8 | 0,006 | 0,08 | | 17,0 21,0 | 0,3 | | 2,8 3,3 | Remainder | 0,015 | 0,4 | 0,6 1,2 | | | | | 50,0 55,0 | | 0,015 | 0,4 | Nb+Ta: 4,7 to 5,5 | | | | | | | 8,0 |
| NW6002 | NiCr21Fe18Mo9 | | 0,010 | 0,05 0,15 | 0,5 2,5 | 20,5 23,0 | | 1,0 | 8,0 10,0 | 17,0 20,0 | 0,040 | 1,0 | 0,2 1,0 | | | | | Remainder | | 0,040 | 1,0 | | | | | | | | 8,2 |
| NW6601 | NiCr23Fe15Al | 1,0 1,7 | | 0,10 | | 21,0 25,0 | 1,0 | | | Remainder | | 0,5 | | | | | | 58,0 63,0 | | 0,015 | 0,5 | | | | | | | | 8,0 |
| NW6455 | NiCr16Mo16Ti | | | 0,015 | 2,0 | 14,0 18,0 | | 1,0 | 14,0 17,0 | 3,0 | 0,040 | 0,08 | 0,7 | | | | | Remainder | | 0,040 | 0,08 | | | | | | | | 8,6 |
| NW6625 | NiCr22Mo8Nb | 0,40 | | 0,10 | 1,0 | 20,0 23,0 | | 0,50 | 8,0 10,0 | 5,0 | 0,015 | 0,15 | 0,40 | | | | | 58,0 | | 0,015 | 0,15 | Nb+Ta: 3,15 to 4,15 | | | | | | | 8,5 |
| NW6621 | NiCr20Ti | | | 0,08 0,15 | 5,0 | 18,0 21,0 | 0,5 | 1,0 | Remainder | 5,0 | | 1,0 | 0,20 0,60 | | | | | Remainder | | 0,020 | 1,0 | Pb: 0,0050(50) | | | | | | | 8,4 |
| NW7080 | NiCr20Ti2Al | 1,0 1,8 | 0,008 | 0,04 0,10 | 2,0 | 18,0 21,0 | 0,2 | 1,0 | Remainder | 1,5 | 0,015 | 1,0 | 1,8 2,7 | | | | | Remainder | | 0,015 | 1,0 | Ag: 0,0005(5) Bi: 0,0001(1) Pb: 0,0020(20) | | | | | | | 8,2 |
| NW4400 | NiCu30 | | | 0,30 | | | | 2,0 | | 28,0 34,0 | 2,5 | 2,0 | | | | | | 63,0 | | 0,025 | 0,5 | | | | | | | | 8,8 |