
Industrija za predelavo nafte in zemeljskega plina - S steklenimi vlakni ojačeni polimerni cevovodi (GRP) - 4. del: Izdelava, vgradnja in delovanje (ISO 14692-4:2002)

Petroleum and natural gas industries - Glass-reinforced plastics (GRP) piping - Part 4: Fabrication, installation and operation (ISO 14692-4:2002)

Erdöl- und Erdgasindustrie - Glasfaserverstärkte Kunststoffrohrleitungen (GFK) - Teil 4: Fertigung, Installation und Betrieb (ISO 14692-4:2002)

Industries du pétrole et du gaz naturel - Canalisations en plastique renforcé de verre (PRV) - Partie 4: Construction, installation et mise en oeuvre (ISO 14692-4:2002)

Ta slovenski standard je istoveten z: EN ISO 14692-4:2002

ICS:

75.200	Oprema za skladiščenje nafte, naftnih proizvodov in zemeljskega plina	Petroleum products and natural gas handling equipment
83.140.30	Cevi, fitingi in ventili iz polimernih materialov	Plastics pipes, fittings and valves

SIST EN ISO 14692-4:2004

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 14692-4:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/2e0b759e-ecc2-4aec-bc1a-bec1730bbeb9/sist-en-iso-14692-4-2004>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 14692-4

December 2002

ICS 75.200; 83.140.30

English version

**Petroleum and natural gas industries - Glass-reinforced plastics
(GRP) piping - Part 4: Fabrication, installation and operation
(ISO 14692-4:2002)**

Industries du pétrole et du gaz naturel - Canalisations en
plastique renforcé de verre (PRV) - Partie 4: Construction,
installation et mise en oeuvre (ISO 14692-4:2002)

This European Standard was approved by CEN on 2 December 2002.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/2e0b759e-ecc2-4aec-bc1a-bec1730bbeb9/sist-en-iso-14692-4-2004>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

EN ISO 14692-4:2002 (E)**Foreword**

This document (EN ISO 14692-4:2002) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum and natural gas industries", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2003, and conflicting national standards shall be withdrawn at the latest by June 2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

NOTE FROM CMC The foreword is susceptible to be amended on reception of the German language version. The confirmed or amended foreword, and when appropriate, the normative annex ZA for the references to international publications with their relevant European publications will be circulated with the German version.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of ISO 14692-4:2002 has been approved by CEN as EN ISO 14692-4:2002 without any modifications.

[SIST EN ISO 14692-4:2004](https://standards.iteh.ai/catalog/standards/sist/2e0b759e-ecc2-4aec-bc1a-bec1730bbeb9/sist-en-iso-14692-4-2004)

<https://standards.iteh.ai/catalog/standards/sist/2e0b759e-ecc2-4aec-bc1a-bec1730bbeb9/sist-en-iso-14692-4-2004>

INTERNATIONAL
STANDARD

ISO
14692-4

First edition
2002-12-15

**Petroleum and natural gas industries —
Glass-reinforced plastics (GRP) piping —
Part 4:
Fabrication, installation and operation**

*Industries du pétrole et du gaz naturel — Canalisations en plastique
renforcé de verre (PRV) —*

Partie 4: Construction, installation et mise en œuvre

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 14692-4:2004](https://standards.iteh.ai/catalog/standards/sist/2e0b759e-ecc2-4aec-bc1a-bec1730bbeb9/sist-en-iso-14692-4-2004)

<https://standards.iteh.ai/catalog/standards/sist/2e0b759e-ecc2-4aec-bc1a-bec1730bbeb9/sist-en-iso-14692-4-2004>



Reference number
ISO 14692-4:2002(E)

© ISO 2002

ISO 14692-4:2002(E)**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 14692-4:2004](https://standards.iteh.ai/catalog/standards/sist/2e0b759e-ecc2-4aec-bc1a-bec1730bbeb9/sist-en-iso-14692-4-2004)

<https://standards.iteh.ai/catalog/standards/sist/2e0b759e-ecc2-4aec-bc1a-bec1730bbeb9/sist-en-iso-14692-4-2004>

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and abbreviated terms	2
5 Fabrication and installation	2
5.1 Delivery, inspection and documentation of GRP piping	2
5.2 Handling and storage	2
5.3 System design documentation	2
5.4 Installer requirements	3
5.5 Installation methods	3
5.6 System testing	12
5.7 Inspection	13
5.8 Certification and documentation	15
5.9 Repair after installation	15
6 Operations	15
6.1 Operator's documentation	15
6.2 Maintenance and repair	17
6.3 Repair methods	19
6.4 Modifications and tie-ins	21
6.5 Requirements for testing and re-certification	21
6.6 Decommissioning	21
Annex A (normative) Defect types — Acceptance criteria and corrective actions	22
Annex B (normative) Handling and storage	29
Annex C (informative) Guidance for use of jointing methods	32
Annex D (normative) Qualification of pipe fitter, supervisor and inspector	41
Annex E (informative) Guidance on NDE methods	47
Annex F (normative) Health and safety	51
Bibliography	52

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 14692-4 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 6, *Processing equipment and systems*.

iTeh STANDARD PREVIEW

ISO 14692 consists of the following parts, under the general title *Petroleum and natural gas industries — Glass-reinforced plastics (GRP) piping*:

- *Part 1: Vocabulary, symbols, applications and materials*
- *Part 2: Qualification and manufacture*
- *Part 3: System design*
- *Part 4: Fabrication, installation and operation*

Introduction

The objective of this part of ISO 14692-4 is to ensure that installed piping systems will meet the specified performance requirements throughout their operational life. Main users of the document are envisaged to be the principal, fabrication/installation contractors, repair and maintenance contractors, certifying authorities and government agencies.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 14692-4:2004](https://standards.iteh.ai/catalog/standards/sist/2e0b759e-ecc2-4aec-bc1a-bec1730bbeb9/sist-en-iso-14692-4-2004)

<https://standards.iteh.ai/catalog/standards/sist/2e0b759e-ecc2-4aec-bc1a-bec1730bbeb9/sist-en-iso-14692-4-2004>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 14692-4:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/2e0b759e-ecc2-4aec-bc1a-bec1730bbeb9/sist-en-iso-14692-4-2004>

Petroleum and natural gas industries — Glass-reinforced plastics (GRP) piping —

Part 4: Fabrication, installation and operation

1 Scope

This part of ISO 14692 gives requirements and recommendations for the fabrication, installation and operation of GRP piping systems for use in oil and natural gas industry processing and utility service applications. The recommendations apply to delivery, inspection, handling, storage, installation, system pressure testing, maintenance, repair and decommissioning.

It is intended to be read in conjunction with ISO 14692-1, which includes an explanation of the pressure terminology used in this part of ISO 14692.

iTeh STANDARD PREVIEW

2 Normative references (standards.iteh.ai)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9712, *Non-destructive testing — Qualification and certification of personnel*

ISO 14692-1:2002, *Petroleum and natural gas industries — Glass-reinforced plastics (GRP) piping — Part 1: Vocabulary, symbols, applications and materials*

ISO 14692-2:2002, *Petroleum and natural gas industries — Glass-reinforced plastics (GRP) piping — Part 2: Qualification and manufacture*

ISO 14692-3:2002, *Petroleum and natural gas industries — Glass-reinforced plastics (GRP) piping — Part 3: System design*

API Spec 5B, 1996, *Gauging and inspection of casing, tubing, and line pipe threads*

ASTM D257, *Standard test methods for DC resistance or conductance of insulating materials*

ASTM D1599, *Standard test method for resistance to short-time hydraulic failure pressure of plastic pipe, tubing, and fittings*

3 Terms and definitions

For the purposes of this part of ISO 14692, the terms and definitions given in ISO 14692-1 and the following apply.

ISO 14692-4:2002(E)

3.1 fabrication
construction of the piping system (and pipeline) on site from either individual components and/or spool pieces

NOTE Individual components may be pipes, tees, bends, etc.

4 Symbols and abbreviated terms

The symbols and abbreviated terms given in ISO 14692-1 apply.

5 Fabrication and installation

5.1 Delivery, inspection and documentation of GRP piping

This part of ISO 14692 assumes that the fittings and pipes have been correctly manufactured and inspected according to the criteria given in ISO 14692-2.

The dimensions of the components and spools shall be available for the installer and operator. The quantity, qualified pressure, nominal dimensions, and relevant special requirements of all piping components and prefabricated spools shall be verified for compliance with the purchase order. Shipments of piping components not complying with the purchase order shall be reported to responsible personnel and to the pipe producer for corrective actions.

All piping components shall be visually inspected in accordance with Table A.1 for damage that may have occurred during storage and shipment. Rejected components shall be replaced. If doubts concerning the extent of defects occur during inspection, a specialist approved by the principal shall perform a second inspection of the delivered items.

Adhesive bonding kits shall be inspected to ensure that the kits contain all necessary materials, are not leaking or visibly damaged, and that at least six months remains until the expiration of shelf-life. All fire protection material shall be inspected to ensure that the original packaging is not damaged.

5.2 Handling and storage

The handling of the GRP components shall follow the guidelines given in Annex B and the requirements of the pipe manufacturer.

5.3 System design documentation

The principal shall provide the installer with the following information, which shall include but not be limited to

- a) operating and design parameters:
- 1) design pressure;
 - 2) design temperature;
 - 3) T_g of the resin used in component manufacture;
 - 4) T_g of the adhesive used in component manufacture (if appropriate);
 - 5) qualified pressure of each component and minimum qualified pressure in each piping system;
 - 6) mean and maximum velocity conditions in each piping system;

- 7) chemical resistance limitations, if applicable;
 - 8) procedures to eliminate or control water hammer and cavitation, if applicable;
 - 9) fire classification and location of fire-rated pipe, if applicable;
 - 10) conductivity classification, location of conductive pipe, earth linkage/grounding requirements and location of earthing points;
 - 11) criticality;
- b) system drawings and support requirements for heavy equipment;
 - c) preferred locations for connection of final joint in pipe loops, if appropriate;
 - d) system criticality and minimum requirements for inspection during installation.

5.4 Installer requirements

5.4.1 Personnel qualification

All pipe, fittings and related items shall be installed by qualified GRP pipe fitters and thereafter approved by a qualified GRP piping inspector. GRP pipe fitters and GRP piping inspectors shall be qualified according to the minimum requirements detailed in Annex D.

5.4.2 Health and safety

In general, all safety precautions set forth by the manufacturer of pipes and fittings, chemicals, etc., shall be adopted. Materials safety data sheets should always be read before commencing work. The installer shall follow the health and safety guidance given in Annex F.

5.5 Installation methods

5.5.1 General

Installation methods shall be agreed between the principal and the manufacturer. Copies of installation methods, procedures and quality plans shall be available on-site before work commences.

5.5.2 Cutting

GRP pipe of nominal diameter up to 100 mm may be cut with a hacksaw, using guides to ensure a square cut. For nominal diameters above 100 mm, an abrasive cutting disc shall be used. The squareness of the cut shall be checked. Pipe of nominal diameter up to 100 mm shall be square to within 1,5 mm. Cuts on larger pipes shall be square to within 3,0 mm. The installer should ensure that the cut end is coated with resin.

For adhesive-bonded connections, the pipe end shall be machined with a pipe shaver. Each manufacturer has specialized equipment for shaving spigots. The pipe end shall be shaved to the manufacturer's recommendations regarding angle, diameter, length and eccentricity.

5.5.3 Supports

GRP piping systems may be supported using the same principles as those for metallic piping systems. However, due to the proprietary nature of piping systems, standard-size supports will not necessarily match the pipe outside diameters. The use of saddles and elastomeric pads may allow the use of standard-size supports.

ISO 14692-4:2002(E)

The following guidelines to GRP piping support should be followed.

- a) Supports in all cases should have sufficient width to support the piping without causing damage and should be lined with an elastomer or other suitable soft material.
- b) Clamping forces, if applied, should be such that crushing of the pipe does not occur. Local crushing can result from a poor fit and all-round crushing can result from over-tightening.
- c) In all cases, support design should be in accordance with the manufacturer's guidelines.
- d) Supports should preferably be located on plain pipe sections rather than at fittings or joints.
- e) Supports shall be spaced to avoid sag (excessive displacement over time) and/or excessive vibration for the design life of the piping system.
- f) Valves or other heavy attached equipment shall be independently supported.
- g) GRP pipe shall not be used to support other piping, unless agreed with the principal.
- h) Consideration shall be given to the support conditions of fire-protected GRP piping. Supports placed on the outside of fire protection can result in loads irregularly transmitted through the coating, which can result in shear/crushing damage and consequent loss of support integrity.
- i) GRP piping should be adequately supported to ensure that the attachment of hoses at locations such as utility or loading stations does not result in the pipe being pulled in a manner that could overstress the material.

The anchor support shall be capable of transferring the required axial loads to the supporting structure without causing overstress of the GRP pipe material.

Anchor clamps are recommended to be placed between two double 180° saddles, adhesive-bonded to the outer surface of the pipe. The manufacturer's standard saddles are recommended and shall be bonded using standard procedures.

5.5.4 Installation**5.5.4.1 General requirements**

The requirements for the handling of piping components are identical to those given in 5.2. Before installation, all piping components shall be inspected for damage as described in 5.1.

All piping components shall as far as possible be installed so that they are stress-free; therefore:

- a) bending of pipes to achieve changes in direction, or forcing misaligned flanges together by over-torquing bolts is not permitted;
- b) the manufacturer's recommendations for bolt-torquing sequence, torque increments and maximum bolt torque shall be followed.

Prefabricated pipework shall be fabricated in accordance with fully dimensioned piping isometrics. Overall spool dimensions shall be sized taking the following into consideration:

- a) site transport and handling equipment limitations;
- b) installation and erection limitations;
- c) limitations caused by the necessity to allow a fitting tolerance for installation ("cut-to-fit" requirements).

If shown on isometric drawings, the fabrication shall include “cut-to-fit” lengths and field joints on fabricated pieces to allow for the setting up of pipework accurately on-site between fixed points. The “cut-to-fit” dimension shall be 150 mm of pipe additional to the length shown on the piping drawings. For hook-up spools, the “cut-to-fit” dimension shall be a minimum of 250 mm in each global direction. “Cut-to-fit” lengths shall be left square and plain.

The installer shall give due consideration to the following:

- a) the need to avoid overstressing of GRP components by the forced pulling of GRP pipework to facilitate alignment at joints, and particularly at flanged joints;
- b) the need to ensure that valves or other heavy attached equipment are independently supported;
- c) the need to prevent damage to joints when handling small-diameter thick-walled pipe, e.g. due to fire protection;

NOTE This is because the high rigidity of the pipe concentrates loading at the thinner sections of pipe wall adjacent to the joint.

- d) the preferred location of the last site joint in a piping loop to ensure that necessary access is available, since this joint is often the most difficult to complete;
- e) delays caused by the time required for adhesive and laminated joints to cure without being disturbed. The scheduling of surrounding construction activities shall take into account the risk of possible disturbances to such joints;
- f) the need to provide temporary protection for installed GRP piping if risk of mechanical damage is high. The installer shall also consider correct sequencing of fabrication activities to minimize risk of damage;
- g) the need to prevent overheating of the GRP pipe material by electric surface heating, if applied. Heat tracing should be spirally wound onto GRP pipe in order to distribute the heat evenly around the pipe wall. Heat distribution can be improved if aluminium foil is first wrapped around the pipe. Care shall be taken that the tracing is not wound too tightly onto the pipework or it may be damaged when the pipe expands;
- h) provision of suitable joints to facilitate isolation or access to the pipe for maintenance purposes.

High levels of supervision and inspection shall be adopted for piping which will be difficult to repair on site (e.g. ballast lines due to be cast in concrete, and piping in ballast water tanks).

5.5.4.2 Components fabricated on-site

All processes used to fabricate spoolpieces and components on-site, e.g. mitred elbows and laterals, shall have been qualified according to procedures given in 6.2.3.3 of ISO 14692-2:2002.

5.5.4.3 Tolerances

Global tolerances shall be within ± 6 mm in all directions, unless otherwise shown on the approved drawings. Dimensional tolerances for finished piping are given in Table 1. The dimension numbers are shown in Figure 1.

The acceptable tolerances for misalignment of flanges during installation are given in Table 2. It is common practice for some flanges to be manufactured with bolt holes larger than the size of bolt being used with the flange. Typically, the hole will be 3 mm larger. This should be taken into account when assessing the flange misalignment tolerance in Tables 1 and 2.