

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE

Specifications for particular types of winding wires –  
Part 12: Polyvinyl acetal enamelled round copper wire, class 120

Spécifications pour types particuliers de fils de bobinage –  
Partie 12: Fil de section circulaire en cuivre émaillé avec acétal de polyvinyle,  
classe 120



## THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2010 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland  
Email: [inmail@iec.ch](mailto:inmail@iec.ch)  
Web: [www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: [www.iec.ch/online\\_news/justpub](http://www.iec.ch/online_news/justpub)

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

[www.iec.ch/online\\_news/justpub](http://www.iec.ch/online_news/justpub)

- Electropedia: [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: [www.iec.ch/webstore/custserv](http://www.iec.ch/webstore/custserv)

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: [csc@iec.ch](mailto:csc@iec.ch)

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

### A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

### A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: [www.iec.ch/searchpub/cur\\_fut-f.htm](http://www.iec.ch/searchpub/cur_fut-f.htm)

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: [www.iec.ch/online\\_news/justpub](http://www.iec.ch/online_news/justpub)

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: [www.electropedia.org](http://www.electropedia.org)

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: [www.iec.ch/webstore/custserv/custserv\\_entry-f.htm](http://www.iec.ch/webstore/custserv/custserv_entry-f.htm)

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: [csc@iec.ch](mailto:csc@iec.ch)

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00



IEC 60317-12

Edition 3.0 2010-03

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE

**Specifications for particular types of winding wires –  
Part 12: Polyvinyl acetal enamelled round copper wire, class 120**

**Spécifications pour types particuliers de fils de bobinage –  
Partie 12: Fil de section circulaire en cuivre émaillé avec acétal de polyvinyle,  
classe 120**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

PRICE CODE  
CODE PRIX

J

ICS 29.060.10

ISBN 978-2-88910-105-4

## CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Terms, definitions and general notes on methods of test and appearance.....	6
3.1 Terms and definition.....	6
3.2 General notes on methods of test.....	6
3.3 Appearance.....	7
4 Dimensions.....	7
5 Electrical resistance.....	7
6 Elongation.....	7
7 Springiness.....	7
8 Flexibility and adherence.....	7
9 Heat shock.....	7
9.1 Nominal conductor diameters up to and including 1,600 mm.....	7
9.2 Nominal conductor diameters over 1,600 mm.....	7
10 Cut-through.....	8
11 Resistance to abrasion (nominal conductor diameters from 0,250 mm up to and including 2,500 mm).....	8
12 Resistance to solvents.....	8
13 Breakdown voltage.....	8
14 Continuity of insulation.....	8
15 Temperature index.....	9
16 Resistance to refrigerants.....	9
17 Solderability.....	9
18 Heat or solvent bonding.....	9
19 Dielectric dissipation factor.....	9
20 Resistance to transformer oil.....	9
21 Loss of mass.....	9
23 Pin hole test.....	9
30 Packaging.....	9
Table 1 – Heat shock.....	7
Table 2 – Resistance to abrasion.....	8

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

**SPECIFICATIONS FOR PARTICULAR TYPES  
OF WINDING WIRES –****Part 12: Polyvinyl acetal enamelled  
round copper wire, class 120**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60317-12 has been prepared by IEC technical committee 55: Winding wires.

This third edition of IEC 60317-12 cancels and replaces the second edition published in 1990, its amendment 1 (1997) and its Amendment 2 (2005). This edition constitutes a technical revision.

The main changes with respect to the previous edition are listed below:

- new pin hole test requirements in Clause 23 have been added.

The text of this standard is based on the following documents:

FDIS	Report on voting
55/1178/FDIS	55/1189/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

This International Standard is to be read in conjunction with the IEC 60317-0-1 (2008).

A list of all the parts in the IEC 60317 series, under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

The committee has decided that the contents of this amendment and the base publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

**ITEH STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 60317-12:2010](https://standards.iteh.ai/catalog/standards/sist/95ea8b7c-e659-4771-b56e-c7b20dd6f297/iec-60317-12-2010)

<https://standards.iteh.ai/catalog/standards/sist/95ea8b7c-e659-4771-b56e-c7b20dd6f297/iec-60317-12-2010>

## INTRODUCTION

This Part of IEC 60317 is one of a series which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

- 1) winding wires and test methods (IEC 60851);
- 2) specifications for particular types of winding wires (IEC 60317);
- 3) packaging of winding wires (IEC 60264).

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 60317-12:2010](https://standards.iteh.ai/catalog/standards/sist/95ea8b7c-e659-4771-b56e-c7b20dd6f297/iec-60317-12-2010)

<https://standards.iteh.ai/catalog/standards/sist/95ea8b7c-e659-4771-b56e-c7b20dd6f297/iec-60317-12-2010>

## SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

### Part 12: Polyvinyl acetal enamelled round copper wire, class 120

#### 1 Scope

This Part of IEC 60317 specifies the requirements of enamelled round copper winding wire of class 120 with a sole coating based on polyvinyl acetal resin, which may be modified providing it retains the chemical identity of the original resin and meets all specified wire requirements.

NOTE A modified resin is a resin that has undergone a chemical change, or contains one or more additives to enhance certain performance or application characteristics.

Class 120 is a thermal class that requires a minimum temperature index of 120 and a heat shock temperature of at least 155 °C.

The temperature in degrees Celsius corresponding to the temperature index is not necessarily that at which it is recommended that the wire be operated and this will depend on many factors, including the type of equipment involved.

The range of nominal conductor diameters covered by this standard is:

- Grade 1: 0,040 mm up to and including 2,500 mm.
- Grade 2: 0,040 mm up to and including 5,000 mm.
- Grade 3: 0,080 mm up to and including 5,000 mm.

The nominal conductor diameters are specified in Clause 4 of IEC 60317-0-1.

#### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60317-0-1:2008, *Specifications for particular types of winding wires – Part 0-1: General requirements – Enamelled round copper wire*

#### 3 Terms, definitions and general notes on methods of test and appearance

##### 3.1 Terms and definition

For terms and definitions, see 3.1 of IEC 60317-0-1. In case of inconsistencies between IEC 60317-0-1 and this standard, IEC 60317-12 shall prevail.

##### 3.2 General notes on methods of test

For general notes on methods of test, see 3.2 of IEC 60317-0-1. In case of inconsistencies between IEC 60317-0-1 and this standard, IEC 60317-12 shall prevail.



### 3.3 Appearance

See 3.3 of IEC 60317-0-1.

### 4 Dimensions

See Clause 4 of IEC 60317-0-1.

### 5 Electrical resistance

See Clause 5 of IEC 60317-0-1.

### 6 Elongation

See Clause 6 of IEC 60317-0-1.

### 7 Springiness

See Clause 7 of IEC 60317-0-1.

### 8 Flexibility and adherence

See Clause 8 of IEC 60317-0-1, where the constant  $K$  used for the calculation of the number of revolutions for the peel test shall be 175 mm.

[IEC 60317-12:2010](https://standards.iteh.ai/catalog/standards/sist/95ea8b7c-e659-4771-b56e-c7b20dd6f297/iec-60317-12-2010)

### 9 Heat shock

<https://standards.iteh.ai/catalog/standards/sist/95ea8b7c-e659-4771-b56e-c7b20dd6f297/iec-60317-12-2010>

The minimum heat shock temperature shall be 155 °C.

#### 9.1 Nominal conductor diameters up to and including 1,600 mm

The coating shall show no crack. The mandrel diameter shall be as specified in Table 1.

**Table 1 – Heat shock**

Nominal conductor diameter mm		Elongation before winding on mandrel %	Mandrel diameter <sup>b</sup>
Over	Up to and including		
–	0,050	20 <sup>a</sup>	0,150 mm
0,050	1,600	–	$D$
<sup>a</sup> Or to the breaking point of the copper, whichever is less. <sup>b</sup> $D$ is the overall diameter of the wire.			

#### 9.2 Nominal conductor diameters over 1,600 mm

See 9.2 of IEC 60317-0-1.

### 10 Cut-through

No failure shall occur within 2 min at 170 °C.

### 11 Resistance to abrasion (nominal conductor diameters from 0,250 mm up to and including 2,500 mm)

The wire shall meet the requirements given in Table 2.

**Table 2 – Resistance to abrasion**

Nominal conductor diameter mm	Grade 1		Grade 2		Grade 3	
	Minimum average force to failure N	Minimum force to failure of each measurement N	Minimum average force to failure N	Minimum force to failure of each measurement N	Minimum average force to failure N	Minimum force to failure of each measurement N
0,250	3,00	2,55	4,90	4,15	5,80	4,90
0,280	3,25	2,75	5,25	4,45	6,25	5,30
0,315	3,50	2,95	5,65	4,80	6,70	5,70
0,355	3,75	3,20	6,05	5,15	7,20	6,10
0,400	4,05	3,45	6,50	5,50	7,70	6,50
0,450	4,35	3,70	7,00	5,90	8,25	7,00
0,500	4,65	3,95	7,50	6,35	8,85	7,50
0,560	5,00	4,25	8,00	6,80	9,50	8,05
0,630	5,35	4,55	8,60	7,30	10,2	8,65
0,710	5,70	4,85	9,20	7,80	10,9	9,25
0,800	6,10	5,15	9,90	8,40	11,7	9,90
0,900	6,55	5,55	10,6	9,00	12,5	10,6
1,000	7,05	5,95	11,3	9,60	13,3	11,3
1,120	7,60	6,45	12,1	10,2	14,2	12,0
1,250	8,20	6,95	12,9	11,0	15,2	12,9
1,400	8,80	7,45	13,9	11,8	16,4	13,9
1,600	9,45	8,00	14,9	12,6	17,6	14,9
1,800	10,1	8,60	16,0	13,5	18,8	16,0
2,000	10,9	9,20	17,1	14,4	20,2	17,1
2,240	11,7	9,90	18,2	15,4	21,6	18,3
2,500	12,5	10,6	19,4	16,4	23,0	19,5

For intermediate nominal conductor diameters, the value of the next larger nominal conductor diameter shall be taken.

### 12 Resistance to solvents

See Clause 12 of IEC 60317-0-1.

### 13 Breakdown voltage

See Clause 13 of IEC 60317-0-1, where the elevated temperature shall be 120 °C.

### 14 Continuity of insulation

See Clause 14 of IEC 60317-0-1.

## **15 Temperature index**

See Clause 15 of IEC 60317-0-1, where the minimum temperature index shall be 120.

## **16 Resistance to refrigerants**

Test appropriate but no requirements specified.

## **17 Solderability**

Test inappropriate.

## **18 Heat or solvent bonding**

Test inappropriate.

## **19 Dielectric dissipation factor**

Test inappropriate.

## **20 Resistance to transformer oil**

Test appropriate but no requirements specified.

## **21 Loss of mass**

Test inappropriate.

## **23 Pin hole test**

See Clause 23 of IEC 60317-0-1.

## **30 Packaging**

See Clause 30 of IEC 60317-0-1.

**ITeH STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 60317-12:2010](#)

<https://standards.iteh.ai/catalog/standards/sist/95ea8b7c-e659-4771-b56e-c7b20dd6f297/iec-60317-12-2010>

---