



# SLOVENSKI STANDARD SIST EN 3997:2009

01-maj-2009

5 YfcbUj h\_U!`5`i a ]b]Yj Un`]h]bU5 @D&\$&(!H`!`D`c Yj ]bU]b`fU\_cj]`\$ž`a a`®`U®  
\*`a a

OE!|.•] æ^Á^!a•ÄÖ { ā ā { Á|| ^ ÁŠËÜÇG È/HÄÜ@^Á} āÁdā ÁÊ Á { ÁÁÁÁÁÁ Á {

Š`-Ä} āÜæ { -@ÄÖ { ā ā { |^\*ā!` } \* ÁŠËÜÇG È/HÄÜ|^&@Á} āÁÔê} ā!ÄÊ Á { Án  
āÁÁ Á {

**iTeh STANDARD PREVIEW**

Ü..!ā Áe.!|.•] æā^ÄÖ|æ^Áö { ā ā { ÁŠËÜÇG È/HÄÜ|^ÁÁæ} ā^ÁÊ Á { ÁnāÁÁ  
{ {

[SIST EN 3997:2009](https://standards.iteh.ai/catalog/standards/sist/b1e978f1-a1f0-453f-8068-46db1572dacd/sist-en-3997-2009)

Ta slovenski standard je istoveten z: **EN 3997:2007**

**ICS:**

49.025.20      Aluminij      Aluminium

**SIST EN 3997:2009**      en,de

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 3997:2009

<https://standards.iteh.ai/catalog/standards/sist/b1e978f4-a1f0-453f-8068-46db1372dacd/sist-en-3997-2009>

EUROPEAN STANDARD

EN 3997

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2007

ICS 77.150.10

English Version

## Aerospace series - Aluminium alloy AL-P2024-T3 - Sheet and strip 0,4 mm < a < 6 mm

Série aérospatiale - Alliage d'aluminium AL-P2024-T3 -  
Tôles et bandes 0,4 mm < a < 6 mm

Luft- und Raumfahrt - Aluminiumlegierung AL-P2024-T3 -  
Bleche und Bänder 0,4 mm < a < 6 mm

This European Standard was approved by CEN on 12 June 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 3997:2009](https://standards.iteh.ai/catalog/standards/sist/b1e978f4-a1f0-453f-8068-46db1372dacd/sist-en-3997-2009)

<https://standards.iteh.ai/catalog/standards/sist/b1e978f4-a1f0-453f-8068-46db1372dacd/sist-en-3997-2009>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## Contents

Foreword.....	3
Introduction .....	4
1 <b>Scope</b> .....	4
2 <b>Normative references</b> .....	4

# iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 3997:2009](https://standards.iteh.ai/catalog/standards/sist/b1e978f4-a1f0-453f-8068-46db1372dacd/sist-en-3997-2009)

<https://standards.iteh.ai/catalog/standards/sist/b1e978f4-a1f0-453f-8068-46db1372dacd/sist-en-3997-2009>

## Foreword

This document (EN 3997:2007) has been prepared by the AeroSpace and Defense Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2007, and conflicting national standards shall be withdrawn at the latest by September 2007.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 3997:2009](https://standards.iteh.ai/catalog/standards/sist/b1e978f4-a1f0-453f-8068-46db1372dacd/sist-en-3997-2009)

<https://standards.iteh.ai/catalog/standards/sist/b1e978f4-a1f0-453f-8068-46db1372dacd/sist-en-3997-2009>

## EN 3997:2007 (E)

### Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-2.

### 1 Scope

This standard specifies the requirements relating to:

Aluminium alloy AL-P2024-T3 — Sheet and strip  $0,4 \text{ mm} \leq a \leq 6 \text{ mm}$  for aerospace application.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use*

EN 4400-2, *Aerospace series — Aluminium and aluminium alloy wrought products — Technical specification — Part 2: Sheet and strip*<sup>1)</sup>

EN 4500-2, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 2: Specific rules for aluminium, aluminium alloys and magnesium alloys*<sup>1)</sup>

*iTeh STANDARD PREVIEW*  
*(standards.iteh.ai)*  
SIST EN 3997:2009  
<https://standards.iteh.ai/catalog/standards/sist/b1e978f4-a1f0-453f-8068-46db1372dacd/sist-en-3997-2009>

---

<sup>1)</sup> Published as ASD Prestandard at the date of publication of this standard.

1	Material designation		Aluminium alloy AL-P2024-										
2	Chemical composition %	Element	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Others		Al
		min.	—	—	3,8	0,30	1,2	—	—	—	—	—	
		max.	0,50	0,50	4,9	0,9	1,8	0,10	0,25	0,15	0,05	0,15	Base
3	Method of melting		—										
4.1	Form		Sheet and strip										
4.2	Method of production		Rolled										
4.3	Limit dimension(s)	mm	$0,4 \leq a \leq 6$										
5	Technical specification		EN 4400-2										

6.1	Delivery condition	T3	
	Heat treatment	490 °C ≤ $\theta$ ≤ 500 °C / WQ $\theta$ ≤ 40 °C + cold work + $\theta$ = ambient / t ≥ 5 d	
6.2	Delivery condition code	U	
7	Use condition	T3	
	Heat treatment	Delivery condition	

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

Characteristics

8.1		Test sample(s)		SIST EN 3997:2009 See EN 4400-2. <a href="https://standards.iteh.ai/catalog/standards/sist/b1e978f1-3140-4531-8068-46db1372dacd/sist-en-3997-2009">https://standards.iteh.ai/catalog/standards/sist/b1e978f1-3140-4531-8068-46db1372dacd/sist-en-3997-2009</a>			
8.2		Test piece(s)		See EN 4400-2.			
8.3		Heat treatment		Use condition			
9	Dimensions concerned	mm	$0,4 \leq a \leq 0,8$	$0,8 < a \leq 1,6$	$1,6 < a \leq 3,2$	$3,2 < a \leq 6$	
10	Thickness of cladding on each face	%	—	—	—	—	
11	Direction of test piece		LT	LT	LT	LT	
12	Temperature	$\theta$	°C	Ambient	Ambient	Ambient	Ambient
13	Proof stress	$R_{p0,2}$	MPa	≥ 290	≥ 290	≥ 290	≥ 290
14	T Strength	$R_m$	MPa	≥ 440	≥ 440	≥ 445	≥ 445
15	Elongation	$A$	%	$A_{50\text{ mm}} \geq 14$	$A_{50\text{ mm}} \geq 14$	$A_{50\text{ mm}} \geq 14$	$A_{50\text{ mm}} \geq 14$
16	Reduction of area	$Z$	%	—	—	—	—
17	Hardness		—				
18	Shear strength	$R_c$	MPa	—	—	—	—
19	Bending	$k$	—	2,5; $\alpha = 180^\circ$	3; $\alpha = 180^\circ$	3; $\alpha = 180^\circ$	4; $\alpha = 180^\circ$
20	Impact strength		—				
21	Temperature	$\theta$	°C	—			
22	Time		h	—			
23	Stress	$\sigma_a$	MPa	—			
24	C Elongation	$a$	%	—			
25	Rupture stress	$\sigma_R$	MPa	—			
26	Elongation at rupture	$A$	%	—			
27	Notes (see line 98)		—				

## EN 3997:2007 (E)

38	Intergranular corrosion	—	See EN 4400-2.			
		7	Dimensions (mm)	$0,4 \leq a \leq 1,6$	$1,6 < a \leq 3,2$	$3,2 < a \leq 6$
			Depth of penetration ( $\mu\text{m}$ )	$\leq 125$	$\leq 150$	$\leq 200$
44	External defects	—	See EN 4400-2.			
82	Batch uniformity	—	See EN 4400-2.			
		7	Electrical conductivity	$\gamma$	MS/m	17,5 (Typical value)
			or			
		7	Hardness	HB	125 (Typical value)	
$\delta \leq 16$ per product	$\Delta \leq 24$ per batch					
<p><b>ITeh STANDARD PREVIEW</b>  <b>(standards.iteh.ai)</b></p> <p>SIST EN 3997:2009  <a href="https://standards.iteh.ai/catalog/standards/sist/b1e978f4-a1f0-453f-8068-46db1372dacd/sist-en-3997-2009">https://standards.iteh.ai/catalog/standards/sist/b1e978f4-a1f0-453f-8068-46db1372dacd/sist-en-3997-2009</a></p>						
95	Marking inspection	—	See EN 4400-2.			
96	Dimensional inspection	—	See EN 4400-2.			
98	Notes	—	—			
99	Typical use	—	—			