

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 4102:2005

<https://standards.iteh.ai/catalog/standards/sist/b9355013-94c1-45a5-aeca-98c9f38d787d/sist-en-4102-2005>

EUROPEAN STANDARD

EN 4102

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2005

ICS 49.025.20

English version

Aerospace series - Aluminium alloy AL-P2219-T81 - Clad sheet and strip - 0,5 mm $\leq a \leq 6$ mm

Série aérospatiale - Alliage d'aluminium AL-P2219-T81 -
Tôles et bandes plaquées - 0,5 mm $\leq a \leq 6$ mm

Luft- und Raumfahrt - Aluminiumlegierung AL-P2219-T81 -
Bleche und Bänder, plattiert - 0,5 mm $\leq a \leq 6$ mm

This European Standard was approved by CEN on 22 April 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 4102:2005](https://standards.iteh.ai/catalog/standards/sist/b9355013-94c1-45a5-acc9-98c9f38d787d/sist-en-4102-2005)

<https://standards.iteh.ai/catalog/standards/sist/b9355013-94c1-45a5-acc9-98c9f38d787d/sist-en-4102-2005>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This document (EN 4102:2005) has been prepared by the European Association of Aerospace Manufacturers - Standardization (AECMA-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2005, and conflicting national standards shall be withdrawn at the latest by December 2005.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 4102:2005

<https://standards.iteh.ai/catalog/standards/sist/b9355013-94c1-45a5-aecca-98c9f38d787d/sist-en-4102-2005>

Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-2.

1 Scope

This standard specifies the requirements relating to:

Aluminium alloy AL-P2219-
T81
Clad sheet and strip
 $0,5 \text{ mm} \leq a \leq 6 \text{ mm}$

for aerospace application.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use.*

EN 4400-2, *Aerospace series — Aluminium and aluminium alloy wrought products — Technical specification — Part 2: Sheet and strip.*¹⁾

EN 4500-2, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 2: Specific rules for aluminium, aluminium alloys and magnesium alloys.*¹⁾

1) Published as AECMA Prestandard at the date of publication of this standard.

EN 4102:2005 (E)

1	Material designation		Aluminium alloy AL-P2219-											
2	Chemical composition %	Element	Si	Fe	Cu	Mn	Mg	Zn	Ti	V	Zr	Others		Al
												Each	Total	
		min.	-	-	5,8	0,20	-	-	0,02	0,05	0,10	-	-	Base
max.	0,20	0,30	6,8	0,40	0,02	0,10	0,10	0,15	0,25	0,05	0,15			
3	Method of melting		-											
4.1	Form		Clad sheet and strip											
4.2	Method of production		Rolled											
4.3	Limit dimension(s)	mm	$0,5 \leq a \leq 6$											
5	Technical specification		EN 4400-2											

6.1	Delivery condition	T31	T81
	Heat treatment	$530\text{ °C} \leq \theta \leq 540\text{ °C} / \text{WQ } \theta \leq 40\text{ °C}$ + approximately 1 % cold work + $\theta = \text{ambient} / t \geq 5\text{ d}$	$530\text{ °C} \leq \theta \leq 540\text{ °C} / \text{WQ } \theta \leq 40\text{ °C}$ + approximately 1 % cold work + $171\text{ °C} \leq \theta \leq 182\text{ °C} / 16\text{ h} \leq t \leq 20\text{ h}$
6.2	Delivery condition code	K	U
7	Use condition	T81	T81
	Heat treatment	Delivery condition $+ 171\text{ °C} \leq \theta \leq 182\text{ °C} / 16\text{ h} \leq t \leq 20\text{ h}$	Delivery condition

iTeh STANDARD PREVIEW
Characteristics
(standards.iteh.ai)

8.1	Test sample(s)		See EN 4400-2.		
8.2	Test piece(s)		See EN 4400-2.		
8.3	Heat treatment		Use condition.		
9	Dimensions concerned	mm	$0,5 \leq a \leq 1,0$	$1,0 < a \leq 2,5$	$2,5 < a \leq 6$
10	Thickness of cladding on each face	%	≥ 8	≥ 4	≥ 2
11	Direction of test piece		LT	LT	LT
12	Temperature	θ °C	Ambient	Ambient	Ambient
13	Proof stress	$R_{p0,2}$ MPa	≥ 255	≥ 285	≥ 295
14	T Strength	R_m MPa	≥ 340	≥ 380	≥ 400
15	Elongation	A %	$A_{50\text{ mm}} \geq 6$	$A_{50\text{ mm}} \geq 7$	$A_{50\text{ mm}} \geq 7$
16	Reduction of area	Z %	-	-	-
17	Hardness		-		
18	Shear strength	R_c MPa	-		
19	Bending	k -	-		
20	Impact strength		-		
21	Temperature	θ °C	-		
22	Time	h	-		
23	C Stress	σ_a MPa	-		
24	Elongation	a %	-		
25	Rupture stress	σ_R MPa	-		
26	Elongation at rupture	A %	-		
27	Notes (see line 98)		-		

44	External defects	–	See EN 4400-2.								
62	Diffusion in the cladding	–	See EN 4400-2.								
72	Cladding chemical composition %	–	See EN 4400-2.								
		7	Material designation	Aluminium alloy AL-P7072-							
			Element	Si + Fe	Cu	Mn	Mg	Zn	Others		Al
									Each	Total	
			min.	–	–	–	–	0,8	–	–	Base
max.	0,7	0,10	0,10	0,10	1,3	0,05	0,15				
82	Batch uniformity	–	See EN 4400-2.								
		5	–		T31			T81			
		7	Electrical conductivity		See EN 4400-2.			See EN 4400-2.			
<p>iTeh STANDARD PREVIEW (standards.iteh.ai)</p> <p><u>SIST EN 4102:2005</u> https://standards.iteh.ai/catalog/standards/sist/b9355013-94c1-45a5-acc4-98c9f38d787d/sist-en-4102-2005</p>											
95	Marking inspection	–	See EN 4400-2.								
96	Dimensional inspection	–	See EN 4400-2.								
98	Notes	–	–								
99	Typical use	–	–								

