



SLOVENSKI STANDARD
SIST EN 3955:2002
01-januar-2002

Aerospace series - Silver base alloy AG-B12401 (AgCu40Zn5Ni) - Filler metal for brazing - Rolled foil

Aerospace series - Silver base alloy AG-B12401 (AgCu40Zn5Ni) - Filler metal for brazing - Rolled foil

Luft- und Raumfahrt - Silberbasislegierung AG-B12401 (AgCu40Zn5Ni) - Hartlot in Form von gewalzter Folie

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Série aérospatiale - Alliage base argent AG-B12401 (AgCu40Zn5Ni) - Métal d'apport de brasage - Feuillard laminé

[SIST EN 3955:2002](https://standards.iteh.ai/catalog/standards/sist/099f1c7f-3d71-4975-96e9-00530a2f0122/sist-en-3955-2002)

[https://standards.iteh.ai/catalog/standards/sist/099f1c7f-3d71-4975-96e9-](https://standards.iteh.ai/catalog/standards/sist/099f1c7f-3d71-4975-96e9-00530a2f0122/sist-en-3955-2002)

[00530a2f0122/sist-en-3955-2002](https://standards.iteh.ai/catalog/standards/sist/099f1c7f-3d71-4975-96e9-00530a2f0122/sist-en-3955-2002)

Ta slovenski standard je istoveten z: EN 3955:2001

ICS:

49.025.15

Neželezove zlitine na splošno

Non-ferrous alloys in general

SIST EN 3955:2002

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 3955:2002

<https://standards.iteh.ai/catalog/standards/sist/099f1c7f-3d71-4975-96e9-00530a2f0122/sist-en-3955-2002>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 3955

June 2001

ICS 49.025.15

English version

Aerospace series - Silver base alloy AG-B12401 (AgCu40Zn5Ni)
- Filler metal for brazing - Rolled foil

Série aérospatiale - Alliage base argent AG-B12401
(AgCu40Zn5Ni) - Métal d'apport de brasage - Feuillard
laminé

Luft- und Raumfahrt - Silberbasislegierung AG-B12401
(AgCu40Zn5Ni) - Hartlot in Form von gewalzter Folie

This European Standard was approved by CEN on 19 April 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 3955:2002](https://standards.iteh.ai/catalog/standards/sist/099f1c7f-3d71-4975-96e9-00530a2f0122/sist-en-3955-2002)

<https://standards.iteh.ai/catalog/standards/sist/099f1c7f-3d71-4975-96e9-00530a2f0122/sist-en-3955-2002>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This European Standard has been prepared by the European Association of Aerospace Manufacturers (AECMA).

After inquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2001, and conflicting national standards shall be withdrawn at the latest by December 2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

0 Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organisation of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-6.

1 Scope

This standard specifies the requirements relating to:

Silver base alloy AG-B12401 (AgCu40Zn5Ni)
Filler metal for brazing
Rolled foil

for aerospace applications.

2 Normative references

This European Standard incorporates by dated or undated reference provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

- | | |
|-----------|--|
| EN 2043 | Aerospace series - Metallic materials - General requirements for semi-finished product qualification (excluding forgings and castings) ¹⁾ |
| EN 3875 | Aerospace series - Metallic materials - Filler metal for brazing - Technical specification ¹⁾ |
| EN 4258 | Aerospace series - Metallic materials - General organization of standardization - Links between types of EN standards and their use |
| EN 4500-6 | Aerospace series - Metallic materials - Rules for drafting and presentation of material standards - Part 6: Specific rules for filler metals for brazing ¹⁾ |

1	Material designation		Silver base brazing alloy AG-B12401 (AgCu40Zn5Ni)										
2	Chemical composition %	Element	Si	P	Cu	Ni	Zn	Al	Bi	Cd	Pb	Others	Ag
												Total	
		min.	-	-	39,0	0,50	4,0	-	-	-	-	-	-
	max.	0,05	80 *)	41,0	1,50	6,0	10 *)	0,030	0,030	0,025	0,15		55,0
3	Method of melting		Air or inert gas melted										
4.1	Form		Rolled foil										
4.2	Method of production		Cold rolled and cleaned										
4.3	Limit dimension(s)	mm	-										
5	Technical specification		EN 3875										

6.1	Delivery condition	As manufactured or annealed
	Heat treatment	-
6.2	Delivery condition code	U
7	Use condition	Delivery condition
	Heat treatment	-

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Characteristics

8.1	Test sample(s)			SIST EN 3955:2002 https://standards.iteh.ai/catalog/standards/sist/099ffc7f-3d71-4975-96e9-00530a2f0122/sist-en-3955-2002		
8.2	Test piece(s)					
8.3	Heat treatment			-		
9	Dimensions concerned	mm	-			
10	Thickness of cladding on each face	%	-			
11	Direction of test piece			-		
12	Temperature	θ	°C	-		
13	Proof stress	$R_{p0,2}$	MPa	-		
14	T Strength	R_m	MPa	-		
15	Elongation	A	%	-		
16	Reduction of area	Z	%	-		
17	Hardness			-		
18	Shear strength	R_c	MPa	-		
19	Bending	k	-	-		
20	Impact strength			-		
21	Temperature	θ	°C	-		
22	Time		h	-		
23	C Stress	σ_a	MPa	-		
24	Elongation	a	%	-		
25	Rupture stress	σ_R	MPa	-		
26	Elongation at rupture	A	%	-		
27	Notes (see line 98)			*)		

44	External defects	-	See EN 3875
53	Thermal analysis (Differential thermal analysis)	-	See EN 3875
		7	Liquidus: 855 °C Solidus: 720 °C
76	Wettability (Fusion test)	-	See EN 3875
82	Batch uniformity (Material verification)	-	See EN 3875
<p>iTeh STANDARD PREVIEW (standards.iteh.ai)</p> <p>SIST EN 3955:2002 https://standards.iteh.ai/catalog/standards/sist/099f1c7f-3d71-4975-96e9-00530a2f0122/sist-en-3955-2002</p>			
95	Marking inspection	-	See EN 3875
96	Dimensional inspection	-	See EN 3875
98	Notes	-	*) p.p.m.
99	Typical use	-	Joining carbon, low alloy and austenitic steels.

100	-	Product qualification	-	See EN 2043 Qualification programme to be agreed between manufacturer and purchaser.

ITeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 3955:2002

<https://standards.iteh.ai/catalog/standards/sist/099f1c7f-3d71-4975-96e9-00530a2f0122/sist-en-3955-2002>