

## SLOVENSKI STANDARD SIST EN 4105:2001

01-januar-2001

Aerospace series - Nickel base alloy NI-B40002 (NiSi4B2) - Filler metal for brazing - Tape

Aerospace series - Nickel base alloy NI-B40002 (NiSi4B2) - Filler metal for brazing - Tape

Série aérospatiale - Alliage base nickel NI-B40002 (NiSi4B2)- Métal d'apport de brasage - Feuillard de poudre agglomérée

https://standards.iteh.ai/catalog/standards/sist/16f23c17-47cb-458f-bdc5-

Ta slovenski standard je istoveten z: EN 4105:2001

ICS:

49.025.99 Drugi materiali Other materials

SIST EN 4105:2001 en

SIST EN 4105:2001

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 4105:2001

https://standards.iteh.ai/catalog/standards/sist/16f23c17-47cb-458f-bdc5-25beb9660ee0/sist-en-4105-2001

## EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

EN 4105

April 1998

ICS 49.025; 49.025.99

Descriptors: aircraft industry, filler metals, brazing, nickel alloys, powdery materials, strips, designation, chemical

compostion, delivery condition, characteristics, specifications

#### English version

# Aerospace series - Nickel base alloy NI-B40002 (NiSi4B2) - Filler metal for brazing - Tape

Série aérospatiale - Alliage base nickel NI-B40002 (NiSi4B2) - Métal d'apport de brasage - Feuillard de poudre agglomérée Luft- und Raumfahrt - Nickelbasislegierung NI-B40002 (NiSi4B2) - Hartlot in Form von Band

This European Standard was approved by CEN on 17 December 1997.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

25beb9660ee0/sist-en-4105-2001



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2 EN 4105:1998

#### Foreword

This European Standard has been prepared by the European Association of Aerospace Manufacturers (AECMA).

After inquiries and votes carried out in accordance with the rules of this Association, this Standard has successively received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 1998, and conflicting national standards shall be withdrawn at the latest by October 1998.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 4105:2001 https://standards.iteh.ai/catalog/standards/sist/16f23c17-47cb-458f-bdc5-25beb9660ee0/sist-en-4105-2001

> MEPUBLIKA SLOVENIJA KELSTRSTVO ZA ŠOLSTVO, ZMANOST IN ŠPORT Und RS za standanizacijo in mamalovja Luublijana

1009 -10-

PRIVAGE FO METODI RAZGLAGITVE



#### 0 Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organisation of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-6.

#### 1 Scope

This standard specifies the requirements relating to:

Nickel base alloy NI-B40002 (NiSi4B2) Filler metal for brazing Tape

for aerospace applications.

#### 2 Normative references

This European Standard incorporates by dated or undated reference provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 2043	Aerospace series - Metallic materials - General requirements for semi-finished product qualification (excluding forgings and castings) 1)
EN 3875	Aerospace series - Metallic materials - Filler metal for brazing - Technical specification 1)
EN 4104	Aerospace series - Nickel base alloy NI-B40002 (NiSi4B2) - Filler metal for brazing - Powder or paste 1)
EN 4258	Aerospace series - Metallic materials - General organization of standardization - Links between types of EN standards and their use $^{1)}$
EN 4500-6	Aerospace series - Metallic materials - Rules for drafting and presentation of material standards - Part 6: Specific rules for filler metals for brazing 1)

<sup>1)</sup> Published as AECMA Prestandard at the date of publication of this standard

Page 4 EN 4105:1998

1	Material designat		Nickel base braze alloy NI-B40002 (NiSi4B2)													
2	Chemical composition 1)	Element		С	Si	Р	S	В	Al	Со	Fe	Se	Ti	Zŗ	Others Total	Ni
	%	min.			3,0		-	1,50	_	_	_	_	-	_		Base
		max.		0,06	4,0	0,02	0,02	2,20	0,05	0,10	1,5	50 *)	0,05	0,05	0,05	Dase
3	Method of melting						Air or	inert ga	as or va	cuum n	nelted					
4.1	Form		<del></del>						Tape							
4.2	Method of production							Prod	uced fro	om pow	der EN	4104	·			
4.3	Limit dimension(s) mm		nm							_			·			
5	Technical specific							E	EN 3875	·		-				

6.1	Delivery condition	As manufactured
	Heat treatment	_
6.2	Delivery condition code	U
7	Use condition	Delivery condition
	Heat treatment	iTeh STANDARD PREVIEW

### (standards.iteh.ai) Characteristics

#### SIST EN 4105:2001

				<u>SIS1 EN 4105:2001</u>
Test sample(s)			ht	hps://standards.iteh.ai/catalog/standards/sist/16f23c17-47cb-458f-bde5- 25beb9660ee0/sist-en-4105-2001
T	est piece(s)			2. //K/1/2/(/K/A/O/SSF-O)F-1/03-2001
.3 Heat treatment				_
Dimensions concerned mm		mm	_	
Thickness of cladding on %		%	<u>-</u>	
_				_
	Temperature	θ	°C	<u>-</u>
	Proof stress	R <sub>p0,2</sub>	MPa	_
Т	Strength	R <sub>m</sub>	MPa	_
	Elongation	Α	%	
	Reduction of area	Z	%	
На	ardness	·	· ,	_
Sh	near strength	Rc	MPa	_
19 Bending k -		-	-	
lm	pact strength			_
	Temperature	θ	°C	_
Time h		h	_	
	Stress	$\sigma_{a}$	MPa	_
c	Elongation	а	%	_
	Rupture stress	$\sigma_{R}$	MPa	_
	Elongation at rupture	Α	%	_
				*) 1)
	TO HE SH IM	Test piece(s)  Heat treatment  Dimensions concern Thickness of claddineach face  Direction of test piece Proof stress  T Strength Elongation Reduction of area  Hardness Shear strength Bending Impact strength Temperature Time Stress  C Elongation		Test piece(s)  Heat treatment  Dimensions concerned mm  Thickness of cladding on each face  Direction of test piece  Temperature θ °C  Proof stress Rp0,2 MPa  Elongation A %  Reduction of area Z %  Hardness  Shear strength R <sub>C</sub> MPa  Bending R —  Impact strength  Temperature θ °C  Time h  Stress σ <sub>a</sub> MPa  C Elongation a %  Rupture stress σ <sub>R</sub> MPa  Elongation a %  Rupture stress σ <sub>R</sub> MPa  Elongation a %  Rupture stress σ <sub>R</sub> MPa

		1	
44	External defects	-	See EN 3875
53	53 Thermal analysis (Differential thermal analysis)		See EN 3875
		7	Liquidus : 1 065 °C Solidus : 980 °C
76	Wettability (Fusion test)	-	See EN 3875
77	Mass per unit area	_	See EN 3875
78	Metallic alloy content	_	See EN 3875
		7	≥91% - `
82	Batch uniformity (Material verification)	_	See EN 3875
			STANDARD PREVIEW (standards.iteh.ai)  SIST EN 4105:2001 iteh.ai/catalog/standards/sist/16f23c17-47cb-458f-bdc5- 25beb9660ee0/sist-en-4105-2001
95	Marking inspection	_	See EN 3875
96	Dimensional inspection	_	See EN 3875
98	Notes	-	*) p.p.m.     1) The chemical composition refers to the metallic alloy content.
99	Typical use	-	Joining nickel and cobalt base heat resisting alloys.
	<u> </u>		I

### Page 6 EN 4105:1998

00 – Produ	uct qualification	-	See EN 2043	
			Qualification programme to be agreed between manufacturer and purchaser.	
DO - Produ		iT		