



Standard Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement¹

This standard is issued under the fixed designation D 792; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 These test methods describe the determination of the specific gravity (relative density) and density of solid plastics in forms such as sheets, rods, tubes, or molded items.

1.2 Two test methods are described:

1.2.1 *Test Method A*—For testing solid plastics in water, and

1.2.2 *Test Method B*—For testing solid plastics in liquids other than water.

NOTE 1—Alternatively, Test Method D 1505 may be applied to many such forms, as well as to films and sheeting.

1.3 The values stated in SI units are to be regarded as the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 2—There is no similar or equivalent ISO standard.

2. Referenced Documents

2.1 *ASTM Standards:*

D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing²

D 891 Test Methods for Specific Gravity, Apparent, of Liquid Industrial Chemicals³

D 1505 Test Method for Density of Plastics by the Density-Gradient Technique²

D 1622 Test Method for Apparent Density of Rigid Cellular Plastics²

D 1898 Practice for Sampling of Plastics²

E 1 Specification for ASTM Thermometers⁴

E 12 Terminology Relating to Density and Specific Gravity of Solids, Liquids, and Gases⁵

¹ These test methods are under the jurisdiction of ASTM Committee D-20 on Plastics and are the direct responsibility of Subcommittee D20.70 on Analytical Methods (Section D20.70.01).

Current edition approved Aug. 10, 1998. Published November 1998. Originally published as D 792 – 44. Last previous edition D 792 – 91.

² *Annual Book of ASTM Standards*, Vol 08.01.

³ *Annual Book of ASTM Standards*, Vol 15.05.

⁴ *Annual Book of ASTM Standards*, Vol 14.03.

⁵ Discontinued; see *1995 Annual Book of ASTM Standards*, Vol 15.05.

E 380 Practice for Use of the International System of Units (SI) (the Modernized Metric System)⁶

E 691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method⁶

3. Terminology

3.1 *General*—The units, symbols, and abbreviations used in these test methods are in accordance with Practice E 380.

3.2 *Definitions:*

3.2.1 *specific gravity (relative density)*—the ratio of the mass in air of a unit volume of the impermeable portion of the material at 23°C to the mass in air of equal density of an equal volume of gas-free distilled water at the same temperature. The form of expression shall be:

$$\text{Specific gravity (relative density) } 23/23^{\circ}\text{C} \\ (\text{or sp gr } 23/23^{\circ}\text{C})$$

NOTE 3—This definition is essentially equivalent to the definition for apparent specific gravity and apparent density in Terminology E 12, because the small percentage difference introduced by not correcting for the buoyancy of air is insignificant for most purposes.

3.2.2 *density*—the mass in kilograms per cubic metre of impermeable portion of the material at 23°C. The form of expression shall be:

$$D^{23}, \text{ kg/m}^3 \text{ (Notes 2-4)}$$

NOTE 4—The SI unit of density, as defined in Practice E 380 is kg/m^3 . To convert density in g/cm^3 to density in kg/m^3 , multiply by 1000.

NOTE 5—Specific gravity 23/23°C can be converted to density 23°C, kg/m^3 , by use of the following equation:

$$D^{23} \text{ C, kg/m}^3 = \text{sp gr } 23/23^{\circ}\text{C} \times 997.6$$

4. Summary of Test Method

4.1 Determine the mass of a specimen of the solid plastic in air. It is then immersed in a liquid, its apparent mass upon immersion is determined, and its specific gravity (relative density) calculated.

5. Significance and Use

5.1 The specific gravity or density of a solid is a property that can be measured conveniently to identify a material, to

⁶ *Annual Book of ASTM Standards*, Vol 14.02.

*A Summary of Changes section appears at the end of this standard.

follow physical changes in a sample, to indicate degree of uniformity among different sampling units or specimens, or to indicate the average density of a large item.

5.2 Changes in density of a single specimen may be due to changes in crystallinity, loss of plasticizer, absorption of solvent, or to other causes. Portions of a sample may differ in density because of difference in crystallinity, thermal history, porosity, and composition (types or proportions of resin, plasticizer, pigment, or filler).

NOTE 6—Reference is made to Test Method D 1622.

5.3 Density is useful for calculating strength-weight and cost-weight ratios.

6. Sampling

6.1 The sampling units used for the determination of specific gravity (relative density) shall be representative of the quantity of product for which the data are required, in accordance with Practice D 1898.

6.1.1 If it is known or suspected that the sample consists of two or more layers or sections having different specific gravities, either complete finished parts or complete cross sections of the parts or shapes shall be used as the specimens, or separate specimens shall be taken and tested from each layer. The specific gravity (relative density) of the total part cannot be obtained by adding the specific gravity of the layers, unless relative percentages of the layers are taken into account.

7. Conditioning

7.1 *Conditioning*—Condition the test specimens at $23 \pm 2^\circ\text{C}$ and $50 \pm 5\%$ relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice D 618, for those tests where conditioning is required. In cases of disagreement, the tolerances shall be 1°C and $\pm 2\%$ relative humidity.

7.2 *Test Conditions*—Conduct tests in the standard laboratory atmosphere of $23 \pm 2^\circ\text{C}$ and $50 \pm 5\%$ relative humidity, unless otherwise specified in the test methods or in this specification. In cases of disagreement, the tolerances shall be 1°C and $\pm 2\%$ relative humidity.

TEST METHOD A FOR TESTING SOLID PLASTICS IN WATER (SPECIMENS 1 TO 50 g)

8. Scope

8.1 This test method involves weighing a one-piece specimen of 1 to 50 g in water, using a sinker with plastics that are lighter than water. This test method is suitable for plastics that are wet by, but otherwise not affected by water.

9. Apparatus

9.1 *Analytical Balance*—A balance with a precision within 0.1 mg, accuracy within 0.05 % relative (that is, 0.05 % of the mass of the specimen in air), and equipped with a stationary support for the immersion vessel above the balance pan (“pan straddle”).

NOTE 7—Assurance that the balance meets the performance requirements should be provided by frequent checks on adjustments of zero point and sensitivity and by periodic calibration for absolute accuracy, using standard masses.

9.2 *Sample Holder*, corrosion-resistant.

9.3 *Sinker*—A sinker for use with specimens of plastics that have specific gravities less than 1.000. The sinker shall: (1) be corrosion-resistant; (2) have a specific gravity of not less than 7.0; (3) have smooth surfaces and a regular shape; and (4) be slightly heavier than necessary to sink the specimen. The sinker should have an opening to facilitate attachment to the specimen and wire.

9.4 *Immersion Vessel*—A beaker or other wide-mouthed vessel for holding the water and immersed specimen.

9.5 *Thermometer*—A thermometer with an accuracy of $\pm 1^\circ\text{C}$ is required if the test is not performed in the standard laboratory atmosphere of Practice D 618, (refer to 17.4).

10. Materials

10.1 *Water*—The water shall be substantially air-free and distilled or demineralized water.

NOTE 8—Water may be rendered substantially air-free by boiling and cooling or by shaking under vacuum in a heavy-walled vacuum flask. (**Precaution:** Use gloves and shielding.) If the water does not wet the specimen, a few drops of a wetting agent shall be added. If this solution does not wet the specimen, Method B shall be used.

11. Test Specimen

11.1 The test specimen shall be a single piece of the material under test of any size and shape that can conveniently be prepared and tested, provided that its volume shall be not less than 1 cm^3 and its surface and edges shall be made smooth. The thickness of the specimen should be at least 1 mm for each 1 g of weight. A specimen weighing 1 to 5 g usually will be found convenient, but specimens up to approximately 50 g may be used (Note 9). Care should be taken in cutting specimens to avoid changes in density resulting from compressive stresses or frictional heating.

NOTE 9—Specifications for certain plastics require a particular method of specimen preparation and should be consulted if applicable.

11.2 The specimen shall be free from oil, grease, and other foreign matter.

12. Procedure

12.1 Measure and record the water temperature.

12.2 Weigh the specimen in air to the nearest 0.1 mg for specimens of mass 1 to 10 g or to the nearest mg for specimens of mass more than 10 to 50 g.

12.3 Attach to the balance a piece of fine wire sufficiently long to reach from the hook above the pan to the support for the immersion vessel. Attach the specimen to the wire such that it is suspended about 25 mm above the vessel support.

NOTE 10—The specimen may be weighed in air after hanging from the wire. In this case, record the mass of the specimen, $a = (\text{mass of specimen} + \text{wire, in air}) - (\text{mass of wire in air})$.

12.4 Mount the immersion vessel on the support, and completely immerse the suspended specimen (and sinkers, if used) in water (10.1) at a temperature of $23 \pm 2^\circ\text{C}$. The vessel must not touch wire or specimen. Remove any bubbles adhering to the specimen, wire, or sinker, paying particular attention to holes in the specimen and sinker. Usually these bubbles can be removed by rubbing them with another wire. If