



## Standard Specification for Poly(Vinyl Chloride) Resins<sup>1</sup>

This standard is issued under the fixed designation D 1755; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers the establishment of requirements for homopolymers of vinyl chloride in original powder form intended for subsequent mixing and processing in thermoplastic compositions. These resins have a nominal specific gravity of 1.4 and a theoretical chlorine content of 56.8 %.

1.2 Two types of resin have been recognized: general purpose and dispersion. When mixed with the customary amount of plasticizer, general-purpose resins yield a dry or moist powder while dispersion resins yield a liquid slurry. Since many resins are polymerized to meet special requirements, a system of classification has been provided that permits a wide choice of grades.<sup>2</sup>

1.3 The values stated in SI units are to be regarded as the standard.

NOTE 1—This standard is similar in content (but not technically equivalent) to ISO 1264 – 1980.<sup>3</sup>

1.4 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

- D 281 Test Method for Oil Absorption of Pigments by Spatula Rub-Out<sup>4</sup>
- D 495 Test Method for High-Voltage, Low-Current, Dry Arc Resistance of Solid Electrical Insulation<sup>5, 6</sup>
- D 883 Terminology Relating to Plastics<sup>6</sup>
- D 1125 Test Methods for Electrical Conductivity and Resistivity of Water<sup>7</sup>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials (Section D20.15.07).

Current edition approved June 15, 1992. Published August 1992. Originally published as D1755 – 60 T. Last previous edition D1755 – 81 (1987).

<sup>2</sup> Hutson, J. L., "Proposed Method for Classifying Poly(Vinyl Chloride) Resins." ASTM Research Report File No. RR: D-20-1: (May 20, 1959). Available from ASTM Headquarters.

<sup>3</sup> Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 06.02.

<sup>5</sup> *Annual Book of ASTM Standards*, Vol 10.02.

<sup>6</sup> *Annual Book of ASTM Standards*, Vol 08.01.

<sup>7</sup> *Annual Book of ASTM Standards*, Vol 11.01.

- D 1243 Test Method for Dilute Solution Viscosity of Vinyl Chloride Polymers<sup>6</sup>
- D 1249 Specification for Octyl Ortho-Phthalate Ester Plasticizers<sup>6</sup>
- D 1600 Terminology for Abbreviated Terms Relating to Plastics<sup>6</sup>
- D 1705 Test Method for Particle Size Analysis of Powdered Polymers and Copolymers of Vinyl Chloride<sup>6</sup>
- D 1755 Specification for Poly(Vinyl Chloride) Resins<sup>6</sup>
- D 1823 Test Method for Apparent Viscosity of Plastics and Organosols at High Shear Rates by Extrusion Viscometer<sup>6</sup>
- D 1824 Test Method for Apparent Viscosity of Plastics and Organosols at Low Shear Rates by Brookfield Viscometer<sup>6</sup>
- D 1895 Test Methods for Apparent Density, Bulk Factor, and Pourability of Plastic Materials<sup>6</sup>
- D 1898 Practice for Sampling of Plastics<sup>6</sup>
- D 1921 Test Method for Particle Size (Sieve Analysis) of Plastic Materials<sup>6</sup>
- D 2132 Test Method for Dust-and-Fog Tracking and Erosion Resistance of Electrical Insulating Materials<sup>5</sup>
- D 2396 Test Method for Powder-Mix Test of Poly(Vinyl Chloride) (PVC) Resins Using a Torque Rheometer<sup>8</sup>
- D 2873 Test Method for Interior Porosity of Poly(Vinyl Chloride) (PVC) Resins by Mercury Intrusion Porosimetry<sup>8</sup>
- D 3030 Test Method for Volatile Matter (Including Water) of Vinyl Chloride Resins<sup>8</sup>
- D 3892 Practice for Packaging/Packing of Plastics<sup>8</sup>
- E 1 Specifications for ASTM Thermometers<sup>9</sup>

### 3. Terminology

3.1 *Definitions*—Definitions are in accordance with Terminology D 883 and Terminology D 1600, unless otherwise indicated.

### 4. Classification

4.1 *Types*—This specification covers two types of resin:

4.1.1 *Type GP*—General-purpose resins primarily intended for either dry blending, preblending, or thermoplastic processing.

<sup>8</sup> *Annual Book of ASTM Standards*, Vol 08.02.

<sup>9</sup> *Annual Book of ASTM Standards*, Vol 14.03.

**TABLE 1 Type GP, General-Purpose Resin Requirements**

Designation Order No.	Property	Cell Limits										
		0	1	2	3	4	5	6	7	8	9	
1	Dilute solution (inherent) viscosity	unspecified	<0.70	0.70 to 0.79	0.80 to 0.89	0.90 to 0.99	1.00 to 1.09	1.10 to 1.19	1.20 to 1.29	1.30 to 1.39	≥1.40	
2	Sieve analysis, percent through No. 200 (75- $\mu$ m) sieve	unspecified	0 to 9	10 to 19	20 to 29	30 to 39	40 to 49	50 to 59	60 to 79	80 to 99	100	
3	Apparent (bulk) density:	g/1000 cm <sup>3</sup>	unspecified	<144	144 to 232	233 to 328	329 to 425	426 to 520	521 to 616	617 to 712	713 to 808	≥809
		lb/ft <sup>3</sup>	unspecified	<9.00	9.00 to 14.50	14.51 to 20.50	20.51 to 26.50	26.51 to 32.50	32.51 to 38.50	38.51 to 44.50	44.51 to 50.50	≥50.51
4	Plasticizer sorption, parts DOP phr <sup>A</sup>	unspecified	<50	50 to 74	75 to 99	100 to 124	125 to 149	150 to 174	175 to 199	200 to 244	≥225	
5	Dry flow, s/400 cm <sup>3</sup>	unspecified	...	...	<2.0	2.0 to 3.9	4.0 to 5.9	6.0 to 7.9	8.0 to 9.9	≥10	...	
6	Conductivity, max, $\mu$ S/cm-g	unspecified	...	...	<6	≥6	...	...	...	...	...	

<sup>A</sup> phr = per 100 parts of resin.

**TABLE 2 Type D, Dispersion Resin Requirements**

Designation Order No.	Property	Cell Limits									
		0	1	2	3	4	5	6	7	8	9
1	Dilute solution (inherent) viscosity	unspecified	<0.90	0.90 to 0.99	1.00 to 1.09	1.10 to 1.19	1.20 to 1.29	1.30 to 1.39	1.40 to 1.49	1.50 to 1.59	≥1.60
2	Brookfield viscosity (RVF), poise	unspecified	0 to 24	25 to 49	50 to 74	75 to 99	100 to 124	125 to 149	150 to 174	175 to 199	>199
3	Severs viscosity, poise	unspecified	0 to 49	50 to 99	100 to 149	150 to 199	200 to 299	300 to 499	500 to 999	1000 to 1499	>1499

**TABLE 3 Requirements of Resin GP6-43054**

Designation Order No.	Property	Unit	Requirement		Cell Code
			min	max	
1	Inherent viscosity		1.10	1.19	6
2	Sieve analysis	percent through No. 200 (75- $\mu$ m) sieve	30	44 (39 + 10/2)	4
3	Apparent (bulk) density	g/1000 cm <sup>3</sup> (lb/ft <sup>3</sup> )	233 (14.51)	328 (20.50)	3
4	Plasticizer sorption	parts DOP phr <sup>A</sup>	none		0
5	Dry flow	s/400 cm <sup>3</sup>	3.0 (4.0-2.0/2)	5.9	5
6	Conductivity	$\mu$ S/cm-g	...	≥6	4

<sup>A</sup> phr = per 100 parts of resin.

4.1.2 *Type D*—Dispersion resins primarily intended for use in organosols and plastisols. As a class, these are small in particle size.

4.2 *Grades*—This specification provides for as many grades of resin as may be selected from the possible combinations of requirements in Table 1 and Table 2. A grade is designated by first indicating the type (GP or D), followed by cell numbers for each property in the order in which they are listed in Table 1 and Table 2. Where there is no interest in a property, a “0” is entered in place of a cell number. Should it be desirable, a cell

limit may be extended by half the cell range into the next higher or lower cell, but not both. When this is done, it is indicated by a dash above the cell number ( $\bar{n}$ ) if the extension is into the higher cell, or a dash below ( $\underline{n}$ ) if into the lower cell. Extension of cell limits applies only to cells where ranges of properties are allowed and not where maximum or minimum values are specified. The cell number of the first property (dilute solution viscosity) is separated from those that follow by a dash.

NOTE 2—Resin GP643054. This is a grade of general-purpose resin (see Table 1) having the requirements given in Table 3.<sup>10</sup> Standard values defined by round-robin testing of eight laboratories are listed in Table 4.

## 5. General Requirements

5.1 The resin shall be in powder form.

5.2 The resin shall conform to the requirements of Table 1 or Table 2, as specified by the type and grade designation agreed upon between the purchaser and the supplier.

NOTE 3—Properties not covered, such as heat stability, color, and volatile loss, may also be important for application performance in compounds.

## 6. Sampling

6.1 Unless otherwise agreed upon between the purchaser and the supplier, the material shall be sampled in accordance with the sampling procedure in Practice D 1898.

## 7. Number of Tests

7.1 One set of test specimens as prescribed in the Sections on General and Specific Sampling Procedures of Practice D 1898 shall be considered sufficient for testing each batch.

## 8. Retest and Rejection

8.1 If any failure occurs, the materials may be retested to establish conformity in accordance with an agreement between the purchaser and the supplier.

## TEST METHODS

### 9. Dilute Solution Viscosity

9.1 Test Method D 1243.

### 10. Apparent (Bulk) Density

10.1 Test Methods D 1895.

### 11. Sieve Analysis

11.1 Test Method D 1921.

NOTE 4—Test Method D 1705 may be substituted at the option of the purchaser and the supplier.

NOTE 5—Specifications for sieve analysis (Table 1) are primarily intended to control fines.

<sup>10</sup> ASTM General Purpose PVC Reference Standard is available from B. F. Goodrich Chemical Co., Manufacturing Services Laboratory, P.O. Box 134, Avon Lake, OH 44012.

**TABLE 4 ASTM PVC Reference Standard No. 1  
(General Purpose)**

NOTE 1—The cell classification of this standard is GP5-15443.

	Method	Accepted Value <sup>A</sup>
Inherent viscosity	D 1243	1.018 ± 0.012
Percent through No. 200 sieve	D 1921	1.3 ± 0.4
Apparent density, g/1000 cm <sup>3</sup>	D 1895	503 ± 5
Plasticizer sorption, phr	D 1755	101 ± 6
Dry flow, s/400 cm <sup>3</sup>	D 1755	2.6 ± 0.2
Conductivity, μS/cm-g	D 1755	1.0 ± 0.3
Porosity, cm <sup>3</sup> /g	D 2873	0.268 ± 0.022
Powder mix time, s	D 2396	163 ± 17

<sup>A</sup> Expected range for mean of two replicates (within a probability of 99.5 %).

## 12. Brookfield Viscosity

12.1 Test Method D 1824. Take readings using a Brookfield RVF viscometer at 20 r/min with a No. 6 spindle. Prepare the plastisol sample as follows:

12.1.1 *Plasticizer*—Di (2-ethylhexyl) phthalate (DOP), Type I in Specification D 1249.

12.1.2 *Apparatus*:

12.1.2.1 *Mixer*, planetary-gear type, equipped with flat beater mixing paddle.<sup>11</sup>

12.1.2.2 *Vacuum Desiccator*, capable of being evacuated to 133 Pa (1 mm Hg).

12.1.3 *Procedure*:

12.1.3.1 Condition the mixing bowl and materials to 23 ± 1°C. Weigh 500 ± 0.5 g of resin into the mixing bowl. Weigh 300 ± 0.5 g of plasticizer and add it directly on top of the resin in the mixing bowl. Hand mix with the flat beater for 1 min.

12.1.3.2 Mount the bowl on the mixer and mix for 5 min at the No. 1 speed. Stop the mixer and scrape down the sides of the bowl and the beater. Resume mixing at the No. 2 speed for an additional 15 min. Note and record the temperature of the plastisol immediately after mixing. The temperature rise must not exceed 5°C. Use a cooling bath if necessary.

12.1.3.3 Place the mixing bowl in the desiccator, evacuate to 133 Pa (1 mm Hg), and allow it to remain in the desiccator for an additional 10 min after the foam collapses. Consider the time in the desiccator as part of the normal aging period. Take care to ensure that the plastisol does not overflow the container during evacuation.

## 13. Severs Viscosity

13.1 Test Method D 1823. Determinations shall be made through a 3.17 ± 0.13-mm (0.125 ± 0.005-in.) diameter orifice at a gas pressure of 0.69 MPa (100 psi). The plastisol sample shall be prepared in accordance with 12.1.1-12.1.3.

## 14. Electrical Conductivity of Water Extract

14.1 *Definitions*—See the Definitions Section of Test Methods D 1125.

14.2 *Summary of Test Method*—This test is intended to distinguish between electrical and nonelectrical grades of unprocessed resin. In general, the test will not detect relatively small differences among different lots of electrical grade resin. A water dispersion of the resin is boiled for a short time and the electrical conductivity of the solution measured. The conductivity of the water extract results from ionic impurities in the resin that adversely affect its use for electrical insulation.<sup>12</sup> Electrical grade resins generally yield conductivity values less than 6 μS/cm-g.

14.3 *Apparatus*:

14.3.1 *A-C Wheatstone Bridge*, having a range up to 250 000Ω, a 100 ± 50-Hz oscillator and a sensitive null point indicator with minimum accuracy of ± 2 %.

<sup>11</sup> A Hobart Model N-50, manufactured by the Hobart Manufacturing Co., Troy, OH, has been found satisfactory for this purpose.

<sup>12</sup> DeCoste, J. B., and Siratelli, B. A., "Characterization of PVC Resins by the Conductivity of Solvent Extract," *Rubber Age*, Vol 87, pp. 279-285.