



# Standard Test Method for Indentation Hardness of Rigid Plastics by Means of a Barcol Impressor<sup>1</sup>

This standard is issued under the fixed designation D 2583; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This test method covers the determination of indentation hardness of both reinforced and nonreinforced rigid plastics using a Barcol Impressor, Model No. 934-1 and Model No. 935.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is currently no ISO standard that duplicates this test method.

## 2. Referenced Documents

### 2.1 ASTM Standards:

- D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing<sup>2</sup>
- D 883 Terminology Relating to Plastics<sup>2</sup>
- D 4000 Classification System for Specifying Plastic Materials<sup>3</sup>
- D 4805 Terminology of Plastics Standards<sup>3</sup>
- E 691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method<sup>4</sup>

## 3. Terminology

3.1 *Definitions*—For definitions of technical terms pertaining to plastics used in this test method, see Terminology D 883 or Terminology D 4805.

## 4. Summary of Test Method

4.1 Model No. 934-1 is used for measuring harder materials and Model No. 935 is used for measuring softer materials.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.10 on Mechanical Properties. Current edition approved Oct. 10, 1995. Published December 1995. Originally published as D 2583 – 67. Last previous edition D 2583 – 93.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 08.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 08.03.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 14.02.

## 5. Significance and Use

5.1 The Barcol Impressor is portable and therefore suitable for testing the hardness of fabricated parts and individual test specimens for production control purposes.

5.2 For many materials, there may be a specification that requires the use of this test method, but with some procedural modifications that take precedence when adhering to the specification. Therefore, it is advisable to refer to that material specification before using this test method. Table 1 of Classification System D 4000 lists the ASTM materials standards that currently exist.

## 6. Apparatus (Fig. 1 and Fig. 2)

6.1 *Indenter*—The indenter shall consist of a hardened steel truncated cone having an angle of 26° with a flat tip of 0.157 mm (0.0062 in.) in diameter. It shall fit into a hollow spindle and be held down by a spring-loaded plunger. See Fig. 2.

6.2 *Indicating Device*—The indicating dial shall have 100 divisions, each representing a depth of 0.0076-mm (0.0003-in.) penetration. The higher the reading the harder the material.

6.3 *Calibration Standards*—“Hard” and “soft” aluminum alloy disks supplied by the manufacturer of the instrument. Other disks should not be used, even if they are of the same alloy and temper as the manufacturer’s disks, as the hardness of aluminum may vary within any given alloy-temper parameter.

6.4 A smooth glass plate is also needed.

## 7. Test Specimens

7.1 The testing area shall be smooth and free from mechanical damage.

7.2 *Dimensions*—Test specimens shall be at least 1.5 mm ( $1/16$  in.) thick and large enough to ensure a minimum distance of 3 mm ( $1/8$  in.) in any direction from the indenter point to the edge of the specimen.

## 8. Preparation and Operation of Apparatus

8.1 The preparation and operation of Models 934-1 and 935 are identical. Place the impressor and the material to be tested (or the calibration disk) on a solidly supported, flat, hard, firm surface such as stone, metal, or ceramic. If softer supporting surfaces are used, a falsely low instrument reading may occur.

**TABLE 1 Recommended Sample Sizes to Equalize the Variance of the Average for Model No. 934-1**

Homogeneous Material				
Hardness M-934 Scale	Reading Variance	Coefficient of Variation, %	Variance of Average	Minimum Number of Readings
20	2.47	2.6	0.27	9
30	2.20	1.7	0.28	8
40	1.93	1.3	0.27	7
50	1.66	1.1	0.28	6
60	1.39	0.9	0.28	5
70	1.12	0.8	0.28	4
80	0.85	0.7	0.28	3
Nonhomogeneous Material (Reinforced Plastics)				
30	22.4	2.9	0.77	29
40	17.2	2.2	0.78	22
50	12.0	1.7	0.75	16
60	7.8	1.5	0.78	10
70	3.6	1.2	0.75	5



**FIG. 1 Barcol Impressor**

8.2 Set the point sleeve on the surface to be tested. Set the legs on the same surface or on solid material of the same thickness, so that the indenter is perpendicular to the surface being tested. Grasp the instrument firmly between the legs and point sleeve. Apply quickly, by hand, uniformly increasing force on the case until the dial indication reaches a maximum (Note 3). Take care to avoid sliding or scraping while the indenter is in contact with the surface being tested.

NOTE 2—It is recommended that measurements be made with Model 934-1 when values above 90 are obtained with Model 935 and that measurements be made with Model 935 when values less than 20 are obtained with Model No. 934-1. Values below 10 using Model 935 are inexact and should not be reported.

NOTE 3—Drift in readings from the maximum may occur in some materials. This can be nonlinear with time.

**9. Calibration**

9.1 With the plunger upper guide backed out until it just engages the spring, place the impressor on a glass surface and press down until the point is forced all the way back into the lower plunger guide. The indicator should now read 100. If it does not, loosen the lock-nut and turn the lower plunger guide

in or out to obtain a 100 reading. Next, read the “hard” aluminum alloy disk supplied by the manufacturer of the impressor and, if necessary, adjust so that the reading is within the range marked on the disk. Then do the same with the “soft” disk. If these readings cannot be obtained, subsequent measurements are not valid.

**10. Conditioning**

10.1 *Conditioning*—Condition the test specimens at  $23 \pm 2^\circ\text{C}$  ( $73.4 \pm 3.6^\circ\text{F}$ ) and  $50 \pm 5\%$  relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice D 618, for those tests where conditioning is required. In cases of disagreement, the tolerances shall be  $\pm 1^\circ\text{C}$  ( $\pm 1.8^\circ\text{F}$ ) and  $\pm 2\%$  relative humidity.

10.2 *Test Conditions*—Conduct tests in the standard laboratory atmosphere of  $23 \pm 2^\circ\text{C}$  ( $73.4 \pm 3.6^\circ\text{F}$ ) and  $50 \pm 5\%$  relative humidity, unless otherwise specified in the test methods or in this test method. In cases of disagreement, the tolerances shall be  $\pm 1^\circ\text{C}$  ( $\pm 1.8^\circ\text{F}$ ) and  $\pm 2\%$  relative humidity.

**11. Procedure**

11.1 Observing the precautions of Section 8, make measurements on the specimens to be tested (Note 4). Impressions should not be made within 3 mm ( $1/8$  in.) of the edge of the specimen or of other impressions.

NOTE 4—Curved surfaces may be more difficult to support. When the load is applied, bending and spring action in the specimen should be avoided.

**12. Number of Readings**

12.1 Application of the Barcol Impressor to reinforced plastic (nonhomogeneous) materials will produce greater variation in hardness readings than on nonreinforced (homogeneous) materials. This greater variation may be caused mainly by the difference in hardness between resin and filler materials in contact with the small diameter indenter. There is less variation in hardness readings on harder materials in the range of 50 Barcol and higher and considerably more variation in the readings of softer materials. On homogeneous materials, five readings are needed to maintain a variance-of-average of 0.28 at a 60 Barcol reading; for the same variance-of-average at 30 Barcol, eight readings are needed. On reinforced plastics, in order to maintain a variance-of-average of 0.78 at 60 Barcol, ten readings are needed; and 29 readings are needed for the same variance at the 30 Barcol level (Table 1).

NOTE 5—These findings were obtained with a round robin conducted in a workshop with all participants present. Eight plastic materials of different hardness were evaluated with six different Barcol (934-1) Impressors.

**13. Report**

- 13.1 Report the following information:
  - 13.1.1 Identification of material tested,
  - 13.1.2 Conditioning of specimen,
  - 13.1.3 Model number of impressor,
  - 13.1.4 Number of readings taken,
  - 13.1.5 Average of hardness values rounded to the nearest whole scale reading, and