



Designation: C 501 – 84 (Reapproved 1996)

## Standard Test Method for Relative Resistance to Wear of Unglazed Ceramic Tile by the Taber Abraser<sup>1</sup>

This standard is issued under the fixed designation C 501; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method<sup>2</sup> covers the establishment of an abrasive wear index by determination of the loss of weight resulting from abrasion of unglazed ceramic tile. It is applicable to tile described in Definitions C 242.

1.2 The values stated in inch-pound units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

C 242 Terminology of Ceramic Whitewares and Related Products<sup>3</sup>

#### 2.2 Federal Specification:

SS-T-308b Tile, Floor, Wall, and Trim Units, Ceramic<sup>4</sup>

### 3. Terminology

#### 3.1 Definitions:

3.1.1 For definitions of terms used in this test method, see Terminology C 242.

### 4. Summary of Test Method

4.1 This test method consists of mounting the tile specimens in suitable holders, attaching the mounted holders to the spindle of the Taber Abraser, and subjecting the specimens to a prescribed number of revolutions under abrasive wheels of specified coarseness and under a definite applied load. From the loss of weight due to abrasion, the abrasive wear index is calculated by a given formula.

### 5. Apparatus

5.1 *Taber Abrading Machine*,<sup>5</sup> equipped with replaceable hard abrasive H-22 Calibrate wheels, which can be loaded by weights.

5.2 *Vacuum Pick-Up*, to remove the abraded material while the machine is in operation.

5.3 *Revolution Counter*.

5.4 *Wheel Refacer*.<sup>5</sup>

5.5 *Balance*, having a sensitivity of 0.05 g.

### 6. Sampling

6.1 Four tile specimens 4 in. (102 mm) square or larger, or if ceramic mosaic tile, sufficient tile for four specimen assemblies 4 in. square shall constitute a sample and shall be chosen from the lot to be tested. Only tile that show no visible warpage when checked with a straightedge shall be used.

### 7. Test Specimen

7.1 The test specimen shall be 4 in. (102 mm) square and in one piece, if possible. If larger, it should be trimmed down to the desired size by removing equal amounts on opposite sides. In case of ceramic mosaic tile where several small units must be used to obtain a 4-in. square specimen assembly, the small units shall be mounted securely on a 4-in. square rigid material, such as a metal plate, by means of a suitable adhesive, and in such a manner that open joints are eliminated and the tile

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C-21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.06 on Ceramic Tile.

Current edition approved Dec. 28, 1984. Published February 1985. Originally published as C 501 – 62. Last previous edition C 501 – 80.

<sup>2</sup> This test method is basically the same as the abrasion test given in Federal Specification SS-T-308b, except two minor changes have been made:

(1) The number of specimens required by the test is changed from three to four, so that the condition of the abrasive wheels used can be specified as new and once dressed. The diameters of wheels redressed more than once vary greatly and nonuniformly, introducing an unnecessary variation in test results.

(2) The bulk specific gravity of the tile tested has been eliminated from calculation of the wear index. The probable resulting maximum error of

2  $\ln S$  % in the wear-index value, when an average is assumed, does not justify the cumbersome determinations of bulk specific gravity of the specimen. Measurements of bulk specific gravities of twenty different unglazed tile from eight different manufacturers, including quarry tile, porcelain tile, natural clay tile and conductive tile showed a range of bulk specific gravity from 2.34 to 2.47, except for that of conductive tile which was as high as 2.98. The average of 2.40 was selected as a constant to be substituted for  $G$  in the SS-T-308b formula to obtain the formula in this test method. Therefore, to obtain the value 88, the constant of 36.75 in the SS-T-308b test has been multiplied by 2.40 to keep the wear indexes of both tests on the same numerical scale.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 15.02.

<sup>4</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

<sup>5</sup> The Taber Abraser and the Model 200 wheel refacer are available from Tedyne Taber Instrument Corp., 17 Goundry St., North Tonawanda, NY 14150.