

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE

**Coaxial communication cables –  
Part 8-7: Detail specification for 75-086 type semi-flexible cables with solid  
polytetrafluoroethylene (PTFE) insulation**

**Câbles coaxiaux de communication –  
Partie 8-7: Spécification particulière pour câbles semi-flexibles de type 75-086 à  
isolation en polytétrafluoroéthylène (PTFE) compact**



## THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2012 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
Fax: +41 22 919 03 00  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

#### Useful links:

IEC publications search - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [csc@iec.ch](mailto:csc@iec.ch).

### A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

### A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

#### Liens utiles:

Recherche de publications CEI - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)

La recherche avancée vous permet de trouver des publications CEI en utilisant différents critères (numéro de référence, texte, comité d'études,...).

Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Just Published CEI - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Restez informé sur les nouvelles publications de la CEI. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - [www.electropedia.org](http://www.electropedia.org)

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (VEI) en ligne.

Service Clients - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: [csc@iec.ch](mailto:csc@iec.ch).



# INTERNATIONAL STANDARD

## NORME INTERNATIONALE

**Coaxial communication cables –  
Part 8-7: Detail specification for 75-086 type semi-flexible cables with solid  
polytetrafluoroethylene (PTFE) insulation**

**Câbles coaxiaux de communication –  
Partie 8-7: Spécification particulière pour câbles semi-flexibles de type 75-086 à  
isolation en polytétrafluoroéthylène (PTFE) compact**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

PRICE CODE  
CODE PRIX

M

ICS 33.120.10

ISBN 978-2-83220-328-6

**Warning! Make sure that you obtained this publication from an authorized distributor.  
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

## CONTENTS

FOREWORD.....	3
1 Scope.....	5
2 Normative references .....	5
3 Detail specification .....	6
Annex A (normative) Power rating.....	10
Annex B (normative) Return loss.....	11
Annex C (normative) Attenuation .....	12
Table A.1 – Typical power rating values.....	10
Table B.1 – Typical return loss values.....	11
Table C.1 – Typical attenuation values .....	12

## **iTeh STANDARD PREVIEW** **(standards.iteh.ai)**

[IEC 61196-8-7:2012](#)

<https://standards.iteh.ai/catalog/standards/sist/255f60be-206c-4df8-a45b-c384d5b3d0fa/iec-61196-8-7-2012>

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

## COAXIAL COMMUNICATION CABLES –

**Part 8-7: Detail specification for 75-086 type semi-flexible cables with solid polytetrafluoroethylene (PTFE) insulation**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61196-8-7 has been prepared by subcommittee 46A: Coaxial cables, of IEC technical committee 46: Cables, wires, waveguides, R.F. connectors, R.F. and microwave passive components and accessories.

The text of this standard is based on the following documents:

FDIS	Report on voting
46A/1092/FDIS	46A/1106/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This International Standard is to be used in conjunction with IEC 61196-1:2005 and IEC 61196-8:2012.

A list of all parts of IEC 61196 series, published under the general title *Coaxial communication cables*, can be found on the IEC website.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

## **iTeh STANDARD PREVIEW (standards.iteh.ai)**

[IEC 61196-8-7:2012](#)

<https://standards.iteh.ai/catalog/standards/sist/255f60be-206c-4df8-a45b-c384d5b3d0fa/iec-61196-8-7-2012>

## COAXIAL COMMUNICATION CABLES –

### Part 8-7: Detail specification for 75-086 type semi-flexible cables with solid polytetrafluoroethylene (PTFE) insulation

#### 1 Scope

This part of IEC 61196 applies to coaxial communication cables described in IEC 61196-8. It specifies the requirements for 75-086 type semi-flexible radio frequency and coaxial cables with polytetrafluoroethylene (PTFE) dielectric. These cables are for use in microwave and wireless equipment or other signal transmission equipment or units at frequencies from 500 MHz up to 18 GHz.

This part of IEC 61196 is to be used in conjunction with IEC 61196-1:2005 and IEC 61196-8:2012. It determines the layout and style with respect to the model and type.

#### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE Documents which are needed to achieve the tests according to Clause 3, item [9] or item [10], respectively, are listed in IEC 61196-8.

IEC 61196-1:2005, *Coaxial communication cables – Part 1: Generic specification – General, definitions and requirements*


IEC 61196-1-115, *Coaxial communication cables – Part 1-113: Electrical test methods – Test for regularity of impedance (pulse/step function return loss)*

IEC 61196-8:2012, *Coaxial communication cables – Part 8: Sectional specification for semi-flexible cables with polytetrafluoroethylene (PTFE) dielectric*

IEC 61196-8-1:2012, *Coaxial communication cables – Part 8-1: Blank detail specification for semi-flexible cables with polytetrafluoroethylene (PTFE) dielectric*

### 3 Detail specification

Numbers in square brackets are explained in IEC 61196-8-1:2012, Clause 3.

Coaxial communication cables –									
Part 8-7: Detail specification for 75-086 type semi-flexible cables with solid polytetrafluoroethylene (PTFE) insulation									
[1]	Prepared by: IEC SC 46A		[2]	Document No.	IEC 61196-8-7				
				Issue:	first				
				Date:	2012				
[3]	Available from: IEC	[4]	Generic specification	IEC 61196-1					
			Sectional specification	IEC 61196-8					
[5]	Additional references: IEC 61196-1-115								
[6]	Cable description:								
	75-086- XX -IEC 61196-8-7				75-086- X -IEC 61196-8-7				
									
[Key:	<p style="text-align: center;"><a href="https://standards.iteh.ai/catalog/standards/sist/255f60be-206c-4df8-a45b-c584d5b3d0fa/iec-61196-8-7-2012">https://standards.iteh.ai/catalog/standards/sist/255f60be-206c-4df8-a45b-c584d5b3d0fa/iec-61196-8-7-2012</a></p> <p>1: Inner conductor (SPC or SPCW)</p> <p>2: Dielectric (Solid PTFE)</p> <p>3: Outer conductor (Tin soaked copper wire braid)</p> <p>4: Sheath (FEP, LSZH or PVC)</p>								
[7]	Cable construction								
	Variants Constructions	75-086-1	75-086-2	75-086-11	75-086-21	75-086-12	75-086-22	75-086-13	75-086-23
Inner conductor	Material	SPC	SPCW	SPC	SPCW	SPC	SPCW	SPC	SPCW
	Diameter (mm)	0,29		0,29		0,29		0,29	
	Tolerance (mm)	±0,01		±0,01		±0,01		±0,01	
Dielectric	Material	PTFE		PTFE		PTFE		PTFE	
	Diameter (mm)	1,65		1,65		1,65		1,65	
	Tolerance (mm)	±0,05		±0,05		±0,05		±0,05	
Outer conductor	Material	tin soaked copper wire braid		tin soaked copper wire braid		tin soaked copper wire braid		tin soaked copper wire braid	
	Diameter (mm)	2,15		2,15		2,15		2,15	
	Tolerance (mm)	±0,07		±0,07		±0,07		±0,07	
Sheath	Material	–		FEP		PVC		LSZH	
	Minimum thickness (mm)	–		0,16		0,40		0,40	
	Diameter (mm)	–		2,55		3,15		3,15	



	Tolerance (mm)	-	±0,10	±0,10	±0,10
<b>NOTE</b>					
Variants – according to IEC 61196-8, 6.1.2.					
SPC – silver plated copper wire.					
SPCW – silver plated copper clad steel wire.					
PTFE – polytetrafluoroethylene.					
FEP – poly fluorinated ethylene propylene.					
LSZH – low smoke zero halogen.					
PVC – polyvinyl chloride.					
<b>[8] Engineering information (reference only)</b>					
<b>Variants Items</b>	<b>75-086-1 75-086-2</b>	<b>75-086-11 75-086-21</b>	<b>75-086-12 75-086-22</b>	<b>75-086-13 75-086-23</b>	
Operating temperature range	-55 °C to 125 °C	-55 °C to 125 °C	-40 °C to 85 °C	-15 °C to 70 °C	
Maximum operating frequency	3 GHz	3 GHz	3 GHz	3 GHz	
Nominal characteristic impedance	75 Ω	75 Ω	75 Ω	75 Ω	
Maximum continue working voltage	1,5 kV rms	1,5 kV rms	1,5 kV rms	1,5 kV rms	
Minimum bending radius (static state)	6 mm	6 mm	6 mm	6 mm	
Minimum bending radius (dynamic state)	25 mm	25 mm	25 mm	25 mm	
Nominal weight	15,5 kg/km	18,5 kg/km	21,5 kg/km	21,5 kg/km	
Power rating	As shown in Annex A				

<b>[9] Inspection value, rating or characteristic</b>	<b>[10] Subclause of IEC 61196-8</b>	<b>[11] Value</b>	<b>[12] Remarks</b>
<b>Electrical characteristics</b>	7.1		
Conductor direct current resistance	7.1.1	≤0,28 Ω/m (SPC) ≤0,686 Ω/m (SPCW)	20 °C
Capacitance	7.1.2	≤76 pF/m	1 000 Hz
Withstand voltage of dielectric	7.1.3	5 kV rms	40 Hz to 60 Hz
Withstand voltage of sheath	7.1.4	1,5 kV rms	40 Hz to 60 Hz (applies to cables with sheath)
Mean characteristic impedance	7.1.5	75 Ω ± 2,5 Ω	200 MHz
Regularity of impedance	7.1.6	Under consideration	
Relative propagation velocity (velocity ratio)	7.1.7	69,5 % to 71 %	200 MHz (if specified)
Return loss	7.1.8	As shown in Annex B	Length of the specimen: 12 m
Attenuation	7.1.9	As shown in Annex C	
Intermodulation (IM3)	7.1.10	Not applicable	
Screening attenuation	7.1.11	≥100 dB	At 1 GHz
Insulation resistance	7.1.12	≥15 000 MΩ·km	

[9] Inspection value, rating or characteristic	[10] Subclause of IEC 61196-8	[11] Value	[12] Remarks
<b>Environmental characteristics</b>	7.2		
Cold bend performance	7.2.1	-55 °C ± 2 °C (FEP sheath) -40 °C ± 2 °C (PVC sheath) -15 °C ± 2 °C (LSZH sheath)	Bending radius: 25 mm
Resistance soldering	7.2.2	Displacement ≤0,5 mm	Bending radius: 25 mm
Ageing	7.2.3	200 °C ± 5 °C (FEP sheath) 98 °C ± 2 °C (PVC sheath) 90 °C ± 2 °C (LSZH sheath)	
<b>Mechanical characteristics</b>	7.3		
Visual examination	7.3.1	Shall be in accordance with 4.2 of IEC 61196-1	
Ovality of dielectric	7.3.2	≤5 %	
Ovality of the sheath	7.3.3	≤7 %	Applies to cables with sheath
Eccentricity of dielectric	7.3.4	≤8 %	
Adhesion testing	7.3.5	Inner conductor to dielectric ≥18 N Outer conductor to dielectric ≥18 N	a) Test temperature: 20 °C ± 5 °C b) Specimen length: 300 mm
Bending	7.3.6	Impedance: 75 Ω ± 2,5 Ω No cracks in the outer conductor	a) Procedure 2 to be used b) Test mandrel diameter: 6 mm c) Number of cycles: 2 d) Number of turns: 1 e) Test temperature: 20 °C ± 5 °C f) After bending, measure the impedance according to IEC 61196-1-115 (procedure B)
Repeated bending	7.3.7	Impedance: 75 Ω ± 2,5 Ω No cracks in the outer conductor	a) Angle of displacement: 180° b) Number of cycles: 20 c) Mass of the weight: 0,9 kg d) Bending radius: 25 mm e) Test temperature: 20 °C ± 5 °C f) After bending, measure the impedance according to IEC 61196-1-115 (procedure B)
Tensile strength of cable (longitudinal pull)	7.3.8	Impedance at maximum load: 75 Ω ± 2,5 Ω No cracks in the outer conductor	Maximum load: 43 N Length of the specimen: 2 m

<b>[9]</b> Inspection value, rating or characteristic	<b>[10]</b> Subclause of IEC 61196-8	<b>[11]</b> Value	<b>[12]</b> Remarks
Pinhole of the finished cable	7.3.9	≤10 pinholes	Length of the specimen: 1 m

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 61196-8-7:2012](https://standards.iteh.ai/catalog/standards/sist/255f60be-206c-4df8-a45b-c384d5b3d0fa/iec-61196-8-7-2012)

<https://standards.iteh.ai/catalog/standards/sist/255f60be-206c-4df8-a45b-c384d5b3d0fa/iec-61196-8-7-2012>