



Standard Classification for Machine-Made “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe¹

This standard is issued under the fixed designation D 2310; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This classification covers machine-made “fiberglass” (glass-fiber-reinforced thermosetting-resin) pressure pipe. Methods of classification, requirements, test methods and the method of marking are included. Both glass-fiber-reinforced thermosetting-resin pipe (RTRP) and glass-fiber-reinforced plastic mortar pipe (RPMP) are fiberglass pipes.

1.2 This classification is based on the method of manufacture, the type of materials used in construction, and the test performance of the product type. It is not based on dimensions or raw material specifications.

1.3 Two methods of classifying long-term strength are included: (1) based on cyclic loads for use in those liquid-handling applications where the effects of pumping by duplex or triplex pumps or other cyclic pressure loads dictate the performance requirements of the piping, and (2) based on the steady (static) loads such as would be required for gas service applications.

1.4 The values stated in inch-pound units are to be regarded as the standard. The values in parentheses are provided for information only.

1.5 The following precautionary caveat pertains only to the test method portion, Section 7, of this classification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no similar or equivalent ISO standard.

2. Referenced Documents

2.1 ASTM Standards:

D 883 Terminology Relating to Plastics²

D 1600 Terminology for Abbreviated Terms Relating to Plastics²

D 2992 Practice for Obtaining Hydrostatic or Pressure De-

sign Basis for “Fiberglass” (Glass-Fiber Reinforced Thermosetting Resin) Pipe and Fittings³

D 3567 Practice for Determining Dimensions of “Fiberglass” (Glass-Fiber-Reinforced Thermosetting Resin) Pipe and Fittings³

F 412 Terminology Relating to Plastic Piping Systems³

3. Terminology

3.1 General—Definitions are in accordance with Terminology D 883 or F 412 and abbreviations are in accordance with Terminology D 1600, unless otherwise indicated.

3.2 *Definitions of Terms Specific to This Standard:* Description of Terms Specific to This Standard:

3.2.1 *fiberglass pipe, n*—a tubular product containing glass fiber reinforcements embedded in or surrounded by cured thermosetting resin; the composite structure may contain aggregate, granular, or platelet fillers, thixotropic agents, pigments, or dyes; thermoplastic or thermosetting liners or coatings may be included.

3.2.2 *reinforced thermosetting resin pipe (RTRP), n*—a fiberglass pipe without aggregate.

3.2.3 *reinforced plastic mortar pipe (RPMP), n*—a fiberglass pipe with aggregate.

3.2.4 *centrifugal casting, n*—a manufacturing process used to produce tubular goods by applying resin and reinforcement to the inside of a mold that is rotated and heated, subsequently polymerizing the resin system. The outside diameter of the finished pipe is fixed by the inside diameter of the mold tube. The inside diameter of the pipe is determined by the amount of material introduced into the mold.

3.2.5 *filament winding, n*—a process used to manufacture tubular goods by winding continuous fibrous glass strand roving or roving tape onto the outside of a mandrel in a predetermined pattern under controlled tension; the roving may be saturated with liquid resin or prepregged with partially cured resin; subsequent polymerization of the resin system may require application of heat; the inside diameter of the finished pipe is fixed by the mandrel outside diameter; the outside diameter of the finished pipe is determined by the amount of material that is wound onto the mandrel.

3.2.6 *liner, n*—the inner portion of the wall, at least 0.005

¹ This classification is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.23 on Reinforced Plastic Piping Systems and Chemical Equipment.

Current edition approved April 10, 1997. Published November 1997. Originally published as D 2310 – 64 T. Last previous edition D 2310 – 91.

² *Annual Book of ASTM Standards*, Vols 08.01 and 08.04.

³ *Annual Book of ASTM Standards*, Vol 08.04.